

प्राकृतिक रबड़ लेटेक्स — परीक्षण
पद्धतियाँ
भाग 6 यांत्रिक स्थिरता का निर्धारण
(दूसरा पुनरीक्षण)

Natural Rubber Latex — Methods of
Test
Part 6 Determination of Mechanical
Stability
(Second Revision)

ICS 83.040.10

© BIS 2024
© ISO 2004



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002
www.bis.gov.in www.standardsbis.in

NATIONAL FOREWORD

This Indian Standard (Part 6) (Second Revision) which is identical to ISO 35 : 2004 'Natural rubber latex concentrate — Determination of mechanical stability' issued by the International Organization for Standardization (ISO) was adopted by the Bureau of Indian Standards on recommendation(s) of the Methods of Test for Rubber and Rubber Products Sectional Committee and approval of the Petroleum, Coal and Related Products Division Council.

This standard was published in 1966 as IS 3708 (Part 1) and revised in 1985 and published as IS 3708 (Part 6) as part of NRL series of IS 3708 comprising of 11 parts. In the first revision, assistance was drawn from ISO 35 : 1982 'Rubber latex, natural — Determination of mechanical stability', issued by the International Organization for Standardization. Second revision of this standard has been undertaken to completely align it with the latest version of ISO 35 : 2004 under dual numbering system. Technical Corrigendum/Amendment published in 2006 to ISO 35 : 2004 has been given at the end of this publication.

The text of ISO standard has been approved as suitable for publication as an Indian Standard without deviations. Certain conventions are, however, not identical to those used in Indian Standards. Attention is particularly drawn to the following:

- a) Wherever the words 'International Standard' appear referring to this standard, they should be read as 'Indian Standard'; and
- b) Comma (,) has been used as a decimal marker while in Indian Standards, the current practice is to use a point (.) as the decimal marker.

In this adopted standard, reference appears to certain International Standards for which Indian Standards also exist. The corresponding Indian Standards, which are to be substituted in their respective places, are listed below along with their degree of equivalence for the editions indicated:

<i>International Standard</i>	<i>Corresponding Indian Standard</i>	<i>Degree of Equivalence</i>
ISO 123 Rubber latex — Sampling	IS 9316 (Part 5) : 2013/ISO 123 : 2001 Methods of test for rubber latex: Part 5 Drawing of samples [RL : 5] (<i>second revision</i>)	Identical
ISO 124 Latex, rubber — Determination of total solids content	IS 9316 (Part 4) : 2023/ISO 124 : 2014 Methods of test for rubber latex: Part 4 Determination of total solids content (<i>second revision</i>)	Identical
ISO 125 Natural rubber latex concentrate — Determination of alkalinity	IS 3708 (Part 4) : 2023/ISO 125 : 2020 Methods of test for natural rubber latex: Part 4 Natural rubber latex concentrate — Determination of alkalinity (<i>fourth revision</i>)	Identical

The Committee has reviewed the provisions of the following International Standard referred in this adopted standard and has decided that it is acceptable for use in conjunction with this standard:

<i>International Standard</i>	<i>Title</i>
ISO 3310-1	Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth

[\(Continued on third cover\)](#)

Contents

	Page
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Reagents	2
6 Apparatus	2
7 Sampling	3
8 Procedure	3
9 Expression of results	4
10 Test report	4
AMENDMENT 1	5

Indian Standard

NATURAL RUBBER LATEX — METHODS OF TEST

PART 6 DETERMINATION OF MECHANICAL STABILITY

(*Second Revision*)

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies a method for the determination of the mechanical stability of natural rubber latex concentrate. It is also applicable to prevulcanized natural rubber latex concentrate.

The method is not necessarily suitable for latices or prevulcanized latex preserved with potassium hydroxide, latices from natural sources other than *Hevea brasiliensis*, or for compounded latex or artificial dispersions of rubber, and it is not applicable to synthetic rubber latices.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 123, *Rubber latex — Sampling*

ISO 124, *Latex, rubber — Determination of total solids content*

ISO 125, *Natural rubber latex concentrate — Determination of alkalinity*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

natural rubber latex concentrate

natural rubber latex containing ammonia and/or other preservatives, with the exception of potassium hydroxide, and which has been subjected to some process of concentration

3.2

mechanical stability

time, in seconds, required to initiate visible flocculation under the specified test conditions

4 Principle

A test portion of the latex concentrate is diluted to 55 % by mass total solids content and stirred at high speed. The time required to initiate visible flocculation is recorded, this being regarded as a measure of the mechanical stability.

5 Reagents

The ammonia solutions (5.1 and 5.2) shall be prepared from ammonium hydroxide of recognized analytical reagent quality and shall be stored in closed containers.

Carbonate-free distilled water or water of equivalent purity shall be used for dilution of the latex. Deionized water may be used for the detection of the end-point.

5.1 Ammonia solution containing 1,6 % by mass of ammonia (NH₃), for use with latex concentrate having an alkalinity of at least 0,30 % (with respect to the latex concentrate).

5.2 Ammonia solution containing 0,6 % by mass of ammonia (NH₃), for use with latex concentrate having an alkalinity of less than 0,30 % (with respect to the latex concentrate).

6 Apparatus

Standard laboratory apparatus, plus the following:

6.1 Mechanical stability measuring apparatus,¹⁾ consisting of the items described in 6.1.1 to 6.1.3.

6.1.1 Latex container: A flat-bottomed, cylindrical container at least 90 mm high, with an internal diameter of 58 mm ± 1 mm and a wall thickness of approximately 2,5 mm. The inner surface shall be smooth.

A poly(methyl methacrylate) or glass container is suitable.

6.1.2 Stirring apparatus, consisting of a vertical stainless-steel shaft of sufficient length to reach the bottom of the latex container (6.1.1) and tapering to approximately 6,3 mm in diameter at its lower end, where an exactly centred, horizontal, smooth, stainless-steel disc, 20,83 mm ± 0,03 mm in diameter and 1,57 mm ± 0,05 mm thick, is attached. The apparatus shall be capable of maintaining a stirring rate of 14 000 rev/min ± 200 rev/min throughout a test, at which frequency the shaft shall not run out of true by more than 0,25 mm.

6.1.3 Holder, for the latex container (6.1.1). The holding arrangement shall ensure that the latex container is held securely, that the axis of the rotating shaft is concentric with that of the container and that the bottom of the stirring disc is 13 mm ± 1 mm from the inner surface of the bottom of the latex container.

6.2 Large Petri dish, with a diameter not less than 150 mm and depth not less than 20 mm. The size of the Petri dish will permit several tests to be carried out in the same dish.

6.3 Pointed rods: Thin rods, of glass or an inert material such as stainless steel, which have been drawn out or machined to a point. The precise dimensions are not important since the function of the rod is to pick up a small droplet of latex.

1) Suitable instruments are available commercially, e.g. from Klaxon Signals Ltd., Honey Pot Lane, Stanmore, HA7 1BE, U.K., Telefax +44 (208) 952 6983. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of this product.

6.4 Means of heating: Use either

— a water bath, capable of maintaining a temperature of $70\text{ }^{\circ}\text{C} \pm 10\text{ }^{\circ}\text{C}$;

or

— a glass tube, bent to a shape suitable for insertion in the latex concentrate. together with a means of circulating water at a temperature of $70\text{ }^{\circ}\text{C} \pm 10\text{ }^{\circ}\text{C}$ through the tube.

6.5 Wire cloth, of stainless steel, complying with the requirements of ISO 3310-1, with an average aperture width of $180\text{ }\mu\text{m} \pm 7,6\text{ }\mu\text{m}$.

7 Sampling

Carry out sampling in accordance with one of the methods specified in ISO 123.

NOTE Mechanical stability may be adversely affected by the duration and temperature of storage of the sample.

8 Procedure

8.1 General

Carry out the determination in duplicate within 24 h of first opening the sample bottle. If the total solids content and alkalinity of the latex concentrate are not known, determine them in accordance with ISO 124 and ISO 125, respectively.

NOTE If the concentration of the carbon dioxide in the atmosphere in the vicinity of the mechanical stability measuring apparatus (6.1) is above normal (about 0,03 % by volume), the mechanical stability of the latex will be reduced. This effect may be pronounced at carbon dioxide concentrations as low as 0,05 % by volume. High concentrations of carbon dioxide in the atmosphere may be caused by the proximity of any apparatus which generates carbon dioxide, such as certain types of gas or oil heater.

8.2 Dilution and stirring

Dilute 100 g of latex concentrate, in a glass beaker, to $55,0\text{ } \% \pm 0,2\text{ } \%$ by mass with the appropriate ammonia solution (5.1 or 5.2). Without delay, warm the diluted latex with gentle stirring to $35\text{ }^{\circ}\text{C}$ to $37\text{ }^{\circ}\text{C}$ (i.e. slightly above the intended test temperature) by one of the means of heating (6.4). Immediately filter the diluted and warmed latex through the wire cloth (6.5) and weigh $80,0\text{ g} \pm 0,5\text{ g}$ of the filtered latex into the container (6.1.1). Check the temperature of the latex is $35\text{ }^{\circ}\text{C} \pm 1\text{ }^{\circ}\text{C}$. Place the container in the holder (6.1.3) and stir the latex, ensuring that the rotational frequency of the stirrer is $14\text{ }000\text{ rev/min} \pm 200\text{ rev/min}$ throughout the test, until the end-point is passed.

8.3 Determination of end-point

The arrival of the end-point is preceded by a marked decrease in the depth of the vortex around the stirring shaft, accompanied by loss of turbulence and a change in the sound of the stirring action.

Two methods are permitted for the determination of the end-point. Inexperienced operators should have the method of determining the end-point demonstrated to them.

- a) **Palm-of-the-hand method:** Determine the end-point by removing a drop of the latex with a clean glass rod at intervals of 15 s and gently spreading the sample on the palm of the hand. Take the end-point as the first appearance of flocculum. Confirm the end-point by the presence of an increased amount of flocculum in a sample taken after stirring the latex for an additional 15 s.

- b) **Dispersibility-in-water method:** Take a large Petri dish (6.2) and introduce 100 cm³ to 150 cm³ of water. It will facilitate observation of the end-point if the Petri dish is standing on a dark surface such as black paper. Using a pointed rod (6.3), pick up a small drop of latex and immediately touch the surface of the water with it. If the latex has not started to flocculate, it will disperse within a few seconds to give a milky cloud. If flocculation has commenced, the droplet will generally remain on the surface of the water without dispersing. If it should start to disperse, then particles of flocculum will be readily apparent to the naked eye.

9 Expression of results

Express the mechanical stability time of the latex concentrate as the number of seconds between the start of stirring and the end-point.

Calculate the mean of the two determinations. If the results of the duplicate determinations do not agree to within 5 % of their mean value, the test shall be repeated.

10 Test report

The test report shall include the following particulars:

- a) a reference to this International Standard;
- b) all details necessary for the identification of the test sample;
- c) the method used for determining the end point [8.3 a) or 8.3 b)];
- d) the mean mechanical stability time of the latex concentrate, quoted to the nearest 15 s;
- e) any unusual features noted during the determination;
- f) details of any operation not included in this International Standard or in the International Standards to which reference is made, as well as details of any procedure regarded as optional;
- g) the date of the test.

Natural rubber latex concentrate — Determination of mechanical stability

AMENDMENT 1: Precision data

Page 1, Clause 2

Add the following reference:

ISO/TR 9272, *Rubber and rubber products — Determination of precision for test method standards*

Page 4

Add the following new clause, renumbering the test report as Clause 11:

10 Precision statement

10.1 The precision of this method was determined in accordance with ISO/TR 9272. Refer to this document for terminology and explanations of statistical concepts.

10.2 The precision details in this precision statement give an estimate of the precision of this test method with the materials used in the particular interlaboratory programme as described below. The precision parameters should not be used for acceptance/rejection testing of any group of materials without documentation that the parameters are applicable to those particular materials and the specific test protocol of this test method.

10.3 The precision results are given in Table 1. The precision is expressed on the basis of a 95 % confidence level for the values established for repeatability r and reproducibility R .

10.4 The results contained in Table 1 are mean values and give an estimate of the precision of this test method as determined in an interlaboratory test programme (ITP) conducted in 2001. Thirteen laboratories performed triplicate analyses, using the dispersibility-in-water method of end-point determination [see 8.3 b)], on two samples, A and B, which were prepared from highly ammoniated latex. The bulk latex was strained and then homogenized by thorough blending and stirring prior to being sub-sampled into 1-litre bottles labelled A and B. Thus, essentially, samples A and B were the same and were treated as such in the statistical computations. Each participating laboratory was required to carry out the test using these two samples on the dates which had been given to the participants in the ITP.

10.5 A type 1 precision was determined, based on the sampling method used for the latex samples in the ITP.

10.6 Repeatability: The repeatability r (in measurement units) of this test method has been established as the appropriate value tabulated in Table 1. Two single test results, obtained in the same laboratory under normal test conditions, that differ by more than the tabulated value of r (for any given level) shall be considered to have come from different (non-identical) sample populations.

10.7 Reproducibility: The reproducibility R (in measurement units) of this test method has been established as the appropriate value tabulated in Table 1. Two single test results, obtained under normal test conditions, that differ by more than the tabulated value of R (for any given level) shall be considered to have come from different (non-identical) sample populations.

10.8 Bias: In test method terminology, bias is the difference between an average test value and the reference (or true) test property value.

Reference values do not exist for this test method since the value (of the test property) is exclusively defined by the test method. Bias, therefore, cannot be determined for this particular test method.

Table 1 — Estimate of precision of determination of mechanical stability time

Mean s	Within laboratory		Between laboratories	
	s_r	r	s_R	R
1 023	15	43	94	265

$r = 2,83 \times s_r$
 where r is the repeatability (in measurement units) and s_r is the within-laboratory standard deviation.
 $R = 2,83 \times s_R$
 where R is the reproducibility (in measurement units) and s_R is the between-laboratory standard deviation.

[\(Continued from second cover\)](#)

In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: PCD 29 (22805).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : Manakalya, 4 th Floor, NTH Complex (W Sector), F-10, MIDC, Andheri (East), Mumbai 400093	{ 283 25838

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.