
गैस सिलिंडर — गैस के संघटक से सिलिंडर
एवं वाल्व सामग्री की अनुरूपता
भाग 1 धात्विय सामग्रियाँ
(पहला पुनरीक्षण)

**Gas Cylinders — Compatibility of
Cylinder and Valve Materials with
Gas Contents**

Part 1 Metallic Materials
(*First Revision*)

ICS 23.020.35

© BIS 2021



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुरशाह ज़फर मार्ग, नई दिल्ली – 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI-110002
www.bis.gov.in www.standardsbis.in

NATIONAL FOREWORD

This Indian Standard (Part 1) (First Revision) which is identical with ISO 11114-1 : 2020 'Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 1: Metallic materials' issued by the International Organization for Standardization (ISO) was adopted by the Bureau of Indian Standards on recommendation of the Gas Cylinders Sectional Committee and approval of the Mechanical Engineering Division Council.

This standard was originally published in 2015 and was identical with ISO 11114-1 : 2012 'Gas cylinders — Compatibility of cylinders and valve material with gas contents — Part 1: Metallic materials'. The first revision of this standard has been undertaken to align it with the latest version of ISO 11114-1 : 2020.

This Indian Standard is published in various parts. The other parts in this series are:

- Part 2 Non-metallic materials
- Part 3 Autogenous ignition test for non-metallic materials in oxygen atmosphere
- Part 4 Test methods for selecting steels resistant to hydrogen embrittlement

Where there is any conflict between this International Standard and any applicable regulation, the regulation always takes precedence.

The text of ISO Standard has been approved as suitable for publication as an Indian Standard without deviations. Certain terminologies and conventions are, however, not identical to those used in Indian Standards. Attention is particularly drawn to the following:

- a) Wherever the words 'International Standard' appear, referring to this standard, they should be read as 'Indian Standard'.
- b) Comma (,) has been used as a decimal marker, while in Indian Standards, the current practice is to use a point (.) as the decimal marker.

In this adopted standard, reference appears to certain International Standards for which Indian Standards also exist. The corresponding Indian Standards, which are to be substituted in their respective places, are listed below along with their degree of equivalence for the editions indicated:

<i>International Standard</i>	<i>Corresponding Indian Standard</i>	<i>Degree of Equivalence</i>
ISO 11114-2 Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 2: Non-metallic materials	IS/ISO 11114-2 : 2013 Transportable gas cylinders — Compatibility of cylinder and valve materials with gas contents: Part 2 Non-metallic materials	Identical with ISO 11114-2 : 2013
ISO 11114-3 Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 3: Autogenous ignition test for non-metallic materials in oxygen atmosphere	IS/ISO 11114-3 : 2010 Gas cylinders — Compatibility of cylinder and valve materials with gas contents: Part 3 Autogenous ignition test for Non-metallic materials in oxygen atmosphere	Identical with ISO 11114-3 : 2010

The technical committee has reviewed the provisions of the following International Standards referred in this adopted standard and has decided that they are acceptable for use in conjunction with this standard:

<i>International Standard</i>	<i>Title</i>
ISO 10286	Gas cylinders — Terminology
ISO 10297	Gas cylinders — Cylinder valves — Specification and type testing

(Continued on third cover)

Introduction

Industrial, medical and special gases (e.g. high-purity gases, calibration gases) can be transported or stored in gas cylinders. An essential requirement of the material from which such gas cylinders and their valves are manufactured is compatibility with the gas content.

Compatibility of cylinder materials with gas content has been established over many years by practical application and experience. Existing national and international regulations and standards do not fully cover this aspect.

This document is based on current international experience and knowledge.

This document has been written so that it is suitable to be referenced in the UN Model Regulations^[1].

This page has been intentionally left blank

*Indian Standard***GAS CYLINDERS — COMPATIBILITY OF CYLINDER
AND VALVE MATERIALS WITH GAS CONTENTS****PART 1 METALLIC MATERIALS***(First Revision)***1 Scope**

This document provides requirements for the selection of safe combinations of metallic cylinder and valve materials and cylinder gas content.

The compatibility data given is related to single gases and to gas mixtures.

Seamless metallic, welded metallic and composite gas cylinders and their valves, used to contain compressed, liquefied and dissolved gases are considered.

NOTE In this document the term “cylinder” refers to transportable pressure receptacles, which also include tubes and pressure drums.

Aspects such as the quality of delivered gas product are not considered.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10156, *Gas cylinders — Gases and gas mixtures — Determination of fire potential and oxidizing ability for the selection of cylinder valve outlets*

ISO 10286, *Gas cylinders — Terminology*

ISO 10297, *Gas cylinders — Cylinder valves — Specification and type testing*

ISO 11114-2, *Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 2: Non-metallic materials*

ISO 11114-3, *Gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 3: Autogenous ignition test for non-metallic materials in oxygen atmosphere*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 10286 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1**competent person**

person who has the necessary technical knowledge, experience and authority to assess and approve materials for use with gases and to define any special conditions of use that are necessary

3.2
acceptable

A
material/gas combination that is safe under normal conditions of use, provided that any indicated non-compatibility risks are taken into account

Note 1 to entry: Low levels of impurities can affect the acceptability of some single gases or gas mixtures.

3.3
not acceptable

N
material/single gas combination that is not safe under all normal conditions of use

Note 1 to entry: For gas mixtures special conditions may apply (see [6.2](#) and [Table 1](#)).

3.4
dry

state in which there is no free water in a cylinder under any service conditions, including at the highest expected operating pressure and at the lowest expected operating temperature

Note 1 to entry: For compressed gases at, for example, 200 bar and -20 °C, the maximum moisture content is not to exceed 5 ppmV, to avoid condensation of free water. For other temperatures and pressures, the maximum moisture content needed to avoid condensation of water will be different. Another source of moisture to be considered is the cylinder itself which implies appropriate drying procedures such as purging and vacuuming.

3.5
wet

state in which the conditions as defined for *dry* ([3.4](#)) are not met

3.6
gas mixture

combination of different single gases deliberately mixed in specified proportions

3.7
single gas

gas which does not contain deliberately added content of another gas or gases

4 Materials

4.1 General

The compatibility of most materials used to manufacture gas cylinders and valves is identified in this document.

Other materials whose compatibility is not identified in this document may be used if all compatibility aspects have been considered and validated by a competent person.

4.2 Cylinder materials

The most commonly used metallic materials for cylinders are (among others) carbon manganese steel, chromium molybdenum steel, chromium molybdenum nickel steel, stainless steel and aluminium alloys, as specified in the following documents:

- aluminium and aluminium alloys: ISO 6361-2, ISO 7866 and ISO 11118;
- steel: ISO 4706, ISO 9328-5, ISO 9809-1, ISO 9809-2, ISO 9809-3, ISO 11118 and ISO 11120;
- stainless steel: ISO 9809-4 and ISO 15510.

4.3 Valve materials

4.3.1 General

The most commonly used metallic materials for valve bodies and internal gas wetted parts are brass and other similar copper-based alloys, carbon steel, stainless steel, refined nickel and nickel alloys, Cu-Be (2 %) and aluminium alloys.

4.3.2 Particular considerations

4.3.2.1 In special cases, non-compatible materials may be used for non-oxidizing gases if suitably plated, protected or coated. This may only be done if all compatibility aspects have been considered and validated by a competent person for the entire life of the valve.

4.3.2.2 Special precautions, in accordance with ISO 11114-3 (which addresses testing, not precautions per se), shall be taken for oxidizing gases as specified in ISO 10156. In this case, non-compatible materials are *not acceptable* (see [3.3](#)) for use in valves, even if plated, protected or coated.

4.3.2.3 For cylinder valves, compatibility in wet conditions shall be considered because of the high risk of contamination by atmospheric moisture and an airborne contaminant.

NOTE Reference is made in this document to stainless steels by their commonly used AISI identification numbers, i.e. 304. For example, the equivalent grades according to EN 10088-1 are as follows:

304	1.4301
304L	1.4306 and 1.4307
316	1.4401
316L	1.4404
316Ti	1.4571
321	1.4541
904L	1.4539

5 Compatibility criteria

5.1 General

Compatibility between a gas and the cylinder/valve material is affected by chemical reactions and physical influences, which can be classified into five categories:

- corrosion;
- stress corrosion cracking;
- hydrogen embrittlement;
- generation of dangerous products through chemical reaction;
- violent reactions, such as ignition.

Non-metallic components (valve sealing, gland packing, O-ring, etc.) shall be in accordance with ISO 11114-2.

Sealing or lubricating materials (when used) at the valve stem shall be compatible with the gas content.

NOTE [Annex A](#) gives the gas/materials NQSAB compatibility codes, for information.

5.2 Corrosion

5.2.1 General

Many types of corrosion mechanisms can occur due to the presence of the gas, as outlined in [5.2.2](#) to [5.2.4](#).

5.2.2 Corrosion in dry conditions

This corrosion is affected by chemical attack by a dry gas on the cylinder material. The result is a reduction of the cylinder wall thickness. This type of corrosion is not very common, because the rate of dry corrosion is very low at ambient temperature.

5.2.3 Corrosion in wet conditions

This is the most common type of corrosion, which only occurs in a gas cylinder due to the presence of free water or aqueous solutions. However, with some hygroscopic gases (e.g. HCl, Cl₂) corrosion would occur even if the water content were less than the saturation value. Therefore, some gas/material combinations are not recommended, even if inert in the theoretical dry conditions. It is thus very important to prevent any water ingress into gas cylinders. The most common sources of or reasons for water ingress are:

- a) the customer, by retro-diffusion/backfilling or when the cylinder is empty, by air entry, if the valve is not closed,
- b) ineffective drying following hydraulic testing, and
- c) during filling.

In some cases, it is very difficult to completely prevent water ingress – particularly when the gas is hygroscopic (e.g. HCl, Cl₂). In cases where the filler cannot guarantee the dryness of gas and cylinder, a cylinder material which is compatible with the wet gas shall be used, even if the dry gas is not corrosive.

There are several different types of “wet corrosion” in alloys:

- 1) general corrosion leading to the reduction of the wall thickness, e.g. by acid gases (CO₂, SO₂) or oxidizing gases (O₂, Cl₂);
- 2) localized corrosion, e.g. pitting corrosion or grain boundary attack.

Additionally, some gases, even inert ones, when hydrolysed could lead to the production of corrosive products.

5.2.4 Corrosion by impurities

Gases which themselves are inert (non-corrosive) can cause corrosion due to the presence of impurities. Contamination of gases can occur, during filling, during use or if the initial product is not properly purified.

The most common pollutants are:

- a) atmospheric air, in which case the harmful impurities can be moisture (see also [5.2.3](#)) and oxygen (e.g. in liquefied ammonia);
- b) aggressive products contained in some gases, e.g. H₂S in natural gas;
- c) aggressive traces (acid, mercury, etc.) remaining from the manufacturing process of some gases.

The materials compatible with the impurities shall be used if the presence of these impurities cannot be prevented and if the corresponding corrosion rate is unacceptable for the intended application.

5.3 Hydrogen embrittlement phenomenon

Embrittlement caused by hydrogen can occur at ambient temperature in the case of certain gases and under service conditions which stress the cylinder or valve material.

This type of stress cracking phenomenon can, under certain conditions, lead to the failure of gas cylinders and/or valve components containing hydrogen, mixtures of hydrogen and other gases.

5.4 Generation of dangerous products

In some cases, reactions of a gas with a metallic material can lead to the generation of dangerous products. Examples are the possible reactions of C_2H_2 with copper alloys containing more than 65 % copper and of CH_3Cl in aluminium alloy cylinders.

5.5 Violent reactions (e.g. ignition)

In principle, violent reactions of gas/metallic material are not very common at ambient temperatures, because high activation energies are necessary to initiate such reactions. In the case where a combination of non-metallic and metallic materials is used, e.g. for valves, this type of reaction can occur with some gases (e.g. O_2 , Cl_2).

5.6 Stress corrosion cracking

Stress corrosion cracking can occur in many metallic materials subjected to stress, moisture and a contaminant at the same time. Stress corrosion cracking can, under certain conditions, lead to the failure of the gas cylinder or valve and/or its components (e.g. ammonia in contact with copper alloy valves or carbon monoxide/carbon dioxide mixtures in steel cylinders).

6 Material compatibility

6.1 Table of compatibility for single gases

Before any gas/cylinder/valve combination is chosen a careful study of all the *key compatibility characteristics* given in [Table 1](#) shall be made. Particular attention shall be paid to any restrictions, which shall be applied to acceptable materials.

NOTE The gases are generally listed in the table in English alphabetical order.

6.2 Compatibility for gas mixtures

Any gas mixtures containing single gases that are all compatible with a given material shall be considered as being compatible with this material.

For gas mixtures containing gases causing embrittlement (see [5.3](#), and [Clause A.4](#), groups 2 and 11) the risk of hydrogen embrittlement only occurs if the partial pressure of the gas is greater than 5 MPa (50 bar) and the stress level of the cylinder material is high enough. In a gas mixture, the partial pressure for hydrogen sulphide and methyl mercaptan shall be less than 0,25 MPa (2,5 bar) at a maximum UTS (ultimate tensile strength) of 950 MPa. If the stress level of the cylinder material is high, see [Table 1](#), row 63.

Some International Standards, such as ISO 11114-4, specify test methods for selecting appropriate steels with a maximum UTS greater than 950 MPa.

For the halogenated gases that are not compatible with aluminium alloy cylinders, the maximum acceptable concentration in gas mixtures shall be limited to 0,1 % as indicated in [Table 1](#) unless higher concentrations have been validated after conducting specific tests (examples of such tests are given in EIGA document 161/16^[14]). The moisture content (dryness) in these mixtures shall be limited to a maximum of 10 ppmV.

For non-compatibility of some halogenated gases with aluminium alloys, the maximum acceptable content is given in [Table 1](#). The level of moisture can affect the acceptability of such mixtures.

6.3 Using [Table 1](#)

6.3.1 Conventions and numbers

In [Table 1](#), **bold face** type indicates that the material is commonly used under normal service conditions:

- A = acceptable (see [3.2](#));
- N = not acceptable (see [3.3](#)).

If there is no UN number listed for a gas (or liquid), the gas has no official UN number but may be shipped using a generic NOS (not otherwise specified) number.

EXAMPLE UN 1954, Compressed gas, flammable, N.O.S.

6.3.2 Abbreviations for materials

CS	carbon steels used for the manufacture of cylinder valve bodies
NS	carbon steels heat treated by normalization that are used for the manufacture of seamless and welded cylinders
QTS	alloy steels that are treated by quenching and tempering and that are used for the manufacture of seamless steel cylinders
SS	austenitic type stainless steels used for the manufacture of seamless and welded cylinders and some valve bodies and valve components
AA	aluminium alloys specified in ISO 7866 when used for the manufacture of seamless cylinders; for aluminium valve bodies, alloys not specified in ISO 7866 may also be used
B	brass and other copper alloys used for the manufacture of cylinder valves
Ni	nickel alloys used for the manufacture of cylinders, valves and valve components
Cu	copper
ASB	aluminium silicon bronze

Table 1 — Gas/material compatibility

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material		
					Cylinder	Valve (body and components)	
					A	N	N
1	(UN 1001) (UN 3374)	ACETYLENE	C ₂ H ₂	Ability to form explosive acetylides with certain metals, including copper and copper alloys. Use <65 % Cu and copper alloy. This also applies to mixtures of more than 1 % C ₂ H ₂ . The acceptable limit of the silver content of alloys should preferably be 43 % (by mass) but in no case exceeding 50 %. There is no known incompatibility between the solvents used and any metallic materials, this is more relevant for ISO 11114-2.	NS	B	B (Cu >65 %)
					QTS	CS	
					AA	AA	Cu-Be (2 %)
					SS	SS	
					Ni	Ni	
2	(UN 1005)	AMMONIA	NH ₃	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric contaminant. This applies to all gases and mixtures containing even traces of NH ₃ .	NS	CS	
					QTS	SS	
					AA	AA	B
					SS	Ni	
					Ni		
3	(UN 1006)	ARGON	Ar	No reaction with any common materials in dry or wet conditions.	NS	B	
					QTS	CS	
					AA	SS	
					SS	AA	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material	
					Cylinder	Valve (body and components)
4	(UN 2188)	ARSINE	AsH ₃	Because of risk of hydrogen embrittlement: — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition. NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2.	A	N
					NS	B
					QTS	CS
					AA	SS
5	(UN 1741)	BORON TRICHLORIDE	BCl ₃	Hydrolyses to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS	AA
					QTS	CS
					SS	SS
					Ni	Ni
6	(UN 1008)	BORON TRIFLUORIDE	BF ₃	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. Mixtures containing less than 0,1 % BF ₃ may be filled into AA cylinders.	NS	AA
					QTS	CS
					SS	SS
					Ni	Ni

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
7	(UN 1974)	BROMOCHLORODIFLUORO-METHANE	CBrClF_2 (R12B1)	No reaction with any common materials when dry but in the presence of free water, corrosion can occur.	NS QTS AA SS		B CS SS AA	
8	(UN 1009)	BROMOTRIFLUOROMETHANE	CBrF_3 (R13B1)	No reaction with any common materials when dry but in the presence of free water, corrosion can occur.	NS QTS AA SS		B CS SS AA	
9	(UN 2419)	BROMOTRIFLUOROETHYLENE	C_2BrF_3	No reaction with any common materials when dry but in the presence of free water, corrosion can occur.	NS QTS AA SS		B CS SS AA	
10	(UN 1010)	BUTADIENE-1,3	$\text{H}_2\text{C:CHCH:CH}_2$	No reaction with any common materials. See 5.2.4 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA	
11	(UN 1010)	BUTADIENE-1,2	$\text{H}_2\text{C:C:CHCH}_3$	No reaction with any common materials. See 5.2.4 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA	
12	(UN 1011)	BUTANE	C_4H_{10}	No reaction with any common materials. See 5.2.4 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
13	(UN 1012)	BUTENE-1	CH ₃ CH ₂ CH:CH ₂	No reaction with any common materials. See 5.2.4 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA	
14	(UN 1012)	BUTENE-2 (CIS)	CH ₃ CH:CHCH ₃	No reaction with any common materials. See 5.2.4 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA	
15	(UN 1012)	BUTENE-2 (TRANS)	CH ₃ CH:CHCH ₃	No reaction with any common materials. See 5.2.4 for the effect of impurities in wet conditions.	NS QTS AA SS		B CS SS AA	
16	(UN 1013)	CARBON DIOXIDE	CO ₂	No reaction with any common materials when dry. Forms acidic carbonic in the presence of free water; corrosive for NS, QTS and CS. Risk (for NS and QTS) of stress corrosion cracking in presence of CO (see carbon monoxide) and water.	NS QTS AA SS		B CS SS AA	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material	
					Cylinder	Valve (body and components)
					A	N
17	(UN 1016)	CARBON MONOXIDE	CO	<p>Risk of formation of toxic metal carbonyls.</p> <p>Highly sensitive to any traces of moisture [>5 ppmV at 20 MPa (200 bar)], in the presence of CO₂ (>5 ppmV). Industrial grades of carbon monoxide normally contain traces of CO₂. This can result in risk of stress corrosion cracking, in the case of QTS, CS and NS cylinders if used at the normal service stress levels. Experience shows that this risk is eliminated if the fill pressure at 15 °C is less than 50 % of the cylinder working pressure. For details, see EIGA/CGA reference in the Bibliography.</p> <p>For QTS, CS, and NS steels this risk of stress corrosion cracking shall be considered for mixtures containing down to 0,1 % CO.</p> <p>Refined nickel gaskets used for some applications are not compatible with CO.</p> <p>NOTE AA and SS are not affected by this stress corrosion cracking phenomenon.</p> <p>Nickel alloys also suffer from a high propensity to form carbonyls. Alloys with less than 50% Nickel, such as the Incoloy[®]1 may be acceptable^[6].</p>	NS QTS AA SS	B CS SS AA
18	(UN 1982)	TETRAFLUORMETHANE (CARBON TETRAFLUORIDE)	CF ₄ (R14)	No reaction with any common materials when dry but in the presence of free water, corrosion can occur.	NS QTS AA SS	B CS SS AA

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material		
					Cylinder	Valve (body and components)	
					A	N	N
19	(UN 2204)	CARBONYL SULPHIDE	COS	Risk of formation of toxic metal carbonyls at temperature >100 °C. Highly sensitive to any traces of moisture (>5 ppmV), in the presence of CO ₂ (>5 ppmV); industrial grades of carbonyl sulphide normally contain traces of CO ₂ . This results in a risk of stress corrosion cracking, in the case of QTS, NS and CS. See also CO (No.17).	NS QTS AA SS	B CS SS AA	
20	(UN 1017)	CHLORINE	Cl ₂	Hydrolyses to hypochlorous acid and to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. The service life of brass valves strongly depends on the operating service conditions. Mixtures containing less than 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS	CS B ^a SS Ni ASB	AA AA
21	(UN 1018)	CHLORODIFLUOROMETHANE	CHClF ₂ (R22)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS QTS AA SS	B CS SS AA ASB	
22	(UN 1063)	METHYL CHLORIDE	CH ₃ Cl (R40)	In the presence of free water, corrosion can occur. Mixtures of dry gas containing not more than 0,1 % of this gas may be filled into AA cylinders. No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS QTS SS Ni	B CS SS Ni	AA AA

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material	
					Cylinder	Valve (body and components)
					A	N
23	(UN 1020)	CHLOROPENTAFLUOROETHANE	C ₂ ClF ₅ (R115)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS	B
					QTS	CS
					AA	SS
					SS	AA
24	(UN 1021)	CHLOROTETRAFLUOROETHANE	CClF ₂ CHF ₂ (R124)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS	B
					QTS	CS
					AA	SS
					SS	AA
25	(UN 1983)	CHLOROTRIFLUOROETHANE	CH ₂ ClCF ₃ (R133a)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS	B
					QTS	CS
					AA	SS
					SS	AA
26	(UN 1082)	CHLOROTRIFLUOROETHYLENE	C ₂ ClF ₃ (R1113)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS	B
					QTS	CS
					AA	SS
					SS	AA
27	(UN 1022)	CHLOROTRIFLUOROMETHANE	CClF ₃ (R13)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS	B
					QTS	CS
					AA	SS
					SS	AA
28	(UN 1027)	CYCLOPROPANE	C ₃ H ₆	No reaction with any common materials.	NS	B
					QTS	CS
					AA	SS
					SS	AA

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO₂, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
29	(UN 1957)	DEUTERIUM	D ₂	<p>Because of risk of hydrogen embrittlement:</p> <ul style="list-style-type: none"> — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition. <p>NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2. Refined nickel is not acceptable for bursting disks and other components. Risk of embrittlement due to the presence of mercury from certain production processes has to be considered, especially with AA.</p>	QTS NS AA SS		B CS AA SS	
30	(UN 1941)	DIBROMODIFLUOROMETHANE	CBBr ₂ F ₂ (R12B2)	<p>No reaction with any common materials when dry, but in the presence of free water corrosion occurs.</p>	QTS NS AA SS		B CS AA SS	
31	(See 6.3.1)	DIBROMOTETRAFLUOROETHANE	C ₂ Br ₂ F ₄	<p>No reaction with any common materials when dry, but in the presence of free water corrosion occurs.</p>	QTS NS AA SS		B CS AA SS	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material	
					Cylinder	Valve (body and components)
32	(UN 1911)	DIBORANE	B_2H_6	<p>Because of risk of hydrogen embrittlement:</p> <ul style="list-style-type: none"> — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition. <p>NOTE Some SS alloys can be sensitive to hydrogen embrittlement.</p> <p>See special conditions for mixtures given in 6.2.</p>	A	A
					N	N
					QTS	B
					NS AA SS	SS CS Ni
33	(UN 1028)	DICHLORODIFLUOROMETHANE	CCl_2F_2 (R12)	<p>No reaction with any common materials when dry, but in the presence of free water corrosion occurs.</p>	QTS	B
					NS	CS
					AA	AA
					SS	SS
34	(UN 1029)	DICHLOROFLUOROMETHANE	$CHCl_2F$ (R21)	<p>No reaction with any common materials when dry, but in the presence of free water corrosion occurs.</p>	QTS	B
					NS	CS
					AA	AA
					SS	SS
35	(UN 2189)	DICHLOROSILANE	SiH_2Cl_2	<p>Hydrolyses to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most materials and risk of hydrogen embrittlement.</p> <p>Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.</p>	QTS	AA
					NS	CS
					SS	SS
					Ni	Ni

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
36	(UN 1958)	DICHLOROTETRA- FLUOROETHANE	C ₂ Cl ₂ F ₄ (R114)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	QTS		B	
					NS		CS	
					AA		AA	
					SS		SS	
37	(UN 1026)	CYANOGEN	C ₂ N ₂	In the presence of free water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. Risk of stress corrosion cracking with brass (and other copper alloys) due to atmospheric moisture, whatever the concentration.	NS		Ni	B
					QTS		CS	
					AA		AA	
					SS		SS	
38	(UN 2517)	1-CHLORO-1,1- DIFLUOROETHANE	CH ₃ CClF ₂ (R142b)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	QTS		B	
					NS		CS	
					AA		AA	
					SS		SS	
39	(UN 1030)	1,1-DIFLUOROETHANE	CH ₃ CHF ₂ (R152a)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	QTS		B	
					NS		CS	
					AA		AA	
					SS		SS	
40	(UN 1959)	1,1-DIFLUOROETHYLENE	C ₂ H ₂ F ₂ (R1132a)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	QTS		B	
					NS		CS	
					AA		AA	
					SS		SS	
41	(UN 1032)	DIMETHYLAMINE	(CH ₃) ₂ NH	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture, whatever the concentration.	QTS		CS	B
					NS		SS	
					AA		AA	
					AA		AA	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material	
					Cylinder	Valve (body and components)
					A	N
42	(UN 1033)	DIMETHYL ETHER	$(\text{CH}_3)_2\text{O}$	No reaction with any common materials.	NS QTS AA SS	B CS AA SS
43	(see 6.3.1)	DISILANE	Si_2H_6	Because of risk of hydrogen embrittlement: — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition. NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2 .	NS AA QTS SS	B CS SS AA
44	(UN 1035)	ETHANE	C_2H_6	No reaction with any common materials.	QTS AA NS SS	B CS AA SS
45	(UN 1036)	ETHYLAMINE	$\text{C}_2\text{H}_5\text{NH}_2$	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture, whatever the concentration.	QTS NS AA SS	SS CS AA B

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
				A	N	A	N	
46	(UN 1037)	ETHYL CHLORIDE	C ₂ H ₅ Cl (R160)	No reaction with any common materials when dry but in the presence of free water, corrosion can occur. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	QTS NS SS Ni	AA	B SS CS Ni	AA
47	(UN 1962)	ETHYLENE	C ₂ H ₄	No reaction with any common materials.	QTS AA NS SS		B CS AA SS	
48	(UN 1040)	ETHYLENE OXIDE	C ₂ H ₄ O	Ethylene oxide polymerizes. Ethylene oxide polymerization increases in the presence of moisture, rust and other contaminants. Use dry and clean cylinders. Copper is not acceptable.	QTS NS AA SS		B CS AA SS	Cu
49	(UN 1045)	FLUORINE	F ₂	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. Risk of violent reaction with AA. Recommended materials are also Ni alloy and refined nickel. Mixtures containing less than 0,1 % of this gas may be filled into AA cylinders.	QTS NS SS Ni	AA	CS SS Ni	AA B ^a
50	(UN 2453)	FLUOROETHANE	C ₂ H ₅ F (R161)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	QTS NS AA SS		B CS AA SS	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
51	(UN 2454)	FLUOROMETHANE	CH ₃ F (R41)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	QTS		B	
					NS		CS	
					AA		AA	
					SS		SS	
52	(UN 1984)	TRIFLUOROMETHANE	CHF ₃ (R23)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	QTS		B	
					NS		CS	
					AA		AA	
					SS		SS	
53	(UN 2192)	GERMANE	GeH ₄	Because of risk of hydrogen embrittlement: — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition. NOTE Some SS alloys can be sensitive to hydrogen embrittlement. See special conditions for mixtures in 6.2.	QTS		B	
					NS		CS	
					AA		SS	
					SS		AA	
54	(UN 1046)	HELIUM	He	No reaction with any common materials.	NS		B	
					QTS		CS	
					AA		SS	
					SS		AA	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material		
					Cylinder	Valve (body and components)	
					A	N	N
55	(UN 2193)	HEXAFLUOROETHANE	C ₂ F ₆ (R116)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS QTS AA SS		B CS SS AA
56	(UN 1858)	HEXAFLUOROPROPENE	C ₃ F ₆ (R1216)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS QTS AA SS		B CS SS AA
57	(UN 1049)	HYDROGEN	H ₂	Because of risk of hydrogen embrittlement: — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — for seamless steel cylinders made to ISO 9809-1 or ISO 11120 from Cr-Mo quenched and tempered steels: unless they are validated by appropriate testing according to ISO 11114-4, and with a hydrogen partial pressure above 5 MPa (50 bar), the maximum UTS of the steel shall not exceed 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition.	NS QTS AA SS		B CS SS AA Cu-Be (2%)

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material		
					Cylinder	Valve (body and components)	
					A	N	N
				NOTE Some SS alloys are sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2 . Refined nickel is not acceptable for bursting disks and other components. Risk of embrittlement due to the presence of mercury from certain production processes has to be considered, especially with AA.			
58	(UN 1048)	HYDROGEN BROMIDE	HBr	This compound is highly hygroscopic and corrosive in wet conditions with most of the materials except some high corrosion resistant nickel alloys (e.g. Hastelloy®). QTS are limited to a maximum ultimate tensile strength of 950 MPa. This limitation also applies to mixtures containing the gas stored at a total pressure at 15 °C greater than half the normal service pressure of the cylinder. However, experience shows that a cylinder can be safely used without any specific strength limitation requirements, providing the maximum working pressure at 15 °C in the cylinder is less than one-fifth of the test pressure (TP/5), in order to maintain a low stress level in the cylinder material. SS shall not be used for valve diaphragms or springs except if the failure of such components does not result in an unsafe situation. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	CS SS Ni B AA

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
				A	N	A	N	
59	(UN 1050)	HYDROGEN CHLORIDE	HCl	<p>This compound is highly hygroscopic and corrosive in wet conditions with most of the materials except some high corrosion resistant nickel alloys (e.g. Hastelloy®¹). QTS are limited to a maximum ultimate tensile strength of 950 MPa. This limitation also applies to mixtures containing this gas and stored at a total pressure at 15 °C greater than half the normal service pressure of the cylinder.</p> <p>However, experience shows that a cylinder can be safely used without any specific strength limitation requirements, providing the maximum working pressure at 15 °C in the cylinder is less than one-fifth of the test pressure (TP/5), in order to maintain a low stress level in the cylinder material.</p> <p>SS shall not be used for valve diaphragm and springs except if the failure of such components does not result in an unsafe situation.</p> <p>Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.</p>	NS QTS SS Ni	AA	CS SS Ni	AA B
60	(UN 1050)	HYDROGEN CYANIDE	HCN	<p>This compound is highly hygroscopic. Risk of corrosion in wet conditions, depending on type of alloy.</p>	NS QTS AA SS		B CS SS AA	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material	
					Cylinder	Valve (body and components)
					A	N
61	(UN 1052)	HYDROGEN FLUORIDE	HF	<p>This compound is highly hygroscopic and corrosive in wet conditions with most of the materials except some high corrosion resistant nickel alloys (e.g. Hastelloy®¹). QTS are limited to a maximum ultimate tensile strength of 950 MPa. This limitation also applies to mixtures containing the gas stored at a total pressure at 15 °C greater than half the normal service pressure of the cylinder.</p> <p>However, experience shows that a cylinder can be safely used without any specific strength limitation requirements, providing the maximum pressure at 15 °C in the cylinder is less than one-fifth of the test pressure (TP/5), in order to maintain a low stress level in the cylinder material.</p> <p>SS shall not be used for valve diaphragms or springs except if the failure of such components does not result in an unsafe situation.</p> <p>Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.</p>	NS QTS SS Ni	AA CS SS Ni

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder	Valve (body and components)		
					A	N	N	
62	(UN 2197)	HYDROGEN IODIDE	HI	<p>This compound is highly hygroscopic and corrosive in wet conditions with most of the materials, except some high corrosion resistant nickel alloys (e.g. Hastelloy®¹). QTS are limited to a maximum ultimate tensile strength of 950 MPa. This limitation also applies to mixtures containing this gas and stored at a total pressure at 15 °C greater than half the normal service pressure of the cylinder.</p> <p>However, experience shows that a cylinder can be safely used without any specific strength limitation requirements, providing the maximum pressure at 15 °C in the cylinder is less than one-fifth of the test pressure (TP/5), in order to maintain a low stress level in the cylinder material.</p> <p>SS shall not be used for valve diaphragm and springs except if the failure of such components does not result in an unsafe situation.</p> <p>Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.</p>	NS QTS SS Ni	AA	CS SS Ni	AA B
					<p>^a Brass is only acceptable as a valve body but not as a general valve component material.</p> <p>^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.</p>			

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
63	(UN 1053)	HYDROGEN SULPHIDE	H ₂ S	<p>— In the presence of free water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316.</p> <p>— In wet conditions, risk of stress corrosion cracking for QTS. Risk of hydrogen embrittlement with NS, QTS.</p> <p>— SS shall not be used for springs or diaphragms except if the failure of such components does not result in an unsafe situation because of possibility of hydrogen embrittlement.</p> <p>— For mixtures with higher partial pressure than the one defined in 6.2 and stored at a total pressure greater than 50 % of the normal service pressure of the cylinder, NS, and QTS at a limited strength shall be used (see 6.2).</p> <p>— Refined nickel is not acceptable for bursting disks and components.</p>	NS QTS AA SS		CS SS AA	B
64	(UN 1969)	ISOBUTANE	CH(CH ₃) ₃	<p>No reaction with any common materials; however, in wet conditions risk of corrosion from impurities shall be considered.</p>	NS QTS AA SS		B CS SS AA	
65	(UN 1055)	ISOBUTYLENE	CH ₂ :C (CH ₃) ₂	<p>No reaction with any common materials; however, in wet conditions risk of corrosion from impurities shall be considered.</p>	NS QTS SS AA		B CS SS AA	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material	
					Cylinder	Valve (body and components)
					A	N
66	(UN 1056)	KRYPTON	Kr	No reaction with any common materials in dry or wet conditions.	NS QTS AA SS	B CS SS AA
67	(UN 1971)	METHANE	CH ₄	No reaction with any common materials; however, in wet conditions risk of corrosion from impurities such as traces of CO, H ₂ S, CO ₂ shall be considered (see CO, H ₂ S, CO ₂ compatibility). NOTE For natural gas see also specific compatibility requirements in ISO 11439.	NS QTS AA SS	B CS SS AA
68	(See 6.3.1)	PROPYLENE	C ₃ H ₄	May contain traces of acetylene. The ability to form explosive acetylides has to be considered. If the C ₂ H ₂ content exceeds 1 % see C ₂ H ₂ .	NS QTS AA SS	B CS SS AA
69	(UN 1062)	METHYL BROMIDE	CH ₃ Br (R40B1)	In the presence of free water pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS	B CS SS Ni

a Brass is only acceptable as a valve body but not as a general valve component material.

b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material	
					Cylinder	Valve (body and components)
					A	N
70	(UN 1064)	METHYL MERCAPTAN	CH ₃ SH	<ul style="list-style-type: none"> — In the presence of free water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. — In wet conditions risk of stress corrosion cracking for QTS. — Risk of hydrogen embrittlement with NS, QTS and some SS. — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition. <p>NOTE Some SS alloys are sensitive to hydrogen embrittlement.</p> <ul style="list-style-type: none"> — For mixtures with higher partial pressure than the one defined in 6.2, stored at a total pressure greater than 50 % the normal service pressure of the cylinder, NS, and QTS are limited to a maximum strength of 950 MPa. — Refined nickel is not acceptable for bursting disks and components. 	NS QTS AA SS	B CS SS AA
				<p>^a Brass is only acceptable as a valve body but not as a general valve component material.</p> <p>^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.</p>		

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material		
					Cylinder	Valve (body and components)	
					A	N	N
71	(See 6.3.1)	METHYL SILANE	CH ₃ SiH ₃	<ul style="list-style-type: none"> — QTS are limited to a maximum ultimate tensile strength of 950 MPa. — SS shall not be used for springs or diaphragms, except if the failure of components does not result in an unsafe situation. — Risk of corrosion by impurities in wet conditions shall be considered, e.g. contamination by sulphuric acid from some manufacturing processes. 	NS QTS AA SS		B CS SS AA
72	(UN 1061)	METHYLAMINE	CH ₃ NH ₂	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture. This applies to all gases and mixtures containing even traces of CH ₃ NH ₂ .	NS QTS AA SS Ni		CS SS AA Ni
73	(UN 1065)	NEON	Ne	No reaction with any common materials in dry or wet conditions.	NS QTS AA SS		B CS SS AA
74	(UN 1660)	NITRIC OXIDE	NO	In the presence of free water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture. This applies to all mixtures containing even traces of NO.	NS QTS AA SS		CS SS AA B ^b AA

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
75	(UN 1066)	NITROGEN	N ₂	No reaction with any common materials in dry or wet conditions.	NS QTS AA SS		B CS SS AA	
76	(UN 1067)	NITROGEN DIOXIDE	NO ₂	In the presence of free water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture. This applies to all mixtures containing even traces of NO ₂ .	NS QTS AA SS		CS SS	B AA
77	(UN 1070)	NITROUS OXIDE	N ₂ O	Risk of stress corrosion cracking for brass and other copper alloy highly stressed components (for any concentration). The potential risk of violent reaction (ignition), especially for valves, shall be considered at the design stage in accordance with ISO 11114-2, ISO 11114-3 and ISO 10297.	NS QTS AA SS		B CS SS AA	
78	(UN 2451)	NITROGEN TRIFLUORIDE	NF ₃	No reaction with any common materials when dry. Becomes a strong oxidizer when decomposed.	NS QTS SS AA		B CS SS	
79	(UN 2422)	OCTOFLUOROBUT-2-ENE	C ₄ F ₈	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS QTS AA SS		B CS SS AA	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material		
					Cylinder	Valve (body and components)	
					A	N	N
80	(UN 1976)	OCTAFLUOROCYCLOBUTANE	C ₄ F ₈ (RC318)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS		B
					QTS		CS
					AA		SS
					SS		AA
81	(UN 2424)	OCTAFLUOROPROPANE	C ₃ F ₈ (R218)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS		B
					QTS		CS
					AA		SS
					SS		AA
82	(UN 1072)	OXYGEN	O ₂	<p>In the presence of free water, NS, QTS and CS are corroded. Water ingress in cylinders should be avoided, e.g. by use of cylinder valves with RPV (residual pressure valve).</p> <p>The potential risk of violent reaction (ignition), especially for valves, shall be considered at the design stage in accordance with ISO 11114-2, ISO 11114-3 and ISO 10297. Cylinder valves shall be subject to testing to establish their suitability for oxygen service and their resistance to ignition (see ISO 11114-2, ISO 11114-3 and ISO 10297).</p> <p>Copper alloys shall contain no more than 2,5% aluminium content.</p> <p>Design assessment by a competent person is recommended before using SS for springs and other internal gas wetted components, unless ignition does not create safety issues.</p>	NS		B
					QTS		CS
					AA		SS
					SS		AA

a Brass is only acceptable as a valve body but not as a general valve component material.

b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
83	(UN 1076)	PHOSGENE	COCl ₂	In wet conditions, phosgene is corrosive with most materials, particularly aluminium alloys (hydrolyses to HCl). Mixtures of dry gas containing not more than 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	B CS SS Ni	AA
84	(UN 2199)	PHOSPHINE	PH ₃	Because of risk of hydrogen embrittlement: — QTS are limited to a maximum ultimate tensile strength of 950 MPa; — SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition. NOTE Some SS alloys are sensitive to hydrogen embrittlement. See special conditions for mixtures given in 6.2.	NS QTS AA SS		B CS SS AA	
85	(UN 1978)	PROPANE	C ₃ H ₈	No reaction with any common materials; however, in wet conditions the risk of corrosion from impurities shall be considered.	NS QTS AA SS		B CS SS AA	
86	(UN 2200)	PROPADIENE	C ₃ H ₄	No reaction with any common materials; however, in wet conditions the risk of corrosion from impurities shall be considered.	NS QTS AA SS		B CS SS AA	

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
87	(UN 1077)	PROPYLENE	C ₃ H ₆	No reaction with any common materials; however, in wet conditions the risk of corrosion from impurities shall be considered.	NS QTS AA SS		B CS SS AA	Cu
88	(UN 1280)	PROPYLENE OXIDE	C ₃ H ₆ O	Propylene oxide polymerizes. The rate of polymerization increases in the presence of moisture, rust and other contaminants. Use a clean, dry cylinder. Copper is not acceptable.	NS QTS AA SS	Cu	B CS SS AA	Cu
89	(UN 2203)	SILANE	SiH ₄	<p>— The filling ratio shall be limited to 320 g/L for steels with tensile strengths above 950 MPa.</p> <p>— SS may be used for valve diaphragms and springs when there is operating experience that shows the design is suitable and safe. Alternatively, use is also authorized if failure of the SS springs or SS diaphragms does not result in an unsafe condition.</p> <p>NOTE Some SS alloys are sensitive to hydrogen embrittlement.</p> <p>See special conditions for mixtures given in 6.2.</p> <p>Risk of corrosion by impurities in wet conditions shall be considered, e.g. contamination by sulphuric acid from some manufacturing processes.</p>	NS QTS SS AA		B CS SS AA	
90	(UN 1818)	SILICON TETRACHLORIDE	SiCl ₄	Hydrolyses to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most materials. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	CS B SS Ni	AA

a Brass is only acceptable as a valve body but not as a general valve component material.

b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material	
					Cylinder	Valve (body and components)
					A	N
91	(UN 1859)	SILICON TETRAFLUORIDE	SiF_4	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most materials. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA CS B SS Ni
92	(UN 1079)	SULPHUR DIOXIDE	SO_2	Highly hygroscopic. Sulphur dioxide hydrolyses in presence of free water to produce sulphurous acid, which is highly corrosive to steel. In the presence of free water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. B might suffer stress corrosion cracking, in long-term wet conditions.	NS QTS AA SS	B CS SS AA Ni
93	(UN 1080)	SULPHUR HEXAFLUORIDE	SF_6	No reaction with any common materials.	NS QTS AA SS	B CS SS AA
94	(UN 2418)	SULPHUR TETRAFLUORIDE	SF_4	In wet conditions, sulphur tetrafluoride is highly corrosive. SS alloys such as 316 and Nickel alloys may be used. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS	AA B CS SS Ni
95	(UN 1081)	TETRAFLUOROETHYLENE	C_2F_4 (R1114)	No reaction with any common materials when dry, but in the presence of free water corrosion can occur.	NS QTS AA SS	B CS SS AA

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material			
					Cylinder		Valve (body and components)	
					A	N	A	N
96	(UN 1295)	TRICHLOROSILANE	SiHCl ₃	Hydrolyses to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most of the materials. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	B CS SS Ni	AA
97	(See 6.3.1)	TRICHLOROTRIFLUOROETHANE	C ₂ Cl ₃ F ₃ (R113)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS QTS AA SS		B CS SS AA Ni	
98	(UN 2035)	1,1,1-TRIFLUOROETHANE	CH ₃ CF ₃ (R143a)	No reaction with any common materials when dry, but in the presence of free water corrosion occurs.	NS QTS AA SS		B CS SS AA	
99	(UN 1083)	TRIMETHYLAMINE	(CH ₃) ₃ N	Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture. This applies to all gases and mixtures containing even traces of NH ₃ .	NS QTS AA SS Ni		CS SS AA Ni	B

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material		
					Cylinder	Valve (body and components)	
					A	N	N
100	(UN 2196)	TUNGSTEN HEXAFLUORIDE	WF ₆	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most materials and risk of hydrogen embrittlement. Due to their highly corrosive-resistant nature, nickel-based alloys and nickel-plated valves are recommended. Mixtures containing less than 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	CS SS Ni AA
101	(UN 1085)	VINYL BROMIDE	C ₂ H ₃ Br (R1140B1)	Risk of corrosion in wet conditions. Some C ₂ H ₂ contamination could be present. Mixtures containing less than 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	B CS SS Ni AA
102	(UN 1086)	VINYL CHLORIDE	C ₂ H ₃ Cl (R1140)	Risk of corrosion in wet conditions. Some C ₂ H ₂ contamination could be present. Mixtures containing less than 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	B CS SS Ni AA
103	(UN 1860)	VINYL FLUORIDE	C ₂ H ₃ F (R1141)	Risk of corrosion in wet conditions. Some C ₂ H ₂ contamination could be present. Mixtures containing less than 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA	B CS SS Ni AA
104	(UN 2036)	XENON	Xe	No reaction with any common materials in dry or wet conditions.	NS QTS SS AA		B CS SS AA

^a Brass is only acceptable as a valve body but not as a general valve component material.

^b For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.

Table 1 (continued)

No.	Gas number UN number	Name	Formula	Key compatibility characteristics	Material	
					Cylinder	Valve (body and components)
					A	N
1		Incoloy® and Hastelloy® are examples of suitable products available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of these products.			A	N
a		Brass is only acceptable as a valve body but not as a general valve component material.			A	N
b		For mixtures containing up to 1 000 ppm of dry NO, brass valves can be used.			A	N

Annex A (informative)

Gas/materials NQSAB compatibility code

A.1 General

A five-digit code allows a rating of the compatibility of each gas with five different classes of materials for use with gas cylinders and cylinder valves. This is termed the NQSAB code, where “N” represents normalized steels and carbon steels, “Q” quenched and tempered steels, “S” stainless steels, “A” aluminium alloys and “B” brass and other copper alloys, and nickel alloys. The degree of compatibility is identified by replacing the letter with the appropriate digit as described in [A.2](#).

[A.3](#) presents the NQSAB code itself, and in [A.4](#) the gases covered in this part of ISO 11114 are divided into 11 groups, depending on their compatibility with cylinder and valve materials.

A.2 Material classes and compatibility identification

A.2.1 Normalized steels and carbon steels (N)

- 0 Not acceptable.
- 1 Acceptable but check [Table 1](#), key compatibility characteristics.
- 9 Acceptable but check [Table 1](#), key compatibility characteristics, to avoid hydrogen embrittlement.

A.2.2 Quenched and tempered steels (Q)

- 0 Not acceptable.
- 1 Acceptable but check [Table 1](#), key compatibility characteristics.
- 9 Acceptable but check [Table 1](#), key compatibility characteristics, to avoid hydrogen embrittlement.

A.2.3 Stainless steels (S)

- 0 Not acceptable.
- 1 Acceptable for gas cylinder but check [Table 1](#), key compatibility characteristics.
- 2 Pitting corrosion can be minimized by using stainless steel alloys such as 316.
- 9 Hydrogen embrittlement can be minimized by using stainless steel alloys such as 316.

A.2.4 Aluminium alloys (A)

- 0 Not acceptable but some mixtures of dry gases may be filled into AA; check [Table 1](#), key compatibility characteristics.
- 1 Acceptable but check [Table 1](#), key compatibility characteristics.

A.2.5 Brass and other copper alloys (B)

- 0 Not acceptable.

- 1 Acceptable to be used but check [Table 1](#), key compatibility characteristics.
- 3 Use brass or other copper alloys containing less than 65 % Cu.

A.3 NQSAB code

The NQSAB code for each gas is given in [Table A.1](#). For gases where the compatibility rating 2, 3 or 9 are specified, refer also to [Table 1](#).

Table A.1 — List of gases with corresponding NQSAB compatibility code

Name and gas number	Formula	N	Q	S	A	B
1 ACETYLENE	C_2H_2	1	1	1	1	3
2 AMMONIA	NH_3	1	1	1	1	0
3 ARGON	Ar	1	1	1	1	1
4 ARSINE	AsH_3	9	9	9	1	1
5 BORON TRICHLORIDE	BCl_3	1	1	2	0	0
6 BORON TRIFLUORIDE	BF_3	1	1	2	0	0
7 BROMOCHLORODIFLUOROMETHANE	$CBrClF_2$ (R12B1)	1	1	1	1	1
8 BROMOTRIFLUOROMETHANE	$CBrF_3$ (R13B1)	1	1	1	1	1
9 BROMOTRIFLUOROETHYLENE	C_2BrF_3	1	1	1	1	1
10 BUTADIENE-1,3	$H_2C:CHCH:CH_2$	1	1	1	1	1
11 BUTADIENE-1,2	$H_2C:C:CHCH_3$	1	1	1	1	1
12 BUTANE	C_4H_{10}	1	1	1	1	1
13 BUTENE-1	$CH_3CH_2CH:CH_2$	1	1	1	1	1
14 BUTENE-2 (CIS)	$CH_3CH:CHCH_3$	1	1	1	1	1
15 BUTENE-2 (TRANS)	$CH_3CH:CHCH_3$	1	1	1	1	1
16 CARBON DIOXIDE	CO_2	1	1	1	1	1
17 CARBON MONOXIDE	CO	1	1	1	1	1

Table A.1 (continued)

Name and gas number	Formula	N	Q	S	A	B
18 TETRAFLUOROMETHANE (CARBON TETRAFLUORIDE)	CF ₄	1	1	1	1	1
19 CARBONYL SULPHIDE	COS	1	1	1	1	1
20 CHLORINE	Cl ₂	1	1	2	0	1
21 CHLORODIFLUOROMETHANE	CHClF ₂ (R22)	1	1	1	1	1
22 METHYL CHLORIDE (CHLOROMETHANE)	CH ₃ Cl (R40)	1	1	1	0	1
23 CHLOROPENTAFLUOROETHANE	C ₂ ClF ₅ (R115)	1	1	1	1	1
24 CHLOROTETRAFLUOROETHANE	CClF ₂ -CHF ₂	1	1	1	1	1
25 CHLOROTRIFLUOROETHANE	CH ₂ ClCF ₃ (R133a)	1	1	1	1	1
26 CHLOROTRIFLUOROETHYLENE	C ₂ ClF ₃ (R1113)	1	1	1	1	1
27 CHLOROTRIFLUOROMETHANE	CClF ₃ (R13)	1	1	1	1	1
28 CYCLOPROPANE	C ₃ H ₆	1	1	1	1	1
29 DEUTERIUM	D ₂	9	9	9	1	1
30 DIBROMODIFLUOROMETHANE	CBr ₂ F ₂ (R12B2)	1	1	1	1	1
31 DIBROMOTETRAFLUOROETHANE	C ₂ Br ₂ F ₄ (R114B2)	1	1	1	1	1
32 DIBORANE	B ₂ H ₆	9	9	9	1	1
33 DICHLORODIFLUOROMETHANE	CCl ₂ F ₂ (R12)	1	1	1	1	1
34 DICHLOROFLUOROMETHANE	CHCl ₂ F (R21)	1	1	1	1	1
35 DICHLOROSILANE	SiH ₂ Cl ₂	1	1	2	0	0
36 DICHLOROTETRAFLUOROETHANE	C ₂ Cl ₂ F ₄ (R114)	1	1	1	1	1
37 CYANOGEN	C ₂ N ₂	1	1	2	1	0

Table A.1 (continued)

Name and gas number	Formula	N	Q	S	A	B
38 1-CHLORO-1,1-DIFLUOROETHANE (1,1-(DIFLUORO-1 CHLOROETHANE))	CH ₃ CClF ₂ (R142b)	1	1	1	1	1
39 1,1-DIFLUOROETHANE	CH ₃ CHF ₂ (R152a)	1	1	1	1	1
40 1,1-DIFLUOROETHYLENE	C ₂ H ₂ F ₂ (R1132a)	1	1	1	1	1
41 DIMETHYL AMINE	(CH ₃) ₂ NH	1	1	1	1	0
42 DIMETHYL ETHER	(CH ₃) ₂ O	1	1	1	1	1
43 DISILANE	Si ₂ H ₆	9	9	9	1	1
44 ETHANE	C ₂ H ₆	1	1	1	1	1
45 ETHYLAMINE	C ₂ H ₅ NH ₂	1	1	1	1	0
46 ETHYL CHLORIDE	C ₂ H ₅ Cl (R160)	1	1	1	0	1
47 ETHYLENE	C ₂ H ₄	1	1	1	1	1
48 ETHYLENE OXIDE	C ₂ H ₄ O	1	1	1	1	1
49 FLUORINE	F ₂	1	1	2	0	1
50 FLUOROETHANE	C ₂ H ₅ F (R161)	1	1	1	1	1
51 FLUOROMETHANE	CH ₃ F (R41)	1	1	1	1	1
52 TRIFLUOROMETHANE	CHF ₃ (R23)	1	1	1	1	1
53 GERMANE	GeH ₄	9	9	9	1	1
54 HELIUM	He	1	1	1	1	1
55 HEXAFLUOROETHANE	C ₂ F ₆ (R116)	1	1	1	1	1
56 HEXAFLUOROPROPENE	C ₃ F ₆ (R1216)	1	1	1	1	1
57 HYDROGEN	H ₂	9	9	9	1	1

Table A.1 (continued)

Name and gas number	Formula	N	Q	S	A	B
58 HYDROGEN BROMIDE	HBr	9	9	2	0	0
59 HYDROGEN CHLORIDE	HCl	9	9	2	0	0
60 HYDROGEN CYANIDE	HCN	1	1	2	1	1
61 HYDROGEN FLUORIDE	HF	9	9	2	0	0
62 HYDROGEN IODIDE	HI	9	9	2	0	0
63 HYDROGEN SULPHIDE	H ₂ S	9	9	9	1	1
64 ISOBUTANE	CH(CH ₃) ₃	1	1	1	1	1
65 ISOBUTYLENE	CH ₂ :C(CH ₃) ₂	1	1	1	1	1
66 KRYPTON	Kr	1	1	1	1	1
67 METHANE	CH ₄	1	1	1	1	1
68 PROPYLENE	C ₃ H ₄	1	1	1	1	3
69 METHYL BROMIDE	CH ₃ Br (R40B1)	1	1	2	0	1
70 METHYL MERCAPTAN	CH ₃ SH	9	9	9	1	1
71 METHYL SILANE	CH ₃ SiH ₃	9	9	9	1	1
72 METHYLAMINE	CH ₃ NH ₂	1	1	1	1	0
73 NEON	Ne	1	1	1	1	1
74 NITRIC OXIDE	NO	1	1	2	1	0
75 NITROGEN	N ₂	1	1	1	1	1
76 NITROGEN DIOXIDE	NO ₂	1	1	2	1	0
77 NITROUS OXIDE	N ₂ O	1	1	1	1	1
78 NITROGEN TRIFLUORIDE	NF ₃	1	1	1	1	1

Table A.1 (continued)

Name and gas number	Formula	N	Q	S	A	B
79 OCTOFLUOROBUT-2-ENE	C_4F_8	1	1	1	1	1
80 OCTAFLUOROCYCLOBUTANE	C_4F_8 (RC318)	1	1	1	1	1
81 OCTAFLUOROPROPANE	C_3F_8 (R218)	1	1	1	1	1
82 OXYGEN	O_2	1	1	1	1	1
83 PHOSGENE	$COCl_2$	1	1	2	0	1
84 PHOSPHINE	PH_3	9	9	9	1	1
85 PROPANE	C_3H_8	1	1	1	1	1
86 PROPADIENE	C_3H_4	1	1	1	1	1
87 PROPYLENE	C_3H_6	1	1	1	1	1
88 PROPYLENE OXIDE	C_3H_6O	1	1	1	1	1
89 SILANE	SiH_4	9	9	9	1	1
90 SILICON TETRACHLORIDE	$SiCl_4$	1	1	2	0	1
91 SILICON TETRAFLUORIDE	SiF_4	1	1	2	0	1
92 SULPHUR DIOXIDE	SO_2	1	1	1	1	1
93 SULPHUR HEXAFLUORIDE	SF_6	1	1	1	1	1
94 SULPHUR TETRAFLUORIDE	SF_4	1	1	2	0	1
95 TETRAFLUROETHYLENE	C_2F_4 (R1114)	1	1	1	1	1
96 TRICHLOROSILANE	$SiHCl_3$	1	1	2	0	1
97 TRICHLOROTRIFLUOROETHANE	$C_2Cl_3F_3$ (R113)	1	1	1	1	1
98 1,1,1-TRIFLUOROETHANE	CH_3CF_3 (R143a)	1	1	1	1	1
99 TRIMETHYLAMINE	$(CH_3)_3N$	1	1	1	1	0

Table A.1 (continued)

Name and gas number	Formula	N	Q	S	A	B
100 TUNGSTEN HEXAFLUORIDE	WF ₆	1	1	2	0	1
101 VINYL BROMIDE	C ₂ H ₃ Br (R1140B1)	1	1	2	0	3
102 VINYL CHLORIDE	C ₂ H ₃ Cl (R1140)	1	1	2	0	3
103 VINYL FLUORIDE	C ₂ H ₃ F (R1141)	1	1	2	0	3
104 XENON	Xe	1	1	1	1	1

A.4 Groups of gases

Single gases are grouped by their compatibility with cylinder and valve materials, as follows:

Group 1: Gases compatible with all materials (code 11111).

Group 2: Gases compatible with all materials but where the risk of hydrogen embrittlement has to be considered (code 99911).

Group 3: Gases compatible with all materials but requiring alloys containing less than 65 % of copper (code 11113).

Group 4: Gases compatible with all materials but 316 type stainless steels recommended (code 11211).

Group 5: Gases compatible with all materials except brass (code 11110).

Group 6: Gases compatible with all materials except brass and 316 type stainless steels recommended (code 11210).

Group 7: Gases compatible with all materials except aluminium (code 11101).

Group 8: Gases compatible with all materials except aluminium and 316 type stainless steels recommended (code 11201).

Group 9: Gases compatible with all materials except aluminium and brass and 316 type stainless steels recommended (code 11200).

Group 10: Gases compatible with all materials except aluminium, 316 type stainless steels recommended and alloys containing less than 65 % of copper (code 11203).

Group 11: Gases compatible with all materials except aluminium and brass and 316 type stainless steels recommended to consider the risk of hydrogen embrittlement (code 99200).

NOTE *All materials* means materials covered in this document.

Group 1			
These gases are compatible with all materials (Code 11111).			
No.	Gas name	No.	Gas name
3	Argon	47	Ethylene
7	Bromochlorodifluoromethane	48	Ethylene oxide
8	Bromotrifluoromethane	50	Fluoroethane
9	Bromotrifluoroethylene	51	Fluoromethane
10	Butadiene-1,3	52	Trifluoromethane
11	Butadiene-1,2	54	Helium
12	Butane	55	Hexafluoroethane
13	Butene-1	56	Hexafluoropropene
14	Butene-2 (cis)	64	Isobutane
15	Butene-2 (trans)	65	Isobutylene
16	Carbon dioxide	66	Krypton
17	Carbon monoxide	67	Methane
18	Carbon tetrafluoride	73	Neon
19	Carbonyl sulphide	75	Nitrogen
21	Chlorodifluoromethane	77	Nitrous oxide
23	Chloropentafluoroethane	78	Nitrogen trifluoride
24	Chlorotetrafluoroethane	79	Octofluorobut-2-ene
25	Chlorotrifluoroethane	80	Octafluorocyclobutane
26	Chlorotrifluoroethylene	81	Octafluoropropane
27	Chlorotrifluoromethane	82	Oxygen
28	Cyclopropane	85	Propane
30	Dibromodifluoromethane	86	Propadiene
31	Dibromotetrafluoroethane	87	Propylene
33	Dichlorodifluoromethane	88	Propylene oxide
34	Dichlorofluoromethane	92	Sulphur dioxide
36	Dichlorotetrafluoroethane	93	Sulphur hexafluoride
38	1,1-Difluoro-1-chloroethane	95	Tetrafluoroethylene
39	1,1-Difluoroethane	97	Trichlorotrifluoroethane
40	1,1-Difluoroethylene	98	1,1,1-Trifluoroethane
42	Dimethyl ether	104	Xenon
44	Ethane		

Group 2	
These gases are compatible with all materials, but the risk of hydrogen embrittlement shall be considered (code 99911).	
No.	Gas name
4	Arsine
29	Deuterium
32	Diborane
43	Disilane
53	Germane
57	Hydrogen
63	Hydrogen sulphide
70	Methyl mercaptan
71	Methyl silane
84	Phosphine
89	Silane

Group 3	
These gases are compatible with all materials, but require alloys containing less than 65 % of copper (code 11113).	
No.	Gas name
1	Acetylene
68	Propyne

Group 4	
This gas is compatible with all materials, but 316 type stainless steels is recommended (code 11211).	
No.	Gas name
60	Hydrogen cyanide

Group 5	
These gases are compatible with all materials except brass (code 11110).	
No.	Gas name
2	Ammonia
41	Dimethylamine
45	Ethylamine
72	Methylamine
99	Trimethylamine

Group 6	
These gases are compatible with all materials except brass, and 316 type stainless steels are recommended (code 11210).	
No.	Gas name
37	Cyanogen
74	Nitric oxide
76	Nitrogen dioxide

Group 7	
These gases are compatible with all materials except aluminium (code 11101).	
No.	Gas name
22	Chloromethane
46	Ethyl chloride

Group 8	
These gases are compatible with all materials except aluminium, and 316 type stainless steels are recommended (code 11201).	
No.	Gas name
20	Chlorine
49	Fluorine
69	Methyl bromide
83	Phosgene
90	Silicon tetrachloride
91	Silicon tetrafluoride
94	Sulphur tetrafluoride
96	Trichlorosilane
100	Tungsten hexafluoride

Group 9	
These gases are compatible with all materials except aluminium, and brass and 316 type stainless steels are recommended (code 11200).	
No.	Gas name
5	Boron trichloride
6	Boron trifluoride
35	Dichlorosilane

Group 10	
These gases are compatible with all materials except aluminium, and 316 type stainless steels and alloys containing less than 65 % of copper are recommended (code 11203).	
No.	Gas name
101	Vinyl bromide
102	Vinyl chloride
103	Vinyl fluoride

Group 11	
These gases are compatible with all materials except aluminium and brass, and 316 type stainless steels are recommended to consider the risk of hydrogen embrittlement (code 99200).	
No.	Gas name
58	Hydrogen bromide
59	Hydrogen chloride
61	Hydrogen fluoride
62	Hydrogen iodide

Bibliography

- [1] United Nations *Recommendations on the Transport of Dangerous Goods – Model Regulations*.
- [2] ISO 4706, *Gas cylinders — Refillable welded steel cylinders — Test pressure 60 bar and below*
- [3] ISO 6361-2, *Wrought aluminium and aluminium alloys — Sheets, strips and plates — Part 2: Mechanical properties*
- [4] ISO 7866, *Gas cylinders — Refillable seamless aluminium alloy gas cylinders — Design, construction and testing*
- [5] ISO 9328-5, *Steel flat products for pressure purposes — Technical delivery conditions — Part 5: Weldable fine grain steels, thermomechanically rolled*
- [6] ISO 9809-1, *Gas cylinders — Design, construction and testing of refillable seamless steel gas cylinders and tubes — Part 1: Quenched and tempered steel cylinders and tubes with tensile strength less than 1 100 MPa*
- [7] ISO 9809-2, *Gas cylinders — Design, construction and testing of refillable seamless steel gas cylinders and tubes — Part 2: Quenched and tempered steel cylinders and tubes with tensile strength greater than or equal to 1 100 MPa*
- [8] ISO 9809-3, *Gas cylinders — Design, construction and testing of refillable seamless steel gas cylinders and tubes — Part 3: Normalized steel cylinders and tubes*
- [9] ISO 9809-4, *Gas cylinders — Refillable seamless steel gas cylinders — Design, construction and testing — Part 4: Stainless steel cylinders with an Rm value of less than 1 100 MPa*
- [10] ISO 11118, *Gas cylinders — Non-refillable metallic gas cylinders — Specification and test methods*
- [11] ISO 11120, *Gas cylinders — Refillable seamless steel tubes of water capacity between 150 l and 3000 l — Design, construction and testing*
- [12] ISO 11439, *Gas cylinders — High pressure cylinders for the on-board storage of natural gas as a fuel for automotive vehicles*
- [13] ISO 15510, *Stainless steels — Chemical composition*
- [14] EIGA 161/16, *Gas compatibility with aluminium alloy cylinders*
- [15] EIGA 95 *Avoidance of failure of CO and of CO/CO₂ mixtures cylinders*
- [16] EIGA 120/14, *Carbon monoxide and syngas pipeline systems*
- [17] EN 10088-1, *Stainless steels — Part 1: List of stainless steels*
- [18] CGA [V-17], *Guideline for Handling and Use of CGA 630/710 Series Ultra High Integrity Service Connections (Formerly TB-9)*

(Continued from second cover)

For the purpose of deciding whether a particular requirement of this standard is complied with the final value, observed or calculated, expressing the result of a test or analysis shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (*revised*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Catalogue' and 'Standards: Monthly Additions'.

This Indian Standard has been developed from Doc No.: MED 16 (17107).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002	{ 2323 7617 2323 3841
Eastern : 1/14 C.I.T. Scheme VII M, V.I.P. Road, Kankurgachi KOLKATA 700054	{ 2337 8499, 2337 8561 2337 8626, 2337 9120
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg CHANDIGARH 160019	{ 265 0206 265 0290
Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113	{ 2254 1216, 2254 1442 2254 2519, 2254 2315
Western : Manakalaya, E9 MIDC, Marol, Andheri (East) MUMBAI 400093	{ 2832 9295, 2832 7858 2832 7891, 2832 7892

Branches : AHMEDABAD. BENGALURU. BHOPAL. BHUBANESHWAR. COIMBATORE.
DEHRADUN. DURGAPUR. FARIDABAD. GHAZIABAD. GUWAHATI.
HYDERABAD. JAIPUR. JAMMU. JAMSHEDPUR. KOCHI. LUCKNOW.
NAGPUR. PARWANOO. PATNA. PUNE. RAIPUR. RAJKOT. VISAKHAPATNAM.