
वस्त्रादि — सूती कैलिको — विशिष्टि
(दूसरा पुनरीक्षण)

**Textiles — Cotton Calico —
Specification**
(*Second Revision*)

ICS 59.080.30

© BIS 2022



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुरशाह ज़फर मार्ग, नई दिल्ली -110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI-110002
www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard (Second Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Man-Made Fibres, Cotton and their Products Sectional Committee had been approved by the Textiles Division Council.

Calico fabric is a plain-woven textile, made from half-processed and unbleached cotton fibres. It is a coarse and rough fabric, but not as sturdy as denim or canvas, nor as fine as Muslin.

This standard was originally published in 1960 and was subsequently revised in 1973. The standard has again been revised. This revision is based on IND/TC/0040 (c) 'Calico, Cotton', issued by the Ministry of Defence, Government of India.

The following changes have been incorporated in the revised standard.

- a) All Amendments have been incorporated.
- b) Tolerances of end per dm, picks per dm and width have been modified.
- c) BIS certification marking clause has been modified.
- d) References to Indian Standards have been updated.

The composition of the Committee responsible for the formulation of this standard is given in Annex B.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard
TEXTILES — COTTON CALICO — SPECIFICATION
(Second Revision)

1 SCOPE

1.1 This standard prescribes constructional details and other particulars of cotton calico, bleached or dyed used for the borders of mosquito nets, and in the fabrication of ground sheets.

1.2 This standard does not specify the general appearance, feel, etc, of the cloth (*see* also **4.3**).

2 REFERENCES

2.1 The standards listed in Annex A contain provisions which, through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of the standards indicated in Annex A.

3 MANUFACTURE

3.1 Yarn — The cotton yarn used in the manufacture of the cloth shall be satisfactory in evenness and reasonably free from neps and spinning defects.

3.2 Cloth — The cloth shall be bleached or dyed to suitable shades as agreed to between the buyer and the seller. The dyeing shall be free from streaks and stains. If bleached it shall have a full bleached finish. It shall be free from blueing or optical whitening agents.

3.2.1 The cloth shall be free from dressing and filling materials and from substances liable to cause subsequent tendering.

NOTE — The desired whiteness of cloth shall be achieved only by imparting full bleached finish free from any blueing or whitening agents, if desired by the buyer.

3.2.2 The cloth, when visually examined shall be reasonably free from spinning, weaving and processing defects.

4 REQUIREMENTS

4.1 Construction — The cloth shall comply with the requirements specified in Table 1 excepting the count of warp and weft which have been given only for guidance.

4.2 Chemical and other requirements of the cloth shall be as given in Table 2.

4.3 Sealed Sample — If, in order to illustrate, indeterminable characteristics such as general appearance, lustre, feel and shade of the cotton calico, a sample has been agreed upon and sealed, the supply shall be in conformity with the sample in such respects.

4.3.1 The custody of the sealed sample shall be a matter of prior agreement between the buyer and the seller.

5 MARKING

5.1 The cloth shall be marked with the following:

- a) Name of the material;
- b) Width and length of the piece;
- c) Manufacturer's name, initials or trade-mark, if any; and
- d) Year of manufacture.

Table 1 Constructional Particulars of Cotton Calico
(Clause 4.1)

Approximate Count of Yarn (Cotton Count (tex))		Ends per dm	Picks per dm	Mass g/m ²	Breaking Strength on 5 × 20 cm Strip, N (kgf), Min		Length, m, Min	Width, cm	Weave
Warp (1)	Weft (2)	(3)	(4)	(5)	Warp (6)	Weft (7)	(8)	(9)	(10)
23s (26)	23s (26)	268	220	120	353 (36)	216 (22)	36 or as agreed	91 or as agreed	Plain
Tolerance, Percent	—	+ 5 - 2.5	+ 5 - 2.5	+ 5 - 2.5	—	—	—	± 2	—
Method of Test	—	← IS 1963 →	IS 1964	← IS 1969 (Part 1) →	← IS 1954 →	Visual			

Table 2 Chemical Requirements of Cotton Calico
(Clause 4.2)

Sl No.	Characteristic	Requirement	Method of Test
(1)	(2)	(3)	(4)
i)	Colour fastness to light (Dyed fabrics only) (<i>see</i> Note 1)	5 or better	IS/ISO 105-B01 or IS/ISO 105-B02
ii)	Colour fastness to washing (Dyed fabrics only)	4 or better	IS/ISO 105-C10 [Test Number A (1)]
iii)	Scouring loss, percent, <i>Max</i>	2.0	IS 1383 (Mild method)
iv)	<i>pH</i> value	6.0 to 8.5	IS 1390
v)	Shrinkage or elongation, percent, <i>Max</i>	2.0	IS 2977
vi)	Iron content, Percent, <i>Max</i> (<i>see</i> Note 2)	0.05	IS 1039
vii)	Copper content, Percent, <i>Max</i> (<i>see</i> Note 2)	0.001	IS 1039
viii)	Manganese content, Percent, <i>Max</i> (<i>see</i> Note 2)	0.002	IS 1039

NOTES

- 1 In case of dispute, the colour fastness to light shall be determined by the method prescribed in IS/ISO 105-B01.
- 2 To be determined only when the cloth is used for the fabrication of ground sheet.

5.1.1 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the product(s) may be marked with the Standard Mark.

6 PACKING

The cloth shall be packed in bales or cases in conformity with the procedure laid down in IS 1347 or in IS 293, as required.

7 SAMPLING

7.1 For determining the conformity in respect of the physical characteristics, namely, ends and picks, mass per square metre, breaking load,

IS 1544 : 2022

width and length, the scale of sampling and the criteria for conformity as given in IS 3919 shall be followed.

7.2 For ascertaining the conformity in respect of chemical requirements (*see* Table 2), the scale of sampling and criteria for conformity as given in IS 5463 shall be followed.

ANNEX A (Clause 2.1)

LIST OF REFERRED INDIAN STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
293 : 1980	Code for seaworthy packaging of cotton yarn and cloth (<i>third revision</i>)	1969 (Part 1) : 2018	Textiles — Tensile properties of fabrics — Part 1 Determination of maximum force and elongation at maximum force using the strip method (<i>fourth revision</i>)
1039 : 1989	Textiles — Estimation of small quantities of copper, iron, manganese, chromium and zinc (<i>first revision</i>)	2977 : 1989	Fabrics (other than wool) — Method for determination of dimensional changes on soaking in water (<i>first revision</i>)
1347 : 1972	Specification for inland packaging of cotton cloth and yarn (<i>first revision</i>)	3919 : 1966	Methods for sampling cotton fabrics for determination of physical characteristics
1383 : 1977	Methods for determination of scouring loss in grey and finished cotton textile materials (<i>first revision</i>)	5463 : 2022	Methods for sampling of cotton fabrics for chemical tests (<i>first revision</i>)
1390 : 2022	Textiles — Determination of pH of aqueous extract (<i>third revision</i>)	IS/ISO 105-B01 : 2014	Textiles — Tests for colour fastness — Part B01 Colour fastness to light: Daylight
1954 : 1990	Determination of length and width of woven fabrics — Methods (<i>second revision</i>)	IS/ISO 105-B02 : 2014	Textiles — Tests for colour fastness — Part B02 Colour fastness to artificial light: Xenon arc fading lamp test
1963 : 1981	Methods for determination of threads per unit length in woven fabrics (<i>second revision</i>)	IS/ISO 105-C10 : 2006	Textiles — Tests for colour fastness Part C10 Colour fastness to washing with soap or soap and soda
1964 : 2001	Textiles — Methods for determination of mass per unit length and mass per unit area of (<i>second revision</i>)		

ANNEX B*(Foreword)***COMMITTEE COMPOSITION**

Man-Made Fibers, Cotton and their Products Sectional Committee,
TXD 31

<i>Organization</i>	<i>Representative(s)</i>
ICAR – Central Institute for Research on Cotton Technology, Mumbai	DR P. K. MANDHYAN (<i>Chairman</i>)
Ahmedabad Textile Industry’s Research Association, Ahmedabad	SHRIMATI DEEPALI PLAWAT SHRI JIGAR DAVE (<i>Alternate</i>)
Association of Synthetic Fibre Industries, New Delhi	SHRI M. S. VERMA
AYM Syntex Ltd, Dadra and Nagar Haveli	SHRI ARNAB SAMANTHA SHRI SAUGATA DAS (<i>Alternate</i>)
Confederation of Indian Textile Industry, New Delhi	SHRI D. K. NAIR SHRI SHAJU MANGALAM (<i>Alternate</i>)
Consumer Guidance Society of India, Mumbai	DR SITARAM DIXIT DR M. S. KAMATH (<i>Alternate</i>)
Cotton Association of India, Mumbai	SECRETARY
Defence Materials and Stores Research and Development Establishment, Kanpur	SHRI ASHOK KUMAR YADAV SHRI BISWA RANJAN DAS (<i>Alternate</i>)
Grasim Industries Limited, Vadodara	SHRI AJAY SARDANA DR ROHITASVA KUMAR (<i>Alternate</i>)
ICAR – Central Institute for Research on Cotton Technology, Mumbai	DR SENTHIL KUMAR DR A ARPUTHARAJ (<i>Alternate</i>)
JCT Limited, Phagwara	SHRI KHUSHWINDER SINGH DHILLON SHRI ARWINDER SINGH (<i>Alternate</i>)
North India Textile Mills Association, Chandigarh	SHRI SANJAY GARG SHRI SIDHARTHA KHANNA (<i>Alternate</i>)
Northern India Textile Research Association, Ghaziabad	SHRI SANJEEV SHUKLA SHRIMATI NEHA KAPIL (<i>Alternate</i>)
Office of Textile Commissioner, Mumbai	SHRI SOURABH KULKARNI SHRI PRANAV PARASHAR (<i>Alternate</i>)

IS 1544 : 2022

<i>Organization</i>	<i>Representative(s)</i>
Reliance Industries Limited, Mumbai	SHRI AJAY GUPTA SHRI KESHAV P PAAREEK (<i>Alternate</i>)
Textile Committee, Mumbai	SHRI J. D. BARMAN SHRI P. N. S. SIVAKUMAR (<i>Alternate</i>)
The Bombay Textile Research Association, Mumbai	SHRI R. A. SHAIKH SHRIMATI PRAGATI KULKARNI (<i>Alternate</i>)
The Cotton Corporation of India Ltd, Navi Mumbai	SHRI P. N. PILLEWAR SHRI V. K. SINHA (<i>Alternate</i>)
The Cotton Textile Export Promotion Council, Mumbai	SHRI SIDDARTHA RAJGOPAL
The Southern India Mills Association, Coimbatore	SHRI D. SURESH ANAND KUMAR
The Synthetic & Rayon Textile Export Promotion Council, Mumbai	SHRI S. BALARAJU
The Synthetic and Art Silk Mills Research Association, Mumbai	DR MANISHA MATHUR SHRIMATI ASHWINI A. SUDAM (<i>Alternate</i>)
Veermata Jijabai Technological Institute, Mumbai	DR (SMT) SURANJANA GANGOPADHYAY
In personal capacity (<i>D-618, Maruti Paradise, Sector - 15, CBD-Belapur, Navi Mumbai - 400614.Maharastra.</i>)	SHRI A. SATHEESAN
BIS Directorate General	SHRI J. K. GUPTA, Scientist E and Head (Textiles) [Representing Director General (<i>Ex-officio</i>)]

Member Secretary
SHRI MAYUR KATIYAR
Scientist 'B' (Textiles), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website- www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 31(18058).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

Telephones

Central: 601/A Konnectus Tower-I, 6th Floor
DMRC Building, Bhavbhuti Marg, New Delhi 110 002

2323 7617

Eastern: 8th Floor, Plot No. 7/7 & 7/8, CP Block, Sector V
Salt Lake, Kolkata 700091

236 7012, 2320 9474

Northern: Plot No. 4A, Sector 27-B, Madhya Marg
Chandigarh 160 019

265 0206, 265 0290

Southern: C I T Campus, IV Cross Road, Taramani
Chennai 600 113

2254 1442, 2254 1216

Western: Plot No. E-9, Road No. 8, MIDC, Andheri (East)
Mumbai 400 093

28218093

Branches: AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HIMACHAL PRADESH, HUBLI, HYDERABAD, JAIPUR, JAMMU & KASHMIR, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PANIPAT, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VISHAKHAPATNAM.