
लघु जलयान — पेटा निर्माण तथा
स्कैंटलिंग

भाग 1 पदार्थ : थर्मोसेटिंग रेज़िन, कॉच-रेशा
प्रबलन, संदर्भ लॉमिनेट

**Small Craft — Hull Construction and
Scantilings**

**Part 1 Materials : Thermosetting Resins,
Glass-Fibre Reinforcement, Reference
Laminate**

ICS 47.080

© BIS 2023
© ISO 2000



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली -

110002

MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002

www.bis.gov.in www.standardsbis.in

NATIONAL FOREWORD

This Indian Standard which is identical with ISO 12215-1 : 2000 'Small craft — Hull construction and scantlings — Part 1 Materials: Thermosetting resins, glass-fibre reinforcement, reference laminate' issued by International Organization for Standardization (ISO), was adopted by the Bureau of Indian Standards on the recommendations of the Inland Harbour Crafts and Fishing Vessels Sectional Committee and approval of the Transport Engineering Division Council.

This standard has been issued in several parts. Other parts in this series are:

- Part 2 Materials : Core materials for sandwich construction, embedded materials
- Part 3 Materials : Steel, aluminium alloys, wood, other materials
- Part 4 Workshop and manufacturing
- Part 6 Structural arrangements and details
- Part 8 Rudders
- Part 9 Sailing craft appendages

The text of ISO Standard may be approved for publication as an Indian Standard without deviations. Certain conventions are, however, not identical to those used in Indian Standards. Attention is particularly drawn to the following:

- a) Wherever the words 'International Standard' appear referring to this standard, they should be read as 'Indian Standard'.
- b) Comma (,) has been used as a decimal marker while in Indian Standards, the current practice is to use a point (.) as the decimal marker.

In this adopted standard, reference appears to certain International Standards for which Indian Standards also exist. The corresponding Indian Standards, which are to be substituted in their respective places, are listed below along with their degree of equivalence for the edition indicated:

<i>International Standard</i>	<i>Corresponding Indian Standard</i>	<i>Degree of Equivalence</i>
ISO 62 : 1999 Plastics — Determination of water absorption.	IS 13360 (Part 8/Sec 1) : 1997 Plastics — Methods of testing: Part 8 Permanence/chemical properties, Section 1 Determination of water absorption.	Identical
ISO 75-1 : 1993 Plastics — Determination of temperature of deflection under load — Part 1: General test method.	IS 13360 (Part 6/ Sec 3) : 2017 Plastics — Methods of testing: Part 6 Thermal properties, Section 3 Determination of temperature of deflection under load — General test method (<i>second revision</i>)	Identical

<i>International Standard</i>	<i>Corresponding Indian Standard</i>	<i>Degree of Equivalence</i>
ISO 75-2 : 1993 Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite.	IS 13360 (Part 6/Sec 17) : 2017 Plastics — Methods of testing: Part 6 Thermal properties, Section 17 Determination of temperature of deflection under load — Plastics and ebonite (<i>second revision</i>)	Identical
ISO 178 : 1993 Plastics — Determination of flexural properties.	IS 13360 (Part 5/Sec 7) : 2017 Plastics — Determination of flexural properties.	Identical
ISO 527-1 Plastics — Determination of tensile properties — Part 1: General principles.	IS 13360 (Part 5/Sec 1) : 2021 Plastics — Determination of tensile properties: Part 1 General principles.	Identical
ISO 527-4 Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites.	IS 13360 (Part 5/Sec 25) : 2004 Plastics — Determination of tensile properties: Part 4 Test conditions for isotropic and orthotropic fibre-reinforced plastic composites.	Identical
ISO 1675 : 1985 Plastics — Liquid resins — Determination of density by the pycnometer method.	IS 13360 (Part 3/Sec 7) : 1999 Plastics — Liquid resins — Determination of density by the pycnometer method.	Identical
ISO 1887 : 1995 Textile glass — Determination of combustible-matter content.	IS 17600 : 2021 Textile glass — Determination of combustible-matter content.	Identical
ISO 1889 : 1997 Reinforcement yarns — Determination of linear density.	IS 17298 : 2019 Reinforcement yarns — Determination of linear density.	Identical
ISO 2078:1993 Textile glass — Yarns — Designation.	IS 17300 : 2019 Textile glass — Yarns — Designation.	Identical
ISO 2555 : 1989 Plastics — Resins in the liquid state or as emulsions or dispersions — Determination of apparent viscosity by the brookfield test method.	IS 13360 (Part 11/Sec 10) : 1999 Plastics — Resins in the liquid state or as emulsions or dispersions — Determination of apparent viscosity by the brookfield test method.	Identical
ISO 2811-1 : 1997 Paints and varnishes — Determination of density — Part 1: Pycnometer method.	IS 101 (Part 1/Sec 7) : 2020 Methods of sampling and test for paints, varnishes and related products: Part 1 Test on liquid paints (general and physical), Section 7 Mass per 10 litres — Determination of density — Pycnometer method	Identical
ISO 3344 : 1997 Reinforcement products — Determination of moisture content.	IS 17313 : 2019 Reinforcement products — Determination of moisture content.	Identical
ISO 3374 : 2000 Reinforcement products — Mats and fabrics — Determination of mass per unit area.	IS 17309 : 2019 Reinforcement products — Mats and fabrics — Determination of mass per unit area.	Identical

<i>International Standard</i>	<i>Corresponding Indian Standard</i>	<i>Degree of Equivalence</i>
ISO 8666 Small craft — Principal data.	IS 17469 : 2020 Small craft — Principal data.	Identical with ISO 8666 : 2016

The technical committee has reviewed the provisions of following International Standards referred in this adopted standard and has decided that it is acceptable for use in conjunction with this standard:

<i>International Standard</i>	<i>Title</i>
ISO 2535:1997	Plastics — Unsaturated polyester resins — Measurement of gel time at 25 °C.
ISO 2884-1:1999	Paints and varnishes — Determination of viscosity using rotary viscometers — Part 1: Cone-and-plate viscometer operated at a high rate of shear.
ISO 3521:1997	Plastics — Unsaturated polyester and epoxy resins — Determination of overall volume shrinkage.
ISO 4901:1985	Reinforced plastics based on unsaturated polyester resins — Determination of residual styrene monomer content.
ISO 14130 : 1997	Fibre-reinforced plastic composites — Determination of apparent interlaminar shear strength by short-beam method.
EN 59 : 1977	Glass reinforced plastics — Measurement of hardness by means of a barcol-impressor.
DIN 16945:1989	Testing of resins, hardeners and accelerators, and catalysed resins.
ASTM D 4255	Testing in-plane shear properties of composite laminates.

Attention is drawn to the possibility that some of the elements of this standard may be the subject of patent rights. The Bureau of Indian Standards shall not be held responsible for identifying any or all such patent rights.

This standard also makes a reference to the BIS Certification Marking. Details of which are given in National Annex A.

In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off it shall be done in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'.

Indian Standard
SMALL CRAFT — HULL CONSTRUCTION AND
SCANTLINGS
**PART 1 MATERIALS : THERMOSETTING RESINS,
GLASS-FIBRE REINFORCEMENT, REFERENCE
LAMINATE**

1 Scope

This part of ISO 12215 is applicable to thermosetting resins and glass-fibre reinforcement used in the construction of small craft with a length of the hull (L_H) of up to 24 m, in accordance with ISO 8666. This part of ISO 12215 specifies the minimum requirements for material properties of glass reinforcement and resin matrix and the reference laminate made thereof.

This part of ISO 12215 may be applicable to materials other than those specified, provided that the minimum requirements and properties of the reference laminate are met.

NOTE The underlying reason for preparing this International Standard is to harmonize existing standards and recommended practices for loads on the hull and the dimensioning of small craft because they differ too considerably and thus limit general worldwide acceptability of boats.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 12215. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 12215 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 62:1999, *Plastics — Determination of water absorption.*

ISO 75-1:1993, *Plastics — Determination of temperature of deflection under load — Part 1: General test method.*

ISO 75-2:1993, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite.*

ISO 178:1993, *Plastics — Determination of flexural properties.*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles.*

ISO 527-4, *Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites.*

ISO 1675:1985, *Plastics — Liquid resins — Determination of density by the pycnometer method.*

ISO 1887:1995, *Textile glass — Determination of combustible-matter content.*

ISO 1889:1997, *Reinforcement yarns — Determination of linear density.*

ISO 2078:1993, *Textile glass — Yarns — Designation.*

ISO 2535:1997, *Plastics — Unsaturated polyester resins — Measurement of gel time at 25 °C.*

ISO 2555:1989, *Plastics — Resins in the liquid state or as emulsions or dispersions — Determination of apparent viscosity by the Brookfield Test method.*

ISO 2811-1:1997, *Paints and varnishes — Determination of density — Part 1: Pyknometer method.*

ISO 2884-1:1999, *Paints and varnishes — Determination of viscosity using rotary viscometers — Part 1: Cone-and-plate viscometer operated at a high rate of shear.*

ISO 3344:1997, *Reinforcement products — Determination of moisture content.*

ISO 3374:2000, *Reinforcement products — Mats and fabrics — Determination of mass per unit area.*

ISO 3521:1997, *Plastics — Unsaturated polyester and epoxy resins — Determination of overall volume shrinkage.*

ISO 4901:1985, *Reinforced plastics based on unsaturated polyester resins — Determination of residual styrene monomer content.*

ISO 8666:—¹⁾, *Small craft — Principal data.*

ISO 14130:1997, *Fibre-reinforced plastic composites — Determination of apparent interlaminar shear strength by short-beam method.*

EN 59:1977, *Glass reinforced plastics — Measurement of hardness by means of a Barcol-impressor.*

DIN 16945:1989, *Testing of resins, hardeners and accelerators, and catalysed resins.*

ASTM D 4255, *Testing in-plane shear properties of composite laminates.*

3 Terms and definitions

For the purposes of this part of ISO 12215, the following terms and definitions apply.

3.1 reinforcement

strong, inert material, usually fibres, strongly bonded into a resin to achieve enhanced strength, stiffness and impact resistance

NOTE Reinforcement fibres are commonly available in the following forms:

- chopped strand mat, formed of strands cut to a short length, randomly distributed, without intentional orientation, and held together by a binder;
- continuous mat, formed of strands, randomly distributed, without intentional orientation, and held together by a binder that is not soluble in styrene;
- roving, which is a collection of parallel strands (multistrand roving) or parallel filaments (multifilament roving) assembled without intentional twist;
- woven roving, which is a fabric woven from rovings;
- multidirectional roving, which is a fabric of crossply rovings in two or more directions;
- unidirectional roving, which is a fabric of rovings arranged in one direction;
- cloth, which is a fabric woven from yarn.

1) To be published.

3.2

resin

reactive synthetic that in its initial stage is a liquid, but during cure is transformed into a solid

NOTE Resins are used in different formulations:

- as gelcoat for the mould side of the laminate, giving a smooth, flexible and water-resistant surface;
- as a matrix material for the reinforcing fibres of the laminate;
- as a topcoat for the non-gelcoated surface to achieve a flexible, water-resistant and tack-free surface;
- as a matrix material for fillers and putties.

3.3

laminate

material composed of successive bonded layers of resin and fibre or other reinforcing substance

4 Requirements for material properties of small craft

4.1 Reinforcement fibres

4.1.1 The reinforcement used as a reference for this International Standard shall be E-glass in accordance with ISO 2078. Other types of glass fibres may be used if the minimum properties of E-glass are met or surpassed and the laminate itself is of equal or higher mechanical property.

4.1.2 The finish and binder of glass fibres shall be compatible with the matrix material used.

4.1.3 Fibres made of material other than glass may be used, provided that their properties are suitable for the intended purpose.

The fibre reinforcement manufacturer shall declare in writing that

- the material upon delivery complies with the requirements of 4.1 and the applicable part of Table 1;
- the actual tolerances of the material as delivered are in accordance with Table 1.

Further the manufacturer shall provide written information on

- the binder and sizing, if applicable;
- the compatibility and/or non-compatibility (if known) that the material with other materials to be used in the laminate;
- the specific requirements concerning storage;
- the specific requirements concerning use.

The boat manufacturer shall keep this information with the documentation established for the small craft.

Table 1 — Properties of fibre reinforcement

Property	Test method	Requirement
Moisture content on delivery % max.		
Roving		0,2
Chopped strand mat	ISO 3344	0,5
Fabrics		0,2
Mass per unit, tolerance on nominal value %		
Roving (length)	ISO 1889	– 5 to + 10
Chopped strand mat (area)	ISO 3374	– 5 to + 10
Woven roving (area)	ISO 3374	– 5 to + 10
Loss on ignition, nominal value % max.	ISO 1887	+ 20

NOTE Equivalent methods for determining moisture content and mass including permissible tolerances should be used for materials other than glass fibre.

4.2 Resin

4.2.1 Properties

The properties of liquid gelcoat, topcoat and laminating resins shall comply with the requirements of Table 2, as applicable.

Table 2 — Properties of liquid resins

Property	Test method	Requirement Tolerance on nominal value specified by the manufacturer ^a %
Viscosity	(1) Brookfield, ISO 2555 or (2) Cone/plate, ISO 2884-1	± 20
Monomer content	ISO 4901	± 5
Gel time (specify activator and initiator and percentage of each, and ambient temperature)	ISO 2535	± 20
Density	ISO 1675 or ISO 2811-1	± 5
Mineral content (laminating resins only)	DIN 16945 ^b	± 5

^a The tolerance stated in percent (%) shall be understood as a percentage of the specified margin.
^b ISO standard pending.

4.2.2 Gelcoat resins

Gelcoat base resins when cured shall meet the requirements of Type A in Table 3.

For specific applications, in order to achieve superior properties as to elongation and/or reduced water absorption, resins used for gelcoats and skin coats may deviate as to their minimum properties from the requirements of Type A resin in Table 3.

Table 3 — Properties of cured resins
(after a postcure schedule of 24 h at 50 °C)

Property	Test method	Requirement			
		A	B ^a	C ^a	
Ultimate tensile strength	MPa min.	ISO 527-1, ISO 527-4	55	45	45
Elongation at break	% min.	ISO 527-1, ISO 527-4	2,5	1,5	1,2
Ultimate flexural strength	MPa min.	ISO 178	100	80	80
Flexural modulus	MPa min.	ISO 178	2 700	2 700	2 700
Heat deflection temperature	°C min.	ISO 75-1, ISO 75-2:1993 Method A	60	60	53
Water absorption	mg max.	ISO 62 ^b	80	100	100
Overall volume shrinkage		ISO 3521	Nominal value specified by the manufacturer + 5 %		
Barcol hardness ^c (Impressor 934-1)	min.	EN 59	35	35	35
The requirements are not applicable to resins used in the formulations of fillers and putties. The tolerances stated in percent (%) shall be understood as a percentage of the specified margin.					
^a The requirements for laminating resins Types B and C are minima of different applications of determining required scantlings.					
^b Test sample: 50 mm ⁺¹ ₀ mm × 50 mm ⁺¹ ₀ mm × 4 mm ^{+0,2} ₀ mm. Distilled water. Exposure time 28 days at 23 °C.					
^c Resin systems may deviate from these values, provided a minimum value of 30 is achieved and adequate cure can be demonstrated by the manufacturer.					

4.2.3 Topcoat resins

The formulation of a topcoat resin as to its physical properties shall consider the specific applications for which it is intended and shall meet the respective requirements for Type A, B or C, for instance

- exposure to weathering;
- oily bilge water;
- tack-free surface only;
- suitability as a paint.

4.2.4 Laminating resins

Laminating resins, including resin blends with permissible amounts of fillers and other additives when cured shall meet the respective requirements specified in Table 3.

4.2.5 Fillers, additives

Quantities and types of fillers and/or additives shall allow sufficient wet out of reinforcement fibres within the resin manufacturer's specified gel time.

4.2.6 Catalysts, accelerators

The use of catalysts and accelerators shall be as specified or recommended by the resin manufacturer.

4.2.7 Declaration

The resin manufacturer shall declare in writing that the material upon delivery complies with the requirements of 4.2, Tables 2 and 3 appropriate to the manufacturer's specified Type A, B or C resin.

If the resin manufacturer claims for exemption according to Table 3, i.e. that the requirements are not applicable to resins used in the formulations of fillers and putties, he shall state the mechanical properties achieved and shall provide information on the intended application of the resin.

The manufacturer of the resin, catalyst, accelerator, filler or other substances used in the laminate shall each provide written information on

- the compatibility or incompatibility (if known) of the material supplied with other materials used in the laminate;
- the shelf life of the material;
- the specific requirements concerning storage;
- the specific requirements concerning use.

The boat manufacturer shall keep this information with the documentation established for the small craft.

4.3 Reference laminate

4.3.1 The mechanical properties of the reference laminate as listed in Table 4 shall be achieved by any manufacturing process.

Table 4 — Minimum mechanical properties of reference laminate ^a

Property	Test method	Requirement ^b MPa
Ultimate tensile strength	ISO 527-1, ISO 527-4	80
Tensile modulus	ISO 527-1, ISO 527-4	6 350
Ultimate flexural strength	ISO 178	135
Flexural modulus	ISO 178	5 200
In-plane shear	ASTM D 4255	50
Apparent interlaminar shear strength (short-beam shear)	ISO 14130	15
^a The reference laminate shall consist of glass chopped-strand mat and resin with a glass content not exceeding 30 % by mass of the fully cured laminate. ^b The test data shall be achieved after a post cure schedule of max. 24 h at max. 50 °C.		

4.3.2 The resin manufacturer shall declare in writing that the mechanical properties of Table 4 are capable of being fulfilled.

The resin manufacturer shall provide detailed information with respect to other substances (e.g. catalyst, accelerator, fillers, additives, etc.) used in the fabrication process of the reference laminate.

NATIONAL ANNEX A
(National Foreword)

A-1 BIS CERTIFICATION MARKING

A-1.1 The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the BIS Act, 2016 and the Rules and Regulations framed thereunder, and the product(s) may be marked with the Standard Mark.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website- www.bis.gov.in or www.standardsbis.com.

This Indian Standard has been developed from Doc No.: TED 18 (17789).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : Plot No. E-9, Road No.-8, MIDC, Andheri (East), Mumbai 400093	{ 2821 8093

Branches : AHMEDABAD. BENGALURU. BHOPAL. BHUBANESHWAR. CHANDIGARH. CHENNAI. COIMBATORE. DEHRADUN. DELHI. FARIDABAD. GHAZIABAD. GUWAHATI. HIMACHAL PRADESH. HUBLI. HYDERABAD. JAIPUR. JAMMU & KASHMIR. JAMSHEDPUR. KOCHI. KOLKATA. LUCKNOW. MADURAI. MUMBAI. NAGPUR. NOIDA. PANIPAT. PATNA. PUNE. RAIPUR. RAJKOT. SURAT. VISAKHAPATNAM.