

क्यूप्रस ऑक्साइड (फन्गीसाईडल ग्रेड),
तकनीकी — विशिष्टि
(दूसरा पुनरीक्षण)

Cuprous Oxide (Fungicidal Grade),
Technical — Specification
(Second Revision)

ICS 65.100.30

© BIS 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002

www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard (Second Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Pesticides Sectional Committee had been approved by the Food and Agriculture Division Council.

Cuprous oxide (fungicidal grade), technical, is extensively used for agricultural and horticultural purposes in fungicidal formulations.

This standard was first published in 1960. In 1973, the standard was first revised so as to bring the standard up-to-date, taking into consideration the views of the industry and consumers.

In this revision, the standard has been brought out in the latest style and format of the Indian Standards as well as references to Indian Standards wherever applicable have been updated.

In the preparation of this standard, due consideration has been given to the provisions of the *Insecticides Act*, 1968 and the rules framed thereunder. However, this standard is subject to the restrictions imposed under these, wherever applicable.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. This number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Indian Standard***CUPROUS OXIDE (FUNGICIDAL GRADE), TECHNICAL —
SPECIFICATION***(Second Revision)***1 SCOPE**

This standard prescribes the requirements and the methods of sampling and test for methods of test for cuprous oxide, technical, used in the formulation of fungicides for agricultural and horticultural purposes.

2 REFERENCES

The standards given below contain provisions which through reference in this text, constitute provision of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards:

<i>IS No.</i>	<i>Title</i>
IS 264 : 2005	Nitric acid — Specification (<i>third revision</i>)
IS 265 : 2021	Hydrochloric acid — Specification (<i>fifth revision</i>)
IS 296 : 2023	Sodium carbonate, anhydrous — Specification (<i>fourth revision</i>)
IS 1070 : 2023	Reagent grade water — Specification (<i>fourth revision</i>)
IS 6940 : 1982	Methods of test for pesticides and their formulations (<i>first revision</i>)
IS 10946 : 1996	Methods of sampling for technical grade pesticides (<i>first revision</i>)

3 REQUIREMENTS**3.1 Description**

The material shall be essentially cuprous oxide. It shall be in the form of a dry powder, or in such a form that it is possible to easily powder it by crushing under a palette knife, without a grinding action. It shall have a yellow-orange to orange-red

colour and shall be free from adulterants and foreign matter.

3.2 The material shall also comply with the requirement given in [Table 1](#).

4 PACKING

The material shall be packed according to **IS 8190 (Part 1)**.

**5 MARKING**

5.1 The containers shall be securely closed and shall bear legibly and indelibly the following information:

- Name of the material;
- Name and address of the manufacturer;
- Batch number;
- Date of manufacture;
- Date of expiry;
- Net quantity;
- Nominal copper content, percent (*m/m*);
- Cautionary notice as worded in the *Insecticides Act*, 1968 and rules framed thereunder; and
- Any other information required under the *Legal Metrology (Packaged Commodities) Rules*, 2011.

5.2 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act*, 2016 and the Rules and Regulations framed thereunder, and the products may be marked with the Standard Mark.

6 SAMPLING

Representative samples of the material shall be drawn as prescribed in IS 10946.

To access Indian Standards click on the link below:

https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knowyourstandards/Indian_standards/isdetails/

7 TESTS

Tests shall be carried out by appropriate methods as referred in col (4) of [Table 1](#).

distilled water (*see* IS 1070) shall be employed in tests.

NOTE — 'Pure chemicals' shall mean chemicals that do not contain impurities which affect the results of analysis.

8 QUALITY OF REAGENTS

Unless specified otherwise, pure chemicals and

Table 1 Requirements of Cuprous Oxide (Fungicidal Grade), Technical
(Clauses [3.2](#) and [7](#))

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Moisture content, percent by mass, <i>Min</i>	1.0	IS 6940
ii)	Total copper, percent by mass, <i>Max</i>	80.0	Annex A
iii)	Total soluble alkali (as Na ₂ CO ₃) percent by mass, <i>Max</i>	0.50	Annex B
iv)	Total soluble chloride (as NaCl), percent by mass, <i>Max</i>	0.50	Annex C

ANNEX A

[Table 1, Sl No. (ii)]

DETERMINATION OF TOTAL COPPER

A-1 PRINCIPLE OF THE METHOD

Copper is determined by titration of the iodine liberated on addition of potassium iodide to the weakly acidic solution. Difficulties with absorption of iodine on the cuprous iodide precipitate are avoided by the addition of potassium or ammonium thiocyanate.

A-2 REAGENTS

A-2.1 Concentrated Nitric Acid — specific gravity 1.42 (conforming to IS 264)

A-2.2 Urea

A-2.3 Sodium Carbonate — anhydrous (conforming to IS 296)

A-2.4 Dilute Acetic Acid — 10 percent (v/v)

A-2.5 Potassium Iodide Solution — 30 percent (m/v)

A-2.6 Standard Sodium Thiosulphate Solution — 0.1 N, standardized against pure copper or against 0.1 N standard potassium dichromate solution (see [A-5](#)).

A-2.7 Starch Indicator Solution — 1 percent (m/v), freshly prepared

A-2.8 Potassium or Ammonium Thiocyanate

A-3 PROCEDURE

Weigh accurately about 0.4 g of the material into a 250 ml Erlenmeyer flask. Add 1 ml to 2 ml of concentrated nitric acid and about 20 ml of water, and allow the material to dissolve by shaking. Boil the contents for 3 min to 5 min, remove the flask from the flame, add 1 g of urea and boil again for about 5 min. Cool and add sodium carbonate in small quantities until a faint permanent precipitate or blue colour appears. Add dilute acetic acid dropwise until the blue colour (or the precipitate) disappears. Add 2 ml to 3 ml of potassium iodide solution and titrate the brown solution with the standard sodium thiosulphate solution to a pale-straw colour. Add about 2 ml of starch indicator solution and about

1.5 g to 2.5 g of potassium or ammonium thiocyanate, and continue titration until the blue colour is just discharged.

A-4 CALCULATION

Total copper content, percent by mass

$$= \frac{0.6357 \times v \times F}{M}$$

where

v = volume, in ml, of the standard sodium thiosulphate solution required for the test with the material (see [A-3](#));

F = factor of the standard sodium thiosulphate solution (see [A-5.2.2](#) and [A-5.3.3](#)); and

M = mass, in g, of the material taken for the test (see [A-3](#)).

A-5 STANDARDIZATION OF SODIUM THIOSULPHATE SOLUTION**A-5.1 General**

For standardization of sodium thiosulphate solution, two methods, namely titration against pure copper of not less than 99.9 percent purity and against standard potassium dichromate solution, have been specified. Experience has shown that the standardization against pure copper gives accurate results but due to difficulty of availability of pure copper, the alternate method has also been specified. Hence, either of these two methods may be used for the standardization of sodium thiosulphate solution, but the method employed should be stated while expressing the results of a test.

A-5.2 Standardization Against Pure Copper of Not Less than 99.9 Percent Purity

A-5.2.1 Weigh accurately 0.2 g of pure copper in a 500 ml Erlenmeyer flask. Dissolve the copper by adding 5 ml of concentrated nitric acid and, after 1 min, add 5 ml of water. Follow the procedure as described in [A-3](#).

A-5.2.2 Calculation

Factor F of 0.1 N sodium thiosulphate solution

$$= \frac{100 \times M}{0.6357 \times v}$$

where

M = mass, in g, of the pure copper taken for the test; and

v = volume, in ml, of the standard sodium thiosulphate solution required for the test with the material.

A-5.3 Standardization Against Standard Potassium Dichromate Solution**A-5.3.1 Reagents**

A-5.3.1.1 Standard potassium dichromate solution — 0.1 N

A-5.3.1.2 Concentrated hydrochloric acid — conforming to IS 265

A-5.3.1.3 Potassium iodide

A-5.3.1.4 Starch indicator solution — 1 percent (m/v), freshly prepared

A-5.3.2 Procedure

Pipette out accurately 25 ml of the standard potassium dichromate solution into a 600 ml

Erlenmeyer flask. Add to this about 125 ml of water, 10 ml of concentrated hydrochloric acid and 4 g to 5 g of potassium iodide. Stopper the Erlenmeyer flask and keep it in dark for about 15 min to complete the reaction. After 15 min, titrate this mixture against the standard sodium thiosulphate solution using about 2 ml of starch indicator solution towards the end.

A-5.3.3 Calculation

Factor F of 0.1 N sodium thiosulphate solution

$$= \frac{V \times N}{v}$$

where

V = volume, in ml, of the standard potassium dichromate solution taken for the test (which in this case is equal to 25 ml);

N = normality of the standard potassium dichromate solution; and

v = volume, in ml, of the 0.1 N sodium thiosulphate solution required for titration of the volume of the standard potassium dichromate solution taken for the test.

ANNEX B

[Table 1, Sl No. (iii)]

DETERMINATION OF TOTAL SOLUBLE ALKALI**B-1 REAGENTS**

B-1.1 Standard Sulphuric Acid — 0.02 N

B-1.2 Methyl Red Indicator — aqueous, 0.1 percent (m/v)

B-2 PROCEDURE

B-2.1 Weigh accurately about 20 g of the material into a 250 ml conical flask. Add about 100 ml of water, mix and warm slightly. Cool and filter into another conical flask. Wash the material several

times with water and collect the washings in the same conical flask as the filtrate. Titrate these total washings (filtrate) with the standard sulphuric acid using methyl red as the indicator.

NOTE — Preserve this solution for the determination of total soluble chloride (see [C-2.1](#)).

B-2.2 Carry out a blank determination on 100 ml of water plus the quantity of water approximately used for washings using methyl red as the indicator.

B-2.3 Calculation

Total soluble alkali (as Na₂CO₃), percent by mass

$$= \frac{5.3 \times (V - v) \times N}{M}$$

where

V = volume, in ml, of the standard sulphuric acid required for the test (see [B-2.1](#));

v = volume, in ml, of the standard sulphuric acid required for the blank determination (see [B-2.2](#));

N = normality of the standard sulphuric acid; and

M = mass, in g, of the material taken for the test (see [B-2.1](#)).

ANNEX C

[Table 1, Sl No. (iv)]

DETERMINATION OF TOTAL SOLUBLE CHLORIDE**C-1 REAGENTS****C-1.1 Calcium Carbonate**

C-1.2 Potassium Chromate Indicator Solution — 5 percent (m/v), aqueous

C-1.3 Standard Silver Nitrate Solution — 0.1 N

C-2 PROCEDURE

C-2.1 To the neutralized solution contained in the conical flask (see [B-2.1](#)), add a small quantity of calcium carbonate and mix. Add a few drops of potassium chromate indicator solution and titrate with the standard silver nitrate solution.

C-2.2 Carry out a blank determination using the same volume of water as the solution with potassium chromate as the indicator.

C-2.3 Calculation

Total soluble chloride (as NaCl), percent by mass

$$= \frac{5.85 \times (V - v) \times N}{M}$$

where

V = volume, in ml, of the standard silver nitrate required for the test (see [C-2.1](#));

v = volume in ml of the standard silver nitrate required for the blank determination (see [C-2.2](#));

N = normality of the standard silver nitrate solution; and

M = mass, in g, of the material taken for the test (see [C-2.1](#)).

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: FAD 01 (25532).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : 5 th Floor/MTNL CETTM Technology Street, Hiranandani Gardens, Powai, Mumbai - 400076	{ 25700030 25702715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.