

काँसे के रासायनिक विश्लेषण की
पद्धतियाँ
भाग 1 इलेक्ट्रोलाइटिक पद्धति द्वारा तांबे
और सीसे का निर्धारण
(दूसरा पुनरीक्षण)

Methods of Chemical Analysis of
Bronzes
Part 1 Determination of Copper and Lead
by Electrolytic Method
(Second Revision)

ICS 73.080

© BIS 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002
www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard (Part 1) (Second Revision) was adopted by the Bureau of Indian Standards after the draft finalized by the Methods of Chemical Analysis of Metals Sectional Committee had been approved by the Metallurgical Engineering Division Council.

This standard was first published in 1967 and it covered determination of copper, lead, tin, manganese, phosphorus, nickel, iron, silicon, aluminium, zinc and antimony in bronzes. Subsequently, the first revision was published in 1987 to bifurcate the standard into different parts which superseded IS 4027 : 1967.

This revision has been brought out to bring the standard in the latest style and format of the Indian Standards. This part is one of that series and covers the determination of copper and lead by electrolytic method. The other parts are as follows:

- Part 2 Determination of manganese — Photometric method
- Part 3 Determination of phosphorus — Volumetric method
- Part 4 Determination of nickel-dimethylglyoxime photometric method
- Part 5 Determination of tin-iodimetric method
- Part 6 Determination of zinc by complexometric (EDTA) method
- Part 7 Determination of antimony by rhodamine B spectrophotometric method
- Part 8 Determination of iron
- Part 9 Determination of aluminium by atomic absorption spectrometric method
- Part 10 Determination of silicon
- Part 11 Determination of lead — Ethylenediamine tetraacetic acid (EDTA) — Titrimetric method

The methods of analysis prescribed in this standard may primarily serve as referee methods and may also be used by the laboratories for their day-to-day work. Due consideration has been given in the preparation of this standard to the facilities available in the country for such analysis.

The composition of the Committee responsible for the formulation of this standard is given in [Annex A](#).

In reporting the result of a test or analysis made in accordance with this standard, it shall be rounded off, it shall be done in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be same as that of the specified value in this standard.

Indian Standard

METHODS OF CHEMICAL ANALYSIS OF BRONZES

PART 1 DETERMINATION OF COPPER AND LEAD BY ELECTROLYTIC METHOD

*(Second Revision)***1 SCOPE**

This standard (Part 1) prescribes a method for determination of copper and lead in the ranges as specified in the relevant Indian Standards on bronzes.

NOTE — The method is not applicable when manganese is present in bronzes and also when lead is of the order of 0.1 percent.

2 REFERENCES

The standards given below contains provisions which through reference in this text, constitutes provisions of this standard. At the time of publication the edition indicated was valid. All standards are subject to revision and parties to agreement based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standard.

<i>IS No.</i>	<i>Title</i>
IS 1070 : 2023	Reagent grade water — Specification (<i>fourth revision</i>)
IS 1817 : 1961	Methods of sampling non-ferrous metals for chemical analysis

3 SAMPLING

Samples shall be drawn and prepared in accordance with IS 1817.

4 QUALITY OF REAGENTS

Unless specified otherwise, analytical grade reagents and distilled water (*see* IS 1070) shall be employed in the test.

5 DETERMINATION OF COPPER AND LEAD BY THE ELECTROLYTIC METHOD**5.1 Outline of the Method**

The sample is dissolved in nitric acid, and copper and lead are electrolytically deposited and weighed.

NOTE — This method is not applicable for too low as well as higher content of lead.

5.2 Apparatus**5.2.1 Electrodes**

The following platinum electrodes are recommended, but strict adherence to the shape and size of the electrodes is not essential. For agitation of electrolyte in order to decrease the time of deposition, one of the types of rotating forms of electrodes, generally available, may be employed.

5.2.2 Cathode

It may be formed either from plain or from perforated sheet or from wire gauge.

5.2.2.1 Gauge cathodes preferably made from gauge containing 400 meshes/cm² should be used. The wire used for making gauge should be approximately 0.20 mm in diameter. Cathodes should be stiffened by doubling the gauge for about three millimetres on the top and the bottom or by reinforcing the gauge at the top and bottom with platinum ring or band.

5.2.2.2 The diameter of the cylinder should be approximately 30 mm and the height 50 mm. The stem should be made from platinum alloy wire, such as platinum-iridium, platinum-rhodium or platinum-ruthenium having diameter of approximately 1.5 mm. It should be flattened and welded throughout the entire length of the gauge. The overall height of the cathode should be approximately 130 mm.

5.2.3 Anode

When the amount of lead in the sample is less than 4.0 mg, a spiral anode should be used. It should be made from 1.0 mm or larger platinum wire formed into spiral of seven turns with a height of approximately 50 mm and diameter of 12 mm, the overall height being 130 mm.

5.2.3.1 When the amount of lead in the sample is more than 4.0 mg, the gauge anode should be used. It should be made of the same material and of the same general design as platinum gauge cathode

To access Indian Standards click on the link below:

https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knowyourstandards/Indian_standards/isdetails/

mentioned under [5.2.2](#). It should be approximately 12 mm in diameter and 50 mm in height, the overall height being 130 mm.

5.3 Reagents

5.3.1 Dilute Nitric Acid — 1 : 1 (v/v)

5.3.2 Hydrobromic Acid — 48 percent

5.3.3 Urea — solid

5.3.4 Sulphamic Acid — solid

5.3.5 Hydrogen Sulphide Solution

Saturate dilute sulphuric acid (1 : 99) with hydrogen sulphide gas. Prepare fresh as needed.

5.3.6 Ethanol — 95 percent (v/v)

5.4 Procedure

5.4.1 Weigh 2.500 g of sample, dissolve in 25 ml of dilute nitric acid and evaporate to syrupy consistency. Add 50 ml of hot water and allow to stand on a steam bath for one hour. If there is any opalescence or precipitate, add paper pulp, filter and wash several times with acidulated water. Reserve the filtrate.

5.4.1.1 Transfer the residue to silica crucible and ignite. Add 10 ml to 12 ml of hydrobromic acid, evaporate to dryness and ignite. Take up residue with dilute nitric acid and boil to expel brown fumes. Add to the filtrate reserved under [5.4.1](#). Repeat the hydrobromic acid treatment till tin is completely volatilized.

5.4.1.2 Adjust the volume of the solution to 150 ml. Add 0.5 g of urea or 0.1 g of sulphamic acid and boil

for a few minutes. Insert the tared electrodes, cover the beaker with split watch-glasses. Electrolyse with a current of 5 A/dm², with constant stirring. When the solution is colourless, wash down the cover glasses, electrodes and sides of the beaker, raising the level of liquid slightly. Continue passing the current noting whether or not copper is being plated on the newly exposed surface of platinum cathode. If no copper appears, transfer about one millilitre of the solution to a spot plate and test for copper with a few drops of freshly prepared acidified hydrogen sulphide solution.

5.4.1.3 As soon as the deposition is complete, lower the beaker slowly while washing the cathode with water without stopping the current. Remove the cathode, rinse it with water and then dip in two successive baths of ethanol. Dry for three minutes to five minutes in an oven at 105 °C, cool and weigh the deposit immediately as metallic copper. Remove the anode, rinse thoroughly with water, and dry the anode in an oven at 100 °C for 30 minutes. The deposit, being fragile, should be handled with care. Cool the anode and weigh as lead peroxide.

5.5 Calculation

$$\text{Copper, percent} = \frac{A}{C} \times 100$$

$$\text{Lead, percent} = \frac{B \times 86.62}{C}$$

where

A = mass, in g, of the copper deposit;

C = mass, in g, of the sample taken; and

B = mass, in g, of the lead peroxide deposit.

ANNEX A

(Foreword)

COMMITTEE COMPOSITION

Methods of Chemical Analysis of Metals Sectional Committee, MTD 34

<i>Organization</i>	<i>Representative(s)</i>
CSIR - National Metallurgical Laboratory, Jamshedpur	DR SANCHITA CHAKRAVARTY (Chairperson)
Arcelor Mittal Nippon Steel, Mumbai	SHRI MANOJ GUPTA SHRI KIRIT TAILOR (<i>Alternate</i>)
Bhabha Atomic Research Centre, Mumbai	MS SANJUKTA A. KUMAR SHRI M. V. RANA (<i>Alternate</i>)
CSIR - National Metallurgical Laboratory, Jamshedpur	DR ASHOK K. MOHANTY (<i>Alternate</i>)
Defence Metallurgical Research Laboratory, Ministry of Defence, Hyderabad	SHRI S. S. KALYAN KAMAL
Directorate General of Quality Assurance, Ministry of Defence, New Delhi	SHRI A. MITRA SHRI D. KARTIKEY (<i>Alternate</i>)
Geological Survey of India, New Delhi	SHRI NITIN PURUSHOTTAM SHRIMATI SANJUKTA DEY PAL (<i>Alternate</i>)
Hindalco Industries Limited, Mumbai	SHRI KRISHANU MAHAPATRA SHRI ASHUTOSH ACHARYA (<i>Alternate</i>)
Indian Metals and Ferro Alloys Limited, Bhubaneswar	SHRI DINESH KUMAR MOHANTY
Jawaharlal Nehru Aluminium Research Development and Design Centre, Nagpur	DR UPENDRA SINGH
JSW Steel Limited, Mumbai	SHRI KOTRABASAVARAJU SHRI MARULASIDDESHA U. M. (<i>Alternate</i>)
National Aluminium Company Limited, Bhubaneswar	SHRIMATI SUKLA NANDI SHRI DEBANANDA BHATTACHARYYA (<i>Alternate</i>)
National Test House, Kolkata	DR RAJEEV KUMAR UPADHYAY SHRI AKBAR H. (<i>Alternate</i>)
Shriram Institute for Industrial Research, Delhi	DR LAXMI RAWAT SHRI PUNEET KAPOOR (<i>Alternate</i>)
Steel Authority of India Limited - Salem Steel Plant, Salem	SHRI L. SIVAKUMAR SHRI VIVEKANANDHAN G. (<i>Alternate</i>)
Tata Steel Limited, Kolkata	DR JATIN MOHAPATRA DR RAVIKRISHNA CHATTI (<i>Alternate</i>)
BIS Directorate General	SHRI SANJIV MAINI, SCIENTIST 'F'/SENIOR DIRECTOR AND HEAD (METALLURGICAL ENGINEERING) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)]

Member Secretary

SHRI ASHISH PRABHAKAR WAKLE
SCIENTIST 'C'/DEPUTY DIRECTOR
(METALLURGICAL ENGINEERING), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: MTD 34 (21051).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

Central : 601/A, Konnectus Tower -1, 6th Floor,
DMRC Building, Bhavbhuti Marg, New
Delhi 110002

Telephones

{ 2323 7617

Eastern : 8th Floor, Plot No 7/7 & 7/8, CP Block, Sector V,
Salt Lake, Kolkata, West Bengal 700091

{ 2367 0012
2320 9474

Northern : Plot No. 4-A, Sector 27-B, Madhya Marg,
Chandigarh 160019

{ 265 9930

Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113

{ 2254 1442
2254 1216

Western : 5th Floor/MTNL CETTM, Technology Street, Hiranandani Gardens, Powai
Mumbai 400076

{ 25700030
25702715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.