

वस्त्रादि — उच्च घनत्व पॉलीइथलीन
मोनोफिलामेंट (उ घ पॉ मो) एकतंतु का गोल
जाली का मच्छरदानी का कपड़ा — विशिष्टी
(दूसरा पुनरीक्षण)

**Textiles — High Density
Polyethylene (HDPE) Monofilament
Mosquito Netting, Round Mesh —
Specification**
(*Second Revision*)

ICS 59.080.30

© BIS 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002
www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard (Second Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Textiles Protective Clothing Sectional Committee had been approved by the Textile Division Council.

This standard was first published in 1981 and was subsequently revised in 1996. This revision has been brought out in the light of experience gained since last revision and to incorporate the following major changes:

- a) Method for identification of polyethylene has been incorporated in the standard;
- b) Packaging clause has been modified;
- c) Marking clause has been updated;
- d) Method of test for count of yarn has been incorporated; and
- e) References to Indian Standard given in [Annex A](#) has been updated.

The composition of the Committee responsible for the formulation of this standard is given in [Annex C](#).

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

TEXTILES — HIGH DENSITY POLYETHYLENE (HDPE) MONOFILAMENT MOSQUITO NETTING, ROUND MESH — SPECIFICATION

(*Second Revision*)

1 SCOPE

1.1 This standard prescribes constructional details and other requirements of HDPE monofilament mosquito netting, round mesh.

1.2 This standard does not specify the general appearance, feel, shade, etc, of the netting.

2 REFERENCES

The standards listed in [Annex A](#) contain provisions which, through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards.

3 MANUFACTURES

3.1 Yarn

The monofilament yarn used for the manufacture of the netting shall be made out of HDPE of designation HDPE LAN A50 T012, or HDPE LAN A57 T012, or HDPE LAN A50 T022 or HDPE LAN A57 T022 according to IS 7328. However, the density of the material used shall not be more than 955 kg/m³ at 27 °C and the melt flow rate (MFR) - 190/50 of the material shall be between 1.3 g/10 min to 2.4 g/10 min. The filament shall be uniform and reasonably free from defects.

3.2 Netting

The shade of the netting shall be as agreed to between the buyer and the seller and the netting shall be free from knitting and other defects.

4 REQUIREMENTS

4.1 Construction

The netting shall comply with the requirements

specified in [Table 1](#). The linear density of filament is given for guidance only.

4.2 Colour Fastness

The colour fastness rating of netting shall comply with the requirements specified in [Table 2](#).

4.3 The polyethylene in the monofilament mosquito netting shall be identified by the method prescribed in IS 667.

5 MARKING

5.1 The netting shall be marked with the following:

- a) Name of the material;
- b) Width and length of the piece;
- c) Source of manufacture; and
- d) Year of manufacture

5.2 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the products may be marked with the Standard Mark.

6 PACKING

Each roll or bundle of mosquito netting shall be packed in low density polyethylene film of 60 gm thickness (150 gauge) or any other suitable material as agreed to between the buyer and the seller. The rolls or bundles shall again be packed in bales or cases. The packaging shall be roadworthy, airworthy and seaworthy.

Table 1 Particulars of HDPE Monofilament Mosquito Netting, Round Mesh

(Clause 4.1)

SI No.	Linear Density of Filament	Number of Holes per cm ²	Mass, g/m ²	Bursting Strength, Min N (or kgf/m ²)	Width, cm	Length, m
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	18 tex to 19 tex (or 160 denier to 170 denier)	16 to 20	80 ± 5 percent	83 (or 8.5)	122 or as agreed ± 1	As agreed
Method of Test	IS 3442	Annex B	IS 1964	IS 1966 (Part 1)	IS 1954	

Table 2 Colour Fastness

(Clause 4.2)

SI No.	Colour Fastness Rating	Requirement	Method of Test
(1)	(2)	(3)	(4)
i)	Light (change in colour), <i>Min</i>	5	IS/ISO 105-B01 or IS/ISO105-B02
ii)	Washing, test 2 (change in colour and staining), <i>Min</i>	4	IS/ISO 105-C10

7 SAMPLING**7.1 Lot**

The number of pieces of mosquito netting delivered to a buyer against one despatch note shall constitute a lot.

7.2 For assessing the conformity of the lot to the

requirements of the standard, the samples as given in [Table 3](#) shall be drawn at random from the lot for inspection. To ensure the randomness of selection, methods given in IS 4905 shall be followed.

7.3 The lot shall be considered as conforming to the requirements of this standard if all the samples meet the requirements specified in the standard.

Table 3 Sample Size

(Clause 7.2)

SI No.	Number of Pieces in the Lot	Number of Pieces to be Inspected for		
		Length, Width and Number of Holes	Mass and Bursting Strength	Colour Fastness
(1)	(2)	(3)	(4)	(5)
i)	Up to 100	8	3	2
ii)	101 to 150	13	5	2
iii)	151 to 300	20	5	2
iv)	301 and above	32	8	3

ANNEX A

(Foreword and Clause 2)

LIST OF REFERRED STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
IS/ISO 105-B01 : 2014	Textiles — Tests for colour fastness: Part B01 Colour fastness to light: Daylight	IS 1966 (Part 1) : 2022/ ISO 13938-1 : 2019	Textiles — Bursting properties of fabrics: Part 1 Hydraulic method for determination of bursting strength and bursting distension (<i>third revision</i>)
IS/ISO 105-B02 : 2014	Textiles — Tests for colour fastness: Part B02 Colour fastness to artificial light: Xenon arc fading lamp test	IS 3442 : 2023	Textiles — Method for determination of crimp and linear density of yarn removed from fabric (<i>second revision</i>)
IS/ISO 105-C10 : 2006	Textiles — Tests for colour fastness: Part C10 Colour fastness to washing with soap or soap and soda	IS 4905 : 2015/ ISO 24153 : 2009	Random sampling and randomization procedures (<i>first revision</i>)
IS 667 : 1981	Methods for identification of textile fibres (<i>first revision</i>)	IS 7328 : 2020	Specification for polyethylene material for moulding and extrusion (<i>third revision</i>)
IS 1954 : 2024/ ISO 22198 : 2006	Textiles — Fabrics — Determination of width and length (<i>third revision</i>)		
IS 1964 : 2001	Textiles — Methods for determination of mass per unit length and mass per unit area of fabrics (<i>second revision</i>)		

To access Indian Standards click on the link below:

https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knowyourstandards/Indian_standards/isdetails/

ANNEX B

(Table 1)

MEASUREMENT OF NUMBER OF HOLES

B-1 APPARATUS

B-1.1 Template

a) A metal plate of about 0.5 mm thickness with a square hole of 2 cm × 2 cm cut accurately in the centre.

or

b) A rigid transparent plastic sheet with a square of 2 cm × 2 cm marked in the centre.

B-2 METHOD

Lay the netting flat without stretching on a flat surface of contrast colour. Count the number of holes in the square marked on/cut in the template in such a way that holes of more than half in size are counted as full hole and holes which are less than half in size are ignored. Divide the number of holes thus counted by 4. Count the number of holes at 5 different places and calculate the average.

ANNEX C

(Foreword)

COMMITTEE COMPOSITION

Textiles Protective Clothing Sectional Committee, TXD 32

<i>Organization</i>	<i>Representative(s)</i>
Northern India Textile Research Association, Ghaziabad	DR ARINDAM BASU (<i>Chairperson</i>)
Aeronav Industrial Safety Appliances, Noida Arvind Limited, Ahmedabad	SHRI SANDEEP HORA SHRI PABITRA SAHOO SHRIMATI PALAK KAKKAR (<i>Alternate</i>)
Avient Protective Materials Limited, Pune	SHRI HARSH WARDHAN SHARMA SHRI RAKESH GAIKWAD (<i>Alternate</i>)
Border Security Force, New Delhi	SHRI SATISH CHANDRA SHRI TARUN RAVI (<i>Alternate</i>)
Central Industrial Security Force, New Delhi	SHRI ANAND SAXENA SHRI RAVINDRA KUMAR MEEL (<i>Alternate</i>)
Central Reserve Police Force, New Delhi	SHRI D. N. LAL SHRI SANJEEV KUMAR SINGH (<i>Alternate</i>)
Centre for Fire and Explosive Environment Safety, Defence Institute of Fire Research, Delhi	SHRI MAHIPAL MEENA SHRI P. K. ROY (<i>Alternate</i>)
Confederation of Indian Industry, New Delhi	SHRI SAUNAK BANERJEE
Defence Bio-Engineering and Electromedical Laboratory, Ministry of Defence, Bengaluru	DR T. M. KOTRESH SHRI VINOTH P. (<i>Alternate</i>)
Defence Institute of Physiology and Allied Science (DRDO), New Delhi	DR MADHUSUDAN PAL SHRI SUNIL KUMAR HOTA (<i>Alternate</i>)
Defence Materials and Stores Research and Development Establishment, Kanpur	SHRIMATI PRIYANKA KATIYAR SHRIMATI SHRADDHA MISHRA (<i>Alternate</i>)
Defence Research and Development Organization, Terminal Ballistics Research Laboratory, Chandigarh	DR PREETI JAIN SHRI SANDEEP BAGGA (<i>Alternate</i>)
Department of Delhi Fire Services, Govt of NCT of Delhi, Delhi	SHRI ATUL GARG DR SANJAY KUMAR TOMAR (<i>Alternate</i>)
Department of Jute and Fibre Technology, University of Kolkata, Kolkata	DR SWAPAN KUMAR GHOSH DR AMIYA KUMAR SINGHA (<i>Alternate</i>)
Directorate General Fire Services, Civil Defence and Home Guards, Ministry of Home Affairs New Delhi	SHRI PRASHANT LONGKAR
Directorate General of Quality Assurance, Ministry of Defence, New Delhi	SHRI AMIYA KUMAR MALLICK SHRI K. I. SINGH (<i>Alternate</i>)
DuPont Specialty Products India Limited, Gurugram	SHRI MANOJ JHAVER SHRIMATI MITHALI CHENGGAPA (<i>Alternate</i>)
Foremost Technico Private Limited, New Delhi	SHRI VINAY KHANNA SHRI ANOOP KHANNA (<i>Alternate</i>)
Indian Institute of Technology Delhi, New Delhi	PROF ABHIJIT MAJUMDAR DR BIPIN KUMAR (<i>Alternate</i>)

<i>Organization</i>	<i>Representative(s)</i>
Indian Technical Textiles Association, Mumbai	DR ANUP RAKSHIT SHRI SANJAY SATHE (<i>Alternate</i>)
Indo Tibetan Border Police, New Delhi	SHRI M. KUMAR SHRI UTTAM KUMAR (<i>Alternate</i>)
Kusumgar Corporates Private Limited, Vapi	SHRI SIDHARTHA KUSUMGAR DR M. K. TALUKDAR (<i>Alternate</i>)
Mishra Dhatu Nigam Limited, Hyderabad	COL ASHWANI KUMAR
National Forensic Sciences University, Gandhinagar	SHRI S. K. KHANDELWAL SHRI SAURABH KUMAR (<i>Alternate</i>)
National Security Guard, New Delhi	SHRI MANU LOCHAB
Northern India Textile Research Association, Ghaziabad	DR M. S. PARMAR SHRIMATI SHWETA SAXENA (<i>Alternate</i>)
Office of the Textile Commissioner, Mumbai	SHRI N. K. SINGH SHRI SANJAY CHARAK (<i>Alternate</i>)
Oil Industry Safety Directorate, Noida	SHRI DEVENDRA M. MAHAJAN SHRI HARENDRA YADAV (<i>Alternate</i>)
Ordnance Clothing Factory, Shahjahanpur	SHRI V. MATHIVANAN SHRI SHANMUGAM B. (<i>Alternate</i>)
SGS India Private Limited, Mumbai	DR ANITHA JEYARAJ DR KARTHIKEYAN K. (<i>Alternate</i>)
SMPP Private Limited, New Delhi	SHRI ASHISH KANSAL DR S. C. KANSAL (<i>Alternate</i>)
Star Safety Hub, Faridabad	SHRI PAWAN KUMAR GUPTA SHRI NAVEEN GUPTA (<i>Alternate</i>)
System 5S Private Limited, Chennai	SHRI SUDHIR TAKKAR SHRIMATI BHAVNA SR. TAKKAR (<i>Alternate</i>)
Teijin India Private Limited, Gurugram	SHRI RAVI KUMAR SHRI SAHIL ANEJA (<i>Alternate</i>)
Tex Corporation Limited, Gurugram	SHRI VIJAY TOLEY SHRI SANJAY AGGARWAL (<i>Alternate</i>)
Textiles Committee, Mumbai	SHRI KARTIKAY DHANDA SHRIMATI SHILPI CHAUHAN (<i>Alternate</i>)
The Synthetic and Art Silk Mills Research Association, Mumbai	DR MANISHA MATHUR SHRIMATI ASHWINI SUDAM (<i>Alternate</i>)
BIS Directorate General	SHRI J. K. GUPTA, SCIENTIST 'E'/DIRECTOR AND HEAD (TEXTILES) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)]

Member Secretary
SHRI MAYUR KATIYAR
SCIENTIST 'B'/ASSISTANT DIRECTOR
(TEXTILES), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 32 (25486).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : 5 th Floor/MTNL CETTM, Technology Street, Hiranandani Gardens, Powai Mumbai 400076	{ 25700030 25702715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.