

वस्त्रादि — कॉटन वेबिंग, विशेष —
विशिष्टि
(दूसरा पुनरीक्षण)

**Textiles — Cotton Webbing,
Special — Specification**
(*Second Revision*)

ICS 59.080.20

© BIS 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002
www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard (Second Revision) was adopted by the Bureau of Indian Standards after the draft finalized by the Technical Textiles for Clothtech Applications including Narrow Fabrics and Braids Sectional Committee had been approved by the Textile Division Council.

Cotton webbing is a versatile, strong narrow fabric commonly used in various applications. It is made from natural cotton fibers, offering durability and a soft texture. Cotton webbing is breathable and comfortable yet its high tensile strength ensures reliability in heavy-duty uses like harnesses and camping gear. This standard focuses on cotton webbing used in defence purposes.

This standard was first published in 1974 and subsequently revised in 1989. This revision has been brought out in the light of experience gained since its publication and to incorporate the following major changes:

- a) Title of the standard has been modified.
- b) BIS certification marking clause has been modified; and
- c) References to standard have been updated.

The composition of the Committee responsible for the formulation of this standard is given in [Annex B](#).

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard
**TEXTILES — COTTON WEBBING, SPECIAL —
 SPECIFICATION**

(*Second Revision*)

1 SCOPE

This standard prescribes constructional particulars and other requirements for 3 varieties of special cotton webbings, dyed or undyed, used by defence personnel.

2 REFERENCES

The standards listed in [Annex A](#) contain provisions which, through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of these standards.

3 MANUFACTURE

3.1 Yarn

The cotton yarn used in the manufacture of webbing

shall conform to the requirements specified in IS 171. The yarn shall be free from spinning and doubling defects.

3.2 The webbing shall be woven uniformly on shuttle looms with firm, straight and properly formed selvages. It shall be free from weaving flaws, weighting, sizing and finishing materials.

The webbings may also be produced on needle looms subject to the agreement between the buyer and the seller. Selvages of the needle loom produced webbings shall be made secure by using one of the systems shown in [Fig. 1](#).

3.3 Dyeing

The webbing shall be dyed as required by the buyer.




FIG. 1 NEEDLE LOOM SELVEDGE SYSTEM

4 REQUIREMENTS

4.1 The webbing shall conform to the constructional particulars specified in [Table 1](#).

4.2 The webbing shall also conform to the requirements specified in [Table 2](#).

4.3 Sealed Sample

If in order to illustrate or specify properties of the webbing not covered in this standard, a sample has been agreed and sealed, the supply shall be in conformity with sample in such respect.

The custody of the sealed sample shall be a matter of prior agreement between the buyer and the seller.

5 MARKING

5.1 Each roll of webbing shall be attached with a label on which the following information shall be marked:

- Name of the material, variety no.;
- Length of webbing;
- Year of manufacture;
- Manufacturer's name, initials or trade-mark, if any; and
- Any other information as required by the law in force.

5.2 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity

assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the product may be marked with the Standard Mark.

6 PACKING

The webbing shall be packed as required by the buyer.

7 SAMPLING

7.1 Unless otherwise agreed, the number of rolls to be selected at random shall be as given in [Table 3](#).

7.2 Criteria for Conformity

The criteria for conformity shall be as follows:

Sl No.	Characteristic	Number of Test Specimens	Criteria for Conformity
(1)	(2)	(3)	(4)
i)	Length, width, ends in full width, picks, weave	As per col (3) under Table 3	Defective rolls not to exceed the number given under col (4) of Table 3
ii)	Mass breaking load, colour fastness, scouring loss and pH value	As per col (5) under Table 3	All the test specimens shall pass the requirements

Table 1 Constructional Particulars of Special Cotton Webbing

(Clause [4.1](#))

Sl No.	Variety No.	Count of Yarn for Warp and Weft (for Guidance Only) (See Note 1)	Width, mm	Length, m	Ends in Full Width, Min	Picks Per dm (See Note 2)	Mass, g/m, Max	Average Breaking Load on Full Width × 90 cm Between Grips, N, Min	Weave
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)
i)	1	60 tex × 2 (10 ^s /2)	44 ± 1.5	20 or as agreed	140	70 ± 2	54	4 115	Herring bone
ii)	2		50 ± 2		160	70 ± 2	62	4 705	
iii)	3		76 ± 3		240	70 ± 2	93	7 095	
Method of test			IS 1954		IS 1963	IS 1963	IS 1964	IS 1969 (Part 1)	Visual
NOTES									
1 For webbing woven on needle looms, count of yarn used in weft should be approximately two times finer than specified.									
2 For needle loom webbing, the number of picks per dm would be 140 ± 4 since two threads would be working as one.									

Table 2 Other Requirements of Special Cotton Webbing*(Clause [4.2](#))*

Sl No.	Characteristic	Requirements	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Colour fastness:		
	a) Light	5 or better	IS/ISO 105-B02
	b) Washing (Test 2)	4 or better	IS/ISO 105-C10
ii)	Scouring loss, percent, <i>Max</i>	2	IS 1383
iii)	pH value	6 to 8.5	IS 1390

Table 3 Sampling*(Clause [7.1](#) and [7.2](#))*

Sl No.	No. of Rolls in the Lot	Sample Size	Permissible No. of Defective Rolls	Sub-Sample Size
(1)	(2)	(3)	(4)	(5)
i)	Up to 100	8	0	3
ii)	101 to 300	13	1	4
iii)	301 to 500	20	2	5
iv)	501 to 1 000	32	3	7
v)	1 000 and above	50	5	10

ANNEX A

(Clause 2)

LIST OF REFERRED STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
IS/ISO 105-B02 : 2014	Textiles — Tests for colour fastness: Part B02 Colour fastness to artificial light: Xenon arc fading lamp test	IS 1954 : 2024/ ISO 22198 : 2006	Textiles — Fabrics — Determination of width and length (<i>third revision</i>)
IS/ISO 105-C10 : 2006	Textiles — Tests for colour fastness: Part C10 Colour fastness to washing with soap or soap and soda	IS 1963 : 1981	Methods for determination of threads per unit length in woven fabrics (<i>second revision</i>)
IS 171 : 1993	Textiles — Ring spun grey cotton yarn for weaving — Specification (<i>fourth revision</i>)	IS 1964 : 2001	Textiles — Methods for determination of mass per unit length and mass per unit area of fabrics (<i>second revision</i>)
IS 1383 : 2023	Methods for determination of scouring loss in grey and finished cotton textile materials (<i>second revision</i>)	IS 1969 (Part 1) : 2018/ISO 13934-1 : 2013	Textiles — Tensile properties of fabrics: Part 1 Determination of maximum force and elongation at maximum force using the strip method (<i>fourth revision</i>)
IS 1390 : 2022/ ISO 3071 : 2020	Textiles — Determination of pH of aqueous extract (<i>third revision</i>)		

To access Indian Standards click on the link below:

https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knowyourstandards/Indian_standards/isdetails/

ANNEX B

(Foreword)

COMMITTEE COMPOSITION

Technical Textiles for Clothtech Applications including Narrow Fabrics and Braids
Sectional Committee, TXD 39

<i>Organization</i>	<i>Representative(s)</i>
Additional Controller CQA (General Stores), DGQA, Ministry of Defence, Kanpur	SHRI A. CHOWDHURY (Chairperson)
Federation of Indian Chambers of Commerce and Industry, New Delhi	SHRI ANU HANDA DR T. SENTHILKUMAR (<i>Alternate</i>)
ICAR - Central Institute for Research on Cotton Technology, Mumbai	DR P. JAGAJANANTHA
Indian Technical Textile Association, Mumbai	DR ANUP RAKSHIT SHRI VIKRAM JAIN (<i>Alternate</i>)
M K U Limited, Kanpur	SHRI SUMIT KHANDELWAL SHRI RAJIB PAL (<i>Alternate</i>)
Motilal Dulichand Pvt Ltd, Kanpur	SHRI SHAILENDRA NATH MISRA SHRI SUDHIR SHIVHARE (<i>Alternate</i>)
National Textile Corporation, New Delhi	SHRI R. K. YADAV
Office of Textiles Commissioner, Mumbai	SHRI V. K. KOHLI SHRI HUMAYUN K. (<i>Alternate</i>)
Ordnance Parachute Factory, Kanpur	SHRI V. M. BAGADE SHRI S. KONDAIAH (<i>Alternate</i>)
SGS Limited, Gurugram	MS ANITHA JEYARAJ SHRI GAURAV SARASWAT (<i>Alternate</i>)
Shipra International, Kanpur	SHRI ABHISHEK KUMAR AGRAWAL
S L Banthia Textiles Industries Pvt Ltd, Surat	SHRI SANTOSH KUMAR BANTHIA
Sky Industries Ltd, Navi Mumbai	SHRI KAPIL MEHROTRA SHRI MICHAEL (<i>Alternate</i>)
Synthetic and Art Silk Mills Research Association, Mumbai	SHRI SANJAY SAINI SHRI PREMNATH SURWASE (<i>Alternate</i>)
Thanawala & Co, Mumbai	SHRI HEMAL THANAWALA SHRI VIVAN THANAWALA (<i>Alternate</i>)
The Bombay Textile Research, Association, Mumbai	SHRI SHAIKH RIYAZ AHMED DR PRASANTA KUMAR PANDA (<i>Alternate</i>)
Universal Yarn & Tex Pvt Ltd, Kanpur	SHRI RAJIV K. BHARTIYA
U P Textile Technological Institute, Kanpur	DR PRASHANT VISHNOI
BIS Directorate General	SHRI J. K. GUPTA, SCIENTIST 'E'/DIRECTOR AND HEAD (TEXTILES) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)]

Member Secretary
SHRI TANISHQ AWASTHI
SCIENTIST 'B'/ASISTANT DIRECTOR
(TEXTILES), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 39 (23557).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : Manakalya, 5 th Floor/MTNL CETTM, Technology Street, Hiranandani Gardens, Powai Mumbai 400076	{ 25700030 25702715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.