

वस्त्रादि — सपाट सूती बत्तियाँ — विशिष्टि
(दूसरा पुनरीक्षण)

Textiles — Flat Cotton Wicks —
Specification
(Second Revision)

ICS 59.080.20

© BIS 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002
www.bis.gov.in www.standardsbis.in

October 2024

Price Group 5

FOREWORD

This Indian Standard (Second Revision) was adopted by the Bureau of Indian Standards after the draft finalized by the Technical Textiles for Clothtech Applications including Narrow Fabrics and Braids Sectional Committee had been approved by the Textile Division Council.

This standard was first published in 1960 and has been revised in 1977. The current revision has been brought out in the light of experience gained since its publication and to incorporate the following major changes:

- a) Title of the standard has been modified;
- b) BIS certification marking clause has been modified; and
- c) References to Indian Standards have been updated.

The composition of the Committee responsible for the formulation of this standard is given in [Annex C](#).

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Indian Standard***TEXTILES — FLAT COTTON WICKS — SPECIFICATION***(Second Revision)***1 SCOPE**

This standard prescribes the requirements of flat cotton wicks (6 mm to 25 mm wide) for use in hurricane lanterns and lamps.

2 REFERENCES

The standards listed in [Annex A](#) contain provisions, which through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards.

3 MANUFACTURE AND WORKMANSHIP**3.1 Yarn**

Cotton yarn used for the manufacture of wicks shall be free from leaf particles, neps, snarls, slubs and

other defects.

The approximate count of yarn is given in [Table 1](#) for the guidance of the manufacturer.

3.2 Wick

The wick shall be woven in double plain weave, uniform in thickness and width free from weaving defects as far as practicable, and also free from sizing and finishing materials.

4 PHYSICAL REQUIREMENTS

The flat cotton wicks conforming to this standard shall also meet the physical requirements given in [Table 2](#).

5 CHEMICAL REQUIREMENTS

The wicks shall also meet the chemical requirements given in [Table 3](#).

Table 1 Count of Yarns Used in Wicks*(Clause [3.1](#))*

Sl No. (1)	Characteristic (2)	Count (3)
i)	<i>Warp</i>	
	a) Face and back	98 tex × 3 (6 ^s /3)
	b) Selvedge and binding	60 tex × 2 (10 ^s /2)
ii)	<i>Weft</i>	20 tex × 2 (30 ^s /2)

Table 2 Physical Requirements of Flat Cotton Wicks

(Clause 4)

Sl No.	Width, mm	Mass, g per Roll, 10 m <i>Min</i>	Nominal Thickness, mm	Ends in Full Width			Total Ends in Selvedges, <i>Min</i>	Picks/cm <i>Min</i>
				Face	Back	Binding		
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
i)	6 ± 1	50	2.15 $\frac{+0}{-0.05}$	6	6	3	5	11
ii)	9 ± 1	65	2.25 $\frac{+0}{-0.05}$	8	8	3	9	11
iii)	12 ± 1	90	2.15 $\frac{+0}{-0.05}$	10	10	4	9	11
iv)	15 ± 2	120	2.00 $\frac{+0}{-0.05}$	14	14	6	9	11
v)	19 ± 2	150	1.90 $\frac{+0}{-0.05}$	18	18	8	9	11
vi)	22 ± 2	165	2.00 $\frac{+0}{-0.05}$	20	20	9	9	11
vii)	25 ± 2	195	2.15 $\frac{+0}{-0.05}$	24	24	11	9	11
Method of Test	IS 1954	IS 1964	IS 7702	IS 1963				

Table 3 Chemical Requirements of Flat Cotton Wicks

(Clause 5)

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	pH of aqueous extract	6.0 to 8.5	IS 1390
ii)	Scouring loss, percent, <i>Max</i>	6.0	IS 1383
iii)	Oil absorption time taken for a rise of 5 cm, s, <i>Max</i>	36	Annex B

6 PACKING

Unless otherwise agreed to between the buyer and the seller, the wicks shall be packed in rolls of 10 m in such a way that the product remains duly protected from moisture.

7 MARKING

7.1 Each roll of wicks shall be attached with a tag legibly marked with the following information:

- Name of the material;
- Width (mm);
- Length of roll (m);

- Lot/Batch no.;
- Indication of the source of manufacture; and
- Any other information as required by the law in force.

7.2 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the product(s) may be marked with the Standard Mark.

8 SAMPLING

8.1 The lot shall consist of all the wicks of the same width delivered to a buyer against one dispatch note.

8.2 Unless otherwise sampling plan is specified in the contract or order, the sampling plan as given in [Table 4](#) may be used for inspecting and testing of wicks against this standard. The number of wicks to be selected from the lot for assessing manufacture and workmanship (see [3.1](#) and [3.2](#)) shall be as per col (3) of [Table 4](#). The number of test specimens to

be selected for other tests shall be in accordance with col (5) of [Table 4](#). To ensure the randomness of selection, IS 4905 may be followed.

8.3 Criteria for Conformity

The lot shall be declared conforming to the requirements of this standard if the total number of defective samples does not exceed the permissible numbers given in col (4) or col (6) of [Table 4](#) as applicable.

Table 4 Sampling Plan for Flat Cotton Wicks

(Clauses [8.2](#) and [8.3](#))

Sl No.	Lot Size	Sample Size	Permissible No. of Defectives Samples	Sub-Sample Size (to be Drawn from Sample)	Permissible No. of Defectives Sub-samples
(1)	(2)	(3)	(4)	(5)	(6)
i)	2 to 25	3	0	3	0
ii)	26 to 90	13	1	3	0
iii)	91 to 150	20	2	13	1
iv)	151 to 280	32	3	13	1
v)	281 to 500	50	5	20	1
vi)	501 to 1 200	80	7	32	2
vii)	1 201 and above	125	10	50	3

NOTE — If sample size equals or exceeds lot size, carry out 100 percent inspection.

Table 5 Criteria for Conformity

(Clause [8.3](#))

Sl No.	Characteristic	Sample Size	Criteria for Conformity
(1)	(2)	(3)	(4)
i)	Mass, width, nominal thickness, ends in full width, total ends in selvages, picks/cm	According to col (3) of Table 4	Non-conforming cotton wicks not to exceed corresponding number given in col (4) of Table 4
ii)	pH of aqueous extract, scouring loss, oil absorption time taken for a rise of 5 cm	According to col (5) of Table 4	All cotton wicks to satisfy the requirements specified in Annex B

ANNEX A

(Clause 2)

LIST OF REFERRED STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
IS 1383 : 2023	Methods for determination of scouring loss in grey and finished cotton textile materials (<i>second revision</i>)	IS 1964 : 2001	Textiles — Methods for determination of mass per unit length and mass per unit area of fabrics (<i>second revision</i>)
IS 1390 : 2022/ ISO 3071 : 2020	Textiles — Determination of pH of aqueous extract (<i>third revision</i>)	IS 4905 : 2015 ISO 24153 : 2009	Random sampling and randomization procedures (<i>first revision</i>)
IS 1459 : 2018	Kerosene — Specification (<i>fourth revision</i>)	IS 7702 : 2012/ ISO 5084 : 1996	Textiles — Determination of thickness of textiles and textile products (<i>first revision</i>)
IS 1954 : 2024/ ISO 22198 : 2006	Textiles — Fabrics — Determination of width and length (<i>third revision</i>)		
IS 1963 : 1981	Methods for determination of threads per unit length in woven fabrics (<i>second revision</i>)		

To access Indian Standards click on the link below:

https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knownyourstandards/Indian_standards/isdetails/

ANNEX B

(Table 3 and Table 5)

METHOD OF TEST FOR OIL ABSORPTION TIME

B-1 Cut one specimen measuring approximately 15 cm from each roll.

B-2 Take a beaker and a stand.

B-3 Take one test specimen and place two marks *X* and *Y* on it at 5 cm and 10 cm respectively from one

of its ends. Suspend the test specimen from the other end vertically in a beaker containing kerosene (see IS 1459) up to a height of 8 cm so that the mark *X* on the test specimen is just submerged in oil (see Fig. 1). Note the time taken by the kerosene to rise up to the mark *Y*.




FIG. 1 APPARATUS FOR MEASURING OIL ABSORPTION TIME

ANNEX C

(Foreword)

COMMITTEE COMPOSITION

Technical Textiles for Clothtech Applications including Narrow Fabrics and Braids Sectional Committee,
TXD 39

<i>Organization</i>	<i>Representative(s)</i>
Additional Controller CQA (General Stores), DGQA, Ministry of Defence, Kanpur	SHRI A. CHOWDHURY (<i>Chairperson</i>)
ICAR - Central Institute for Research on Cotton Technology, Mumbai	DR P. JAGAJANANTHA
Federation of Indian Chambers of Commerce and Industry, New Delhi	SHRI ANU HANDA DR T. SENTHILKUMAR (<i>Alternate</i>)
Indian Technical Textile Association, Mumbai	DR ANUP RAKSHIT SHRI VIKRAM JAIN (<i>Alternate</i>)
M K U Limited, Kanpur	SHRI SUMIT KHANDELWAL SHRI RAJIB PAL (<i>Alternate</i>)
Motilal Dulichand Pvt Ltd, Kanpur	SHRI SHAILENDRA NATH MISRA SHRI SUDHIR SHIVHARE (<i>Alternate</i>)
National Textile Corporation, New Delhi	SHRI R. K. YADAV
Office of Textiles Commissioner, Mumbai	SHRI V. K. KOHLI SHRI HUMAYUN K. (<i>Alternate</i>)
Ordinance Parachute Factory, Kanpur	SHRI V. M. BAGADE SHRI S. KONDAIAH (<i>Alternate</i>)
SGS Limited, Gurugram	MS ANITHA JEYARAJ SHRI GAURAV SARASWAT (<i>Alternate</i>)
Shipra International, Kanpur	SHRI ABHISHEK KUMAR AGRAWAL
Sky Industries Ltd, Navi Mumbai	SHRI KAPIL MEHROTRA SHRI MICHAEL (<i>Alternate</i>)
S L Banthia Textiles Industries Pvt Ltd, Surat	SHRI SANTOSH KUMAR BANTHIA
Synthetic and Art Silk Mills Research Association, Mumbai	SHRI SANJAY SAINI SHRI PREMNATH SURWASE (<i>Alternate</i>)
Thanawala & Co, Mumbai	SHRI HEMAL THANAWALA SHRI VIVAN THANAWALA (<i>Alternate</i>)
The Bombay Textile Research, Association, Mumbai	SHRI SHAIKH RIYAZ AHMED DR PRASANTA KUMAR PANDA (<i>Alternate</i>)
Universal Yarn & Tex Pvt Ltd, Kanpur	SHRI RAJIV K. BHARTIYA
U P Textile Technological Institute, Kanpur	DR PRASHANT VISHNOI
BIS Directorate General	SHRI J. K. GUPTA, SCIENTIST 'E'/DIRECTOR AND HEAD (TEXTILES) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)]

Member Secretary

SHRI TANISHQ AWASTHI
SCIENTIST 'B'/ASISTANT DIRECTOR
(TEXTILES), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 39 (24422).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : Manakalya, 5 th Floor/MTNL CETTM, Technology Street, Hiranandani Gardens, Powai Mumbai 400076	{ 25700030 25702715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.