

वस्त्रादि — हथकरघा ऊनी कंबल, प्राकृतिक
ग्रे/भूरा — विशिष्टि
(तीसरा पुनरीक्षण)

**Textiles — Handloom Wool Blankets,
Natural Grey/Brown — Specification**
(*Third Revision*)

ICS 59.080.30

© BIS 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002

www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard (Third Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Handloom and Khadi Sectional Committee had been approved by the Textiles Division Council.

This standard was first published in 1957 and subsequently revised in 1972, and 1980. This revision has been brought out to standard has again been revised to incorporate the following changes:

- a) Tolerances for breaking load has been incorporated;
- b) Marking clause has been modified;
- c) References to Indian Standards have been updated;
- d) *pH* value of aqueous extract has been incorporated; and
- e) Sampling plan has been updated.

The composition of the Committee responsible for the formulation of this standard is given in [Annex C](#).

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Indian Standard***TEXTILES — HANDLOOM WOOL BLANKETS, NATURAL
GREY/BROWN — SPECIFICATION***(Third Revision)***1 SCOPE**

1.1 This standard prescribes constructional particulars and other requirements for two varieties of handloom wool blankets, namely, barrack blankets, natural grey in shade and hospital blankets, natural brown in shade.

1.2 This standard does not specify general appearance and feel of the blankets (*see* [4.3](#)).

2 REFERENCES

The standards listed in [Annex A](#) contain provisions which, through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards.

3 MANUFACTURE**3.1 Yarn**

The yarn shall be spun on woollen system. Yarn for Type A blankets shall be manufactured from 100 percent wool having average fibre fineness of up to 41 microns, while that for Type B blankets shall be made from a blend of a minimum of 90 percent wool, having average fineness of up to 41 microns, and a maximum of 10 percent viscose rayon or nylon (*see* Note in [Table 2](#)).

3.2 Blankets

The blankets shall be properly washed and shall be free from grease, soap, filling or any other admixture which would give fictitious mass or firmness.

3.2.1 The blankets shall be milled and given a raised finish.

3.2.2 The hospital blankets shall have white borders, 5 cm wide, running along the length of the blankets, woven at a distance of 10 cm from each edge.

3.2.3 The blankets shall be rendered mothproof with dichloro-diphenyl-trichloro ethane (DDT), or otherwise heavily preserved with naphthalene.

NOTE — The manufacturer shall declare whether the blanket have been rendered mothproof or not.

3.2.4 The blankets when visually examined, both against light and on a flat surface shall not have more than one objectionable flaw per blanket. The objectionable flaws shall be those which immediately strike the eyes of the person examining the blankets and shall be deemed to include:

- a) missing ends and picks;
- b) floats;
- c) cuts and holes;
- d) stains;
- e) weft bars and warp section marks; and
- f) big slubs and knots.

Reference may be made to IS 14466 for details of the flaws.

4 REQUIREMENTS

4.1 The constructional particulars of the blankets shall be as given in [Table 1](#).

4.2 The blanket shall also conform to the requirements given in [Table 2](#).

4.3 Sealed Sample

If in order to illustrate or specify general appearance, feel, shade, etc, of blankets, a sample has been agreed upon and sealed, the supply shall be in conformity with the sample in such respects.

4.3.1 The custody of the sealed sample shall be a matter of prior agreement between the buyer and the seller.

5 SAMPLING**5.1 Lot**

The quantity of blankets of the same type, delivered to a buyer against a dispatch note, shall constitute a lot.

5.2 The conformity of the lot shall be determined on the basis of the tests carried out on samples drawn from the lot.

5.3 Unless otherwise agreed to between the buyer and the seller, the number of blankets selected at random from a lot shall be according to [Table 3](#). To ensure the randomness of selection, methods given in IS 4905 shall be followed.

Table 1 Constructional Particulars of Handloom Wool Blankets, Natural Grey/Brown

(Clause 4.1)

Sl No.	Ends/ dm	Picks/ dm	Mass/ m ² g	Mass per Blanket kg	Breaking Load on Strips 15 cm × 20 cm, <i>Min</i> N (kgf)		Length cm	Width cm	Weave
					Warp way	Weft way			
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)
i)	80	60	650	2.3	950 (97)	660 (67)	230	152	2/2 twill
Tolerance	± 10 percent	± 10 percent	+ 50 g – 20 g	+ 0.02 kg – 0.05 kg	± 10 percent	± 10 percent	± 2 cm		—
Method of test, Refer to	IS 1963		IS 1964	Annex B	IS 1969 (Part 1)		IS 1954		Visual

NOTE — 1 N (Newton) is approximately equal to 0.102 kgf.

Table 2 Other Requirements of Handloom Wool Blankets, Natural Grey/Brown

(Clauses 3.1 and 4.2)

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Relaxation shrinkage, percent, <i>Max</i>	4	IS 665
ii)	Scouring loss, percent, <i>Max</i>	4	Annex B
iii)	DDT, percent, <i>Min</i>	0.3	IS 3522 (Part 2)
iv)	Wool content	<i>see</i> 3.1	IS 8476
v)	Average wool fabric diameter (<i>see</i> Note), <i>Max</i>	44 microns	IS 744
vi)	pH value of aqueous extract	5 to 7.5	IS 1390

NOTE — The blankets having wool fibres of average diameter up to 44 microns may be accepted, if agreed to between the buyer and the seller, with suitable price deviation.

Table 3 Sample Size and Criterion for Conformity

(Clauses 5.3 and 5.4)

Sl No.	Lot Size	Sample Size	Permissible No. of Non-conforming Blankets	Sub Sample Size
(1)	(2)	(3)	(4)	(5)
i)	Up to 90	5	0	3
ii)	91 to 150	8	0	3
iii)	151 to 500	13	1	5
iv)	501 to 1 200	20	1	5
v)	1 201 to 10 000	32	2	8
vi)	10 001 to 35 000	50	3	8
vii)	35 001 to 500 000	80	5	13
viii)	500 001 and above	125	7	13

5.4 Number of Tests and Criterion for Conformity

<i>Sl No.</i>	<i>Characteristic(s)</i>	<i>No. of Tests</i>	<i>Criterion for Conformity</i>
(1)	(2)	(3)	(4)
i)	Visual examination, ends, picks, mass per blanket, length and width	According to col (3) of Table 3	Permissible number of non-conforming blankets does not exceed the corresponding number given in col (4) of Table 3
ii)	Mass per square metre, breaking load, relaxation shrinkage, scouring loss, DDT percent, wool content and wool fibre diameter	According to col (5) of Table 3	All the test specimens meet the relevant requirements

6 MARKING

6.1 The blankets shall be marked with the following:

- a) Name of the material, with type (*see* [3.1](#));
- b) Manufacturer's name, initials or trade-mark, if any;
- c) Month and year of manufacture;
- d) Length and width of the blankets;
- e) Indication of the source of manufacture; and
- f) Other declarations required as per law in force.

6.2 BIS Certification Marking

The product conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules

and Regulations framed thereunder, and the product may be marked with the Standard Mark.

7 PACKING

7.1 The blankets shall be packed in bales in conformity with the procedure laid down in IS 741 or by the method given in [7.2](#) if specifically required by the buyer.

7.2 Fifteen blankets of the same variety shall be individually folded and placed one over the other. The folded blankets shall be wrapped in a layer each of polyethylene film, kraft paper and hessian (305 g/m²) in such a way that hessian forms the outermost layer. Each layer shall have an overlap of minimum 10 cm. The outermost layer shall be suitably stitched with jute twine and the package made secure by means of steel strips or hoops of medium grade. The gross mass of the bale shall normally not exceed 38 kg.

ANNEX A

(Clause 2)

LIST OF REFERRED STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
IS 665 : 1989	Textiles — Determination of dimensional changes of fabrics containing wool on soaking in water (<i>first revision</i>)	IS 1964 : 2001	Textiles — Methods for determination of mass per unit length and mass per unit area of fabrics (<i>second revision</i>)
IS 741 : 1971	Code for inland packaging of woollen and worsted yarn and cloth (<i>first revision</i>)	IS 1969 (Part 1) : 2018/ISO 13934-1 : 2013	Textiles — Tensile properties of fabrics: Part 1 Determination of maximum force and elongation at maximum force using the strip method (<i>fourth revision</i>)
IS 744 : 2000	Textiles — Methods for determination of wool fibre diameter, percentage of medullated fibres and kemp fibre (<i>third revision</i>)	IS 3522 (Part 2) : 1989	Textiles — Estimation of common preservatives: Part 2 (<i>first revision</i>)
IS 1390 : 2022/ ISO 3071 : 2020	Textiles — Determination of pH of aqueous extract (<i>third revision</i>)	IS 4905 : 2015/ ISO 24153 : 2009	Random sampling and randomization procedures (<i>first revision</i>)
IS 1954 : 2024/ ISO 22198 : 2006	Textiles — Fabrics — Determination of width and length (<i>third revision</i>)	IS 8476 : 1977	Method for determination of wool content in woollen textile materials
IS 1963 : 1981	Methods for determination of threads per unit length in woven fabrics (<i>second revision</i>)	IS 14466 : 1997/ ISO 8498 : 1990	Fabrics — Description of defects — Vocabulary

To access Indian Standards click on the link below:

https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knowyourstandards/Indian_standards/isdetails/

ANNEX B

(Table 1 and Table 2)

METHODS OF TEST

B-1 MASS PER BLANKET

B-1.1 Condition all blankets in the test sample to moisture equilibrium in standard atmosphere (65 percent \pm 2 percent relative humidity and 27 °C \pm 2 °C temperature) for a period of 48 h in such a way as to expose as far as possible all portions of the blankets to the atmosphere.

B-1.2 Measure the length and width of each blanket, correct to the nearest centimetre and determine the mass and correct to the nearest 10 g. Calculate the mass of the blanket of dimensions specified in [Table 1](#).

B-2 SCOURING LOSS**B-2.1 Test Specimen**

From each piece in the test sample cut a test specimen square in shape, with sides parallel to warp and weft threads, and weighing approximately 10 g.

B-2.2 Procedure

B-2.2.1 Heat the test specimen to constant mass in a

drying oven at 105 °C \pm 3 °C and determine its mass accurately.

NOTE — Constant mass shall be deemed to have been reached, if the difference between the two successive weighings at an interval of 20 min is less than 0.05 percent.

B-2.2.2 Extract the above test specimen with a mixture of benzene and methyl alcohol in the proportion of 3 : 2 in a Soxhlet apparatus for 4 h at the rate of 5 extractions per hour, by placing the specimen in a thimble and covering it with cotton wool previously extracted with the above mixture of benzene and methyl alcohol. Distil off the solvents from the extract. Heat the residue to a constant mass (*see* Note under [B-2.2.1](#)) at 105 °C \pm 3 °C and determine the mass accurately.

B-2.3 Calculations

$$\text{Scouring loss, percent} = 100 \times \frac{a+R}{b+R}$$

where

a = mass of the dry residue ([B-2.2.2](#)); R

= moisture regain percent; and

b = mass of the test specimen ([B-2.2.1](#)).

ANNEX C

(Foreword)

COMMITTEE COMPOSITION

Handloom and Khadi Sectional Committee, TXD 08

<i>Organization</i>	<i>Representative(s)</i>
Weavers Service Centre, Delhi	SHRI VISHESH NAUTIYAL (Chairperson) SHRI VIKAS KUMAR (<i>Alternate</i>)
Center of Excellence for Khadi (COEK) - NIFT, New Delhi	REPRESENTATIVE
Central Pollution Control Board, New Delhi	SHRI P. K. MISHRA SHRI RISHABH SRIVASTAV (<i>Alternate</i>)
CRPF, New Delhi	SHRI D. P. UPADHYAY SHRI SANJEEV KUMAR SINGH (<i>Alternate</i>)
Department of Handlooms & Textiles, Chennai	SHRI THIRU R. RAGHUNATH SHRI THIRU K. MUNUSAMY (<i>Alternate</i>)
Fabindia, New Delhi	REPRESENTATIVE
Flag Foundation of India, New Delhi	SHRI ASHIM KOHLI
Gandhigram Rural Institute, Dindigul	DR B. SENTHIL KUMAR
Haryana Khadi Gramodyog Sangh, Karnal	SHRI PAWAN GARG SHRI R. S. YADAV (<i>Alternate</i>)
ICAR – Central Institute for Research on Cotton Technology (CIRCOT), Mumbai	DR SUJATA SAXENA DR A. S. M. RAJA (<i>Alternate</i>)
Indian Institute of Handloom Technology (IIHT), Salem	DR P. THENNARASU
Indian Institute of Handloom Technology, Jodhpur	DR J. SIVAGNAMAM
Indian Institute of Handloom Technology, Varanasi	DR AMIN HIRENBHAI NAVINBHAI SHRI JITENDER TAK (<i>Alternate</i>)
Indian Institute of Technology, Delhi	DR BIPIN KUMAR DR WAZED ALI (<i>Alternate</i>)
Indo Tibetan Border Police, New Delhi	SHRI UTTAM KUMAR SHRI ANAND KUMAR (<i>Alternate</i>)
Jan Sewa Ashram, Aligarh	SHRI R. K. SHARMA SHRI AKHILESH KUMAR AWASTHI (<i>Alternate</i>)
Karnatka Khadi Gramodyog Samyuktha Sangha, Hubli	SHRI K. V. PATTAR SHRI SHIVANANDA S. MATHAPATI (<i>Alternate</i>)
Khadi and Village Industries Commission, Mumbai	SHRI VIJAYSRIDHAR DR SENTIL KUMAR C. B. (<i>Alternate</i>)
Khadi Dyers & Printers, Mumbai	SHRI D. N. BHATT SHRI V. D. JOSHI (<i>Alternate</i>)

<i>Organization</i>	<i>Representative(s)</i>
Khadi Gramodyog Mandal, Rampur	SHRI RAKESH CHAUDHARY SHRI PRINCE CHAUDHARY (<i>Alternate</i>)
Kshetriya Khadi Gramodyog Samiti, Dausa	SHRI R. K. SINGH
Madhya Bharat Khadi Sangh, Gwalior	SHRIMATI NEELU MEKLE SHRI HARISH MEKLE (<i>Alternate</i>)
Mahatma Gandhi Institute for Rural Industrialization, Wardha	SHRI MAHESH KUMAR DR TAPAN RANJAN KAR (<i>Alternate</i>)
Metpalli Khadi Gramodyog Pratisthan, Metpalli	SHRI G. MADHAV
Ministries of Defence (DGQA), New Delhi	SHRI ARVIND COMPATHANE SHRI N. SENTHIL KUMAR (<i>Alternate</i>)
Ministries of Health, New Delhi	REPRESENTATIVE
National Handloom Development Corporation Ltd, Gautam Budh Nagar	DR SAKTHIVEL PERUMAL SAMY SHRI JITENDRA TOLAMBIYA (<i>Alternate</i>)
Northern India Textile Research Association, Ghaziabad	DR M. S. PARMAR SHRI SANJEEV SHUKLA (<i>Alternate</i>)
Northern Railways, New Delhi	SHRI SANJEEV KUMAR JAIN SHRI RAJESH KUMAR (<i>Alternate</i>)
Office of the Development Commissioner for Handlooms, New Delhi	SHRI SIDDHARTH SINGH SHRI VINAY KUMAR (<i>Alternate</i>)
Orient Processes Pvt Ltd, Guwahati	SHRI ROBIN CHANDRA GOSWAMI SHRI RAJ BURAGOHAJIN (<i>Alternate</i>)
Rastriya Khadi Gramodyog Federation, Moradabad	SHRI ANIL KUMAR SINGH SHRI KULDEEP SINGH (<i>Alternate</i>)
Swastik Gramodyog Samiti, Delhi	SHRI M. L. PATHAK SHRI ABHISHEK DIXIT (<i>Alternate</i>)
The Cotton Textiles Export Promotion Council (TEXPROCIL) 	DR SIDDHARTHA RAJAGOPAL SHRI RAJESH SATAM (<i>Alternate</i>)
The Handloom Export Promotion Council, Chennai	DR M. SUNDAR SHRI N. SREEDHAR (<i>Alternate</i>)
The Tamil Nadu Handloom Weavers' Cooperative Society Ltd, Chennai	SHRI T. N. VENKATESH, I.A.S. SHRI K. KATHIRESAN (<i>Alternate</i>)
BIS Directorate General	SHRI J. K. GUPTA, SCIENTIST 'E'/DIRECTOR AND HEAD (TEXTILES) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)]

Member Secretary
SHRI SWAPNIL
SCIENTIST 'B'/ASSISTANT DIRECTOR
(TEXTILES), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 08 (24032).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

Central : 601/A, Konnectus Tower -1, 6th Floor,
DMRC Building, Bhavbhuti Marg, New
Delhi 110002

Telephones

{ 2323 7617

Eastern : 8th Floor, Plot No 7/7 & 7/8, CP Block, Sector V,
Salt Lake, Kolkata, West Bengal 700091

{ 2367 0012
{ 2320 9474

Northern : Plot No. 4-A, Sector 27-B, Madhya Marg,
Chandigarh 160019

{ 265 9930

Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113

{ 2254 1442
{ 2254 1216

Western : 5th Floor/MTNL CETTM, Technology Street, Hiranandani Gardens,
Powai, Mumbai 400076

{ 2570 0030
{ 2570 2715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.