

वस्त्रादि — अपतटीय स्टेशन के रखरखाव
के लिए रेशों से बनी रस्सियाँ
भाग 5 अरामिड

**Textiles — Fibre Ropes for
Offshore Station Keeping
Part 5 Aramid**

ICS 59.080.50

© BIS 2024
© ISO 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002

www.bis.gov.in www.standardsbis.in

NATIONAL FOREWORD

This Indian Standard which is identical to ISO 18692-5 : 2024 'Textiles — Fibre ropes for offshore station keeping — Part 5: Aramid' issued by the International Organization for Standardization (ISO) was adopted by the Bureau of Indian Standards on recommendation of the Cordage Sectional Committee and after approval of the Textiles Division Council.

The text of ISO standard has been approved as suitable for publication as Indian Standard without deviations. Certain conventions are, however, not identical to those used in Indian Standards. Attention is particularly drawn to the following:

- a) Wherever the words 'International Standard' appear referring to this standard, they should be read as 'Indian Standard'; and
- b) Comma (,) has been used as a decimal marker while in Indian Standards, the current practice is to use a point (.) as the decimal marker.

In this adopted standard, reference appears to the following International Standards for which Indian Standards also exist. The corresponding Indian Standards which are to be substituted in their respective places are given below along with its degree of equivalence for the editions` indicated.

<i>International Standard</i>	<i>Corresponding Indian Standard</i>	<i>Degree of Equivalence</i>
ISO 1968 Textiles — Fibre ropes and cordage — Vocabulary	IS 3871 : 2013/ISO 1968 : 2004 Fibre ropes and cordage — Vocabulary (<i>third revision</i>)	Identical
ISO 18692-1 : 2018 Fibre ropes for offshore station keeping — Part 1: General specification	IS 17929 (Part 1) : 2022/ISO 18692-1 : 2018 Fibre ropes for offshore station keeping: Part 1 General specification	Identical

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Contents

	Page	
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Materials	1
5	Requirements — Rope properties	2
	5.1 Minimum breaking strength.....	2
	5.2 Minimum core tenacity.....	2
	5.3 Axial compression fatigue properties.....	2
	5.4 Torque properties.....	2
	5.5 Cyclic loading performance.....	2
	5.6 Particle ingress protection.....	3
6	Requirements — Rope layout and construction	3
7	Rope testing	3
	7.1 Type testing.....	3
	7.1.1 General.....	3
	7.1.2 Sampling.....	3
	7.1.3 Breaking strength, core tenacity, and stiffness tests.....	3
	7.1.4 Axial compression fatigue properties test.....	3
	7.1.5 Torque properties tests.....	3
	7.1.6 Linear density test.....	4
	7.1.7 Cyclic loading (endurance) test.....	4
	7.1.8 Protective cover thickness.....	4
	7.1.9 Particle ingress protection.....	4
	7.2 Testing of current production.....	4
8	Report	4
9	Certification	4
10	Marking, labelling and packaging	4
	Annex A (normative) Fibre qualification and testing	5
	Annex B (normative) Axial compression fatigue properties test	6
	Annex C (informative) Additional information and guidance	8
	Bibliography	9

Indian Standard

TEXTILES — FIBRE ROPES FOR OFFSHORE STATION KEEPING
PART 5 ARAMID

1 Scope

This document specifies the main characteristics and test methods of new aramid fibre ropes used for offshore stationkeeping.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1968, *Fibre ropes and cordage — Vocabulary*

ISO 18692-1:2018, *Fibre ropes for offshore stationkeeping — Part 1: General specification*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1968, ISO 18692-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

aramid

long-chain synthetic polyamide in which at least 85 % of the amide linkages are attached directly to two aromatic rings

Note 1 to entry: Adapted from ISO 2076:2021, 5.9.

3.2

axial compression fatigue

failure mode for fibre rope such as *aramid* (3.1) under low tension or compression

4 Materials

The fibre used in the core of the rope shall be aramid fibre, with an average tenacity of not less than 1,8 N/tex, and shall be qualified and tested in accordance with [Annex A](#).

Rope cover material and other materials employed in rope assembly shall be in accordance with ISO 18692-1.

5 Requirements — Rope properties

5.1 Minimum breaking strength

The minimum breaking strength (MBS) of the rope (spliced), when tested according to ISO 18692-1, shall conform to [Table 1](#).

Table 1 — Minimum breaking strength (MBS)

Reference number(RN) ^a	Minimum breaking strength kN
80	2 500
90	3 100
100	3 900
106	4 400
112	5 000
118	5 600
125	6 300
132	7 000
140	7 800
150	8 700
160	10 000
170	11 200
180	12 500
190	14 000
200	15 500
212	17 500
224	19 500

^a The reference number corresponds to the approximate outer diameter of the rope, in millimetres (mm). Actual diameters may vary for a given reference number.

5.2 Minimum core tenacity

The minimum tenacity of the aramid rope core shall be 0,90 N/tex, measured according to ISO 18692-1. All samples tested shall comply with this minimum value.

5.3 Axial compression fatigue properties

The rope shall have demonstrated a residual strength not less than 95 % of MBS, following the axial compression fatigue test method in [Annex B](#). Additional information is given in [Annex C](#).

5.4 Torque properties

Torque-neutral rope or torque-matched rope shall be defined according to ISO 18692-1.

5.5 Cyclic loading performance

The rope shall have demonstrated performance under cycling loading following the requirements of ISO 18692-1.

5.6 Particle ingress protection

Unless otherwise specified, the rope shall be constructed with a protection of the core against the ingress of particles in accordance with ISO 18692-1.

6 Requirements — Rope layout and construction

Rope layout and construction shall be in accordance with ISO 18692-1.

7 Rope testing

7.1 Type testing

7.1.1 General

Type tests shall be performed in accordance with ISO 18692-1 and the specific requirements of this clause.

7.1.2 Sampling

The number of rope samples to be tested is given in [Table 2](#).

Table 2 — Number of samples for testing

Test	Number of samples
Breaking strength, core tenacity, and stiffness ^d	3
Axial compression fatigue ^a	1
Torque properties ^b	1
Linear density	1
Cyclic loading endurance ^c	1
^a See 7.1.4 .	
^b See ISO 18692-1:2018, 7.1.4.	
^c See ISO 18692-1:2018, 7.1.6.	
^d See ISO 18692-1:2018, 7.1.3	

7.1.3 Breaking strength ,core tenacity, and stiffness tests

The number of samples from [Table 2](#) shall be tested, and each sample shall be capable of meeting the requirements of [5.1](#) and of [5.2](#).

NOTE The measurements of the dynamic stiffness at end of bedding-in — and, when required, those of the quasi-static stiffness and the dynamic stiffness at several mean load level — are performed for design purposes only. There are no acceptance criteria on these parameters.

7.1.4 Axial compression fatigue properties test

One sample shall be tested for axial compression fatigue properties.

There is no need to perform this test when data are available from the previous qualification test of another rope with the same design, material and method of manufacture of rope core, and a size not less than reference number 90.

7.1.5 Torque properties tests

Where applicable, torque properties tests shall be performed according to the procedure specified in ISO 18692-1:2018, 7.1.4 and Annex B.

7.1.6 Linear density test

The linear density shall be calculated from the measured mass and elongation according to the method defined in ISO 18692-1:2018, 7.1.5 and Annex B.

7.1.7 Cyclic loading (endurance) test

The cyclic loading endurance test shall be performed according to the procedure specified in ISO 18692-1.

The residual strength of the rope shall be not less than 80 % of the MBS.

7.1.8 Protective cover thickness

The thickness of the protective cover shall be verified. See ISO 18692-1:2018, 7.1.7

7.1.9 Particle ingress protection

See [5.6](#) and ISO 18692-1:2018, Annex B.

7.2 Testing of current production

Testing of current production shall be in accordance with ISO 18692-1:2018, 7.2.

8 Report

The report shall be in accordance with ISO 18692-1.

9 Certification

Certification shall be in accordance with ISO 18692-1.

10 Marking, labelling and packaging

The marking, labelling and packaging shall be in accordance with ISO 18692-1.

Annex A

(normative)

Fibre qualification and testing

A.1 General

Fibre qualification and testing shall be in accordance with ISO 18692-1:2018, Annex A, and the following requirements.

A.2 Fibre testing — Hydrolysis properties of aramid fibres

The material shall have a residual strength of at least 90 % of its nominal value (new fibre), after immersion for two weeks in 80 °C water (alternatively 20 weeks at 60 °C).

NOTE The water for this test can be either natural or artificial seawater (e.g. ASTM D 1141).

Testing may be performed on fibres or small cords (braided or twisted).

Accelerated test based on a factor 1 000 in time over 60 °C increase of temperature, e.g. see ISO 9080, to simulate the conditions of a mooring line (20 years in seawater at 4 °C to 20 °C). Test duration may be adjusted if this can be documented by suitable test data.

Annex B

(normative)

Axial compression fatigue properties test

B.1 General

This annex specifies the requirements for axial compression fatigue properties test of aramid ropes for offshore station keeping.

B.2 Testing conditions

B.2.1 Rope samples

The axial compression fatigue tests shall be performed on one sample of the full-size rope. Terminations of samples shall be identical to those used in supplied ropes.

Termination fittings shall be provided with the same type of material and the same profile and dimensions (radius, groove shape) as the thimbles for the supplied rope.

B.2.2 Ambient conditions

The axial compression fatigue test shall be performed under ambient conditions similar as those described for cyclic loading endurance test (see ISO 18692-1:2018, B.2.2).

B.2.3 Testing machine and measurement

The testing machine and the measurement system shall be in accordance with the provisions of ISO 18692-1:2018, B.2.3 and B.2.4. The machine shall be capable of accurately controlling the trough load at 1 % of MBS.

B.3 Testing

B.3.1 Test procedure

The axial compression fatigue test shall be performed according to the following steps.

- a) The sample shall be soaked for at least 4 h in fresh water.
- b) The test piece shall be installed in the test machine.
- c) A load of 2 % of MBS shall be applied.
- d) The extensometer shall be installed in a section of the rope undisturbed by the termination.
- e) A tension of 50 % of the rope MBS shall be applied at a rate of 10 % MBS/min and held for 30 min.
- f) The tension shall be reduced to 20 % of the rope MBS, at a rate of 10 % MBS/min.
- g) Cycling tension between 10 % and 30 % of the rope MBS shall be applied 300 times at a frequency between 0,03 Hz and 0,1 Hz.
- h) Cycling tension between 1 % and 20 % of the rope MBS shall be applied 2 000 times at a frequency between 0,03 Hz and 0,1 Hz.

- i) Unload the sample and pull the rope to failure at a loading rate of approximately 20 % of MBS/min.

B.3.2 Recorded data

The following data shall be recorded:

- type and length of the sample, linear density, and MBS;
- applied cyclic tension load;
- residual strength and as % of MBS.

Annex C (informative)

Additional information and guidance

C.1 Axial compression fatigue of aramid fibre

The main characteristics of aramid fibre that make it attractive for mooring applications are its high strength, high modulus, and low creep properties even at elevated temperatures^{[12], [15]}. However, compared to PET fibres, aramid fibre is more susceptible to damage from axial compression fatigue. In a rope, this effect will appear when subjected to tension-tension cycles at low loads. This susceptibility contributed to the premature failure of the first aramid fibre mooring rope deployed in 1983^{[8], [9]}. However, in the same period, aramid fibre ropes were successfully used^[7] indicating that the actual risk from compression fatigue on a rope level depends on the actual rope design and handling.

Studies and design improvements to address axial compression fatigue issues had resulted in several successful trials or use of aramid fibre mooring or tugging rope^{[3], [4], [6], [12], [15]}. Care should be taken to properly design and test aramid fibre ropes for axial compression fatigue performance in order to ensure endurance of the rope in station keeping use.

C.2 Technical considerations

C.2.1 To avoid failures due to improper design of a rope, it is important to understand and distinguish the factors that play a role in causing compression fatigue. Compression fatigue should be separated in the following effects.

a) Tension-tension fatigue due to cycling at low loads:

Cycling at low loads can give more damage to materials than cycling the same range at a higher load. With aramids, this effect can be more explicit than with, e.g. PET^[13], but the principle is similar. The cause of this fatigue effect is partly from the fact that aramids are less abrasion-resistant. During the low load cycling, the movement in a rope is relatively high causing abrasion, but this can be minimized by applying a marine finish and rope jacket material^{[12], [13], [15]}. This has been demonstrated for marine finished aramids with a commonly utilized testing standard for tension fatigue the thousand cycle load limit (TCLL), see Reference ^[12].

b) Compression of filaments due to length differences, e.g. in the splice area:

When aramid filaments are compressed for more than a 0,6 % strain (up to 1 %), a weak spot will be created which is generally referred to as a kink-band^[14]. The effect of such kink-band with regards to the strength of the filament is only significant when the fibre is repetitively compressed more than 0,6 % for at least several hundreds of cycles. When the fibre is subjected to 0,5 % or less compressive strain, studies have showed that no strength loss is found even after several hundred thousands of cycles^[8]. Especially when filaments are locked into their position, this effect might appear. This affects the splice area (and ropes with large length differences within the rope also causing low strength efficiency).

C.2.2 The risk from the axial compression fatigue can be minimized by the following methods.

- a) Improve rope design to minimize local compression especially in the splice areas;
- b) Establish proper rope minimum tension criteria and analysis procedure;
- c) Conduct rope axial compression fatigue test to demonstrate adequate resistance to failure.

Bibliography

- [1] ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*
- [2] ASTM D1141, *Standard Practice for the Preparation of Substitute Ocean Water*
- [3] ASSAYAG M.I., CASTRO G. Minami, K., Assayag, S., Campos Basin, *A Real Scale Lab for Deepwater Technology Development*, OTC 8492, 1997
- [4] CHI C.H., LUNDHILD E.M., VESELIS T., HUNTLEY M.B. *Enabling ultra-deepwater mooring with aramid fiber rope technology*, OTC 20074, 2009
- [5] FRANÇOIS M. DAVIES P., Grosjean F., Legerstee F., *Modelling Fiber Rope load elongation properties - Polyester and other fibers*, OTC 20846, 2010
- [6] KORALEK A.S., BARDEN D.K. *Performance of a Lightweight Aramid Mooring Line*, OTC 5381, 1987
- [7] MCKENNA H.A., HEARLE J.W.S., O'HEAR N., *Handbook of fibre rope technology*. Woodhead Publishing, Cambridge, England, 2004, pp. 366.
- [8] RIEWALD P.G. *Performance Analysis of an Aramid Mooring Line*, OTC 5187, 1986
- [9] RIEWALD P.G., WALDEN R.G., WHITEHILL A.S., KORALEK A.S., *Design and Deployment Parameters Affecting the Survivability of Stranded Aramid Fiber Ropes in the Marine Industry*. IEEE Oceans, 1986
- [10] ASTM D7269, *Standard Test Methods for Tensile Testing of Aramid Yarns*
- [11] WELLER S., JOHANNING L., DAVIES P., BANFIELD S.J., *Synthetic mooring ropes for marine renewable energy applications*, Renewable Energy, 2015
- [12] RIDGE I.M.L., WANG P., GRABANDT O., O'HEAR N. *Appraisal of ropes for LNG moorings*, OIPEEC, ODN 0918, 2015
- [13] VANNUCCHI DE CAMARGO F., GUILHERMEA C.E.M., FRAGASSA C., PAVLOVIC A., *Cyclic stress analysis of polyester, aramid, polyethylene and liquid crystal polymer yarns*, Acta Polytechnica **56**(5):402–408, 2016
- [14] KNOESTER H., CORNELISSEN B. *The effect of compression on the tenacity of high-performance fibers*, OIPEEC, ODN 0997, 2022
- [15] VAN WEZEL M.J., VAN DEN HEUVEL H.N. *Rope lifetime estimation for the delta escort tug active constant tension winch*, OIPEEC, ODN 0993, 2022

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 09 (25725).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : 5 th Floor/MTNL CETTM, Technology Street, Hiranandani Gardens, Powai Mumbai 400076	{ 25700030 25702715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.