

---

---

# पीसने का सूचकांक — परीक्षण पद्धति

( पहला पुनरीक्षण )

## Grindability Index — Method of Test

( First Revision )

ICS 25.080.50

© BIS 2025

Follow us @



भारतीय मानक ब्यूरो  
BUREAU OF INDIAN STANDARDS  
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI - 110002  
[www.bis.gov.in](http://www.bis.gov.in) [www.standardsbis.in](http://www.standardsbis.in)

July 2025

Price Group 4

## FOREWORD

This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Chemical Engineering Plants and Related Equipment Sectional Committee had been approved by the Mechanical Engineering Division Council.

This standard was first published in 1982. This standard has been revived to keep pace with the latest technological developments and international practices. Also, in this revision, the standard has been brought into the latest style and format of Indian Standards, and references of Indian Standards, wherever applicable have been updated.

This standard provides a method for determining grindability index of particular materials which are subjected to shear force during their size reduction process. In a large number of size reduction units, the materials are ground by shear force applied between two surfaces. In such cases the strength of the material under shear is an important criterion.

The grindability of a material is a measure of the ease with which it can be ground and as such it reflects some of the physical properties of the material like hardness, strength, tenacity and fracture.

The composition of the Committee, responsible for the revision of this standard is given in [Annex A](#).

In reporting the result of a test or analysis made in accordance with this standard, is to be rounded off, it shall be done in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Indian Standard*  
**GRINDABILITY INDEX — METHOD OF TEST**  
*( First Revision )*

**1 SCOPE**

The standard covers a test method for determining grindability index for materials subjected which are subjected to shear for size reduction.

**2 REFERENCES**

The standards given below contain provisions which, through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards:

| <i>IS No.</i>          | <i>Title</i>  |
|------------------------|---|
| IS 460 (Part 2) : 2020 | Test Sieves — Specification: Part 2 Perforated plate test sieves ( <i>fourth revision</i> ) |
| IS 4642 : 2024         | Ball, pebble and tube mills — Code of practice ( <i>first revision</i> )                    |

**3 DEFINITION**

**3.1 Grindability** — It is the resistance of a material to comminution.

NOTE — The absolute grindability cannot be measured. However, relative grindability can be measured either by direct or indirect measurement.

**4 METHOD FOR DETERMINING GRINDABILITY INDEX****4.1 Test Equipment**

The components and details of test equipment shall be as follows:

- Ball mill;
- Balls of standard sizes and weights;
- Vibrating sieve shaker;
- Standard sieves as per IS 460 (Part 2);
- Balances with weight boxes — 2 (one analytical and one up to 2 000 g);
- Trays for sampling — 1 m × 1 m; and
- Measuring cylinder.

**4.1.1 Ball Mill**

The ball mill used shall be as per IS 4642, cylindrical in shape with smooth inside surface and with round corners. The mill shall have the following internal dimensions:

|          |           |
|----------|-----------|
| Diameter | : 30.5 cm |
| Length   | : 30.5 cm |

The mill shall be provided with a mechanical revolution counter and shall be rotated at a constant speed of 70 rev/min.

**4.1.2** The balls shall be of forged alloy steel with mirror finish. The ball charge shall consist of 285 balls with total weight  $20\,125\text{ g} \pm 25\text{ g}$ . The size distribution of the ball charge shall be:

| <i>Sl No.</i> | <i>Nominal Size</i><br>mm | <i>No. of</i><br><i>Balls</i> | <i>Weight</i><br>g |
|---------------|---------------------------|-------------------------------|--------------------|
| (1)           | (2)                       | (3)                           | (4)                |
| i)            | 38.0                      | 43                            | 8 730              |
| ii)           | 31.5                      | 67                            | 7 197              |
| iii)          | 25.0                      | 10                            | 705                |
| iv)           | 19.0                      | 71                            | 2 085              |
| v)            | 12.5                      | 94                            | 1 441              |

**4.2 Test Procedure**

**4.2.1** About 25 kg of the representative sample shall be sufficient to carry out grindability test. The sample shall first be crushed to 6 mm in jaw crusher. The 6 mm crushed sample shall then be crushed through rolls and screened through 2.8 mm sieve. Crushing and sieving of the oversize shall be continued until the whole sample passes through the 2.8 mm sieve. A screen analysis of 2.8 mm size sample shall be made using a sieve set in the range of 2.36 mm to 150 microns sieves.

NOTE — For taking samples from the 25 kg lot, standard sampling procedure like coning and quartering shall be used.

**4.2.2** The 80 percent passing size of test sample ( $F$ ) shall be determined by plotting cumulative weight passing against size in microns.

**4.2.3** 700 ml of the 2.8 mm size sample shall be weighed and placed in the ball mill. To take 700 ml of the sample, the material 2.8 mm size shall be placed in a 1 000 ml measuring cylinder, 50 mm diameter, and compacted by shaking to yield a

To access Indian Standards click on the link below:

[https://www.services.bis.gov.in/php/BIS\\_2.0/bisconnect/knownyourstandards/Indian\\_standards/isdetails/](https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knownyourstandards/Indian_standards/isdetails/)

volume of 700 ml. The measuring cylinder shall be placed on a vibrating sieve shaker for 30 s.

**4.2.4** The sample shall be grounded for a known number of revolutions ( $N$ ) say 100. The grounded sample shall be removed and screened through a specific sieve of ( $P_1$ ) microns.

**4.2.5** The screened undersize produce shall be weighed, from which the quantity finer than ( $P_1$ ) size (undersize) originally present in the test sample shall be deducted so as to get the net undersize produce due to grinding for ( $N$ ) revolutions. From this, the net weight grinded per revolution shall be calculated ( $G_{op}$ ).

**4.2.6** A second feed sample for the ball mill shall be prepared by mixing the screen oversize with a fresh test sample from the stock so as to get the total weight of the same as in [4.2.3](#).

**4.2.7** The grinding and screening as given in [4.2.3](#) to [4.2.5](#) shall be repeated until a circulating load of 25 percent is achieved, which is equivalent to 28.6 percent of the mill discharge (finer than  $P_1$  size) at equilibrium under standard conditions. The average quantity of finer produce per revolution ( $G_{op}$ ) shall be calculated from the last two or three grinds.

**4.2.8** The final produce obtained shall be

screen analyzed, so that the sieve size in microns ( $P$ ) through which 80 percent of the produce passes shall be determined.

## 5 CALCULATION OF GRINDABILITY UNDER CIRCULATING LOAD

The following equation shall be used for calculating grindability index ( $G_i$ ) in kWh/tonne:

$$G_i = \frac{44.5 \times 1.1}{(P_1)^{0.23} \times (G_{op})^{0.82} \times \left[ \frac{10}{\sqrt{P}} \times \frac{10}{\sqrt{F}} \right]}$$

where

- $P_1$  = screen size in microns;
- $G_{op}$  = net weight grinded per revolution;
- $P$  = sieve size in micron through which 80 percent produce passes; and
- $F$  = sieve size in micron through which 80 percent feed passes.

### NOTES

**1** As already mentioned, different sizes of sieves may be used in [4.2.4](#) ( $P_1$ ). However, by using fine sieves, the sieving is inaccurate and takes long time. Normally 150  $\mu$ m size sieve shall serve the purpose but sieving has to be done twice.

**2** 1 tonne = 1 000 kg.

## ANNEX A

(Foreword)

## COMMITTEE COMPOSITION

Chemical Engineering Plants and Related Equipment Sectional Committee, MED 17

| <i>Organization</i>   | <i>Representative(s)</i>   |
|---|--|
| CSIR - Indian Institute of Petroleum, Dehradun  | DR MRITUNJAY KUMAR SHUKLA ( <b><i>Chairperson</i></b> )  |
| Advance Valves Global, Noida  | SHRI PRANAY S. GARG<br>SHRI RAJIV GUPTA ( <i>Alternate</i> )   |
| Auma India Private Limited, Bengaluru   | SHRI GIRISH PN<br>SHRI MOHAN KUMAR KT ( <i>Alternate I</i> )<br>SHRI PAVAN KUMAR A. ( <i>Alternate II</i> )  |
| Bharat Heavy Electrical Limited, New Delhi  | SHRI Y. SRINIVASA RAO<br>SHRI ABHISHEK KUMAR PANDEY ( <i>Alternate I</i> )<br>SHRI RAJESH RANJAN ( <i>Alternate II</i> )<br>SHRI SUBHASHISH GUPTA ( <i>Alternate III</i> ) |
| Bharat Petroleum Corporation Limited Corporate Research & Development Centre, Greater Noida | MS ISHA KHULLAR<br>SHRI VINOD KUMAR ( <i>Alternate</i> )   |
| Bhumistha Infra Services, Navi Mumbai   | SHRI DHAWAL SAXENA   |
| Chemtrols Industries Private Limited, New Delhi   | SHRI P. KRISHNA KUMAR  |
| Confederation of Indian Industry, New Delhi   | SHRI NANDAKUMAR KALATH<br>SHRI ABILASH UTTAM ( <i>Alternate</i> )  |
| Directorate General Factory Advice Service and Labour Institutes, Mumbai                    | SHRI TANOJ CHANDAN<br>SHRI KUNAL SHARMA ( <i>Alternate</i> )   |
| Engineers India Limited, Gurugram   | SHRI HASMUKH K. PARMAR<br>SHRI MRAGANG SHEAKHAR ( <i>Alternate</i> )   |
| Fab-Tech Works and Constructions Private Limited, Mumbai                                    | SHRI AASHISH JAYPRAKASH LAKHANI<br>SHRI PRADEEP ( <i>Alternate</i> )   |
| GMM Pfaudler Limited, Anand   | SHRI DHIREN PANCHAL<br>SHRI SATVIK PATEL ( <i>Alternate</i> )  |
| Kejriwal Casting Limited, Kolkata   | SHRI SANDEEP KEJRIWAL<br>SHRI SABARNA ROY ( <i>Alternate</i> )   |
| L&T Valves, Chennai   | SHRI SURIYANARAYANAN<br>SHRI MASWOOD AHMED ( <i>Alternate</i> )  |
| L&T-Sargent & Lundy Limited, Vadodara   | SHRI PINKESH PATEL<br>SHRI RAVI KUMAR BANCHHOR ( <i>Alternate</i> )  |
| Lathia Rubber Manufacture Company Private Limited, Mumbai                                   | SHRI SANJIV S. LATHIA<br>SHRI ASHIT ( <i>Alternate</i> )   |
| MECON Limited, Ranchi   | SHRI YOGENDRA KUMAR SINGH<br>SHRI ARVIND BHUSHAN ( <i>Alternate</i> )  |

| <i>Organization</i>                                   | <i>Representative(s)</i>   |
|---|--|
| Nuclear Power Corporation of India Limited,<br>Mumbai | SHRI CHANDRAKANT RAJARAM KAKADE<br>SHRI ARUNAVA SINHA ( <i>Alternate</i> )   |
| Project and Development India Limited, Noida          | SHRI SANJIV KUMAR MISHRA<br>SHRI RAJEEV RANJAN KUMAR ( <i>Alternate</i> )  |
| Tata Consulting Engineers Limited, Navi Mumbai        | SHRI SHIVNARAYAN PAREEK<br>SHRI SHIREESH S. SWAMI ( <i>Alternate</i> )   |
| BIS Directorate General                               | SHRI KUMAR ANIMESH, SCIENTIST 'E'/DIRECTOR<br>AND HEAD (MECHANICAL ENGINEERING)<br>[REPRESENTING DIRECTOR GENERAL ( <i>Ex-officio</i> )] |

*Member Secretary*  
MS NEHA THAKUR  
SCIENTIST 'C'/DEPUTY DIRECTOR  
(MECHANICAL ENGINEERING), BIS



## Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

### Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

### Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website- [www.bis.gov.in](http://www.bis.gov.in) or [www.standardsbis.in](http://www.standardsbis.in).

This Indian Standard has been developed from Doc No.: MED 17 (27270).

### Amendments Issued Since Publication

| Amend No. | Date of Issue | Text Affected |
|-----------|---------------|---------------|
|           |               |               |
|           |               |               |
|           |               |               |
|           |               |               |

## BUREAU OF INDIAN STANDARDS

### Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: [www.bis.gov.in](http://www.bis.gov.in)

### Regional Offices:

|   | Telephones               |
|---|--------------------------|
| Central : 601/A, Konnectus Tower -1, 6 <sup>th</sup> Floor,<br>DMRC Building, Bhavbhuti Marg, New<br>Delhi 110002 | { 2323 7617              |
| Eastern : 8 <sup>th</sup> Floor, Plot No 7/7 & 7/8, CP Block, Sector V,<br>Salt Lake, Kolkata, West Bengal 700091 | { 2367 0012<br>2320 9474 |
| Northern : Plot No. 4-A, Sector 27-B, Madhya Marg,<br>Chandigarh 160019   | { 265 9930               |
| Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113   | { 2254 1442<br>2254 1216 |
| Western : 5 <sup>th</sup> Floor/MTNL CETTM, Technology Street, Hiranandani Gardens, Powai<br>Mumbai 400076        | { 25700030<br>25702715   |

**Branches :** AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.