भारतीय मानक Indian Standard

> बोरवेल/नलकूप के लिए असुघटियत पॉलीविनॉयल क्लोराइड (पीवीसी-यू) के चूड़ीदार कॉलम पाइप — विशिष्टि

Unplasticized Polyvinyl Chloride (PVC-U) Threaded Column Pipes for Borewells/Tubewells — Specification

ICS 23.040.20

© BIS 2023



भारतीय मानक ब्यूरो BUREAU OF INDIAN STANDARDS मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002 MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI - 110002 www.bis.gov.in www.standardsbis.in

October 2023

Price Group 11

Plastic Piping System Sectional Committee, CED 50

FOREWORD

This Indian Standard was adopted by the Bureau of Indian Standards, after the draft finalized by the Plastic Piping System Sectional Committee had been approved by the Civil Engineering Division Council.

This standard has been formulated to cover requirements and test methods for unplasticized polyvinyl chloride (PVC-U) threaded column pipes for use with jet and submersible pumps in borewells/tubewells.

It is the responsibility of the purchaser or the supplier to make the appropriate selection of pipes taking into account their particular requirements and any relevant national guidelines or regulations. Relevant guidelines for installation practices should be followed.

The composition of the Committee responsible for the formulation of this standard is given in Annex D.

For the purpose of deciding whether a particular requirement of the standard is complied with, the final value observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

UNPLASTICIZED POLYVINYL CHLORIDE (PVC-U) THREADED COLUMN PIPES FOR BOREWELLS/ TUBEWELLS — SPECIFICATION

1 SCOPE

1.1 This standard covers the requirements of unplasticized polyvinyl chloride (PVC-U) threaded column pipes of the following types and sizes, for use with jet or submersible pumps in borewells/tubewells for water supply:

- a) Bell ended (socketed) type with external thread at spigot end and internal thread at bell (socket) end, of nominal sizes 25 mm, 32 mm and 40 mm; and
- b) Coupler joint type with external threads at both ends, connected with coupler, of nominal sizes 25 mm to 150 mm.

1.2 These pipes are recommended for water temperatures ranging from 1 °C to 45 °C.

2 REFERENCES

The standards listed in Annex A contain provisions which, through reference in this standard, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of these standards.

3 TERMINOLOGY

For the purpose of this standard, the following definitions shall apply:

3.1 Column Pipes — Pipes with external threads at both ends, or with external thread at one end and internal thread at the other end, for carrying out ground water with jet/submersible pump from borewell/tubewell.

3.2 Column Pipe Couplers — Cut piece of pipe with internal threads at both ends to assemble/join the column pipes.

3.3 Bell End Column Pipes — Column pipes with bell and spigot end, in which female (internal) thread is provided at bell end and male (external) thread at spigot end for connection of pipes.

3.4 Nominal Size (DN) — The numerical designation for the size of the pipe other than a pipe designated by thread size, which is a convenient round number approximately equal to the manufactured dimension, in mm.

3.5 Nominal Outer Diameter (d_0) — The specified outside diameter, in mm, assigned to a nominal size.

3.6 Mean Outer Diameter (d_{em}) — The quotient of the outer circumference of a pipe and 3.142 (π) in any cross-section, rounded off to the next higher 0.1 mm.

3.7 Minimum Mean Outer Diameter (d_{em}, Min) — The minimum value for the mean outside diameter as specified for a given nominal size.

3.8 Maximum Mean Outer Diameter (d_{em}, Max) — The maximum value for the mean outside diameter as specified for a given nominal size.

3.9 Outer Diameter at Any Point (d_e) — The value of the measurement of the outer diameter of a pipe through its cross-section at any point of the pipe, rounded off to next higher 0.1 mm.

3.10 Out-of-Roundness (Ovality) — The difference between the measured maximum and the measured minimum outside diameter in the same cross-section of the pipe.

3.11 Nominal Wall Thickness (e_{ne} and e_{nb}) — A numerical designation of the wall thickness of a component which is a convenient round number, approximately equal to the manufacturing dimensions, in mm.

NOTE — e_{nb} and e_{ne} are nominal wall thickness of barrel (thin portion) and end side (thick portion), respectively.

3.12 Wall Thickness at any Point (e_e and e_b) — The value of the measurement of the wall thickness at any point around the circumference of the pipe, rounded off to the next higher 0.1 mm.

NOTE — e_b and e_e are wall thickness at any point of barrel (thin portion) and end side (thick portion), respectively.

3.13 Mean Wall Thickness $(e_{me} \text{ and } e_{mb})$ — The arithmetical mean of at least four measurements

regularly spaced around the circumference and in the same cross-section of the pipe, including the measured minimum and the measured maximum values of the wall thickness in that cross-section, rounded off to the next higher 0.1 mm.

NOTE — $e_{\rm mb}$ and $e_{\rm me}$ are mean wall thickness of barrel (thin portion) and end side (thick portion), respectively.

3.14 Tolerance — The permitted variation of the specified value of a quantity, expressed as the difference between the permitted maximum and the permitted minimum value.

3.15 Working Pressure (*PN*) — The numerical designation of a pipe related to the mechanical characteristics of that pipe used for reference purposes. For plastic piping systems, it corresponds to the allowable operating pressure, in MPa, conveying water at 27 $^{\circ}$ C.

3.16 Allowable Operating Pressure (*PFA*) — The maximum hydrostatic pressure excluding surge which is allowed in continuous use with water within the temperature range concerned. It is calculated using the following equation:

$$PFA = f_{\rm T} \ge PN$$

where

 $f_{\rm T}$ = derating factor depending on water temperature; and PN = working pressure.

NOTE — In cases where a further derating (or uprating) factor depending on the application is required,

$$PFA = f_A \ge f_T \ge PN$$

where

 $f_{\rm A}$ = factor depending on the application.

3.17 Hydrostatic Stress (σ) — The stress induced in the wall of a pipe when a pressure is applied using water as a medium. The hydrostatic stress is related to the applied pressure, *P*, the wall thickness of thin portion at any point, *e*_b, and the mean outside diameter, *d*_{em}, of a pipe and calculated using the following approximation equation:

$$\sigma = \frac{P(d_{\rm em} - e_{\rm b})}{2e_{\rm b}}$$

where σ and *P* are in same units.

3.18 Virgin Material — Material in such form as granules or powder that has not been subjected to use or processing other than that required for its manufacture and to which no reprocessable or recyclable material(s) have been added.

3.19 Own Rework Material — Material prepared from rejected unused pipes, including trimmings from the production of pipes, that will be reprocessed in a manufacturer's plant by a process such as extrusion and for which the complete formulation is known.

4 COMPOSITION

4.1 The material from which the pipe is produced shall consist substantially of unplasticized polyvinyl chloride to which may be added only those additives that are needed to facilitate production of sound and durable pipe of good surface finish and mechanical strength under conditions of use. None of these additives shall be used, separately or together, in quantities sufficient to constitute a toxic, organoleptic or microbial growth hazard or to materially impair the fabrication or welding properties of the pipe, or to impair the chemical, physical or mechanical strength and impact strength) as defined in this standard. The additives to be used shall be selected from IS 10148 and shall be uniformly dispersed.

4.1.1 The monomer content (VCM content) in the resin shall be within the limits specified in **4.4.1** of IS 10151, when tested as per Annex B of IS 10151.

4.1.2 The composition shall be based on PVC resin having a K-value of 64 or greater, when tested in accordance with IS 4669.

4.1.3 A test report or certificate of conformity may be obtained from the manufacturer for the VCM content (*see* **4.1.1**) and K-value (*see* **4.1.2**) of the resin being used, unless the same is tested in an independent laboratory. The frequency of this test report or certificate of conformity shall be once in every three months.

4.2 The addition of not more than 5 percent of the manufacturer's own rework material conforming to this standard is permissible. No other rework material shall be used.

5 COLOUR

The pipe and coupler shall be of regular ivory white colour throughout. Slight colour deviation is permissible.

6 CLASSIFICATION

The pipes shall be classified by pressure ratings (working pressures) at 27 °C as per Table 1. The maximum permissible hydraulic head of different classes of column pipes shall be as given in Table 1.

The maximum safe working stress considered is 14 MPa at 27 $^{\circ}$ C.

Sl No.	Class	Working Pressure, (<i>PN</i>)	Maximum Permissible Hydraulic Head
			m
(1)	(2)	(3)	(4)
i)	Class 1	1.0	100
ii)	Class 2	1.25	125
iii)	Class 3	1.5	150
iv)	Class 4	2.0	200
v)	Class 5	2.5	250
vi)	Class 6	3.5	350
vii)	Class 7	4.0	400

Table 1	Classification	of	Column	Pipes
	(Clause	6)		

7 DIMENSIONS


7.1 The diameters and wall thicknesses of unthreaded column pipes with thick-end portion shall be as given in Table 2 and Table 3 read with Fig. 1A and threaded column pipe with thick/thin portion is shown in Fig. 1B. The dimensional details of unthreaded column pipe couplers shall be as given in Table 4 read with Fig. 1C. The (design indicated as c and d in Fig. 1C) and number of ribs shall be as agreed between the manufacturer and the purchaser so as to ensure proper gripping during installation. The square threads on column pipes and column pipe couplers shall be as shown in Fig. 1D and Fig. 1E, respectively read with Tables 5 and 6. However, the assembly/jointing design (sealing ring/ groove) shown in these figures are typical. The dimensional details of bell-ended pipes shall be as given in Table 7 read with Fig. 2. Belling dimensions of pipe

shall be as per manufacturer's design or as per the mutual agreement between the manufacturer and the purchaser.


7.2 Mean outer diameter and outer diameter at any point of unthreaded column pipes shall be measured according to IS 12235 (Part 1). The pipe diameter shall be measured at the thick end portion of the pipe.

7.3 Wall thickness of unthreaded column pipes shall be measured in accordance with the method given in IS 12235 (Part 1).


7.4 Nominal effective length of column pipe shall be minimum 3 000 mm. The pipes may be supplied in other lengths where so agreed upon between the manufacturer and the purchaser.




1B THREADED PIPE




1C RIBBED COUPLER BEFORE THREADING




NOTE — The assembly/jointing design shown in figure is typical.





All dimensions in millimetres



1E THREADS OF COLUMN PIPE COUPLER

FIG. 1 COUPLER JOINTED THREADED COLUMN PIPES

Table 2 Outer Diameter of Unthreaded Column Pipes

Sl No.	Nominal Size, <i>DN</i>	Diamo	Mean Outer Diameter of Pipe, d _{em}		Diameter Point, d _e
(1)	(2)	Min (3)	Max (4)	Min (5)	<i>Max</i> (6)
(1) i)	25	33.0	33.3	32.8	33.5
ii)	32	42.0	42.3	41.8	42.5
iii)	40	48.0	48.3	47.8	48.5
iv)	50	60.0	60.3	59.8	60.5
v)	65	75.0	75.3	74.8	75.6
vi)	80	88.0	88.4	87.8	88.6
vii)	100	113.0	113.4	112.8	113.6
viii)	125	140.0	140.4	139.8	140.6
ix)	150	165.0	165.4	164.8	165.6

(*Clause* 7.1) All dimensions in millimetres.

8 THREADING OF COLUMN PIPES AND COUPLERS

8.1 Column Pipes

Pipes with external threads at both ends shall be used with couplers. Bell end pipes shall have external threads at one end and internal threads at the other end.

8.2 Column Couplers

Column couplers shall have internal threads at both ends.

8.3 Pipes shall have basic thread dimensions as given in Table 5 read with Fig. 1D. Couplers shall have basic thread dimensions as given in Table 6 read with Fig. 1E.

8.4 Sealing rings and elements made of elastomeric material such as EPDM, and of appropriate dimensions ensuring secure fit, shall be used to seal the joint. These sealing materials shall be of hardness class 60 IRHD as per IS 5382. The design of the profile of the sealing ring is left to the manufacturer as long as the pipe with sealing ring meets the requirements of the standard and ensures leak free installation.

8.4.1 A test report or conformity certificate shall be obtained from the manufacturer of the sealing ring for conformity to IS 5382. The frequency of this test report or conformity certificate shall be once in three months.

8.5 The design for the locking of permanent end pipe with coupler is left to the manufacturer as long as the pipe and coupler assembly meets the requirements of the standard and ensures leak free installation.

8.5.1 The manufacture should declare regarding the use of adhesive/solvent if any. Such material, when used, shall not have any detrimental effect on the quality of water for its intended use.

9 TESTS

9.1 Visual Appearance

The internal and external surfaces of the pipe shall be smooth, clean and free from other defects. Slight shallow longitudinal grooves or irregularities in the wall thickness shall be permissible provided the pipe dimensions remain within permissible limits. The ends shall be clean, smoothly cut and reasonably square to the axis of the pipe.

9.2 Resistance to External Blows at 0 °C

When tested by the method described in IS 12235 (Part 9), the pipe shall have a true impact rate of not more than 10 percent. The total mass of the striker and height of free fall shall correspond to the values given in Table 8.

9.3 Flattening Test

Flatten the specimens of pipe of at least 50 mm length, taken from both end (thick) and barrel (thin) portion of the pipe and from the column pipe coupler, between parallel plates in a suitable press until the distance between the plates is 40 percent of the outside diameter of the pipe or the inner walls of the pipe touch, whichever occurs first. This test shall be carried out in accordance with the method given in IS 12235 (Part 19). The rate of the loading shall be uniform and such that the compression is completed within 2 min to 5 min. On removal of load, examine the specimen for evidence of splitting, cracking or breaking.

Sl No.	Nominal Size, DN	Class of Pipe	Both End Port	, ,	Barrel Port		Length of Thick Portion at Both Side (<i>L</i> 1 and <i>L</i> 3),	Induced Stress, Min
							Min	
			Min	Max	Min	Max		MDa
	mm	mm	mm	mm	mm	mm	mm	MPa
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
		Class 1	2.9	3.30	1.50	1.80	150	12
i)	25	Class 2	3.3	3.80	1.70	2.00	150	12
1)	25	Class 3	3.8	4.40	1.90	2.20	150	13
		Class 4	4.6	5.30	2.40	2.80	150	13
		Class 1	3.3	3.80	1.50	1.80	180	14
		Class 2	3.7	4.30	1.80	2.10	180	14
•••		Class 3	4.3	5.00	2.20	2.50	180	14
ii)	32	Class 4	5.40	6.20	2.80	3.20	180	14
		Class 5	6.50	7.50	3.50	4.00	180	14
		Class 6	8.30	9.60	4.70	5.40	180	14
		Class 7	8.50	9.80	5.80	6.70	200	14
		Class 1	3.50	4.00	1.70	2.00	180	14
		Class 2	4.10	4.70	2.10	2.40	180	14
iii)	40	Class 3	4.90	5.70	2.50	2.90	180	14
		Class 4	5.90	6.80	3.20	3.70	180	14
		Class 5	7.20	8.30	4.00	4.60	180	14 14
		Class 6 Class 7	9.30 9.60	10.70 11.00	5.40 6.50	6.20 7.50	180 200	14 14
		Class 7 Class 1	4.20	4.90	2.10	2.40	180	14
		Class 1 Class 2	4.20 4.90	4.90 5.60	2.10	2.40 3.00	180	14
		Class 2 Class 3	4.90 5.90	5.00 6.80	3.10	3.60 3.60	180	14
:)	50	Class 3 Class 4	3.90 7.20	8.30	4.00	5.60 4.60	200	14
iv)	30							
		Class 5	8.80	10.10	5.00	5.80	200	14
		Class 6	11.10	12.80	6.70 8.20	7.70	200	14
		Class 7	11.30	13.00	8.20	<u>9.20</u> 3.00	200	<u>14</u> 14
		Class 1 Class 2	5.00 6.00	5.80 6.90	2.60 3.30	3.00 3.80	180 180	14 14
		Class 2 Class 3	8.00 7.00	8.90 8.10	3.30 3.90	5.80 4.50	180	14 14
v)	65	Class 3 Class 4	7.00 8.60	8.10 9.90	5.00	4.30 5.80	200	14
		Class 4 Class 5	10.40	9.90 12.00	6.20	7.10	200	14
		Class 5 Class 6	13.50	12.00	8.40	9.70	200	14
		Class 1	5.60	6.40	3.10	3.60	180	14
		Class 1 Class 2	6.50	7.50	3.80	4.40	180	14
	_	Class 2 Class 3	7.90	9.10	4.50	5.20	180	14
vi)	80	Class 4	9.70	11.20	5.90	6.80	200	14
		Class 5	11.60	13.30	7.30	8.40	200	14
		Class 6	15.20	17.50	9.80	11.30	200	14
		Class 1	6.80	7.80	3.90	4.50	180	14
		Class 2	8.20	9.40	4.90	5.70	180	14
•••	100	Class 3	9.60	11.00	5.80	6.70	180	14
vii)	100	Class 4	11.90	13.70	7.60	8.60	200	14
		Class 5	14.30	16.50	9.30	10.70	200	14
		Class 6	19.00	21.90	12.60	14.50	200	14
		Class 1	8.20	9.40	4.90	5.60	230	14
		Class 2	9.70	11.20	6.00	6.90	230	14
viii)	125	Class 3	11.50	13.20	7.20	8.30	230	14
		Class 4	14.40	16.60	9.40	10.80	250	14
		Class 5	17.30	19.90	11.50	13.20	250	14
		Class 6	23.00	26.50	15.60	18.00	250	14

Table 3 Wall Thickness of Different Classes of Unthreaded Column Pipes with Thick-Thin Portion (Clause 7.1)

Sl No.	Nominal Size, <i>DN</i>	Class of Pipe	Both End Port	. ,	Barrel (Port	. ,	Length of Thick Portion at Both	Induced Stress, Min
			Min	Max	Min	Max	Side (L1 and L3), Min	
	mm	mm	mm	mm	mm	mm	mm	MPa
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
		Class 1	9.30	10.70	5.70	6.60	230	14
		Class 2	11.20	12.90	7.10	8.20	230	14
• 、	150	Class 3	13.10	15.10	8.40	9.70	230	14
ix)	150	Class 4	16.60	19.10	11.00	12.70	250	14
		Class 5	20.10	23.10	13.60	15.70	250	14
		Class 6	26.90	31.00	18.40	21.20	250	14

Table 3 (Concluded)

each other with couplers.

Table 4 Dimensional Details of Column Pipe Couplers

Sl No.	Nominal Size, <i>DN</i>		Outer Pipe Coupler, a, Min	Internal Diameter of Column Pipe Coupler, b, Max
		For Classes	For Classes	
(4)		1 to 3	4 to 7	
(1)	(2)	(3)	(4)	(5)
i)	25	45.0	51.0	29.0
ii)	32	55.0	60.0	38.0
iii)	40	62.0	72.0	44.0
iv)	50	80.0	86.0	55.0
v)	65	92.0	99.0	70.0
vi)	80	108.0	115.0	83.0
vii)	100	136	145.0	108.0
viii)	125	165	175.0	134.0
ix)	150	190	205.0	159.0

(*Clause* 7.1) All dimensions in millimetres.

Table 5 Thread Dimensions for Both Male Ends of Column Pipe

(Clauses 7.1 and 8.3)

All dimensions in millimetres.


SI No.	Nominal Size, <i>DN</i>		Male End (Tolerance $^{+0.0}_{-0.3}$)		Free End Side Length, Min		Permanent End Side Length, Min		
		Major Diameter	Minor Diameter	$L_{\rm f}$	$\sum_{l_{\rm f}}$	L_p	lp		
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	
i)	25	32.80	30.80	56.0	3.0	60.0	12	3.0	
ii)	32	41.50	39.50	56.0	3.0	60.0	12	3.0	
iii)	40	47.50	45.50	56.0	3.0	60.0	12	3.0	
iv)	50	59.50	56.50	64.0	3.5	80.0	12	4.0	
v)	65	74.50	71.50	64.0	3.5	80.0	12	4.0	
vi)	80	87.50	84.30	64.0	3.5	85.0	14	4.0	
vii)	100	112.50	109.10	74.0	5.0	85.0	14	6.0	
viii)	125	139.50	135.50	84.0	5.0	104.0	14	6.0	
ix)	150	164.50	160.50	84.0	5.0	104.0	14	6.0	

Sl No.	Nominal Size, DN					Perman Side Len	ent End gth, <i>Min</i>	Pitch
		Major Diameter	Minor Diameter	$L_{\rm f}$	$\sum_{l_{\rm f}}$	\mathcal{L}_{p}	lp	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
i)	25	33.20	31.20	60.0	15	51.0	14	3.0
ii)	32	41.90	39.90	60.6	15	51.0	14	3.0
iii)	40	47.90	45.90	60.6	15	51.6	14	3.0
iv)	50	60.00	57.00	66.3	15	72.3	14	4.0
v)	65	75.00	72.00	66.3	15	72.3	14	4.0
vi)	80	88.20	85.00	66.3	15	77.3	14	4.0
vii)	100	113.30	109.90	76.8	15	77.8	14	6.0
viii)	125	140.30	136.30	86.8	15	95.8	14	6.0
ix)	150	165.30	161.30	86.8	15	95.8	14	6.0

Table 6 Thread Dimensions for Both Female Ends of Column Pipe Coupler

(Clauses 7.1 and 8.3)

All dimensions in millimetres.






FIG. 2 BELL ENDED COLUMN PIPES WITH INTERNAL THREADS AT ONE END AND SPIGOT AT ANOTHER END WITH EXTERNAL THREADS

	(<i>Clause</i> 7.1) All dimensions in millimetres.														
Sl No.	Nominal Size, <i>DN</i>	$D^{+0.2}_{-0.0}$	$D_{1-0.2}^{+0.0}$	$D_2 \stackrel{+0.0}{_{-0.2}}$	Major d ^{+0.0} -0.2	Minor d ^{+0.2} -0.0	$A ^{+2.0}_{-0.0}$	$B^{+2.0}_{-0.0}$	C +2.0 -0.0	E +0.0 -0.2	F ^{+0.0} -0.2	$G^{+0.1}_{-0.0}$	H ^{+0.0} -0.2	Thread Depth	Pitch
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)
i)	25	35.2	30.6	31.1	32.8	31.2	8	51	60	12	48	2.5	3.0	1.0	3.0
ii)	32	43.4	39.3	39.8	41.5	39.9	8	51	60	12	48	2.5	3.0	1.0	3.0
iii)	40	49.4	45.3	45.8	47.5	45.9	8	51	60	12	48	2.5	3.0	1.0	3.0

Table 7 Dimensions of Bell-Ended Pipes

9.4 Tensile Strength and Elongation at Break

When tested by the method described in IS 12235 (Part 13), the average tensile strength of three test specimens cut longitudinally from barrel (thin) portion of the same pipe at maximum load shall not be less than 45 MPa and the elongation at break shall not be less than 30 percent.

The specimen for the test shall be prepared from a section of the pipe. The specimens shall be cut or machined from lengths of pipe in the longitudinal direction, that is, along the pipe axis.

9.5 Ultimate Breaking load

Ultimate breaking load shall be checked at both sides of the threaded assembly of column socketed pipe or cut piece of thick end portion of pipe with coupler. Threaded assembly shall be fitted in suitable end fixtures. End fixtures shall then be mounted on the universal testing machine (UTM) of adequate capacity. The test temperature and test speed shall be (27 ± 2) °C and 10 mm/min, respectively. The jaws of the UTM shall be pulled until the assembly breaks. The pick load shall be noted. Minimum pick load shall be as per Table 9 for all size and class of pipes. A typical ultimate breaking load assembly is shown in Fig. 3 for reference.

9.6 Izod Impact Strength Test

When tested in accordance with the method described in Annex B, the notch izod-impact strength shall not be less than 60 J/m.

9.7 Resistance to Dichloromethane Test

When tested in accordance with the method described in IS 12235 (Part 11), there shall be no attack observed on any part of the surface of test piece taken from pipe and coupler.

9.8 Density

When tested by the method described in IS 12235 (Part 14), the density of the material of the pipe and coupler shall be between 1.40 g/cm^3 and 1.44 g/cm^3 .


9.9 Vicat Softening Temperature

The vicat softening temperature shall not be less than 80 °C when tested by the method described in IS 12235 (Part 2) for both pipe and coupler. The test may be done on a test piece cut from a sample of the pipe used for some other test (such as density or resistance to external blows) as long as that sample has not been subjected to conditions that could influence the Vicat softening temperature.

Sl No.	Nominal Size, <i>DN</i>	Total Mass of Striker	Height of Free Fall	Number of Equidistant Lines to be Drawn
		kg	mm	
(1)	(2)	(3)	(4)	(5)
i)	25	$0.25 \pm 0.5 \%$	$1\ 000 \pm 10$	1
ii)	32	0.25 \pm 0.5 %	$1\ 000 \pm 10$	1
iii)	40	0.25 \pm 0.5 %	$1\ 000 \pm 10$	3
iv)	50	0.25 \pm 0.5 %	$2\ 000 \pm 10$	3
v)	65	0.25 \pm 0.5 %	$2\ 000 \pm 10$	4
vi)	80	$0.50 \pm 0.5 \%$	$2\ 000 \pm 10$	4
vii)	100	$0.50 \pm 0.5 \%$	$2\ 000 \pm 10$	6
viii)	125	$1.00 \pm 0.5 \%$	$2\ 000 \pm 10$	8
ix)	150	$1.00 \pm 0.5 \%$	$2\ 000 \pm 10$	8

 Table 8 Total Mass of Striker and Height of Free Fall for Resistance to External Blows Test

 (Clause 9.2)



3A PIPE WITH COUPLER

3B BELL AND SPIGOT ENDED PIPE

FIG. 3 TYPICAL ULTIMATE BREAKING LOAD ASSEMBLY

SI No.	Nominal Diameter, <i>DN</i>	Class of Pipe	Ultimate Breaking Load, <i>Min</i>
			kg
(1)	(2)	(3)	(4)
		Class 1	588
i)	25	Class 2	717
		Class 3	802
		Class 4	1 008
		Class 1	859
		Class 2	1 023
::)	20	Class 3	1 238
ii)	32	Class 4	1 552
		Class 5	1 906
		Class 6	2 479
		Class 7	2 669

Table 9 Ultimate Breaking Load

(*Clause* 9.5)

SI No.	Nominal	Class of	Ultimate Breaking Load,
	Diameter, DN	Pipe	Min
			kg
(1)	(2)	(3)	(4)
		Class 1	1 113
		Class 2	1 363
		Class 3	1 609
iii)	40	Class 4	2 027
		Class 5	2 489
		Class 6	3 253
		Class 7	3 815
		Class 1	1 720
		Class 2	2 111
i)	50	Class 3	2 495
iv)	50	Class 4	3 168
		Class 5	3 889
		Class 6	5 050
		Class 7	6 007
		Class 1	2 662
		Class 2	3 346
v)	65	Class 3	3 922
		Class 4	4 950
		Class 5	6 033
		Class 6	7 912
		Class 1	3 722
		Class 2	4 525
vi)	80	Class 3	5 314
	00	Class 4	6 851
		Class 5	8 332
		Class 6	10 838
		Class 1	6 018
		Class 2	7 491
vii)	100	Class 3	8 793
		Class 4	11 329
		Class 5	13 639
		Class 6	17 891
		Class 1	9 362
		Class 2	11 371
viii)	125	Class 3	13 523
		Class 4	17 362
		Class 5	20 899
		Class 6	27 446
		Class 1	12 842
		Class 2	15 855
ix)	150	Class 3	18 604
		Class 4	23 905
		Class 5	29 120
		Class 6	38 149

 Table 9 (Concluded)

9.10 Effect on Water

The pipes shall not have any detrimental effect on the composition of water flowing through them. When tested in accordance with the method described in IS 12235 (Part 4) and IS 12235 (Part 10), the quantities of lead, dialkyl tin C4 and higher homologues (measured as tin) and any other toxic substances extracted from the internal walls of the pipes shall not exceed the concentrations as specified in **10.3** of IS 4985 and meet the other requirements given in **10.3.1** of IS 4985.

NOTE — Implementation of the phase-out programme of the Government of India for use of lead stabilizers in PVC pipe and fitting manufacturing shall be borne in mind.

9.11 Hydrostatic Pressure Test

When subjected to internal hydrostatic pressure test in accordance with the procedure given in IS 12235 (Part 8/Sec 1), the pipe shall not fail during the prescribed test duration. The temperature and duration of the test shall conform to the requirement given in Table 10. The test shall be carried out not earlier than 24 h after the pipes have been manufactured. This test should be performed on thin barrel portion.

9.12 Joint Leak Pressure Test

When subjected to internal hydrostatic pressure test in accordance with the procedure given in Annex C, the representative assembly of pipe and coupler or bell end side and spigot end side of pipe sample shall withstand for 1 h without rupture, separation or leakage with an internal hydrostatic pressure of 1.5 times the working pressure (*PN*) at room temperature.

10 SAMPLING AND CRITERIA FOR CONFORMITY

10.1 Acceptance Tests

10.1.1 The scale of sampling and criteria for conformity of a lot for acceptance tests specified in 7, 8 and 9.1 to 9.3 shall be as given in 10.1.5 and 10.1.6 read along with Table 11 and for those specified in 9.4, 9.5, 9.7, 9.8, 9.9, 9.11 and 9.12 shall be as given under 10.1.7.

10.1.2 All pipes, in a single consignment, of the same type, same size and same class, manufactured under essentially similar conditions, shall constitute a lot.

10.1.3 For ascertaining conformity of the lot to the requirements of the specification, samples shall be tested from each lot separately.

10.1.4 The pipes shall be selected at random from the lots in order to ensure randomness of selection, a random number table shall be used. For guidance on the use of random number tables, IS 4905 may be referred to. In the absence of a random number table, the following procedure may be adopted:

Starting from any pipe in the lot, count them as 1, 2, 3, etc, up to r and so on; where r is the integral part of *Nln*, *N* being the number of pipes in the lot and n the number of pipes in the sample. Every 'r th' pipe so counted shall be withdrawn so as to constitute the required sample size.

10.1.5 The number of samples given for the first sample in col (5) of Table 11 shall be taken from the lot and examined for requirements given in 7, 8 and 9.1. A pipe failing to satisfy any of these requirements shall be considered as defective. The lot shall be deemed to have satisfied the requirements if the number of defectives found in the first sample is less than or equal to the corresponding acceptance number given in col (7). The lot shall be deemed not to have met these requirements, if the number of defectives found in the first sample is greater than or equal to the corresponding rejection number given in col (8). If, however, the number of defectives found in the first sample lies between the corresponding acceptance and rejection numbers given in col (7) and (8), a second sample of the size given in col (5) shall be taken and examined for these requirements. The lot shall be considered to have satisfied these requirements if the number of defectives found in the cumulative sample is less than or equal to the corresponding acceptance number given in col (7), otherwise not.

SI No.	Test	Test Temperature, <i>Min</i>	Test Duration (Minimum Holding Time)	Test Pressure, Min
		°C	h	MPa
(1)	(2)	(3)	(4)	(5)
i)	Acceptance Test	27 ± 2	1	$2.5 \times PN$

 Table 10 Test Parameters for Internal Hydrostatic Pressure Test

 (Clause 9.11)

10.1.6 The lot, having satisfied the requirements under 10.1.5 shall be tested for the requirements in 9.2 and 9.3. For this purpose, a sub-sample from those tested under **10.1.5** shall be drawn as given in col (10) of Table 11 for the first/second sample size. The lot shall be deemed to have met the requirements given in the standard, if the number of defectives found in the first sample is less than or equal to the corresponding acceptance number given in col (12). The lot shall be deemed not to have met these requirements, if the number of defectives found in the first sample is greater than or equal to the corresponding rejection number given in col (13). If, however, the number of defectives found in the first sample lies between the corresponding acceptance and rejection numbers given in col (12) and (13), a second sample of the size given in col (10) shall be taken and tested for the requirement, the lot shall be deemed to have satisfied the requirements, if the number of defectives found in the cumulative sample is less than or equal to the corresponding acceptance number given in col (12), otherwise not.

10.1.7 The lot, having satisfied the requirements under 10.1.5 and 10.1.6, shall be tested for 9.4, 9.5, 9.7, 9.8, 9.9, 9.11 and 9.12. For this, a sub-sample of 3 pipes from each lot irrespective of the lot size shall be selected from those tested under 10.1.5 and 10.1.6. All pipes in the sub-sample shall be tested for requirements as specified in 9.4, 9.5, 9.7, 9.8, 9.9, 9.11 and 9.12. The lot shall be considered to have passed only if no failure is reported.

10.2 Type Tests

These tests are intended to prove the suitability and performance of pipes whenever there is a change in the composition, size and type of pipe as well as in the method/technique in the manufacturing process. Tests specified in **9.6** and **9.10** shall be taken as type test.

10.2.1 Izod Impact Strength Test

10.2.1.1 For this type test, the manufacturer or the supplier shall furnish to the testing authority three samples of pipes of different diameters and different classes of the same type (selected preferably from a regular production lot).

10.2.1.2 Three samples so selected shall be tested for compliance with the requirements of type test as given in **9.6**.

10.2.1.3 If all the three samples pass the requirements of the izod impact strength test, the type test of the pipe under consideration shall be considered to be eligible for approval, which shall be normally valid for a period of one year.

10.2.1.4 In case any of the samples fails in this test, the testing authority, at its discretion, may call for fresh samples not exceeding the original number, and subject them to the test for izod impact strength test. If, in the repeat test, no single failure occurs, the type of pipe under consideration shall be considered eligible for type approval. If any of the samples fails in the repeat test, the type of pipe shall not be approved. The manufacturer or the supplier may be asked to improve the design and resubmit the product for type approval.

10.2.1.5 At the end of the validity period (normally one year) or earlier, if necessary, the testing authority may call for fresh samples for izod impact strength test for the purpose of type approval.

IS 18166 : 2023

Table 11 Sampling and Acceptance Criteria

(Clauses 10.1.1, 10.1.5 and 10.1.6)

Sl No.	Number	Nominal Size	e, D N		For Tests und	ler 7, 8 and 9.1				For Tests unde	er 9.2 and 9.3				
	of Pipes		_			<u> </u>				入	_				
	in the Lot				mm	Sai	mple		Acceptance Rejection		Sub-Sample		Cumulative	Acceptance	Rejection
				<u>ل</u>	Sample Size	Number	Number		<u> </u>	Sample Size	Number	Number			
			No.	Size				No.	Size						
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)			
i)	Up to	∫ ≤100	1st	13	13	0	2	1st	3	3	0	2			
	1 000		2nd	13	26	1	2	2nd	3	6	1	2			
		> 100	1 st	5	5	0	2	1st	3	3	0	2			
			2nd	5	10	1	2	2nd	3	6	1	2			
ii)	1 001 -	∫ ≤ 100	1st	20	20	0	3	1st	3	3	0	2			
	3 000	$\left\{ \right.$	2nd	20	40	3	4	2nd	3	6	1	2			
		L > 100	1st	8	8	0	2	1st	3	3	0	2			
			2nd	8	16	1	2	2nd	3	6	1	2			
iii)	3 001-	∫ ≤100	1st	32	32	0	3	1st	3	3	0	2			
	10 000	$\frac{1}{1}$	2nd	32	64	3	4	2nd	3	6	1	2			
		> 100	1st	13	13	0	3	1st	3	3	0	2			
			2nd	13	26	3	4	2nd	3	6	1	2			
iv)	10 001	∫ ≤100	1st	50	50	2	5	1st	6	6	0	2			
	and	$\left\{ \right.$	2nd	50	100	6	7	2nd	6	12	2	3			
	above	L > 100	1st	20	20	1	4	1st	4	4	0	2			
			2nd	20	40	4	5	2nd	4	8	1	2			

NOTE — For test under 9.2, the numbers mentioned in col (10) to col (13) represent the number of times the test is to be carried out. They do not represent the number of pipe samples nor the number of failures.

10.2.2 Test for Effect on Water

10.2.2.1 For this type test, the manufacturer or the supplier shall furnish to the testing authority three samples of the smallest size of pipe taken from each machine (selected preferably from a regular production lot).

10.2.2.2 Three samples so selected shall be tested for compliance with the requirements for effect on water as given in **9.10**.

10.2.2.3 If all three samples pass the requirements for effect on water, the type test of the pipe under consideration shall be considered to be eligible for approval, which shall be normally valid for a period of one year.

10.2.2.4 In case any of the samples fails in this test, the testing authority, at its discretion, may call for fresh samples not exceeding the original number, and subject them to the test for effect on water. If, in the repeat test, no single failure occurs, the type of pipe under consideration shall be considered eligible for type approval. If any of the samples fails in the repeat test, the type of pipe shall not be approved. The manufacturer or the supplier may be asked to improve the design and resubmit the product for type approval.

10.2.2.5 At the end of the validity period (normally one year) or earlier, if necessary, the testing authority may call for fresh samples for effect on water test for the purpose of type approval.

11 MARKING

11.1 Each pipe shall be clearly and indelibly marked in ink/paint at intervals of not more than 1 metre, and strip in colour as indicated in **11.2**. The markings shall show the following:

a) Manufacturer's name or trade-mark;

- b) Nominal size (DN);
- c) Class of pipe and working pressure rating;
- d) The phrase 'column pipe'; and
- e) Lot number/Batch number containing information of date of manufacture.

The lot number/batch number shall include the details of production in the following manner:

Year	Month	Day	Machine No.	Shift
XXXX	XX	XX	XXX	Х

11.2 The information according to **11.1** shall be marked in black colour and a strip of minimum 3 mm width of colour as indicated below for different classes of pipes shall be provided. Alternatively, the information to be marked/painted can be printed in colour as given below without any strip.

Sl	Class	Colour of
No.		Marking/Strip
(1)	(2)	(3)
i)	Class 1	Red
ii)	Class 2	Blue
iii)	Class 3	Green
iv)	Class 4	Brown
v)	Class 5	Yellow
vi)	Class 6	Black
vii)	Class 7	Pink

11.3 BIS Certification Marking

Each column pipe and coupler conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act*, 2016 and the Rules and Regulations framed thereunder, and the pipe may be marked with the Standard Mark.

ANNEX A

(Clause 2) LIST OF REFERRED STANDARDS

IS No.	Title	IS No.	Title	
IS 4669 : 1968	Methods of tests for polyvinyl chloride resins	IS 12235	Thermoplastics pipes and fittings — Methods of test (<i>first revision</i>)	
IS 4905 : 2015/	Random sampling and randomization procedures (<i>first revision</i>)	(Part 1) : 2004	Measurement of dimensions	
ISO 24153 : 2009		(Part 2) : 2004	Determination of vicat softening temperature	
IS 4985 : 2021	Unplasticized PVC pipes for water supplies — Specification	(Part 4) : 2004	Determining the detrimental effect on the composition of water	
	(fourth revision)	(Part 8/Sec 1) : 2004	Resistance to internal hydrostatic pressure, Section 1 Resistance to	
IS 5382 : 2018/ ISO 4633 : 2015	Rubber seals — Joint rings for water supply, drainage and sewerage pipelines — Specification for materials (second revision)	2004	internal hydrostatic pressure at constant internal water pressure	
		(Part 9) : 2004	Resistance to external blows (impact resistance) at 0 °C (round the-clock method)	
IS 10148 : 2023	Positive list of constituents of polyvinyl chloride (PVC) and	(Part 10) : 2004	Determination of organotin as tin aqueous solution	
	its copolymers in contact with foodstuffs, pharmaceuticals and drinking water (<i>first revision</i>)	(Part 11) : 2004	Resistance to dichloromethane at specified temperature	
IS 10151 : 2019	Polyvinyl chloride (PVC) and its copolymers for its safe use in contact with foodstuffs, pharmaceuticals and drinking	(Part 13) : 2004	Determination of tensile strength and elongation	
		(Part 14) : 2004	Determination of density/relative density (specific gravity)	
	water — Specification (first revision)	(Part 19) : 2004	Flattening test	

ANNEX B

(Clauses 4.1.1 and 9.6)

METHOD OF TEST FOR DETENMINATION OF IZOD IMPACT STRENGTH

B-1 GENERAL

Izod impact strength is the striking energy absorbed by a notched test specimen relative to the cross-sectional area. This test is used to assess toughness or brittleness of the test specimen.

B-2 APPARATUS

Apparatus required for the test are:

- a) V-Notch cutting Machine; and
 - b) Impact testing machine as per the requirements given below;
 - 1) The striker of the pendulum shall be hardened steel and shall be a cylindrical surface having a radius of curvature of (0.80 ± 0.20) mm with its axis horizontal and perpendicular to the plane of swing of the pendulum.
 - 2) The position of the pendulum holding and releasing mechanism shall be such that the vertical height of fall of the striker shall be (610 ± 2) mm. This will produce a velocity of the striker at the moment of impact of approximately 3.5 m/s.

B-3 TEST SPECIMEN

B-3.1 Shape and Size

Test specimen shall be as per Fig. 4.

B-3.2 Preparation

The specimen after cutting and grinding to the specified size as above, shall be subjected to

conditioning at temperature of (23 ± 2) °C and (50 ± 5) percent relative humidity in the environmental test chamber for a minimum duration of 16 h. Five test specimens shall be prepared for the test from each pipe sample.

B-4 PROCEDURE

B-4.1 The test shall be conducted in the same atmosphere as that used for conditioning, unless otherwise agreed upon by the interested parties, for example for testing at high or low temperature. The test piece shall be mounted on the pendulum impact testing machine as shown in Fig. 5 and the hammer shall be released to strike on the front side of the notch of the test specimen. Striking energy absorbed by the test specimen in joule shall be indicated on the scale of the impact testing machine.


B-4.2 The test piece shall be kept in vertical position while testing the impact, and before striking the specimen, the dissipation energy shall be noted by releasing the hammer without test specimen. This dissipation energy shall be subtracted from the energy absorbed by specimen during the test and the reading shall be noted as G_0 , in joule.


Izod impact strength of the specimen shall be calculated as:


$$H_{\rm n} = \frac{G_0 \times 1000}{F} \, \mathrm{J/m}$$

where

 $H_{\rm n}$ = Izod impact strength; G_0 = Noted energy; and F = Actual thickness of the specimen.







PLANES C AND D ARE PARALLEL



ANNEX C

(Clause 9.12)

JOINT LEAK PRESSURE TEST

C-1 SCOPE

C-1.1 This Annex specifies the method for joint leak pressure test for the assembly of threaded pipe and coupler and that of threaded bell end socket and threaded spigot pipe.

C-2 TEST PIECES

C-2.1 Typical assembly of specimen for joint leak pressure test is shown in Fig. 6.


C-2.2 For the assembly of coupler type threaded column pipe, take 2 numbers of 300 mm long cut piece of one side threaded column pipe and 1 number of threaded coupler. Assemble 2 numbers of pipe cut piece at both end of the coupler, that is, at its permanent and temporary side, as shown in Fig. 6A. Seal the joint of pipe and coupler with a sealing ring as per the standard design of manufacturer for practical use.

C-2.3 For the assembly of bell end pipe, take one

number of 300 mm long pipe having threaded bell end (female thread) at one side and other side plain and 1 number of 300 mm long pipe having spigot end (male thread) at one side and other side plain. Assemble spigot end pipe into the bell end socket as shown in Fig. 6B. Seal the joint with a sealing ring as per the standard design of manufacturer for practical use.

C-3 TEST METHOD

After assembly, close both end of the pipe with suitable metal end caps. Fill the water into the assembly. This test should be performed at the floor and all precautions shall be taken for ensuring human safety. Attach assembly with hydrostatic pressure testing machine. Apply the hydrostatic pressure of 1.5 times the pressure rating (PN) for a period of 1 h. During the testing, monitor for any leakage from the coupler and pipe junction or pipe and bell end junction.





ANNEX D

(Foreword) COMMITTEE COMPOSITION

Plastic Piping System Sectional Committee, CED 50

Organization	Representative(s)
In Personal Capacity (Vice Chancellor, Ravenshaw University, Cuttack - 753003)	DR S. K. NAYAK (<i>Chairperson</i>)
Borouge India Pvt Ltd, Mumbai	Shri Prashant D. Nikhade
Brihan Mumbai Licensed Plumbers Association, Mumbai	SHRI KISHOR V. MERCHANT SHRI BIJAL M. SHAH (Alternate)
Central Institute of Plastic Engineering and Technology, Chennai	DR S. N. YADAV SHRI D. ANJANEYA SHARMA (<i>Alternate</i>)
Central Public Health Environmental Engineering Organization, New Delhi	DR RAMAKANT Shri Vipin Kumar Patel (<i>Alternate</i>)
Central Public Works Department, New Delhi	SHRI M. K. MALLICK SHRI DIVAKAR AGRAWAL (<i>Alternate</i>)
Chennai Metropolitan Water Supply & Sewerage Board, Chennai	ENGINEERING DIRECTOR SUPERINTENDING ENGINEER (P&D) (Alternate)
CSIR - Central Building Research Institute, Roorkee	DR B. SINGH Shri Rajiv Kumar (Alternate)
CSIR - National Environmental Engineering Research Institute, Nagpur	DR (SHRIMATI) ABHA SARGONKAR DR RITESH VIJAY (<i>Alternate</i>)
Delhi Development Authority, New Delhi	SUPERINTENDING ENGINEER (D) EXECUTIVE ENGINEER (R&D) (Alternate)
Delhi Jal Board, New Delhi	SHRI Y. K. SHARMA SHRI S. L. MEENA (<i>Alternate</i>)
Department of Chemical & Petrochemicals Govt of India, New Delhi	JOINT INDUSTRIAL ADVISOR
Finolex Industries Limited, Pune	SHRI ARUN SONAWANE SHRI D. J. SALUNKE (<i>Alternate</i>)
GAIL India Limited, New Delhi	SHRI MANISH KHANDELWAL SHRI KULDEEP NEGI (<i>Alternate</i> I) SHRI NITIN GUPTA (<i>Alternate</i> II)
Haldia Petrochemicals Ltd, Kolkata	SHRI RAJ K. DATTA SHRI AMARTYA MAITY (Alternate)
HPCL - Mittal Energy Ltd, Noida	SHRI VINEET KUMAR GUPTA Shri Alakesh Ghosh (<i>Alternate</i>)

Organization	Representative(s)
HSIL Ltd (Pipe Divison), Hyderabad	SHRI TUSHAR LOKARE SHRI VINOY KUMAR (<i>Alternate</i>)
Indian Oil Corporation Ltd, Panipat	Shri Sumit Basu Shri Raja Poddar (<i>Alternate</i> I) Shri Naveen Garg (<i>Alternate</i> II)
Jain Irrigation System Limited, Jalgaon	SHRI S. NARAYANASWAMI SHRI P. H. CHAUDHARI (<i>Alternate</i>)
Mahindra EPC Irrigation Ltd, Nashik	SHRI SANKAR KUMAR MAITI SHRI ASHISH KUMAR (<i>Alternate</i>)
Military Engineer Services, Engineer-in-Chief's Branch, Integrated HQ of MoD (Army), New Delhi	SHRI N. K. GOEL SHRI RAJIV KHARE (<i>Alternate</i>)
Ministry of Drinking Water and Sanitation, New Delhi	SHRI DINESH CHAND SHRI SUMIT PRIYADARSHI (<i>Alternate</i>)
NSF Safety and Certification India Pvt Ltd, Gurugram	SHRI B. B. SINGH SHRI NASRIN KASHEFI (Alternate)
Panchayati Raj and Drinking Water Department, Govt. of Odisha, Bhubaneswar	CHIEF ENGINEER
Plastindia Foundation, Mumbai	SHRI RAJIV J. RAVAL DR E. SUNDARESAN (<i>Alternate</i>)
Public Health Engineering Department, Government of Rajasthan, Jaipur	SUPERINTENDING ENGINEER (D&S) EXECUTIVE ENGINEER (D&S) (Alternate)
Reliance Industries Limited, Mumbai	SHRI S. V. RAJU SHRI SAURABH BAGHAL (<i>Alternate</i>)
RITES Limited, New Delhi	SHRI PANKAJ AGGARWAL SHRI MUKESH SINHA (<i>Alternate</i>)
Shaktiman Extrusions Pvt Ltd, Perumbavoor	SHRI N. SURESH SHRI T. S. MANOJ (<i>Alternate</i>)
Supreme Industries Limited, Mumbai	SHRI G. K. SAXENA SHRI ANUP MANDAL (<i>Alternate</i>)
Tamil Nadu Water Supply & Drainage Board, Chennai	ENGINEERING DIRECTOR JOINT CHIEF ENGINEER (COM) (Alternate)
Tata Consulting Engineers Ltd, Mumbai	Representative
In Personal Capacity (A-59, Sector 35, Noida - 201301)	SHRI KANWAR A. SINGH
In Personal Capacity (L-202 Metrozone, Anna Nagar West, Chennai - 600040)	SHRI G. K. SRINIVASAN

Organization

Representative(s)

BIS Directorate General

SHRI ARUNKUMAR S., SCIENTIST 'E'/ DIRECTOR AND HEAD (CIVIL ENGINEERING) REPRESENTING DIRECTOR GENERAL (*Ex-officio*)]

Member Secretary Shrimati Madhurima Madhav Scientist 'D'/Joint Director (Civil Engineering), BIS

Composition of Polyolefins and GRP Piping System Subcommittee, CED 50:1

Organization

In Personal Capacity (A-59, Sector 35, Noida - 201301)

Alom Poly Extrusion Ltd, Kolkata

Assam Gas Company Limited, Dibrugarh

Bhimrajka Impex Limited, Mumbai

Central Ground Water Board, Faridabad

Central Institute of Plastics Engineering & Technology, Chennai

Central Public Works Department, New Delhi

CSIR - National Environmental Engineering Research Institute, Nagpur

Chennai Water Supply & Sewerage Board, Chennai

Delhi Jal Board, New Delhi

Duraline India Pvt Ltd, Mumbai

Engineers India Ltd, New Delhi

EPP Composite Pipes, Rajkot

GAIL India Limited, New Delhi

SHRI KANWAR A. SINGH (*Convener*)
SHRI ARNAV JHUNJHUNWALA SHRI ANIK KUMAR CHOWDHURY (*Alternate*)
SHRI SURJAYA TAMULIK SHRI AHIJIT BARUAH (*Alternate*)
SHRI V. K. SHARMA SHRI VINOD BHIMRAJKA (*Alternate*)
SHRI D. N. ARUN SHRI K. R. BISWAS (*Alternate*)
DR K. PRAKALATHAN DR A. K. MOHAPATRA (*Alternate*)
SHRI M. K. SHARMA (CSQ) SHRI AMAR SINGH (*Alternate*)

Representative(s)

DR (SHRIMATI) ABHA SARGAONKAR DR RITESH VIJAY (*Alternate*)

ENGINEERING DIRECTOR CHIEF ENGINEER (O&M) (*Alternate*)

SHRI Y. K. SHARMA SHRI S. L. MEENA (Alternate)

SHRI RAJEEV CHATURVEDI SHRI SUNIL SAXENA (Alternate)

SHRI N. KAUL SHRI R. B. BHUTDA (*Alternate*)

SHRI JAYRAJ SHAH Shrimati Seema Vaidya (*Alternate*)

DR DEBASISH ROY SHRI MANISH KHANDELWAL (Alternate I) SHRI NITIN GUPTA (Alternate II) Godavari Polymers Pvt Limited, Secunderabad

Government E-Marketplace, New Delhi

Indraprastha Gas Limited, New Delhi

Industrial Toxicology Research Centre, Lucknow

Jain Irrigation Systems Limited, Jalgaon

Kimplas Piping Systems Ltd, Nashik

KITEC Industries India Limited, Mumbai

Mahanagar Gas Limited, Mumbai

Mahanagar Telephone Nigam Limited, New Delhi

Maruthi Tubes Pvt Ltd, Secunderabad

Military Engineer Services, Engineer- in-Chief's Branch, Integrated HQ of MoD (Army), New Delhi

National Test House, Kolkata

Ori-Plast Limited, Kolkata

Public Health & Municipal Engineering Department, Hyderabad

Reliance Industries Limited, Mumbai

Sangir Plastics Pvt Ltd, Mumbai

In Personal Capacity (Panchjyot CHS; H-23/01 Sector 29, Vashi, Navi Mumbai - 400703) SHRI C. VENKATESHWAR RAO SHRI G. SRIDHAR RAO (*Alternate*)

REPRESENTATIVE

REPRESENTATIVE

DR V. P. SHARMA DR VIRENDRA MISRA (*Alternate*)

SHRI M. R. KHARUL SHRI M. D. CHAUDHARI (*Alternate*)

SHRI KIRAN SARODE SHRI SANTOSH KUMAR (*Alternate*)

SHRI DALIP V. KOLHE SHRI MANORANJAN G. CHOUDHARY (*Alternate*)

SHRI K. VENUGOPAL Shrimati Neha Kharya (*Alternate*)

CHIEF ENGINEER (BW)

SHRI MANCHAALA RAGHAVENDRA SHRI M. NAGESH KUMAR (Alternate)

SHRI A. K. DUBEY SHRI R. K. CHAUHAN (*Alternate*)

SHRI S. P. KALIA SHRI M. M. PABALKAR (*Alternate*)

SHRI ASHISH AGARWAL SHRI SOMNATH MUKHERJEE (*Alternate*)

SHRI K. SURESH KUMAR SHRI CH. MALLIKARJUNUDU (Alternate)

SHRI S. V. RAJU SHRI SAURABH BAGHAL (*Alternate* I) SHRI TUSHAR DONGRE (*Alternate* II)

SHRI PRASHANT TRIVEDI SHRI K. V. C. DORA (*Alternate*)

SHRI V. K. SHARMA

Composition of PVC and ABS Piping System Subcommittee, CED 50:2

Organization

Representative(s)

In Personal Capacity (L-202 Metrozone, Anna Nagar West, Chennai - 600040) SHRI G. K. SRINIVASAN (Convener)

Organization

Ashirvad Pipes Pvt Ltd, Bengaluru

Astral Poly Technik Ltd, Ahmedabad

Baerlocher India Additives Pvt Ltd, Mumbai

Central Ground Water Board, Faridabad

Central Institute of Plastic Engineering & Technology, Chennai

Central Public Works Department, New Delhi

Delhi Jal Board, New Delhi

Department of Telecommunications Ministry of Communications, Govt of India, New Delhi

Finolex Industries Limited, Pune

Government E-marketplace, New Delhi

Jain Irrigation Systems Limited, Jalgaon

Kimplas Piping Systems Ltd, Nashik

Mahanagar Telephone Nigam Limited, New Delhi

National Test House, Kolkata

Optiflux Pipe Industries, Jodhpur

Reliance Industries Limited, Mumbai

Rex Polyextrusion Limited, Sangli

RITES Limited, New Delhi

Rural Water Supply & Sanitation Department, Govt of Orissa, Bhubaneswar

Supreme Industries Limited, Jalgaon

Representative(s)

SHRI MOHAMMAD NOUFAL SHRI MILIND B. MAGAR (*Alternate*)

SHRI SANDEEP ENGINEER SHRI LALIT TRIVEDI (Alternate)

DR SHREEKANT DIWAN SHRI SACHIN BIDKAR (*Alternate*)

SHRI D. N. ARUN SHRI K. R. BISWAS (*Alternate*)

SHRI M. NAVANEETHAN

CHIEF ENGINEER (CSQ) EXECUTIVE ENGINEER (S&S) (Alternate)

SHRI Y. K. SHARMA SHRI S. L. MEENA (*Alternate*)

SHRI V. L. VENKATARAMAN Shri P. Adinarayana (*Alternate*)

SHRI ARUN SONAWANE SHRI D. J. SALUNKE (Alternate)

REPRESENTATIVE

SHRI NARAYANASWAMI SHRI M. R. KHARUL (*Alternate*)

Representative

SUPERINTENDING ENGINEER (CIVIL) SHRI M. K. SINGHAL (Alternate)

SHRI D. SARKAR DR NISHI SRIVASTAVA (Alternate)

SHRI PRAVEEN PARIHAR SHRI AMIT BORANA (*Alternate*)

SHRI S. V. RAJU SHRIMATI ARUNA KUMARI (*Alternate* I) SHRI JAYESH DESAI (*Alternate* II)

SHRI SHASHANK PARGAONKAR SHRI C. B. DANDEKAR (*Alternate*)

SHRI PANKAJ AGGARWAL SHRI MUKESH SINHA (Alternate)

CHIEF ENGINEER

SHRI G. K. SAXENA SHRI P. L. BAJAJ (*Alternate*)

Organization	<i>Representative(s)</i>
Tamil Nadu Water Supply & Drainage Board, Chennai	Engineering Director Joint Chief Engineer (COM) (<i>Alter</i>
In Personal Capacity (A-59, Sector 35, Noida - 201301)	SHRI KANWAR A. SINGH
Composition of the Working Group	for UPVC Column Pipes, CED 50/WG2
Organization	Representative(s)
Central Institute of Plastic Engineering and Technology, Chennai	SHRI M. NAVANEETHAN (Coordinator)

Ashirvad Pipes Pvt Ltd, Bengaluru

Astral Polytechnik Ltd, Ahmedabad

Duke Pipes Pvt Ltd, Palanpur

Finolex Industries Ltd, Pune

Jain Irrigation System Ltd, Jalgaon

Supreme Industries Ltd, Jalgaon

In Personal Capacity (Church Lane, Balasore -756001)

In Personal Capacity (A-59, Sector 35, Noida -201301)

SHRI MOHAMMAD NOUFAL SHRIMATI SWATI SARALAYA (Alternate)

SHRI RITESH PATEL

SHRI GIRISH A. PATEL

SHRI D. J. SALUNKE SHRI CHUNILAL PARVANI (Alternate)

SHRI M. R. KHARUL

SHRI G. K. SAXENA SHRI ANUP MANDAL (Alternate)

SHRI SANJAY KUMAR MOHAPATRA

SHRI KANWAR A. SINGH

ntativa(s) D.

OM) (Alternate)

nizatio 0

this Page has been intertionally left blank

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act*, 2016 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: CED 50 (15770).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002Telephones: 2323 0131, 2323 3375, 2323 9402Website: www.bis.gov.in				
Regional Offices:				
Central	: 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002		<i>Telephones</i> { 2323 7617	
Eastern	: 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091		{ 2367 0012 2320 9474	
Northern	: Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019		{ 265 9930	
Southern	: C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113		{ 2254 1442 2254 1216	
Western	: Plot No. E-9, Road No8, MIDC, Andheri (East), Mumbai 400093		{ 2821 8093	

Branches : AHMEDABAD. BENGALURU. BHOPAL. BHUBANESHWAR. CHANDIGARH. CHENNAI. COIMBATORE. DEHRADUN. DELHI. FARIDABAD. GHAZIABAD. GUWAHATI. HIMACHAL PRADESH. HUBLI. HYDERABAD. JAIPUR. JAMMU & KASHMIR. JAMSHEDPUR. KOCHI. KOLKATA. LUCKNOW. MADURAI. MUMBAI. NAGPUR. NOIDA. PANIPAT. PATNA. PUNE. RAIPUR. RAJKOT. SURAT. VISAKHAPATNAM.