भारतीय मानक Indian Standard

चूना पत्थर, डोलोमाइट और सम्बद्ध सामग्री का रासायनिक विश्लेषण भाग 2 सिलिका का निर्धारण

IS 1760 (Part 2): 2024

(दूसरा पुनरीक्षण)

Chemical Analysis of Limestone, Dolomite and Allied Materials Part 2 Determination of Silica

(Second Revision)

ICS 73.080

© BIS 2024



भारतीय मानक ब्यूरो

BUREAU OF INDIAN STANDARDS मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002 MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI - 110002

www.bis.gov.in www.standardsbis.in

November 2024

Price Group 4

FOREWORD

This Indian Standard (Part 2) (Second Revision) was adopted by the Bureau of Indian Standards after the finalized by the Methods of Chemical Analysis of Metals Sectional Committee had been approved of the Metallurgical Engineering Division Council.

This standard was first published in 1962 and subsequently revised in 1991. This revision has been brought out to bring the standard in the latest style and format of the Indian Standards. It covers the determination of different elements in various grades of minerals like limestone, dolomite, calcite and magnesite. It also covers the methods for magnesite refractories.

This part covers determination of silica, other parts are as follows:

Part 1	Determination of loss on ignition
Part 3	Determination of iron oxide, alumina, calcium oxide and magnesia
Part 4	Determination of carbon dioxide
Part 5	Determination of chlorides
Part 6	Determination of free silica

The composition of the Committee responsible for the formulation of this standard is given in Annex A.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2:2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be same as that of the specified value in this standard.

Indian Standard

CHEMICAL ANALYSIS OF LIMESTONE, DOLOMITE AND ALLIED MATERIALS

PART 2 DETERMINATION OF SILICA

(Second Revision)

1 SCOPE

This standard (Part 2) describes the method for determination of silica in limestone, dolomite and allied materials.

2 REFERENCES

The standard given below contains provisions which through reference in this text, constitutes provisions of this standard. At the time of publication the edition indicated was valid. All standards are subject to revision and parties to agreement based on this standard are encouraged to investigate the possibility of applying the most recent edition of the standard:

IS No.	Title	
IS 1070 : 2023	Reagent grade Specification revision)	water — (fourth
IS 2109 : 1982	Methods of dolomite, limestor allied materials	1 0

3 SAMPLING

- **3.1** The sample shall be drawn and prepared in accordance with IS 2109.
- **3.2** Grind 5 g to 10 g of the prepared sample drawn under 3.1, so that it passes through IS sieve 15 (100 mesh). Dry to constant mass at 105 °C \pm 2 °C and use it for the purpose of chemical analysis.

4 QUALITY OF REAGENTS

Unless specified otherwise, analytical grade reagents and distilled water (*see* IS 1070) shall be employed for the test.

5 DETERMINATION OF SILICA BY GRAVIMETRIC METHOD

5.1 Outline of the Method

Sample is dissolved in dilute hydrochloric acid and baked. The baked mass is extracted with dilute hydrochloric acid. The insoluble residue is then fused with anhydrous sodium carbonate and the melt is extracted with dilute hydrochloric acid. The silica is dehydrated and determined by hydro-fluorization.

5.2 Reagents

- **5.2.1** *Dilute Hydrochloric Acid* 40 percent (*v/v*)
- **5.2.2** Fusion Mixture mix carbonates of sodium and potassium in equal proportion
- **5.2.3** *Dilute Sulphuric Acid* 1 : 4 and 1 : 1 (v/v)
- **5.2.4** Hydrofluoric Acid 40 percent (v/v)

5.3 Procedure

- **5.3.1** For other than Magnesite Refractory Materials
- **5.3.1.1** Weigh accurately 1.0 g of the test sample into a beaker or a porcelain dish and add to it 40 ml to 50 ml of dilute hydrochloric acid. Cover the beaker by means of a suitable cover glass immediately after the addition of the acid. As soon as effervescence stops, wash the lower surface of the cover glass into the beaker and set contents for drying and baking at 110 °C to 115°C. After baking for about 20 min to 25 min, cool to room temperature, add 25 ml to 30 ml dilute hydrochloric acid, boil and filter. Thoroughly transfer all the residue as well as that adhering to the sides of the beaker, to the filter by hot water. Wash the residue free from chlorides by means of hot water. Collect the filtrate and washings in the same beaker and preserve it.
- **5.3.1.2** Transfer the filtrate with its residue into a previously heated platinum crucible and char at low temperature. Finally ignite at 900 °C to 950 °C and cool.
- **5.3.1.3** Fuse the residue in the platinum crucible with about 3 g of fusion mixture. Cool and extract the melt in about 50 ml of dilute hydrochloric acid. Mix with the filtrate preserved under <u>5.3.1.1</u> and repeat the process of drying and baking. Extract the baked mass with about 30 ml to 40 ml of dilute hydrochloric acid and filter. Transfer all the silica in the beaker to the filter thoroughly by means of hot

To access Indian Standards click on the link below:

water. Wash silica on the filter free from chloride by means of hot water. Collect the filtrate and washings in the same beaker and preserve the filtrate.

5.3.1.4 Transfer the filter with its residue into a platinum crucible and smoke off the filter paper at a low heat without burning the paper. Finally ignite at 900 °C to 950 °C to a constant mass. Moisten the residue with few millilitres of dilute sulphuric acid (1:1) and add to it about 10 ml of hydrofluoric acid. Evaporate to dryness, ignite, cool and weigh.

5.3.1.5 Carry out a blank determination following the procedure specified in <u>5.3.1.1</u> to <u>5.3.1.4</u> using the same amount of reagents but without the sample.

5.3.1.6 Calculation

Silica, percent by mass

$$= \frac{[(A-B)-C]}{D} \times 100$$

where

A = mass, in g, of platinum crucible with residue of silica before hydro-fluorization;

B =mass, in g, of platinum crucible with residue obtained after repeated hydro-fluorization;

C = mass, in g, of silica obtained in blank determination; and

D =mass, in g, of the sample taken.

5.3.2 For Magnesite Refractory Materials

5.3.2.1 Weigh accurately one gram of the sample in a platinum crucible and fuse it with 6 g to 8 g of pure anhydrous sodium carbonate. Extract the melt carefully with 0 ml to 50 ml of dilute hydrochloric acid in a 500 ml beaker and when dissolution is complete, wash the crucible thoroughly with hot water. Evaporate the solution to dryness on hot-plate and bake for about 20 min.

5.3.2.2 Cool the beaker, add 25 ml to 30 ml of dilute hydrochloric acid, boil and filter. Transfer thoroughly all the residue in the beaker to the filter paper by a jet of hot water and wash it free from acid by means of hot water. Collect the filtrate and washings in the same beaker and preserve it. Further, complete the estimation as described under **5.3.1.2** to **5.3.1.6**.

IS 1760 (Part 2): 2024

ANNEX A

(<u>Foreword</u>)

COMMITTEE COMPOSITION

Methods of Chemical Analysis of Metals Sectional Committee, MTD 34

Organization	Representative(s)
CSIR - National Metallurgical Laboratory, Jamshedpur	DR SANCHITA CHAKRAVARTY (Chairperson)
Arcelor Mittal Nippon Steel, Mumbai	SHRI MANOJ GUPTA SHRI KIRIT TAILOR (<i>Alternate</i>)
Bhabha Atomic Research Centre, Mumbai	MS SANJUKTA A. KUMAR SHRI M. V. RANA (<i>Alternate</i>)
CSIR - National Metallurgical Laboratory, Jamshedpur	Dr Ashok K. Mohanty (Alternate)
Defence Metallurgical Research Laboratory, Ministry of Defence, Hyderabad	SHRI S. S. KALYAN KAMAL
Directorate General of Quality Assurance, Ministry of Defence, New Delhi	SHRI KESAVAMOORTHY M. SHRI E. SUMAN KUMAR (<i>Alternate</i>)
Geological Survey of India, New Delhi	SHRI NITIN PURUSHOTTAM SHRIMATI SANJUKTA DEY PAL (Alternate)
Hindalco Industries Limited, Mumbai	SHRI KRISHANU MAHAPATRA SHRI ASHUTOSH ACHARYA (<i>Alternate</i>)
Indian Metals and Ferro Alloys Limited, Bhubaneswar	SHRI DINESH KUMAR MOHANTY
Jawaharlal Nehru Aluminium Research Development and Design Centre, Nagpur	Dr Upendra Singh
JSW Steel Limited, Mumbai	SHRI KOTRABASAVARAJU SHRI MARULASIDDESHA U. M. (<i>Alternate</i>)
National Aluminium Company Limited, Bhubaneswar	SHRIMATI SUKLA NANDI SHRI DEBANANDA BHATTACHARYYA (<i>Alternate</i>)
National Mineral Development Corporation, Hyderabad	Dr Saroj Kumar Sahu Shri Ashish Shrivastava (<i>Alternate</i>)
National Test House, Kolkata	Dr Rajeev Kumar Upadhyay Shri Akbar H. (<i>Alternate</i>)
Research Designs and Standards Organization (RDSO), Lucknow	SHRI SANDEEP SHRIMATI SUNIA (<i>Alternate</i>)
Shriram Institute for Industrial Research, Delhi	Dr Laxmi Rawat Shri Puneet Kapoor (<i>Alternate</i>)
Steel Authority of India Limited - Salem Steel Plant, Salem	SHRI L. SIVAKUMAR SHRI VIVEKANANDHAN G. (<i>Alternate</i>)
Tata Steel Limited, Kolkata	Dr Jatin Mohapatra
TRL Krosaki Refractories Limited, Belpahar	SHRI S. K. SUBUDHI

IS 1760 (Part 2): 2024

BIS Directorate General

Organization

Representative(s)

SHRI SANJIV MAINI, SCIENTIST 'F'/SENIOR DIRECTOR (METALLURGICAL ENGINEERING) AND HEAD [REPRESENTING DIRECTOR GENERAL (Ex-officio)]

Member Secretary SHRI ASHISH PRABHAKAR WAKLE SCIENTIST 'D'/JOINT DIRECTOR (METALLURGICAL ENGINEERING), BIS This Page has been literationally left blank

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act*, 2016 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: MTD 34 (20747).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected	

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402 Website: www.bis.gov.in

Regional Offices:		Telephones
Central	: 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern	: 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	2367 0012 2320 9474
Northern	: Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern	: C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	2254 1442 2254 1216
Western	: 5 th Floor/MTNL CETTM, Technology Street, Hiranandani Gardens, Powai Mumbai 400076	25700030 25702715

Branches: AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.