

शमन तेल — विशिष्टि  
( तीसरा पुनरीक्षण )

Quenching Oil — Specification  
( Third Revision )

ICS 75.100

© BIS 2024



भारतीय मानक ब्यूरो  
BUREAU OF INDIAN STANDARDS  
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI - 110002  
[www.bis.gov.in](http://www.bis.gov.in) [www.standardsbis.in](http://www.standardsbis.in)

July 2024

Price Group 6

## FOREWORD

This Indian Standard (Third Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Lubricants and their Related Products Sectional Committee had been approved by the Petroleum, Coal and Related Products Division Council.

Quenching is a type of metal heat treatment process, which involves the rapid cooling of a metal to adjust the mechanical properties of its original state. Quenching operation is generally carried out in a media, such as (a) water; (b) fatty oils, mineral oils and mixtures of fatty and mineral oils; and (c) molten lead and molten salt baths. The selection of quenching media depends upon the metal used, the hardness and other properties that the metallic article is desired to attain. The important characteristics of a quenching medium are: (a) the rate of transfer of heat from the metal to the medium, and (b) the ability of the medium to resist change in its properties due to frequent contact with the glowing metal.

This standard was first published in 1964 and subsequently revised in 1974 and 1980. In the second revision, the requirements for ash, pour point, flash point, viscosity, volatility and resistance to oxidation for the various grades of oils were modified. An additional requirement for viscosity index for compounded and additive type oils was added. In addition to the physico-chemical requirements, a performance test based on GM magnetic quenchometer was also included.

This revision has been brought out to keep pace with the latest technological developments and international practices. In this revision, the following major changes have been incorporated:

- a) Amendment 1 published in 1993 has been incorporated;
- b) Additional requirement for viscosity index for mineral type quenching oils has been added, as the viscosity index of a quenching oil is directly related to its performance, affecting its behaviour over varying temperatures; and
- c) A performance test based on a quenchometer with cooling curve analysis has been included. In addition to quenching time, this test offers cooling profiles which leads to better interpretation of cooling characteristics of the fluid.

The composition of the Committee responsible for the formulation of this standard is given in [Annex E](#).

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Indian Standard*  
**QUENCHING OIL — SPECIFICATION**  
*(Third Revision )*

**1 SCOPE**

This standard prescribes the requirements and the methods of sampling and test for quenching oils.

**2 REFERENCES**

The standards listed in [Annex A](#) contain provisions which, through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revisions, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards.

**3 TYPES**

The material shall be of the following types:

- a) Mineral type;
- b) Compounded type; and
- c) Additive type.

**4 GRADES**

The material of the mineral type shall be of the following viscosity grades:

- a) Light;
- b) Medium; and
- c) Heavy.

**5 REQUIREMENTS****5.1 Description**

The material shall be made from refined petroleum oils with or without admixture of fatty oils and/or additives. It shall be a clean, homogeneous liquid, free from water, dirt and suspended matter.

**5.2** The material shall comply with the requirements given in [Table 1](#), when tested according to the methods prescribed under the annexes to this standard and parts of IS 1448. Reference to the relevant method of test is given in col (8) of the [Table 1](#).

**5.3 Performance Requirement**

The material shall also pass the performance test on

a quenchemeter with cooling curve analysis as described in [Annex D](#). The value for this test shall be as agreed to between the purchaser and the supplier.

**6 PACKING AND MARKING****6.1 Packing**

The material shall be packed in securely closed metal or any other suitable container as agreed to between the purchaser and the supplier.

**6.2 Marking**

The packaging containing the material shall be marked with the following information:

- a) Name and type of material;
- b) Manufacturer's name, initials or trademark, if any;
- c) Net mass of material;
- d) Identification in code or otherwise to enable the lot of consignment or manufacture to be traced back from records; and
- e) Any other statutory requirements.

**6.2.1 BIS Certification Marking**

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the products may be marked with the standard mark.

**7 SAMPLING**

**7.1** Representative samples of the material shall be drawn as prescribed in IS 1447 (Part 1).

**7.2** All the requirements given in 5 shall be tested on the composite sample.

**7.3** The lot shall be declared as conforming to the requirements of the specification if all the test results on the composite sample satisfy the relevant requirements.

Table 1 Requirement for Quenching Oil

(Clause 5.2)

SI No.	Characteristic	Requirement					Method of Test
		Mineral type			Compounded Type	Additive Type	
(1)	(2)	Light	Medium	Heavy			(6)
i)	Acidity, inorganic, mg of KOH per g of the oil	Nil	Nil	Nil	Nil	Nil	IS 1448 (Part 2)
ii)	Acidity, organic, mg of KOH per g of the oil, <i>Max</i>	0.1	0.1	0.1	1.3	0.6	IS 1448 (Part 2)
iii)	Ash, percent by mass, <i>Max</i>	0.01	0.01	0.01	0.05	-	IS 1448 (Part 4/Sec 1)
iv)	Pour point, °C, <i>Max</i>	0	0	3	3	0	IS 1448 (Part 10/Sec 2)
v)	Flash point, cleveland (open) cup, °C, <i>Min</i>	160	175	200	175	175	IS 1448 (Part 69)
vi)	Kinematic viscosity at 40 °C, cSt	11.5 to 17.5	20.5 to 36	36 to 73	19.5 to 34	19.5 to 34	IS 1448 (Part 25/Sec 1)
vii)	Viscosity index, <i>Min</i>	90	90	90	90	90	IS 1448 (Part 56)
viii)	Saponification value, <i>Max</i>	0.5	0.5	0.5	5 to 15	-	IS 1448 (Part 55/Sec 1)
ix)	Volatility (loss on heating at 150 °C for two h), percent by mass, <i>Max</i>	8	4	3	4	4	<a href="#">Annex B</a>
x)	Resistance to oxidation:						IS 1448 (Part 65)
	a) Kinematic viscosity of the oxidized oil at 40 °C, mm <sup>2</sup> /s	Not more than 1.70 of the original oil at the same temperature			-	-	IS 1448 (Part 25/Sec 1)
	b) Carbon residue (conradson) of the oxidized oil, percent by mass, <i>Max</i>	2	2	2	-	-	IS 1448 (Part 122)
	c) Insolubles in the oxidized oil, percent by mass, <i>Max</i>	0.5	0.5	0.5	-	-	<a href="#">Annex C</a>
	d) Acidity of the oxidized oil, organic (mg KOH/g of the oil), <i>Max</i>	1	1	1	-	-	IS 1448 (Part 2)
xi)	Copper strip corrosion test at 100 °C for 3 h	Not worse than No. 1					IS 1448 (Part 15)

## ANNEX A

(Clause 2)

## LIST OF REFERRED STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
IS 1447 (Part 1) : 2021	Methods of sampling of petroleum and its products: Part 1 Manual sampling ( <i>second revision</i> )	(Part 19) : 2015/ISO 5275 : 2003	Detection of thiols and other sulphur species — Doctor test ( <i>second revision</i> )
IS 1448	Methods of test for petroleum and its products:	(Part 25/ Sec 1) : 2018/ISO 3104 : 1994	Transparent and opaque liquids, Section 1 Determination of kinematic viscosity and calculation of dynamic viscosity ( <i>second revision</i> )
(Part 2) : 2007/ISO 6619 : 1998	Petroleum products and lubricants — Neutralization number — Potentiometric titration method ( <i>second revision</i> )	(Part 29) : 2021/ISO 6246 : 2017	Petroleum products — Gum content of fuels — Jet evaporation method ( <i>fourth revision</i> )
(Part 4/Sec 1) : 2021	Determination of ash ( <i>fourth revision</i> )	(Part 43) : 2018	Bromine number by colour indicator method ( <i>third revision</i> )
(Part 10/Sec 2) : 2021/ISO 3016 : 2019	Petroleum and related products from natural or synthetic sources, Section 2 Determination of pour point ( <i>third revision</i> )	(Part 55/Sec 1) : 2004	Determination of saponification value of petroleum products ( <i>first revision</i> )
(Part 12) : 2013/ISO 2049 : 1996	Determination of colour (ASTM Scale) ( <i>second revision</i> )	(Part 56) : 2013/ISO 2909 : 2002	Calculation of viscosity index from kinematic viscosity ( <i>third revision</i> )
(Part 15) : 2004/ISO 2160 : 1998	Petroleum products — Corrosiveness to copper — Copper strip test ( <i>third revision</i> )	(Part 65) : 2018	Oxidation test for lubricating oils ( <i>third revision</i> )
(Part 16) : 2014/ISO 3675 : 1998	Crude petroleum and liquid petroleum products — Laboratory determination of density — Hydrometer method ( <i>fourth revision</i> )	(Part 69) : 2019/ISO 2592 : 2017	Determination of flash and fire points — Cleveland open cup Method ( <i>second revision</i> )
(Part 18) : 2020	Distillation of petroleum products ( <i>third revision</i> )	(Part 122) : 2013/ISO 6615 : 1993	Determination of carbon residue — Conradson method ( <i>first revision</i> )

To access Indian Standards click on the link below

[https://www.services.bis.gov.in/php/BIS\\_2.0/bisconnect/knowyourstandards/Indian\\_standards/isdetails/](https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knowyourstandards/Indian_standards/isdetails/)

## ANNEX B

[Table 1, Sl No. (ix)]

## TEST FOR VOLATILITY

## B-1 PROCEDURE

Weigh  $20 \text{ g} \pm 1 \text{ g}$  of the material in a glass petri dish of approximately 9 cm diameter and keep the dish in a ventilated oven maintained at  $150 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$  for two

hours. Cool the dish with its contents in a desiccator to room temperature and then weigh accurately. Calculate the loss in mass as a percentage on the mass of the material taken for the test.

## ANNEX C

[Table 1, Sl No. (x)(c)]

## DETERMINATION OF INSOLUBLES IN THE OXIDIZED OIL

## C-1 REAGENT

Petroleum hydrocarbon solvent — conforming to the following requirements:

Sl No. (1)	Characteristic (2)	Requirements (3)	Methods of test (4)
i)	Density at $15 \text{ }^\circ\text{C}$ , $\text{kg/m}^3$	0.679 8 to 0.689 8	IS 1448 (Part 16)
ii)	Distillation test:		IS 1448 (Part 18)
	a) Initial boiling point, $^\circ\text{C}$ , <i>Min</i>	55	
	b) Distillation between $60 \text{ }^\circ\text{C}$ , and $80 \text{ }^\circ\text{C}$ , percent by volume, <i>Min</i>	90	
	c) Final boiling point, $^\circ\text{C}$ , <i>Max</i>	90	
iii)	Doctor test	Negative	IS 1448 (Part 19)
iv)	Colour	Waterwhite (1.0)	IS 1448 (Part 12)
v)	Residue on evaporation, $\text{mg}/100 \text{ ml}$ , <i>Max</i>	2	IS 1448 (Part 29)
vi)	Bromine number, <i>Max</i>	1	IS 1448 (Part 43)

## C- 2 PROCEDURE

Oxidize the oil as prescribed in IS 1448 (Part 65). Weigh about 10 g of the well stirred oxidized oil accurate to the nearest 0.1 g, in a 250 ml conical flask, add 100 ml of petroleum hydrocarbon solvent and after thorough mixing allow it to stand in the dark for 16 h to 24 h. Decant the clear liquid in the conical flask through an accurately weighed whatman filter paper (No. 40) or equivalent, which was previously dried at  $95 \text{ }^\circ\text{C}$  to  $100 \text{ }^\circ\text{C}$ . Care should be taken to prevent the sludge from coming to the

filter paper at this stage. Wash the insoluble in the flask twice by decantation, using 75 ml of petroleum hydrocarbon solvent in each operation. Wash the insolubles on the filter paper using more petroleum hydrocarbon solvent and finally wash it on the filter paper until it is free from oil. Transfer the filter paper with the insoluble to an oven maintained at  $5 \text{ }^\circ\text{C}$  to  $100 \text{ }^\circ\text{C}$  and dry it to constant mass.

Express the mass of insolubles as a percentage of the mass of the oxidized oil taken for the test.

**ANNEX D***(Clause 5.3)***TEST FOR DETERMINATION OF COOLING CHARACTERISTICS BY COOLING CURVE ANALYSIS****D-1 APPARATUS**

**D-1.1** Nickel probe assembly made of nickel alloy 600 of diameter  $12.5 \text{ mm} \pm 0.01 \text{ mm}$  and a length of  $60 \text{ mm} \pm 0.25 \text{ mm}$ , with a 1.45 mm to 1.65 mm sheathed K-Type thermocouple in the centre, with a computer based data acquisition system capable of providing cooling curve analyses.

**D-1.2** Electric furnace capable of maintaining a temperature of  $850 \text{ }^\circ\text{C}$  over the length of the probe.

**D-1.3** Sample container of diameter and height able to provide 50 ml of tested fluid above and below the transferred probe during the quenching process.

**D-2 PROCEDURE**

Heat the nickel probe assembly in the furnace till it maintains  $850 \text{ }^\circ\text{C}$  for at least 2 min. Fill the

sample container with the quenching oil sample. Transfer the heated probe into the centre of the oil sample, activating the data acquisition software to record the cooling characteristics.

**D-3 REPORT**

**C-3.1** From the temperature-time graph, report the time at  $600 \text{ }^\circ\text{C}$ ,  $400 \text{ }^\circ\text{C}$  and  $200 \text{ }^\circ\text{C}$ , to the nearest 0.1 s.

**D-3.2** From the cooling rate – temperature graph, report maximum cooling rate, in  $^\circ\text{C/s}$ , temperature where the maximum cooling rate occurs, in  $^\circ\text{C}$ , and cooling rate at  $300 \text{ }^\circ\text{C}$ , in  $^\circ\text{C/s}$ .

**D-3.3** Report the cooling curves and the cooling rate curves.

## ANNEX E

(Foreword)

## COMMITTEE COMPOSITION

## Lubricants and their Related Products, PCD 25

<i>Organization</i>	<i>Representative(s)</i>
In Personal Capacity ( <i>Flat - 1002, Raheja Heights, D - Wing, off Gen A K Vaidya Marg, Dindoshi, Malad East Mumbai - 400097</i> )	DR Y. P. RAO ( <i>Chairperson</i> )
Afton Chemicals Private Limited, Mumbai	SHRI ANAND KUMAR
Ashok Leyland Limited, Chennai	SHRI MAHESH P. SHRI D. BALAKRISHNAN ( <i>Alternate</i> )
Bajaj Auto Limited, Pune	SHRI YOGESH R. MAHAJAN SHRI RAMESH GOYKAR ( <i>Alternate</i> )
Balmer Lawrie and Company Limited, Kolkata	DR MOHAN LAL DAS SHRI SRINIVASAN MURLI ( <i>Alternate</i> )
BASF India Limited, Mumbai	SHRI NEVILLE COLACO SHRI ASHOK SAMBANDAM ( <i>Alternate</i> )
Bharat Petroleum Corporation Limited, Mumbai	SHRI R. SUBRAMANIAN DR TARUNENDER SINGH ( <i>Alternate</i> )
Bosch Limited, Bengaluru	DR FREDRICK A. SHRI RAGHUVVEER RAO ( <i>Alternate</i> )
Central Pollution Control Board, New Delhi	SHRI DINABANDHU GOUDA
Centre for High Technology, New Delhi	DR P. RAMAN DR N. S. RAMAN ( <i>Alternate I</i> ) SHRI SHEKAR KULKARNI ( <i>Alternate II</i> )
Chennai Petroleum Corporation Limited, Chennai	DR V. SELVAVATHI SHRI H. RAMAKRISHNAN ( <i>Alternate</i> )
Consumer Guidance Society of India, Mumbai	DR SITARAM DIXIT DR M. S. KAMATH ( <i>Alternate</i> )
CSIR - Indian Institute of Petroleum, Dehradun	DR ANIL KUMAR SINHA DR G. D. THAKRE ( <i>Alternate I</i> ) SHRI SAILESH KUMAR SINGH ( <i>Alternate II</i> )
Defence Research and Development Organization, Research Centre Imarat, Hyderabad	SHRI KAMAL PRAKASH SINGH SHRI SONAM GUPTA ( <i>Alternate</i> )
Directorate General of Quality Assurance, Ministry of Defence, Kanpur	DR OM PRAKASH SINGH SHRI A. K. KANAUIA ( <i>Alternate</i> )
Gulf Oil Lubricants India Limited, Mumbai	SHRI GIRISH JANGE DR JENCEN MATHAI ARIVANNOOR ( <i>Alternate</i> )



<i>Organization</i>	<i>Representative(s)</i>
Hero Motocorp Limited, New Delhi	SHRI FERAZ ALI KHAN SHRI RAKESH SHARMA ( <i>Alternate I</i> ) SHRI DIWIT PRAJAPATI ( <i>Alternate II</i> )
Hindustan Petroleum Corporation Limited, Mumbai	SHRI LOKENDER SINGH TEVATHIYA SHRI ASHISH KHANNA ( <i>Alternate</i> )
Indian Oil Corporation Limited - Refineries and Pipelines Division, New Delhi	SHRI ASHWANI SHARMA SHRI R. K. CHUGH ( <i>Alternate</i> )
Indian Oil Corporation (MKTG), Mumbai	SHRI RAJESH NAMBIAR DR S. VENKATESAN ( <i>Alternate</i> )
Indian Oil Corporation (R and D Centre), Faridabad	DR DEEPAK SAXENA DR PANKAJ BHATNAGAR ( <i>Alternate</i> )
IPSS Sail, New Delhi	SHRI AVADESH KUMAR GUPTA SHRI G. SNEHA RAJU ( <i>Alternate</i> )
Lubrizol India Limited, Mumbai	SHRI KAILASH SAWANT SHRI SREEHARI KUMAR ( <i>Alternate</i> )
Mahindra and Mahindra Limited, Mumbai	SHRI R. RAMAPRABHU
Maruti Udyog Limited, Gurugram	SHRI ASHOK PERMUDE SHRI NARINDER KUMAR ( <i>Alternate</i> )
Ministry of Road Transport and Highways, New Delhi	SHRI G. SHARAN SHRI S. S. NAHAR ( <i>Alternate</i> )
National Test House, Kolkata	DR S. N. BANDHOPADHYAY DR UMESH SINGH ( <i>Alternate</i> )
Netra NTPC Limited, Noida	SHRI RAJIV SATYAKAM DR VANI G. D. ( <i>Alternate</i> )
Oil Industry Safety Directorate, Noida	SHRI RAJESH MANOCHA
Reliance India Limited, Mumbai	SHRI RAHUL SAXENA
Research Designs and Standards Organization (RDSO), Lucknow	SHRI KAMAL PRAKASH SINGH SHRI RAJESH SRIVASTAVA ( <i>Alternate</i> )
Society of Indian Automobile Manufacturers (SIAM), Delhi	SHRI PRASHANT KUMAR BANERJEE DR SANDEEP GARG ( <i>Alternate</i> )
Steel Authority of India, Centre for Engineering and Technology, Ranchi	SHRI BALAKRISHNA BISOYI SHRI ANUJEET RITURAJ ( <i>Alternate</i> )
Swastik Oil Products Manufacturing Company Private Limited, Mumbai	SHRI BHUPENDRA RATHOD SHRI SANAT RATHOD ( <i>Alternate</i> )
Tata Motors Limited, Pune	SHRI MANISH GOPAL SHRI PALLIPALAYAM GOWRISHANKAR ( <i>Alternate</i> )

<i>Organization</i>	<i>Representative(s)</i>
TVS Motor Company Limited, Hosur	SHRI AJITH KUMAR
BIS Directorate General	SHRIMATI MEENAL PASSI, SCIENTIST 'F'/ SENIOR DIRECTOR AND HEAD (PETROLEUM, COAL AND RELATED PRODUCTS) [REPRESENTING DIRECTOR GENERAL ( <i>Ex-officio</i> )]

*Member Secretary*  
SHRIMATI KRETI DAS  
SCIENTIST 'C'/DEPUTY DIRECTOR  
(PETROLEUM, COAL AND RELATED PRODUCTS), BIS



## Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

### Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

### Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-[www.bis.gov.in](http://www.bis.gov.in) or [www.standardsbis.in](http://www.standardsbis.in).

This Indian Standard has been developed from Doc No.: PCD 25 (18660).

### Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

## BUREAU OF INDIAN STANDARDS

### Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: [www.bis.gov.in](http://www.bis.gov.in)

### Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 <sup>th</sup> Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 <sup>th</sup> Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : Manakalya, 4 <sup>th</sup> Floor, NTH Complex (W Sector), F-10, MIDC, Andheri (East), Mumbai 400093	{ 283 25838

**Branches :** AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYNA, HUBLI, HYDERABAD, JAIPUR, JAMMU & KASHMIR, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.