

वस्त्रादि — स्कूल यूनीफॉर्म के लिए
हथकरघा सूती कपड़ा — विशिष्टि
(पहला पुनरीक्षण)

**Textiles — Handloom Cotton
Fabric for School Uniforms —
Specification**
(*First Revision*)

ICS 59.080.30

© BIS 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002
www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Handloom and Khadi Sectional Committee had been approved by the Textiles Division Council.

This standard was first published in 1978. The standard has been revised to incorporate the following changes:

- a) Marking clause has been modified;
- b) References to standards have been updated;
- c) Test method for identification of material has been incorporated; and
- d) Sampling clause has been modified.

The composition of the Committee responsible for the formulation of this standard is given in [Annex C](#).

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Indian Standard***TEXTILES — HANDLOOM COTTON FABRIC FOR SCHOOL UNIFORMS — SPECIFICATION***(First Revision)***1 SCOPE**

1.1 This standard prescribes the constructional particulars and other requirements of 11 varieties of handloom cotton fabric used in the manufacture of school uniforms. The cloth shall be bleached or dyed.

1.2 This standard does not specify the general appearance, feel, finish, etc of the cloth (*see* [4.3](#)).

2 REFERENCES

The standards listed in [Annex A](#) contain provisions which through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subjected to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards.

3 MANUFACTURE**3.1 Yarn**

The cotton yarn used in the manufacture of the cloth shall be satisfactory in evenness and reasonably free from neps and spinning defects. The yarns shall conform to IS 171.

3.2 Cloth

The cloth shall be free from dressing and filling materials and from substances liable to cause subsequent tendering.

4 REQUIREMENTS

4.1 The constructional particulars of cloth shall conform to those given in [Table 1](#).

4.2 The colour fastness ratings and other requirements of cloth shall conform to those given in [Table 2](#).

4.3 If in order to illustrate or specify the indeterminable characteristics, such as general

appearance, lustre, feel and shade of the cloth, a sample has been agreed upon and sealed, the supply shall be in conformity with the sample in such respects.

The custody of the sealed sample shall be a matter of prior agreement between the buyer and the seller.

5 INSPECTION

The cloth, when visually inspected, shall be reasonably free from the following defects:

- a) Weft crack of more than two missing picks across the width of the material;
- b) Prominently noticeable weft bar due to the fineness in raw material, count, twist, lustre, colour, shade, etc;
- c) More than two adjustment ends running parallel, broken or missing and extending beyond 15 cm;
- d) prominent selvedge defects;
- e) Noticeable warp or weft float in the body;
- f) Noticeable oil or other stains;
- g) Noticeable cut or tear up to 3 mm in size;
- h) Smash rupturing the texture of the fabric; and
- j) Prominently noticeable dyeing defects.

A reference may be made to IS 14466 for details of these defects.

6 SAMPLING

6.1 The quantity of handloom cotton fabric for school uniforms of the same variety delivered to a buyer against a despatch not shall constitute a lot.

6.2 To ascertain the conformity of the lot to the requirements of this standard, samples shall be drawn and inspected from each lot separately.

6.3 The number of pieces to be selected at random for inspection shall be in accordance with [Table 3](#).

Table 1 Constructional Particulars of Handloom Cotton Fabric for School Uniforms

(Clause 4.1)

SI No.	Variety No.	Count of Yarn [Cotton Count (Universal Count)]		Ends/ cm	Picks/ cm	Length m	Width cm	Weave	
		Warp	weft						
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	
i)	1	20 s (30 tex)	10s (59 tex)	22	18	20 or as agreed	71, 82, 92, 112 or as agreed	Plain	
ii)	2	20 s (30 tex)	10s (59 tex)	25	18				
iii)	3	20 s (30 tex)	10s (59 tex)	28	20				
iv)	4	14 s (42 tex)	12s (50 tex)	18	17			Cellular	
v)	5	20 s (30 tex)	14s (42 tex)	28	18				
vi)	6	30 s/2 (20 tex × 2)	10s (59 tex)	18	17				
vii)	7	14 s (42 tex)	14s (42 tex)	28	19				
viii)	8	30 s/2 (20 tex × 2)	10s (59 tex)	25	14				3/1 Twill
ix)	9	30 s/2 (20 tex × 2)	10s (59 tex)	26	16				
x)	10	30 s/2 (20 tex × 2)	10s (59 tex)	28	17				
xi)	11	40 s/2 (14.5 tex × 2)	14s (42 tex)	30	22				
Tolerance, Percent	—	± 5	± 5	± 5	± 5	—	± 2	—	
Method of Test, Ref to	—	IS 3442		IS 1963		IS 1954		Visual	

Table 2 Requirements of Handloom Cotton Fabric for School Uniforms

(Clause 4.2)

SI No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Colour fastness to:		
	a) Light	5 or better	IS/ISO 105-B01 or IS/ISO 105-B02
	b) Washing test 4	4 or better	IS/ISO 105-C10
ii)	Dimensional change, percent, <i>Max</i>	4.0	IS 2977
iii)	Scouring loss, percent, <i>Max</i>	2.5	IS 1383
iv)	pH value of aqueous extract	6.0 to 8.5	IS 1390 or Annex B
v)	Fiber identification	100 percent cotton	IS 667

Table 3 Sample Size and Permissible Number of Non-Conforming Pieces

(Clauses 6.3 and 6.4)

Sl No.	Lot Size	Sample Size	Permissible No. of Non-conforming Pieces	Sub-ample Size
(1)	(2)	(3)	(4)	(5)
i)	Up to 90	5	0	3
ii)	91 to 150	8	0	3
iii)	151 to 500	13	1	5
iv)	501 to 1 200	20	1	5
v)	1 201 to 10 000	32	2	8
vi)	10 001 to 35 000	50	3	8
vii)	35 001 to 500 000	80	5	13
viii)	500 001 and above	125	7	13

6.4 Number of Tests and Criterion for Conformity

Sl No.	Characteristic(s)	No. of Tests	Criterion for Conformity
(1)	(2)	(3)	(4)
i)	Count of yarn, ends, picks, length, width and weave	According to col (3) of Table 3	Permissible number of non-conforming piece does not exceed the corresponding number given in col (4) of Table 3
ii)	Colour fastness, dimensional changes, scouring loss, pH and fibre identification	According to col (5) of Table 3	All the test specimens meet the relevant requirements

7 MARKING

7.1 The cloth shall be suitably marked or labelled with the following information:

- Name of the material;
- Manufacturer's name, initials or trade-mark;
- Length and width;
- Count of warp and weft yarn;
- Indication of the source of manufacture; and
- Other declarations required as per law in force.

7.2 BIS Certification Marking

The product(s) conforming to the requirements of this

standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the product may be marked with the Standard Mark.

8 PACKING

Unless otherwise agreed upon by the buyer and the seller, the cloth shall preferably be packed in bales or cases in conformity with the procedure laid down either in IS 1347 or IS 293.

ANNEX A

(Clause 2)

LIST OF REFERRED STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
IS/ISO 105-B01 : 2014	Textiles — Tests for colour fastness: Part B01 Colour fastness to light: Daylight	IS 1383 : 2023	Methods for determination of scouring loss in grey and finished cotton textile materials (<i>second revision</i>)
IS/ISO 105-B02 : 2014	Textiles — Tests for colour fastness: Part B02 Colour fastness to artificial light: Xenon arc fading lamp test	IS 1390 : 2022/ ISO 3071 : 2020	Textiles — Determination of pH of aqueous extract (<i>third revision</i>)
IS/ISO 105-C10 : 2006	Textiles — Tests for colour fastness: Part C10 Colour fastness to washing with soap or soap and soda	IS 1954 : 2024/ ISO 22198 : 2006	Textiles — Fabrics — Determination of width and length (<i>third revision</i>)
IS 171 : 1993	Textiles — Ring spun grey cotton yarn for weaving — Specification (<i>fourth revision</i>)	IS 1963 : 1981	Methods for determination of threads per unit length in woven fabrics (<i>second revision</i>)
IS 293 : 1980	Code for seaworthy packaging of cotton yarn and cloth (<i>third revision</i>)	IS 2977 : 1989	Fabrics (other than wool) — Method for determination of dimensional changes on soaking in water (<i>first revision</i>)
IS 667 : 1981	Methods for identification of textile fibres (<i>first revision</i>)	IS 3442 : 2023	Textiles — Method for determination of crimp and linear density of yarn removed from fabric (<i>second revision</i>)
IS 1070 : 2023	Reagent grade water specification (<i>fourth revision</i>)	IS 14466 : 1997/ ISO 8498 : 1990	Fabrics — Description of defects — Vocabulary
IS 1347 : 1972	Specification for inland packaging of cotton cloth and yarn (<i>first revision</i>)		

To access Indian Standards click on the link below:

https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knowyourstandards/Indian_standards/isdetails/

ANNEX B

*(Table 2)*METHOD FOR DETERMINATION OF *pH* VALUE OF AQUEOUS EXTRACT**B-1 APPARATUS****B-1.1 Erlenmeyer Flask****B-1.2 Reflux Condenser****B-2 REAGENTS****B-2.1 Distilled Water** — *see* IS 1070**B-2.2 Indicator *pH* Papers****B-3 PROCEDURE**

B-3.1 Draw from each piece in the test sample at least two test specimens each weighing 5 g.

B-3.2 Rinse the Erlenmeyer flask with distilled water. Take one test specimen and cut it into small bits. Put the bits in the Erlenmeyer flask and add to

this 50 ml of distilled water. Boil the contents for one hour under the reflux condenser. Stopper the flask and cool the contents. Decant the supernatant extract in a test tube.

B-3.3 Take the *pH* indicator paper. Dip it in the extract and compare the colour of the moistened indicator paper with those printed on the booklet or dispenser containing the indicator paper. Designate the number, written on a particular colour shade with which the moistened indicator paper matches, as *pH* of the extract.

B-3.4 Similarly test the remaining test specimen(s).

B-4 REPORT

Report the *pH* value of the extract as determined above.

ANNEX C

(Foreword)

COMMITTEE COMPOSITION

Handloom and Khadi Sectional Committee, TXD 08

<i>Organization</i>	<i>Representative(s)</i>
Weavers Service Centre, Delhi	SHRI VISHESH NAUTIYAL (<i>Chairperson</i>) SHRI VIKAS KUMAR (<i>Alternate</i>)
Center of Excellence for Khadi (COEK)-NIFT, New Delhi	REPRESENTATIVE
Central Pollution Control Board, New Delhi	SHRI P. K. MISHRA SHRI RISHABH SRIVASTAV (<i>Alternate</i>)
CRPF, New Delhi	SHRI D. P. UPADHYAY SHRI SANJEEV KUMAR SINGH (<i>Alternate</i>)
Department of Handlooms & Textiles, Chennai	SHRI THIRU R. RAGHUNATH SHRI THIRU K. MUNUSAMY (<i>Alternate</i>)
Fabindia, New Delhi	REPRESENTATIVE
Flag Foundation of India, New Delhi	SHRI ASHIM KOHLI
Gandhigram Rural Institute, Dindigul	DR B. SENTHIL KUMAR
Haryana Khadi Gramodyog Sangh, Karnal	SHRI PAWAN GARG SHRI R. S. YADAV (<i>Alternate</i>)
ICAR - Central Institute for Research on Cotton Technology, Mumbai (CIRCOT)	DR SUJATA SAXENA DR A. S. M. RAJA (<i>Alternate</i>)
Indian Institute of Handloom Technology, Jodhpur	DR J. SIVAGNANAM
Indian Institute of Handloom Technology, Salem	DR P. THENNARASU
Indian Institute of Handloom Technology, Varanasi	DR AMIN HIRENBHAI NAVINBHAI SHRI JITENDER TAK (<i>Alternate</i>)
Indian Institute of Technology, Delhi	DR BIPIN KUMAR DR WAZED ALI (<i>Alternate</i>)
Indo Tibetan Border Police, New Delhi	SHRI UTTAM KUMAR SHRI ANAND KUMAR (<i>Alternate</i>)
Jan Sewa Ashram, Aligarh	SHRI R. K. SHARMA SHRI AKHILESH KUMAR AWASTHI (<i>Alternate</i>)

<i>Organization</i>	<i>Representative(s)</i>
Karnatka Khadi Gramodyog Samyuktha Sangha, Hubli	SHRI K. V. PATTAR SHRI SHIVANANDA S. MATHAPATI (<i>Alternate</i>)
Khadi and Village Industries Commission, Mumbai	SHRI VIJAYSRIDHAR DR SENTIL KUMAR C. B. (<i>Alternate</i>)
Khadi Dyers & Printers, Mumbai	SHRI D. N. BHATT SHRI V. D. JOSHI (<i>Alternate</i>)
Khadi Gramodyog Mandal, Rampur	SHRI RAKESH CHAUDHARY SHRI PRINCE CHAUDHARY (<i>Alternate</i>)
Kshetriya Khadi Gramodyog Samiti, Dausa	SHRI R. K. SINGH
Madhya Bharat Khadi Sangh, Gwalior	SHRIMATI NEELU MEKLE SHRI HARISH MEKLE (<i>Alternate</i>)
Mahatma Gandhi Institute for Rural Industrialization, Wardha	SHRI MAHESH KUMAR DR TAPAN RANJAN KAR (<i>Alternate</i>)
Metpalli Khadi Gramodyog Pratisthan, Metpalli	SHRI G. MADHAV
Ministries of Defence (DGQA), New Delhi	SHRI ARVIND COMPATHANE SHRI N. SENTHIL KUMAR (<i>Alternate</i>)
Ministries of Health, New Delhi	REPRESENTATIVE
National Handloom Development Corporation Ltd, Gautam Budh Nagar	DR SAKTHIVEL PERUMAL SAMY SHRI JITENDRA TOLAMBIYA (<i>Alternate</i>)
Northern India Textile Research Association, Ghaziabad	DR M. S. PARMAR SHRI SANJEEV SHUKLA (<i>Alternate</i>)
Northern Railways, New Delhi	SHRI SANJEEV KUMAR JAIN SHRI RAJESH KUMAR (<i>Alternate</i>)
Office of the Development Commissioner for Handlooms, New Delhi	SHRI SIDDHARTH SINGH SHRI VINAY KUMAR (<i>Alternate</i>)
Orient Processes Pvt Ltd, Guwahati	SHRI ROBIN CHANDRA GOSWAMI SHRI RAJ BURAGOHAIN (<i>Alternate</i>)
Rastriya Khadi Gramodyog Federation, Moradabad	SHRI ANIL KUMAR SINGH SHRI KULDEEP SINGH (<i>Alternate</i>)
Swastik Gramodyog Samiti, Delhi	SHRI M. L. PATHAK SHRI ABHISHEK DIXIT (<i>Alternate</i>)
The Cotton Textiles Export Promotion Council (TEXPROCIL), Mumbai	DR SIDDHARTHA RAJAGOPAL SHRI RAJESH SATAM (<i>Alternate</i>)

<i>Organization</i>	<i>Representative(s)</i>
The Handloom Export Promotion Council, Chennai	DR M. SUNDAR SHRI N. SREEDHAR (<i>Alternate</i>)
The Tamil Nadu Handloom Weavers Cooperative Society Ltd, Chennai	SHRI T. N. VENKATESH, I. A. S. SHRI K. KATHIRESAN (<i>Alternate</i>)
BIS Directorate General	SHRI J. K. GUPTA, SCIENTIST 'E'/DIRECTOR AND HEAD (TEXTILES) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)]

Member Secretary
SHRI SWAPNIL
SCIENTIST 'B'/ASSISTANT DIRECTOR
(TEXTILES), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 06 (24942).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

Central : 601/A, Konnectus Tower -1, 6th Floor,
DMRC Building, Bhavbhuti Marg, New
Delhi 110002

Telephones

{ 2323 7617

Eastern : 8th Floor, Plot No 7/7 & 7/8, CP Block, Sector V,
Salt Lake, Kolkata, West Bengal 700091

{ 2367 0012
2320 9474

Northern : Plot No. 4-A, Sector 27-B, Madhya Marg,
Chandigarh 160019

{ 265 9930

Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113

{ 2254 1442
2254 1216

Western : 5th Floor/MTNL CETTM, Technology Street, Hiranandani Gardens, Powai
Mumbai 400076

{ 25700030
25702715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.