

वस्त्रादि — वर्दी के लिए पॉलिएस्टर सूती
मिश्रित खादी (पॉलीवस्त्र) की
सूटिंग — विशिष्टि
(पहला पुनरीक्षण)

Textiles — Polyester Cotton
Blended Khadi (Polyvastra) Suitings
for Uniform — Specification
(First Revision)

ICS 59.080.30

© BIS 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002
www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Handloom and Khadi Sectional Committee had been approved by the Textiles Division Council.

Polyester blended suitings are being increasingly used by the organized consumers like DGS&D, Ministry of Defence, Railways, P&T, etc for making uniforms. Polyvastra is a polyester-cotton blended fabric which is being produced in the khadi sector under the aegis of Khadi Village Industries Commission. In simple terms, polyvastra is a smart choice for uniforms because it combines the strengths of natural and synthetic fibers, making it perfect for the demands of today's workplaces.

This standard was first published in 1993. The standard has been revised to incorporate the following changes:

- a) Marking clause has been modified;
- b) References to standards have been updated;
- c) Method of test for count of yarn along with its tolerance has been specified;
- d) Method for determination of heat shrinkage of fabric has been modified; and
- e) Sampling clause has been modified.

The composition of the Committee responsible for the formulation of this standard is given in [Annex D](#).

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

TEXTILES — POLYESTER COTTON BLENDED KHADI (POLYVASTRA) SUITINGS FOR UNIFORM — SPECIFICATION

*(First Revision)***1 SCOPE**

1.1 This standard prescribes constructional particulars and performance requirements of polyester cotton blended khadi (polyvastra) suitings for making uniforms.

1.2 This standard does not specify the general appearance, feel, shade, etc of the fabric.

2 REFERENCES

The standards listed in [Annex A](#) contain provisions which through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards.

3 MANUFACTURE

3.1 The hand spun yarn shall be used in the manufacture of the fabric.

3.2 The fabric shall be woven on handloom with uniform construction having firm and straight selvages.

The fabric shall be well singed, heat set and fully shrunk.

4 REQUIREMENTS

4.1 The cloth shall conform to the requirements specified in [Table 1](#).

4.2 The cloth shall be free from major flaws (defects) which shall not exceed 15 per 100 metres length. A list of major flaws (defects) is given in [Annex B](#) (see also IS 14466). The allowance for providing extra length of cloth in lieu of flaws (defects) not exceeding the permissible limits may be as agreed to between the buyer and the seller.

NOTE — The number of defects shall be determined on all pieces under test and converted into number of defects per 100 metre length.

4.3 Sealed Sample

If in order to illustrate or specify the indeterminable characteristics, such as general appearance, lustre, feel and shade of the cloth a sample has been agreed upon and sealed, the supply shall be in conformity with the sample in such respect.

The custody of the sealed sample shall be a matter of prior agreement between the buyer and the seller.

5 SAMPLING

5.1 The quantity of polyester cotton blended khadi cloth of the same variety delivered to a buyer against a despatch note shall constitute a lot.

5.2 To ascertain the conformity of the lot to the requirements of this standard, samples shall be drawn and inspected from each lot separately.

5.3 The number of pieces to be selected at random for inspection shall be in accordance with [Table 2](#).

5.4 Number of Tests and Criterion for Conformity

<i>Sl No.</i>	<i>Characteristic(s)</i>	<i>No. of Tests</i>	<i>Criterion for Conformity</i>
(1)	(2)	(3)	(4)
i)	Count, threads/dm, length, width and freedom from defects	According to co1 (3) of Table 2	Permissible number of non-conforming piece does not exceed the corresponding number given in co1 (4) of Table 2
ii)	Colour fastness, breaking load, mass, blend composition, relaxation shrinkage, crease recovery angle, pilling, water soluble matter, pH value and heat shrinkage	According to co1 (5) of Table 2	All the test specimens meet the relevant requirements

Table 1 Requirements of Polyester Cotton Blended Khadi (Polyvastra) Suitings for Uniforms
(Clause [4.1](#))

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Approximate count of warp and weft yarns (for guidance only)	20 tex × 2 (30s/2) ± 5 percent	IS 3442
ii)	Blend composition, percent		IS 3416
	a) Polyester	67 ± 5	
	b) Cotton	33 ± 5	
iii)	Threads/dm		IS 1963
	a) Warp	260 ± 5 percent	
	b) Weft	190 ± 5 percent	
iv)	Mass, g/m ²	190 ± 5 percent	IS 1964
v)	Length, m	As agreed	IS 1954
vi)	Width, cm	70 ± 2	
vii)	Breaking load on 5.0 cm × 20 cm strip, <i>Min</i>		IS 1969 (Part 1)
	a) Warp way	840 N	
	b) Weft way	610 N	
viii)	Crease recovery angle, <i>Min</i> (initially and after three repeated washings, etc)	240°	IS 4681 (Part 2)
ix)	Pilling (after 5 h test)	4 or better	IS 10971 (Part 1)
x)	Relaxation shrinkage, percent, <i>Max</i>		IS 2977
	a) Warp way	2	
	b) Weft way	2	
xi)	pH value of the aqueous extract	6.0 to 8.5	IS 1390
xii)	Water soluble matter, percent, <i>Max</i>	1	IS 3456
xiii)	Colour fastness		
	a) Light	5 or better	IS/ISO 105-B01 or IS/ISO 105-B02
	b) Washing Test 3 (After 4 washings)		IS/ISO 105-C10
	1) Change in colour	4 or better	
	2) Staining on fabric	4 or better	
	c) Perspiration	4 or better	IS/ISO 105-E04
	d) Rubbing	4 or better	IS/ISO 105-X12
xiv)	Heat shrinkage, percent, <i>Max</i>	2.0	Annex C

Table 2 Sample Size and Permissible Number of Non-Conforming Pieces

(Clauses 5.3 and 5.4)

Sl No.	Lot Size	Sample Size	Permissible No. of Non-Conforming Pieces	Sub Sample Size
(1)	(2)	(3)	(4)	(5)
i)	Up to 90	5	0	3
ii)	91 to 150	8	0	3
iii)	151 to 500	13	1	5
iv)	501 to 1 200	20	1	5
v)	1 201 to 10 000	32	2	8
vi)	10 001 to 35 000	50	3	8
vii)	35 001 to 500 000	80	5	13
viii)	500 001 and above	125	7	13

6 MARKING

6.1 The cloth shall be suitably marked or labelled with the following information:

- a) Name of the material, namely, polyvastra suiting;
- b) Composition, namely, polyester 67 percent and cotton 33 percent;
- c) Manufacturer's name, initials or trade-mark;
- d) Length and width;
- e) Count of warp and weft yarn;
- f) Indication of the source of manufacture; and
- g) Other declarations required as per law in force.

6.2 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the product may be marked with the Standard Mark.

7 PACKING

Unless otherwise agreed between the buyer and the seller, the cloth shall preferably be packed in bales or cases in conformity with the procedure laid down in IS 1347 or IS 293.

ANNEX A

(Clause 2)

LIST OF REFERRED STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
IS/ISO 105-B01 : 2014	Textiles — Tests for colour fastness: Part B01 Colour fastness to light: Daylight	IS 1969 (Part 1) : 2018/ISO 13934-1 : 2013	Textiles — Tensile properties of fabrics: Part 1 Determination of maximum force and elongation at maximum force using the strip method (<i>fourth revision</i>)
IS/ISO 105-B02 : 2014	Textiles — Tests for colour fastness: Part B02 Colour fastness to artificial light: Xenon arc fading lamp test	IS 2977 : 1989	Fabrics (other than wool) — Method for determination of dimensional changes on soaking in water (<i>first revision</i>)
IS/ISO 105-C10 : 2006	Textiles — Tests for colour fastness: Part C10 Colour fastness to washing with soap or soap and soda	IS 3416 : 2024/ ISO 1833-11 : 2017	Textiles — Quantitative chemical analysis — Mixtures of certain cellulose fibres with certain other fibres (method using sulphuric acid) (<i>third revision</i>)
IS/ISO 105-E04 : 2013	Textiles — Tests for colour fastness: Part E04 Colour fastness to perspiration (<i>first revision</i>)	IS 3442 : 2023	Textiles — Method for determination of crimp and linear density of yarn removed from fabric (<i>second revision</i>)
IS/ISO 105-X12 : 2016	Textiles — Tests for colour fastness: Part X12 Colour fastness to rubbing (<i>first revision</i>)	IS 3456 : 2022	Method for determination of water-soluble matter of textile materials (<i>first revision</i>)
IS 293 : 1980	Code for seaworthy packaging of cotton yarn and cloth (<i>third revision</i>)	IS 4681 (Part 2) : 2024/ISO 2313-2 : 2021	Textiles — Determination of the recovery from creasing of a folded specimen of fabric by measuring the angle of recovery: Part 2 Method of the vertically folded specimen (<i>second revision</i>)
IS 1347 : 1972	Specification for inland packaging of cotton cloth and yarn (<i>first revision</i>)	IS 6359 : 2023	Method for conditioning of textiles (<i>first revision</i>)
IS 1390 : 2022/ ISO 3071 : 2020	Textiles — Determination of pH of aqueous extract (<i>third revision</i>)	IS 10971 (Part 1) : 2022/ISO 12945-1 : 2020	Textiles — Determination of fabric propensity to surface pilling fuzzing or matting: Part 1 Pilling box method (<i>second revision</i>)
IS 1954 : 2024/ ISO 22198 : 2006	Textiles — Fabrics — Determination of width and length (<i>third revision</i>)	IS 14466 : 1997/ ISO 8498 : 1990	Fabrics — Description of defects — Vocabulary
IS 1963 : 1981	Methods for determination of threads per unit length in woven fabrics (<i>second revision</i>)		
IS 1964 : 2001	Textiles — Methods for determination of mass per unit length and mass per unit area of fabrics (<i>second revision</i>)		

To access Indian Standards click on the link below:

https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knownyourstandards/Indian_standards/isdetails/

ANNEX B*(Clause 4.2)***LIST OF MAJOR FLAWS**

- a) One or more ends missing in the body of the material throughout its length, more than three ends missing at a place and running over 60 cm, or prominently noticeable double and running throughout the piece;
- b) Undressed snarls noticeable over a length exceeding 5 percent of the length of the piece;
- c) Smash definitely rupturing the texture of the fabric;
- d) Hole, cut or tear;
- e) Reed marks prominently noticeable over a length exceeding 5 percent of the piece;
- f) Defective or damaged selvedge noticeable over a length exceeding 5 percent of the length of the piece;
- g) Skewing of more than three percent on weft. Weft crack or two or more missing picks across the width of the fabric;
- h) Warp or weft bar due to the difference in raw material, count, twist, lustre, colour, shade or spacing of adjacent groups of yarns (starting mark);
- j) More than two adjacent ends running parallel, broken or missing and extending beyond 10 cm;
- k) Noticeable warp or weft float in the body of the fabric;
- m) Noticeable oil or other stain in the fabric;
- n) Oily weft in the fabric;
- p) Prominently noticeable slub;
- q) Conspicuous broken pattern;
- r) Gout due to foreign matter, usually lint or waste woven into the fabric;
- s) Prominent selvedge defect;
- t) Significant shading or listing in fabrics having a gradual change in tone or depth of shade of fabric (excluding selvedge or border running parallel to the selvedge);
- u) Coloured flecks;
- v) Blurred or dark patch;
- w) Patchy, streaky or uneven dyeing;
- y) Dye bar; and
- z) Fuzzy appearance.

ANNEX C

[\(Table 1\)](#)

METHOD FOR DETERMINATION OF HEAT SHRINKAGE OF FABRIC

C-1 Cut a sample of fabric measuring 30 cm × 30 cm and bring it to moisture equilibrium by conditioning in standard atmospheric conditions of 67 percent ± 2 percent RH and 27 °C ± 2 °C temperature (*see* IS 6359). Mark a square of 25 cm × 25 cm on the sample. Make four reference points on each side of the square at 5 cm intervals so that by including the sides of the square, six determinations can be made in warp and weft direction. Make two slits of 1.25 cm from opposite edges of the fabric and pass a rod through the slits. Mount the sample in the ventilated oven by means

of the rod so that air circulates freely around the sides of the sample. Bring the oven to a temperature of 160 °C ± 4 °C before the sample is inserted into the oven and the sample shall remain in the oven for 16 s. Then withdraw the sample and remove it from the rod, lay in on a flat smooth surface and allow it to cool. Measure the distance between each pair of marks to the nearest millimeter and record the change in the dimensions. Determine the average of the readings in the warp and weft directions separately and express it as a percentage of the original length.

ANNEX D

(Foreword)

COMMITTEE COMPOSITION

Handloom and Khadi Sectional Committee, TXD 08

<i>Organization</i>	<i>Representative(s)</i>
Weavers Service Centre, Delhi	SHRI VISHESH NAUTIYAL (Chairperson) SHRI VIKAS KUMAR (<i>Alternate</i>)
Center of Excellence for Khadi (COEK)-NIFT, New Delhi	REPRESENTATIVE
Central Pollution Control Board, New Delhi	SHRI P. K. MISHRA SHRI RISHABH SRIVASTAV (<i>Alternate</i>)
CRPF, New Delhi	SHRI D. P. UPADHYAY SHRI SANJEEV KUMAR SINGH (<i>Alternate</i>)
Department of Handlooms & Textiles, Chennai	SHRI THIRU R. RAGHUNATH SHRI THIRU K. MUNUSAMY (<i>Alternate</i>)
Fabindia, New Delhi	REPRESENTATIVE
Flag Foundation of India, New Delhi	SHRI ASHIM KOHLI
Gandhigram Rural Institute, Dindigul	DR B. SENTHIL KUMAR
Haryana Khadi Gramodyog Sangh, Karnal	SHRI PAWAN GARG SHRI R. S. YADAV (<i>Alternate</i>)
ICAR - Central Institute for Research on Cotton Technology, Mumbai (CIRCOT)	DR SUJATA SAXENA DR A. S. M. RAJA (<i>Alternate</i>)
Indian Institute of Handloom Technology, Jodhpur	DR J. SIVAGNANAM
Indian Institute of Handloom Technology, Salem	DR P. THENNARASU
Indian Institute of Handloom Technology, Varanasi	DR AMIN HIRENBHAI NAVINBHAI SHRI JITENDER TAK (<i>Alternate</i>)
Indian Institute of Technology, Delhi	DR BIPIN KUMAR DR WAZED ALI (<i>Alternate</i>)
Indo Tibetan Border Police, New Delhi	SHRI UTTAM KUMAR SHRI ANAND KUMAR (<i>Alternate</i>)
Jan Sewa Ashram, Aligarh	SHRI R. K. SHARMA SHRI AKHILESH KUMAR AWASTHI (<i>Alternate</i>)
Karnatka Khadi Gramodyog Samyuktha Sangha, Hubli	SHRI K. V. PATTAR SHRI SHIVANANDA S. MATHAPATI (<i>Alternate</i>)

<i>Organization</i>	<i>Representative(s)</i>
Khadi and Village Industries Commission, Mumbai	SHRI VIJAYSRIDHAR DR SENTIL KUMAR C. B. (<i>Alternate</i>)
Khadi Dyers & Printers, Mumbai	SHRI D. N. BHATT SHRI V. D. JOSHI (<i>Alternate</i>)
Khadi Gramodyog Mandal, Rampur	SHRI RAKESH CHAUDHARY SHRI PRINCE CHAUDHARY (<i>Alternate</i>)
Kshetriya Khadi Gramodyog Samiti, Dausa	SHRI R. K. SINGH
Madhya Bharat Khadi Sangh, Gwalior	SHRIMATI NEELU MEKLE SHRI HARISH MEKLE (<i>Alternate</i>)
Mahatma Gandhi Institute for Rural Industrialization, Wardha	SHRI MAHESH KUMAR DR TAPAN RANJAN KAR (<i>Alternate</i>)
Metpalli Khadi Gramodyog Pratisthan, Metpalli	SHRI G. MADHAV
Ministries of Defence (DGQA), New Delhi	SHRI ARVIND COMPATHANE SHRI N. SENTHIL KUMAR (<i>Alternate</i>)
Ministries of Health, New Delhi	REPRESENTATIVE
National Handloom Development Corporation Ltd, Gautam Budh Nagar	DR SAKTHIVEL PERUMAL SAMY SHRI JITENDRA TOLAMBIYA (<i>Alternate</i>)
Northern India Textile Research Association, Ghaziabad	DR M. S. PARMAR SHRI SANJEEV SHUKLA (<i>Alternate</i>)
Northern Railways, New Delhi	SHRI SANJEEV KUMAR JAIN SHRI RAJESH KUMAR (<i>Alternate</i>)
Office of the Development Commissioner for Handlooms, New Delhi	SHRI SIDDHARTH SINGH SHRI VINAY KUMAR (<i>Alternate</i>)
Orient Processes Pvt Ltd, Guwahati	SHRI ROBIN CHANDRA GOSWAMI SHRI RAJ BURAGOHAIN (<i>Alternate</i>)
Rastriya Khadi Gramodyog Federation, Moradabad	SHRI ANIL KUMAR SINGH SHRI KULDEEP SINGH (<i>Alternate</i>)
Swastik Gramodyog Samiti, Delhi	SHRI M. L. PATHAK SHRI ABHISHEK DIXIT (<i>Alternate</i>)
The Cotton Textiles Export Promotion Council (TEXPROCIL), Mumbai	DR SIDDHARTHA RAJAGOPAL SHRI RAJESH SATAM (<i>Alternate</i>)

<i>Organization</i>	<i>Representative(s)</i>
The Handloom Export Promotion Council, Chennai	DR M. SUNDAR SHRI N. SREEDHAR (<i>Alternate</i>)
The Tamil Nadu Handloom Weavers Cooperative Society Ltd, Chennai	SHRI T. N. VENKATESH, I. A. S. SHRI K. KATHIRESAN (<i>Alternate</i>)
BIS Directorate General	SHRI J. K. GUPTA, SCIENTIST 'E'/DIRECTOR AND HEAD (TEXTILES) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)]

Member Secretary

SHRI SWAPNIL
SCIENTIST 'B'/ASSISTANT DIRECTOR
(TEXTILES), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 08 (24943).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : 5 th Floor/MTNL CETTM, Technology Street, Hiranandani Gardens, Powai Mumbai 400076	{ 25700030 25702715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.