

वस्त्रादि — कपास, इंटरलॉक बुना हुआ
कपड़ा — विशिष्टि
(पहला पुनरीक्षण)

**Textiles — Cotton, Interlock Knitted
Fabric — Specification**
(*First Revision*)

ICS 59.060.10; 59.080.30

© BIS 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002


www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Hosiery Sectional Committee had been approved by the Textile Division Council.

Interlock fabric is a double 1×1 rib-knitted fabric with crossed sinker wales. The wales on one side of the fabric are immediately behind the wales of the other side of the fabric. The appearance of this fabric is same on both the sides.

This standard was first published in 1991. This revision has been brought out in the light of experience gained since its publication and to incorporate the following major changes:

- a) Title of the standard has been modified;
- b) The amendment issued has been incorporated;
- c) **References to standard given** in Annex  has been updated;
- d) BIS certification marking clause has been updated; and
- e) Sampling and criteria for conformity has been modified.

The composition of the Committee responsible for the formulation of this standard is given in [Annex C](#).

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

*Indian Standard***TEXTILES — COTTON, INTERLOCK KNITTED FABRIC —
SPECIFICATION***(First Revision)***1 SCOPE**

1.1 This standard prescribes the requirements of grey, scoured, bleached, dyed or printed interlock fabric knitted on circular machines.

1.2 This standard also covers coloured interlock knitted fabric produced by knitting with dyed yarn.

1.3 This standard does not specify the general appearance, feel, lustre, degree of whiteness or shade of the knitted fabric (*see* [5.4](#)).

2 REFERENCES

The standards listed in [Annex A](#) contain provisions which, through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards.

3 TERMINOLOGY

For the purpose of this standard, the definitions given in IS 3596 shall apply (*see* SP 45).

4 MANUFACTURE

4.1 The tubular fabric shall be evenly knitted on interlock machine. The width of the tubular fabric shall be uniform throughout and shall correspond to the diameter of the knitting machine. The fabric shall not be over boarded or pulled in length while calendaring. If required by the buyer, the bleached fabric may also be treated with optical whitening agents.

4.2 The fabric shall be reasonably free from knitting defects such as ladders, dropped stitches, holes, cuts and mends and chemical defects such as defective bleaching in case of bleached fabric or streaks, stains and uneven dyeing in case of dyed fabric and defective printing in case of printed fabric.

5 REQUIREMENTS

5.1 The yarn used in knitting the fabric shall conform

to IS 834. medium 'C', fine and superfine fabrics (*see* [Table 1](#)) shall be knitted from combed yarn only.

5.2 The construction requirements of the fabric shall be as specified in [Table 1](#).

5.3 The fabric shall also conform to the requirements specified in [Table 2](#).

5.4 Sealed Sample

In order to illustrate or specify the indeterminable characteristics such as general appearance, degree of whiteness, colour, shade or print design of fabric, a sample has been agreed upon and sealed, the supply shall be in conformity with the sample in such respects.

The custody of the sealed sample shall be a matter of prior agreement between the buyer and the seller.

6 MARKING

6.1 Each roll of fabric shall be marked with the following information:

- a) Count of yarn and type (carded or combed);
- b) Designation of fabric (*see* [Table 1](#));
- c) Hundred percent cotton, if required by the buyer;
- d) Diameter of the knitting machine;
- e) Indication of the source of manufacture; and
- f) Any other information/instruction provided by the manufacturer/required under law.

6.2 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the product may be marked with the Standard Mark.

7 PACKING

Unless otherwise agreed to between the buyer and the seller, the fabric shall be well packed and supplied in a clean and dry state free from stains, greases, etc.

8 SAMPLING AND CRITERIA FOR CONFORMITY

8.1 Lot

In any consignment, all rolls knitted of a particular diameter of knitting machine of the same designation and of the same quality (type) and count of yarn and delivered to a buyer against one dispatch note shall constitute a lot.

The conformity of a lot to the requirements of this specification shall be determined on the basis of the tests carried out on the samples selected from the lot.

8.2 Unless otherwise agreed to between the buyer and the seller, number of rolls depending upon the size of the lot shall be selected at random from the lot to constitute the gross sample. The number of rolls so selected shall be in accordance with col (3) of [Table 3](#).

Table 1 Construction Requirements of Interlock Knitted Cotton Fabric

(Clauses [5.1](#), [5.2](#) and [6.1](#))

SI No.	Designation	Gauge of Machine (see Note)	Nominal Count of Yarn Cotton Count, Ne (Tex)	Wales/dm, <i>Min</i>	Courses/dm, <i>Min</i>
(1)	(2)	(3)	(4)	(5)	(6)
i)	Coarse 'A'	18	18s (33), 20s (30)	98	102
ii)	Coarse 'B'	20	22s (27), 24s (25) 26s (22.5)	106	110
iii)	Medium 'A'	20	28s (21), 30s (20), 34s (17.5)	114	118
iv)	Medium 'B'	20	34s (17.5), 36s (16.5), 38s (15.5), 39s (15), 40s (14.5)	122	134
v)	Medium 'C'	22	40s (14.5), 42s (14), 44s (13.5), 45s (13), 50s (12)	138	164
vi)	Fine	24	50s to 60s (12 to 9.8)	152	180
vii)	Superfine	26	60s to 80s (9.8 to 7.4)	168	196
Method of test, ref to		—	IS 1315	B-2	B-2
NOTE — As determined by the number of needles per 2.5 cm.					

Table 2 Requirements of Interlock Knitted Cotton Fabric

(Clause [5.3](#) and [B-3.1](#))

SI No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Length, <i>Min</i>	As agreed to between the buyer and the seller	IS 1954

Table 2 (Concluded)

SI No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
ii)	Width		
	a) Grey fabric b) Scoured, bleached, calendared, dyed or printed fabric	± 2 cm of the size (see Note) ± 1 cm of the size (see Note)	IS 1954
iii)	Dimensional change (due to relaxation) percent, <i>Max</i>		B-3
	a) Grey fabric:		
	i) Wales direction; and	10.0	
	ii) Courses direction.	12.0	
b) Scoured, bleached, calendared, dyed or printed fabric:			
i) Wales direction; and	5.0		
ii) Courses direction.	10.0		
iv)	pH value	6 to 8	IS 1390
v)	Minimum colour fastness rating of dyed or printed fabric:		
	a) Light, change in colour	5	IS/ISO 105-B01 or IS/ISO 105-B02 IS/ISO 105-C10
	b) Washing: Test A (1)		
	i) Change in colour; and	4	
	ii) Staining of adjacent fabric.	4	
	c) Perspiration:		IS/ISO 105-E04
i) Change in colour; and	4		
ii) Staining of adjacent fabric.	4		
NOTE — Diameter of the knitting machine.			

Table 3 Sample Size and Permissible Number of Non-Conforming Rolls

(Clauses [8.2](#) and [8.2](#))

SI No.	Number of Rolls in the Lot	Physical Characteristics		Number of Rolls to be Tested
		Number of Rolls to be Inspected	Permissible Number of Non-conforming Rolls	
(1)	(2)	(3)	(4)	(5)
i)	Up to 50	5	0	2
ii)	51 to 90	5	0	3
iii)	91 to 150	8	0	3

Table 3 (Concluded)

SI No.	Number of Rolls in the Lot	Physical Characteristics		Number of Rolls to be Tested
		Number of Rolls to be Inspected	Permissible Number of Non-conforming Rolls	
(1)	(2)	(3)	(4)	(5)
iv)	151 to 280	13	1	3
v)	280 to 500	20	1	3
vi)	500 and above	32	2	5

8.3 The number of rolls to be tested and criteria for conformity for each of the characteristics shall be as follows:

Sl No.	Characteristic	Number of Rolls to be Tested	Criterion for Conformity
(1)	(2)	(3)	(4)
i)	Physical		
	Visual inspection, construction and width/diameter	see col (3) of Table 3	Non-conforming rolls not to exceed the corresponding number given in col (4) of Table 3
ii)	Other requirements		
	a) Dimensional change and pH value; and	see col (5) of Table 3	All rolls to satisfy the requirements
	b) Colour fastness.	1 specimen each of the same colour, shade and/or print for lot size up to 150 and 2 above 150	All the test satisfies the requirements specimens relevant

ANNEX A

(Clause 2)

LIST OF REFERRED STANDARDS

<i>IS No./Other Standard</i>	<i>Title</i>	<i>IS No./Other Standard</i>	<i>Title</i>
IS/ISO 105-B01 : 2014	Textiles — Tests for colour fastness: Part B01 Colour fastness to light:Daylight	(Part 2) : 2003	Control charts for attributes (<i>third revision</i>)
IS/ISO 105-B02 : 2014	Textiles — Tests for colour fastness: Part B02 Colour fastness to artificial light: Xenon arc fading lamp test	IS 834 : 2006	Textiles — Ring spun grey cotton yarn for hosiery — Specification (<i>fifth revision</i>)
IS/ISO 105-C10 : 2006	Textiles — Tests for colour fastness: Part C10 Colour fastness to washing with soap or soap and soda	IS 1315 : 1977	Method for determination of linear density of yarns spun on cotton system (<i>first revision</i>)
IS/ISO 105-E04 : 2013	Textiles — Tests for colour fastness: Part E04 Colour Fastness to Perspiration (<i>first revision</i>)	IS 1390 : 2022/ ISO 3071 : 2020	Textiles — Determination of pH of aqueous extract (<i>third revision</i>)
IS 394 : 1985	Specification for ink, cloth marking (<i>second revision</i>)	IS 1954 : 2024/ ISO 22198 : 2006	Textiles — Fabrics — Determination of width and length (<i>third revision</i>)
IS 397	Method for statistical quality control during production:	IS 3596 : 1967	Glossary of terms relating to hosiery
(Part 1) : 2003	Control charts for variables (<i>second revision</i>)	IS 6359 : 2023	Method for conditioning of textiles (<i>first revision</i>)
		SP 45 : 1988	Handbook on glossary of textile terms

To access Indian Standards click on the link below:

https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knowyourstandards/Indian_standards/isdetails/

ANNEX B

(Table 1 and Table 2)

METHODS OF TEST

B-1 CONDITIONING OF TEST SPECIMENS AND ATMOSPHERIC CONDITIONS FOR TESTING

The test specimens shall be tested in prevailing atmospheric conditions. In case of dispute, the samples shall be conditioned and tested in standard atmosphere as given in IS 6359.

B-2 WALES AND COURSES

Take one of the rolls and lay it flat on a table. Remove all creases and wrinkles without distorting it. On one side of the test specimen, count with the help of a pick glass or magnifying glass, the number of wales and courses in 10 cm at three different places in the roll and calculate the average number of wales and courses per dm.

B-3 DIMENSIONAL CHANGE (DUE TO RELAXATION)**B-3.1 Marking of Test Specimens**

Take one of the rolls from the lot cut a piece measuring approximately 30 cm in length × full width. Mark centrally on it by means of indelible ink (see IS 394 and Note 2) an area 15 cm × 15 cm with two of its sides in the direction of wales and the other two in the direction of courses. Spread this test specimen on a flat smooth surface, carefully removing by hand all creases and wrinkles. Within this area, mark six pairs of marks, three pairs each in the wales and courses direction in such a way that the distance between each pair of marks is the same.

NOTE — If marking ink is not available, dyed cotton sewing thread having a minimum colour fastness rating as given in SI No. (v) (b) of Table 2 may be used.

B-3.2 Procedure

Take the test specimen and spread it on a flat smooth surface. Carefully remove by hand all creases and wrinkles without stretching the test specimen.

B-3.2.1 Measure correct to the nearest mm the distance between each pair of marks separately.

B-3.2.2 Lay the test specimen flat in a watertight tray of suitable size, having depth of minimum 10 cm. Soak it under a head of 25 mm of water containing 0.5 percent suitable wetting agent at 30 °C to 35 °C for 2 h. Drain out the water and remove the test specimen carefully so that it is not stretched and lay it flat on a smooth surface. Remove the excess of water by absorbent material and dry it at room temperature.

B-3.2.3 After drying, condition the test specimen to moisture equilibrium in a standard atmosphere, if needed (see B-1). Place it on the glass plate, carefully remove all wrinkles and creases and place the other glass plate on the test specimen. Measure correct to the nearest mm, the distance between each pair of marks separately.

B-3.2.4 Calculate, separately, the percentage of dimensional change both in the direction of wales and courses by the following formula:

$$S = \frac{(a - b)}{a \times 100}$$

where

S = dimensional change, percent;

a = the distance between a pair of marks (along the wales or courses, as the case may be) before soaking; and

b = the distance between the same pair of marks after soaking.


B-3.2.5 Calculate separately the dimensional change of all the three lines in the direction of wales and in the direction of courses and calculate average dimensional change in each direction.

ANNEX C

(Foreword)

COMMITTEE COMPOSITION

Hosiery Sectional Committee, TXD 10

<i>Organization</i>	<i>Representative(s)</i>
The South India Textile Research Association, Coimbatore	DR PRAKASH VASUDEVAN (<i>Chairperson</i>)
Apparel Export Promotion Council, Gurugram	SHRI K. S. BISHT
Central Reserve Police Force, New Delhi	SHRI SANJEEV KUMAR SINGH SHRI RANDHIR KUMAR JHA (<i>Alternate</i>)
Defence Materials and Stores Research and Development Establishment, Kanpur	SHRI ASHOK KUMAR YADAV
Directorate General of Quality Assurance, Ministry of Defence, New Delhi	SHRI ARVIND KAMTHANE SHRI J. K. YADAV (<i>Alternate</i>)
DKTE Centre of Excellence in Nonwovens, Ichalkaranji	PROF UDAY J. PATIL SHRI ANIL U. USAWARE (<i>Alternate</i>)
Essa Garments Private Limited, Tiruppur	SHRI DURGA I 
JKR Garments, Tiruppur	SHRI JAILANI
Knitwear & Apparel Manufacturers Association, Ludhiana	SHRI SUDARSHAN KUMAR JAIN SHRI ARUN AGGARWAL (<i>Alternate</i>)
National Institute of Fashion Technology, New Delhi	PROF ASHOK PRASAD PROF AMRITA ROY (<i>Alternate</i>)
NIFT-TEA College of Knitwear Fashion, Tiruppur	DR K. P. BALAKRISHNAN DR P. P. BALAKRISHNAN (<i>Alternate</i>)
Office of Development Commissioner (SSI), New Delhi	SHRI KULDEEP SINGH SHRI S. SURESH BABUJI (<i>Alternate</i>)
Office of the Textile Commissioner, Mumbai	SHRI HUMAYUN K. SHRI SATISH KUMAR N (<i>Alternate</i>)
SGS India Private Limited, Mumbai	DR KARTHIKEYAN K. SHRI MICHEL FRANCIS (<i>Alternate</i>)
South Indian Hosiery Manufactures Association, Tiruppur	SHRI M. TYAGRAJAN SHRI R. BALASARAVANAN (<i>Alternate</i>)
Textiles Committee, Mumbai	SHRI R. CHANDRAN SHRI J. PARAMESWARAN (<i>Alternate</i>)
The Southern India Mills Association, Coimbatore	DR K. SELVARAJU DR SURESH ANAND KUMAR (<i>Alternate</i>)
The Synthetic and Rayon Textiles Export Promotion Council, Mumbai	SHRI ANIL RAJVANSHI SHRI BHADRESH M. DHODIA (<i>Alternate</i>)

IS 13003 : 2024

<i>Organization</i>	<i>Representative(s)</i>
Tiruppur Exporters Association, Tiruppur	SHRI T. R. VIJAYKUMAR
Veermata Jijabai Technological Institute, Mumbai	SHRI S. P. BORKAR DR ARVIND BHONGADE (<i>Alternate</i>)
Wool Research Association, Thane	DR MRINAL CHOUDHARI SHRI MAYUR BASUK (<i>Alternate</i>)
BIS Directorate General	SHRI J. K. GUPTA, SCIENTIST 'E'/DIRECTOR AND HEAD (TEXTILES) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)]

Member Secretary
SHRI TANISHQ AWASTHI
SCIENTIST 'B'/ASISTANT DIRECTOR
(TEXTILES), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 10 (20558).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : 5 th Floor/MTNL CETTM Technology Street, Hiranandani Gardens, Powai, Mumbai - 400076	{ 25700030 25702715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.