
कच्चे नारियल के रेशों की पिथ ब्लाक —
विशिष्टि

Coir Pith Block — Specification

ICS 65.020.20

© BIS 2024



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110002
www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard was adopted by the Bureau of Indian Standards after the draft finalized by the Coir and Coir Products Sectional Committee had been approved by the Textile Division Council.

Coir pith, which is also known as coir dust is the main byproduct from coir fibre extraction industries in double the quantity of coir fibre during extraction of fibre from coconut husk. Coir pith blocks of different electrical conductivity (EC) and with varying packaging dimensions and weight needs to be standardized and certified for its reliable use in agriculture/horticulture applications. The composition and properties of coir pith vary depending on maturity of coconut, method of fibre extraction and processing including environmental factors. Coir pith is a recalcitrant agro-residue containing high amount of lignin and cellulose resisting decomposition by microorganisms under natural conditions. Coir pith has high water holding capacity of six to eight times of its weight. Nutrient content of coir pith varies with the location, method of extraction, rate of decomposition and storage conditions. Sunlight, air, water and nutrients are the basic requirements for healthy plant growth. However, a good plant growth medium is a vital link essential for the proper utilization of nutrients and water. Coir pith is converted in to the form of blocks for its easy transportation and storage which can be used in agri/flori/horticulture.

The composition of the Committee responsible for the formulation of this standard is given in [Annex G](#).

For the purpose of deciding whether a particular requirement of this standard is complied with the final value, observed or calculated, expressing the result of a test or analysis shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

COIR PITH BLOCK — SPECIFICATION

1 SCOPE

This standard prescribes the various requirements of widely and commonly used coir pith blocks made from dried and sieved coir pith extracted from coconut husk by mechanical means.

2 REFERENCES

The standards given below contain provisions which through reference in this text, constitute provision of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of these standards:

| <i>IS No.</i> | <i>Title</i> |
|------------------------|---|
| IS 460 (Part 1) : 2020 | Test sieves — Specification: Part 1 Wire cloth test sieves (<i>fourth revision</i>) |
| IS 6359 : 2023 | Method for conditioning of textiles (<i>first revision</i>) |
| IS 15651 : 2006 | Textiles — Requirements for environmental labelling — Specification |
| IS 17739 : 2024 | Raw coir pith — Specification |

3 TERMINOLOGY

For the purpose of this standard, the following definitions shall apply.

3.1 Coir Pith — The coir pith is light weight, elastic, granular material having uniform, cylindrically opened cells, with foam like structure. Due to its porosity, it also gives buoyancy to the coconut fruit during its transport in water while falling from the tree. The coir fibre is embedded in the matrix of coir pith and during the extraction of coir fibres nearly the double the quantity of coir pith is obtained. Besides being rich in lignin, the coir pith has high water holding capacity up to 800 percent.

3.1.1 Coir pith is lignocellulosic in nature, brown colored, lightweight corky dust, particle size varies from 100 microns to 300 microns with porous structure. The pores are responsible for allowing good aeration around the roots of plants and retain water content in the pores for rewetting when dry.

Coir pith has readily available nutrients like nitrogen, phosphorus and potassium suitable for plant growth. The organic matter content of soil/substrate is an indicator to its fertility and nutrient availability and coir pith has a higher organic matter content as compared to peat moss.

3.1.2 Coir pith containing three major constituents like cellulose, hemicellulose and lignin.

3.2 Coir Pith Blocks — The Coir pith block is the material in which the loose coir pith particles were converted into blocks of different dimensions and weight. The conversion of coir pith into coir pith blocks have been accomplished by mechanical means using hydraulic pressure by suitable machinery.

3.3 Electrical Conductivity (EC) — Electrical conductivity of a material is the ability to allow the transport of an electric charge and expressed in dS/m.

4 GRADES

4.1 The coir pith blocks shall be graded on the basis of electric conductivity as given in [Table 1](#) and the test of electric conductivity is to be carried as per the method prescribed in [Annex A](#).

Table 1 Grading of Coir Pith

(*Clauses 4.1 and F-2*)

| SI No. | Grade | EC, dS/m |
|--------|----------------------|------------|
| (1) | (2) | (3) |
| i) | Grade I (Low EC) | < 0.5 |
| ii) | Grade II (Medium EC) | 0.5 to 0.8 |
| iii) | Grade III (High EC) | > 0.8 |

5 MANUFACTURE, WORKMANSHIP AND FINISH

5.1 Coir pith, which is also known as coir dust is the main byproduct from coir extraction industries. In the husk, coconut fibres are seen tightly packed along with non-fibrous, fluffy and light weight corky material known as coir pith or coir dust, which constitutes about 50 percent to 70 percent of the husk. In the process of extraction of coir fiber from husk generally about one third of it is obtained as fiber and two third of it is obtained as coir pith. After

To access Indian Standards click on the link below:

https://www.services.bis.gov.in/php/BIS_2.0/bisconnect/knownyourstandards/Indian_standards/isdetails/

the coir fibre is extracted from the husk the pith can be collected and processed to enter the supply chain for the production of agri/horticultural grade material. The process for the production of coir pith block for agri/horticultural grade material follows a number of steps depending on the requirement as agreed between the buyer and the seller.

5.2 Washing and Buffering of Coir Pith (Optional)

The Coir pith is washed with water to further reduce the salt content. Washing is important to remove the additional salt content that cause high electrical conductivity of the media. Washing removes all the water-soluble elements such as sodium and potassium and thereby reduces the electrical conductivity. Due to the strength of some of the bonds made between the ions and the media, washing cannot eliminate all of the salt which may present in the coir pith. For which buffering may be done if agreed between the buyer and the seller. The pith can be buffered using the same process as washing by mixing a solutions of calcium nitrate and or magnesium nitrate as required, followed by a further washing step. Buffering balances the naturally occurring sodium and potassium in coir pith and prevents the unwanted lock out of calcium and magnesium and avoids sodium toxicity issue. Sodium, magnesium, potassium and calcium will all be absorbed at different rates even if they were all introduced into a solution at the same concentrations. Calcium and magnesium are absorbed at double the rate due to them having a double-positive charge while potassium and sodium have a single-positive charge (Ca^{2+} , Mg^{2+} , K^+ , Na^+). Buffering products that have high levels of calcium and magnesium have a slower buffering rate but they help to effectively create a lower potassium and sodium percentage on the exchange and offer beneficial magnesium to the cation exchange capacity (CEC).

5.3 Coir Pith Blocks

5.3.1 The washed coir pith is then dried and subjected to sieving/mixing process. The resultant pith is fed into the compacting machine in which the pith is converted into blocks of different weight such as 650 g, 5 000 g. Coir pith has a unique ability to withstand high compaction force without leaving its beneficial structure. Then the blocks are packed and then dispatched to sales.

5.3.2 When wrapped, it is highly compressed but can be expanded by sprinkling water. Hydrate the blocks slowly by using required amount of water and allow the moisture to be fully absorbed. And the material is ready to use it to improve the potting soils or use as a 100 percent soil-less growing medium. It is a perfect growing media for flower and vegetables cultivation as well for soil conditioning.

6 REQUIREMENTS

6.1 Texture

The material shall be clean and free from adulterants such as sand, metallic pieces, weeds and seeds.

6.2 Colour and Odour

The colour of the coir pith shall be golden brown and have no foul odour.

6.3 Dimensions and Weight

The coir pith blocks may be supplied in fabricated shapes such as square or rectangular forms or as agreed between the buyer and seller.

6.3.1 The dimensions of the pith block can be measured using a steel rule nearest to 1 mm shall be as agreed between the buyer and the seller.

6.3.2 The weight of the coir pith block when measured using an electronic balance to the nearest 0.1 g subject to the tolerance given below in [Table 2](#) for coir pith blocks of weight 650 g and 5 kg. Any other suitable weight as per the agreement between buyer and seller shall be manufactured.

Table 2 Tolerance for Weight of Coir Pith Blocks

([Clause 6.3.2](#))

| SI No. | Particulars | 650 g Block | 5 000 g Block |
|--------|-------------------|-------------|---------------|
| (1) | (2) | (3) | (4) |
| i) | Weight tolerance, | ± 20 | ± 100 |
| | g | | |

6.4 The coir pith blocks shall comply with the requirements given in [Table 3](#) when tested according to the methods prescribed in col (5) of [Table 3](#).

Table 3 Requirements of Coir Pith Block*(Clauses 6.4 and 10.2)*

| SI No. | Characteristic | Requirements for Coir Pith Block of 650 g | Requirements for Coir Pith Block of 5 000 g | Method of Test, Ref to |
|--------|---|---|---|-------------------------|
| (1) | (2) | (3) | (4) | (5) |
| i) | pH | 5.0 to 7.0 | 5.0 to 7.0 | Annex B |
| ii) | Moisture, percent, <i>Max</i> | 20.0 | 20.0 | Annex C |
| iii) | Sand content, percent, <i>Max</i> | 2.0 | 2.0 | Annex D |
| iv) | Hydration volume/ expansion volume on hydration, l/kg, <i>Min</i> | 10.0 | 15.0 | Annex E |
| v) | Particle size less than 1 mm, percent, <i>Max</i> | 20.0 | 35.0 | Annex F |
| vi) | Fibre content, percent, <i>Max</i> | 3.0 | 3.0 | Annex F |

6.5 If agreed between the buyer and seller, the requirements for nitrogen percent, phosphorus percent, potassium percent, ppm of copper, organic carbon percent, lignin, carbon-nitrogen ratio, total organic matter, ash content, Water holding capacity, porosity percent, sand content percent of the coir pith block shall conform as per IS 17739.

7 ADDITIONAL REQUIREMENTS FOR ECO-MARK (OPTIONAL)

7.1 The product shall meet the requirement specified in this Indian Standard.

7.2 The manufacturer shall produce the consent clearance as per the provisions of *Water Prevention and Control of Pollution Act, 1974* and *Air Prevention and Control of Pollution Act, 1981* and authorizations, if required under the rules notified under the (*Environment Protection Act*), 1986 and rules made there under as per *Bureau of Indian Standards Act, 2016* while applying for the Eco-Mark.

7.3 The product(s) or product packaging(s) may display in brief the criteria based on which the product has been labeled environment friendly.

7.4 The material used for product packaging(s) shall be recyclable, reusable or biodegradable.

7.5 The product shall meet the specific requirements as given in [Table 4](#).

Table 4 Specific Requirements for Eco-Mark*(Clause 7.5)*

| SI No. | Parameter | Requirement | Method of Test, Ref to |
|--------|---|-------------|-------------------------|
| (1) | (2) | (3) | (4) |
| i) | Residual pesticides (sum parameter) ppm, <i>Max</i> | 1.0 | IS 15651 |
| ii) | pH of aqueous extract | 6 to 7 | Annex B |

8 PACKING

The material shall be packed as agreed to between the buyer and the seller.

9 MARKING

Each bag shall be marked indicating clearly with the following information attached to it:

- Name and type of the material;
- Name of the manufacturer;
- Grade;
- Gross and net weight in kg;
- Shape;
- Date of packing;
- Criteria for which coir pith has been labeled as ECO-Mark (optional); and

- h) Any other information as required by the buyer or by the law in force.

9.1 BIS Certification Marking

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act, 2016* and the Rules and Regulations framed thereunder, and the products may be marked with the Standard Mark.

10 SAMPLING AND CRITERIA FOR CONFORMITY

10.1 Sampling

10.1.1 Lot

Quantity of coir pith block manufactured under similar conditions and delivered to a buyer against one dispatch note shall constitute a lot.

10.1.2 The conformity of a lot to the requirements of the standard shall be determined on the basis of the tests carried out on the samples selected from it.

10.1.3 Unless otherwise agreed to between the buyer and the seller, the number of coir pith block samples to be selected from the lot shall be in accordance with [Table 5](#).

Table 5 Size of Gross Sample and Number of Test Specimen for Each Test

(Clause 10.1.3)

| SI No. | Lot Size (N) | No. of Sample (n) |
|--------|----------------------|----------------------|
| (1) | (2) | (3) |
| i) | Up to 1 000 kg | 2 |
| ii) | 1 000 kg to 5 000 kg | 3 |
| iii) | 5 000 kg and above | 5 |

The samples shall be selected at random where N is the lot size and ‘n’ is the number of samples drawn.

10.2 CRITERIA FOR CONFORMITY

The lot shall be considered conforming to the requirements of this standard if the following conditions are satisfied:

- a) Texture, color and odour, dimensions and weight shall satisfy the requirements as specified in [6.1](#), [6.2](#) and [6.3](#); and
- b) The observed values for all required parameters shall be in accordance with the applicable value of the relevant grade as specified in [Table 3](#).

ANNEX A

(Clause 4.1)

METHOD FOR DETERMINATION OF ELECTRICAL CONDUCTIVITY (E.C)

A-1 APPARATUS AND REAGENTS

estimation of EC.

A-1.1 Conductivity Meter

Fitted with a conductivity cell, equipped with an adjustable measuring range setting and (automatic) temperature correction and having an accuracy of 1 mS/m at 25 °C. Preferably, the conductivity meter should also be equipped with a cell-constant control.

A-3 CALIBRATION OF CONDUCTIVITY METER

Calibrate the conductivity meter using standard buffer solutions (see [B-1.3](#)) as per the manufacturer's instructions.

A-1.2 Analytical Balance**A-4 PROCEDURE****A-1.3 Potassium Chloride (0.1 mol/l)**

Dissolve 0.745 6 g of potassium chloride (dried for 24 h at 220 °C ± 10 °C) in 100 ml water. The specific electrical conductivity of this solution should be 12.8 mS/cm.

A-4.1 Weigh 10g air-dried finely crushed coir pith material and transfer into 500 ml beaker. Add 200 ml of water at (27 ± 2) °C. Mix the test sample thoroughly to ensure that it is homogeneous. Let the coir pith soak for 6 h, with occasional stirring.

A-2 SAMPLE PREPARATION

Crush the coir pith block to remove all the lumps. Take a portion of the crushed coir pith block for the

A-4.2 Read on Conductivity Meter**A-5 EXPRESSION OF RESULTS**

Calculate the mean of the three readings that agreed and round to the nearest 1 dS/m of unit.

ANNEX B

[\[Table 3, Sl No. \(i\) and Table 4, Sl No. \(ii\)\]](#)

METHOD FOR DETERMINATION OF pH VALUE

B-1 APPARATUS AND REAGENTS

Take a portion of the crushed coir pith block for the estimation of pH.

B-1.1 pH Meter

Potentiometer equipped with a glass-calomel electrode system. Follow the manufacturer's instructions for the pH meter used.

B-4 PROCEDURE**B-1.2 Analytical Balance**

B-4.1 Weigh 10 g air-dried finely crushed coir pith block or equivalent moist material into 500 ml beaker. Add 200 ml of water, so as to maintain a material to water ratio of 1 : 20. Mix the test sample thoroughly to ensure that it is homogeneous. Let soak for 60 min, with occasional stirring.

B-1.3 Carbon dioxide-free water distilled water. Use water with a pH of not less than 6.5 nor more than 7.5 obtained by boiling distilled water 15 min and cooling under CO₂ free conditions.

B-4.2 Read on pH meter.

B-1.4 Standard Buffer Solution — pH of 4, 7 and 10

B-5 EXPRESSION OF RESULTS**B-2 CALIBRATION OF pH METER**

Calibrate the pH meter using standard buffer solutions as per the manufacturer's instructions.

B-5.1 Calculate the mean of the three readings that agreed and round to the nearest 0.1 of a pH unit.

B-3 SAMPLE PREPAATION

Crush the coir pith block to remove all the lumps.

B-5.2 Otherwise, also specify the temperature at which the test is carried out.

ANNEX C

[Table 3, Sl No. (ii)]

METHOD FOR DETERMINATION OF MOISTURE CONTENT

C-1 APPARATUS

C-1.1 Conditioning oven with forced ventilation, provided with positive valve control and capable of maintaining a temperature of 100 °C to 110 °C.

C-2 PROCEDURE

C-2.1 Remove about 50 g of coir pith from the test sample (see [10.1.3](#)) and weigh it correct to the nearest 0.5 g. Place the test specimen in the conditioning oven and dry for one hour and weigh to the nearest 0.5 g. Dry for another 30 min and weigh to the nearest 0.5 g. Provided the loss in mass in drying of the test specimen, as disclosed by the first and second weighing's, does not exceed 0.25 percent of the first mass, take the second mass to be the dry mass of the test specimen. If the loss

exceeds 0.25 percent, weigh the test specimen at 30 min intervals till the loss between two successive weighing is 0.25 percent or less.

C-2.2 Calculate the percentage of moisture content by the following:

$$\text{Moisture content, percent by mass} = \frac{m_1 - m_2}{m_1} \times 100$$

where,

m_1 = mass, in g, of the original test specimen;
and

m_2 = mass, in g, of the oven-dried test specimen.

ANNEX D

[Table 3, Sl No. (iii)]

METHOD FOR DETERMINATION OF SAND CONTENT

D-1 TEST SPECIMENS

For the purpose of this test, test specimens each weighing about 50 g shall be drawn from the test sample as given in [10.1.3](#).

D-2 CONDITIONING OF THE SPECIMENS

Prior to evaluation, the test specimens shall be conditioned in standard atmosphere at 65 percent \pm 2 percent relative humidity and (27 \pm 2) °C temperature (see also IS 6359) for 48 h.

D-3 PROCEDURE

D-3.1 Immediately after conditioning (see [D-2](#)), weigh one test specimen to the nearest 0.5 g. Burn it in an iron pan (see Note) to ash. Put the ash in water and allow the sand to settle. Separate the

sand, condition it and weigh it

NOTE — Kerosine oil may be used to quicken the process of burning.

D-3.2 Calculate the sand content by the following formula:

$$\text{Sand content, percent} = \frac{W_2}{W_1} \times 100$$

where

W_2 = weight, in g, of sand; and

W_1 = weight, in g, of conditioned test specimen.

D-3.3 Determine similarly the sand content, percent, of the remaining test specimens.

D-3.4 Calculate the average and range of all the observations (see [D-3.2](#) and [D-3.3](#)).

ANNEX E

[Table 3, Sl No. (iv)]

DETERMINATION OF HYDRATION/EXPANSION VOLUME

E-1 TEST SPECIMENS

For the purpose of this test, test specimens each

weighing about 100 g shall be drawn from the test sample as given in [10.1.3](#).

E-2 CONDITIONING OF THE SPECIMENS

Prior to evaluation, the test specimens shall be conditioned in standard atmosphere at 65 percent \pm 2 percent relative humidity and (27 ± 2) °C temperature for 48 h.

E-3 PROCEDURE

Immediately after conditioning (*see* [E-2](#)), break and

crush the block by hand into dust particles. Remove the fibre by rubbing between the palms. Weigh one test specimen to the nearest 0.5 g and add to a large tub. To the dust slowly mix water until completely expand all the coir pith particles. Measure the volume of the loose expanded fluffy coir pith without compacting on a litre by litre basis. The number of litres multiplied by 10 gives the expansion or hydration volume corresponds to 1 kg of coir pith.

ANNEX F

[[Table 3](#), [Sl No. \(v\)](#) and [Sl No. \(vi\)](#)]

DETERMINATION OF PARTICLE SIZE LESS THAN 1 MM AND FIBRE CONTENT

F-1 APPARATUS

F-1.1 Balance — sensitive to 0.1 percent of the mass of sample to be weighed

F-1.2 Sieves

The following Indian Standard Sieves conforming to IS 460 (Part 1) 4.75 mm, 2.36 mm, 2 mm, 1.00 mm, 600 microns, 425 microns, 300 microns, 150 microns and 75 microns. Sieves should be periodically checked up for aperture sizes.

F-1.3 Receiving Pan — with cover

F-1.4 Brushes

Sieve brushes and a wire brush or similar stiff brush.

F-1.5 Mechanical Sieve Shaker

F-2 PROCEDURE

Clean the sieves of sieve shaker using cleaning brush if any particles are struck in the openings. Record the weight of each sieve and receiving pan. Weigh approximately 100 g (W) of representative dry sample. Assemble the sieves in an order such that each lower sieve has smaller openings than the one above. Carefully pour the coir pith sample into the top sieve and place the cap over it. Place the sieve stack in the mechanical shaker and shake for 10 min in a mechanical sieve shaker. Remove the stack from the shaker and carefully weigh and record the weight of each sieve with its retained sample. In addition, remember to weigh and record the weight of the bottom pan with its retained sample. Obtain the

mass of sample retained on each sieve by subtracting the weight of the empty sieve from the mass of the sieve+ retained sample, and record this mass as the weight retained on the data sheet shown in [Table 1](#). The sum of these retained masses should be approximately equals the initial mass of the coir pith sample. A loss of more than two percent is unsatisfactory.

F-3 CALCULATION

F-3.1 Determination of particle size less than 1 mm. Calculate the percent retained on each sieve by dividing the weight retained on each sieve by the original sample mass and insert in [Table 6](#). Calculate the cumulative percentage retained (X) on each sieve by adding the percentage of sample retained on that sieve and all the sieves above it. Calculate the percent passing (or percent finer) by starting with 100 percent and subtracting the cumulative percent retained on each sieve. Make a semi logarithmic plot of particle size vs percent finer. The percentage finer corresponding to 1 mm particle size is then determined.

Particle size less than 1 mm = Percentage finer corresponding to 1 mm

F-3.2 Determination of Fibre Content

Separate the fibres from the sample retained on each sieve and total weight of the fibres were determined correct to the nearest 0.5 g.

Fibre content, percent =

$$\frac{\text{Total weight of the fibre retained in the sieves}}{\text{Weight of sample taken for test}} \times 100$$

Table 6 Data Sheet for Calculation

(Clause F-3.1)

| Sl No. | Sieve Size, (mm) | Weight of Sieve, M1, (g) | Weight of Sieve + Retained Sample (M2), g | Weight of Sample Retained (M2 - M1), g | Retained, Percent $\frac{M2 - M1}{w} \times 100$ | Cumulative Percent Retained (X) | Cumulative Percent Passing or Percent Finer (100 - X) |
|--------|---------------------|-----------------------------|--|--|---|---------------------------------|---|
| (1) | (2) | (3) | (4) | (5) | (6) | (7) | (8) |
| i) | 4.75 | | | | | | |
| ii) | 2.36 | | | | | | |
| iii) | 2.00 | | | | | | |
| iv) | 1.00 | | | | | | |
| v) | 0.600 | | | | | | |
| vi) | 0.425 | | | | | | |
| vii) | 0.300 | | | | | | |
| viii) | 0.150 | | | | | | |
| ix) | 0.075 | | | | | | |
| x) | Pan | | | | | | |

ANNEX G

(Foreword)

COMMITTEE COMPOSITION

Coir and Coir Products Sectional Committee, TXD 25

| <i>Organization</i> | <i>Representative(s)</i> |
|---|---|
| Coir Board, Kochi | SHRI J. K. SHUKLA (<i>Chairperson</i>) |
| All India Rubberized Coir Products Manufacturers Association, New Delhi | MS JYOTHI PRADHAN SHRI MATHEW GEORGE (<i>Alternate</i>) |
| Central Coir Research Institute, Kochi | DIRECTOR, RDTE SENIOR SCIENTIFIC OFFICER (<i>Alternate</i>) |
| Central Institute of Coir Technology, Bengaluru | JOINT DIRECTOR (TECH) SENIOR SCIENTIFIC OFFICER (<i>Alternate</i>) |
| Charankattu Coir Manufacturing Corporation Private Limited, Shertallay | SHRI C. R. DEVARAJ SHRI C. D. ATHUL RAJ (<i>Alternate</i>) |
| Coimbatore District Coir Mnaufacturer's Association, Coimbatore | SHRI P. SUDHAKAR SHRI N. ANBURAJ (<i>Alternate</i>) |
| Coir and Coir Mattings Association, New Delhi | SHRI V. A. JOSEPH |
| Coir Board, Kochi | DIRECTOR MARKETING JOINT DIRECTOR (<i>Alternate</i>) |
| Coir on Foam Products, Noida | SHRI PHILIP VARGHESE SHRI HARIRAJ (<i>Alternate</i>) |
| Coir Pith and Allied Products Manufacturers and Exporters Association, Coimbatore | SHRI MAHESH |
| Coir Shippers Council, Cherthala | SHRI K. J. JOSEPH SHRI SAJAN B. NAIR (<i>Alternate</i>) |
| Federation of Indian Coir Exporters Associations, Alappuzha | SHRI JOHN CHACKO |
| Hindustan Coir, Coir Board, Kochi | WEAVING MASTER |
| ICAR - Indian Institute of Horticultural Research, Bengaluru | DR G. SELVAKUMAR DR D. KALAIVANAN (<i>Alternate</i>) |
| Indian Institute of Technology, Chennai | PROF K. RAJGOPAL |
| Indian Plywood Industries Research and Training Institute, Bengaluru | DR SUJATHA D. |
| Karnataka State Coir Development Corporation Limited, Bengaluru | SHRI VENKATESH |
| Kerala State Coir Corporation Limited, Alappuzha | SHRI G. SREEKUMAR SHRI N. SUNURAJ (<i>Alternate</i>) |
| Kerala State Coir Marketing Federation Limited, Thiruvananthapuram | SHRI SURESH KUMAR |

| <i>Organization</i> | <i>Representative(s)</i> |
|---|--|
| Kurlon Enterprise Limited, Bengaluru | SHRI V. RAVI PRASAD SHRI P. ANIL (<i>Alternate</i>) |
| National Coir Research and Management Institute (NCRMI), Thiruvananthapuram | DIRECTOR, NCRMI SHRI RINU PREMRAJ (<i>Alternate</i>) |
| National Coir Training and Design Centre, Alappuzha | ASSISTANT DIRECTOR |
| Natura Green Tech (P) Ltd, Bengaluru | SHRI TOMMY MATHEW SHRI ABHISHEK THOMAS (<i>Alternate</i>) |
| Rubber Research Institute of India, Rubber Board, Kottayam | DR SHERA MATHEW DR SIBY VARGHESE (<i>Alternate</i>) |
| SFURTI (Coir Cluster), Kochi | SHRI SHIJU NESAMONY SHRI NAGARAJAN (<i>Alternate</i>) |
| Travancore Cocotuft Private Limited, Cherthala | SHRI P. MAHADEVAN |
| BIS Directorate General | SHRI J. K. GUPTA, SCIENTIST 'E'/DIRECTOR AND HEAD (TEXTILES) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)] |

Member Secretary
SHRI TANISHQ AWASTHI
SCIENTIST 'B'/ASSISTANT DIRECTOR
(TEXTILES), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website-www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: TXD 25 (20685).

Amendments Issued Since Publication

| Amend No. | Date of Issue | Text Affected |
|-----------|---------------|---------------|
| | | |
| | | |
| | | |
| | | |

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

Central : 601/A, Konnectus Tower -1, 6th Floor,
DMRC Building, Bhavbhuti Marg, New
Delhi 110002

Telephones

{ 2323 7617

Eastern : 8th Floor, Plot No 7/7 & 7/8, CP Block, Sector V,
Salt Lake, Kolkata, West Bengal 700091

{ 2367 0012
{ 2320 9474

Northern : Plot No. 4-A, Sector 27-B, Madhya Marg,
Chandigarh 160019

{ 265 9930

Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113

{ 2254 1442
{ 2254 1216

Western : 5th Floor/MTNL CETTM, Technology Street, Hiranandani Gardens,
Powai, Mumbai 400076

{ 2570 0030
{ 2570 2715

Branches : AHMEDABAD, BENGALURU, BHOPAL, BHUBANESHWAR, CHANDIGARH, CHENNAI, COIMBATORE, DEHRADUN, DELHI, FARIDABAD, GHAZIABAD, GUWAHATI, HARYANA (CHANDIGARH), HUBLI, HYDERABAD, JAIPUR, JAMMU, JAMSHEDPUR, KOCHI, KOLKATA, LUCKNOW, MADURAI, MUMBAI, NAGPUR, NOIDA, PARWANOO, PATNA, PUNE, RAIPUR, RAJKOT, SURAT, VIJAYAWADA.