

(PREVIEW)

*Indian Standard***GRADING GLASS FOR ALKALINITY****PART 2 HYDROLYTIC RESISTANCE OF GLASS CONTAINERS****1 SCOPE**

This Indian Standard specifies methods for determining the hydrolytic resistance of the interior surfaces of glass containers when subjected to attack by water at  $121^{\circ}\text{C} \pm 1^{\circ}\text{C}$  for  $60 \text{ min} \pm 1 \text{ min}$ .

**2 REFERENCES**

The following Indian Standards are necessary adjuncts to this standard:

<i>IS No.</i>	<i>Title</i>
1070 : 1992	Reagent grade water ( <i>third revision</i> )
1117 : 1975	One-mark pipettes ( <i>first revision</i> ) (Reaffirmed July 1991)
1997 : 1982	Burettes ( <i>second revision</i> ) (Reaffirmed Nov 1993)
1382 : 1981	Glossary of terms relating to glass and glassware ( <i>first revision</i> ) (Reaffirmed June 1992)
6654 : 1992	Glossary of terms relating to glass containers ( <i>second revision</i> )