

**BUREAU OF INDIAN STANDARDS**

**DRAFT FOR COMMENTS ONLY**

*(Not to be reproduced without the permission of BIS or used as an Indian Standard)*

भारतीय मानक  
पोटेंशियोमेट्रिक पद्धति द्वारा कठोर धातुओं में कोबाल्ट का निर्धारण  
(आई एस 12513 का पहला पुनरीक्षण)

***Indian Standard***  
**DETERMINATION OF COBALT IN HARDMETALS**  
**BY POTENTIOMETRIC METHOD**  
*( First Revision of IS 12513 )*

ICS 77.160

---

Powder Metallurgical Materials and Products  
Sectional Committee, MTD 25

Last date for receipt of comment:  
10 Aug 2024

---

Foreword

*(Formal clause may added later)*

This standard was first published in 1988. This revision has been brought out to bring the standard in the latest style and format of the Indian Standards.

In the preparation of this standard, assistance has been derived from ISO 3909 : 1978 'Hardmetals - Determination of Cobalt - Potentiometric method'.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be same as that of the specified value in this standard.

*Indian Standard*

**DETERMINATION OF COBALT IN HARDMETALS BY POTENTIOMETRIC —  
METHOD**

*(First Revision of IS 12513)*

**1 SCOPE**

**1.1** This standard covers a potentiometric method for the determination of cobalt content in hardmetals.

**1.2** This method is applicable to the following, having cobalt content exceeding 1 *percent* (m/m):

- a) Carbides and binder metal powder mixtures free of lubricant; and
- b) All grades of pre sintered or sintered hardmetals.

**2 PRINCIPLE**

Oxidation of cobalt to the trivalent state in a strongly ammoniacal solution with an excess of potassium ferricyanide  $K_3[Fe(CN)_6]$ . Potentiometric back titration of the excess with cobalt sulphate solution.

**3 INTERFERING ELEMENTS**

**3.1** The effect of interfering elements, for example, vanadium and manganese, shall be taken into account. Vanadium and manganese are also oxidized by potassium ferricyanide. Vanadium reacts stoichiometrically and a correction can be applied if the vanadium content is below 0.5 *percent* (m/m).

**3.2** Manganese reacts almost stoichiometrically up to 0.2 *percent* (m/m) only if the sum of tantalum and niobium in the hardmetal is less than 0.02 *percent* (m/m). Above this level, the method is applicable only if the manganese content is less than 0.03 *percent* (m/m).

**4 REAGENTS**

During the analysis, use only reagents of analytical grade and distilled water or water of equivalent purity.

**4.1 Ammonium Sulphate**

**4.2 Concentrated Hydrochloric Acid** ( $\rho = 1.19$  g/ml )

**4.3 Hydrofluoric Acid** ( $\rho = 1.12$  g/ml )

**4.4 Concentrated Nitric Acid** ( $\rho = 1.42$  g/ml )

**4.5 Concentrated Sulphuric Acid** ( $\rho = 1.84$  g/ml )

**4.6 Ammonia Solution** ( $\rho = 0.91$  g/ml )

**4.7 Ammonium Citrate Solution**

Dissolve 100 g citric acid in 900 ml of water and add 100 ml of ammonia solution.

#### 4.8 Standard Cobalt Solution ( 1 litre = 1 g of cobalt )

Prepare the solution from compact metallic cobalt, or from diammonium cobalt sulphate or from cobalt sulphate. If necessary, establish the title gravimetrically with 1 nitroso-naphthol2, or electrolytically.

NOTE — ( 1 litre = 1 g of cobalt ) depicts that, the solution is a standard cobalt solution.

#### 4.9 Standard Potassium Ferricyanide Solution ( 1 litre = 3 g of cobalt )

Dissolve 17 g of potassium ferricyanide in one litre of water. Determine the relationship between the volume of standard cobalt sulphate solution and potassium ferricyanide solution in the following way.

4.9.1 Transfer into a 400 ml beaker, 5 g ammonium sulphate, 40 ml ammonium citrate solution, 50 to 100 ml water, 80 ml ammonia solution and from a burette, approximately 9 ml potassium ferricyanide solution. Volume used :  $V_3$  ml.

Immediately titrate with standard cobalt sulphate solution. Volume used:  $V_4$  ml.

4.9.2 Calculate the relationship according to the formula:

$$K = \frac{V_4}{V_3}$$

4.10 Methyl Red Indicator Solution ( 1 g/litre ), or indicator paper for pH 3 to 5.

### 5 APPARATUS

#### 5.1 Ordinary Laboratory Apparatus

5.2 Potentiometric Titration Apparatus - With stirrer or some other arrangement for agitation.

#### 5.2 Platinum Electrode

#### 5.3 Tungsten Wire or any other Reference Electrode

5.4 Burettes - Capacity 10 ml.

### 6 SAMPLING

6.1 The sample shall be crushed to a powder in a mortar made of a material which does not alter the sample composition. The powder shall pass through a 180  $\mu$ m sieve.

NOTE - For sintered hardmetals, the preparation of sample may be as agreed to between the purchaser and the manufacturer.

6.2 The analysis shall be carried out on at least two test portions.

### 7 Procedure

7.1 Weigh ( to the nearest 0.000 1 g ) 0.1 g to 0.5 g of the test sample, depending on the cobalt content.

7.2 Transfer the test portion into a 400 ml beaker, add 10 ml to 15 ml concentrated sulphuric acid, 3 ml concentrated hydrochloric acid and 5 g ammonium sulphate. Cover the beaker with

a watch-glass and heat until complete dissolution is achieved. Cool. Add, in small portions, 40 ml to 60 ml ammonium citrate solution. Rinse the watch-glass and the beaker walls with 20 ml to 60 ml of water. Heat the solution gently until all salts are dissolved. Cool.

**7.2.1** The following alternative method for dissolution may be used:

Transfer the test portion into a 400 ml polypropylene beaker or into a platinum dish. Add 10 ml of water and 5 ml of hydrofluoric acid and cover the beaker with a polypropylene cover. Warm to approximately 60°C. Add the concentrated nitric acid, drop by drop, until dissolution is complete. Cool. Add, in small portions, 10 ml concentrated sulphuric acid and 40 ml to 50 ml ammonium citrate ( If vanadium is present, heat the solution and cool again ). Rinse the cover and the beaker walls with 20 to 50 ml of Water.

**7.3** Add 1 drop of methyl red indicator solution or use indicator paper. Carefully neutralize the solution with ammonia solution and maintain pH 3 to 5 and cool. Avoid over-neutralizing.

**7.4** Add 80 ml of ammonia solution and preferably cool to 10°C. Immediately add potassium ferricyanide solution from the burette to an excess of a few millilitres. Volume used :  $V_1$  ml. Back titrate with a standard cobalt sulphate solution. Volume used :  $V_2$  ml.

## 8 TEST RESULTS

### 8.1 Calculation

The cobalt content, expressed as a percentage by mass, is given by formula

$$\text{Cobalt content (percent by mass)} = \frac{K \times (V_1 - V_2) \times T \times 100}{m}$$

where,

$K$  = defined in 4.9.2;

$T$  = mass, in g, of cobalt in 1 ml of the cobalt sulphate solution; and

$m$  = mass, in g, of the test portion.

**NOTE** — The result shall be rounded to the nearest 0.01 percent.

### 8.2 Corrections

The following correction values may be used:

Vanadium: 0.100 percent ( $m/m$ ) vanadium is equal to 0.116 percent ( $m/m$ ) cobalt; and

Manganese: 0.100 percent ( $m/m$ ) manganese is equal to 0.107 percent ( $m/m$ ) cobalt.

### 8.3 Tolerances

The deviations between two or three independent determinations shall not exceed the values shown in the Table 1.

TABLE 1 TOLERANCES ( Clause 8.3 )			
SI No.	Cobalt Content	Range for two Determinations	Range for three determination
	<i>Percent</i>	<i>Percent</i>	<i>Percent</i>
i)	From 1 to 5	0.10	0.12

ii)	Over 5 to 8	0.15	0.18
iii)	Over 8 to 20	0.20	0.25
iv)	Over 20	0.30	0.35

#### **8.4 Final Result**

Report the arithmetical mean of acceptable determinations rounded to the nearest 0.1 *percent*.

#### **9 Test Report**

The test report shall include the following information:

- a) Reference to this Indian Standard IS 12513;
- b) All details necessary for identification of the test sample;
- c) The result obtained; and
- d) Details of any occurrence which may have affected the result.