

BUREAU OF INDIAN STANDARDS

DRAFT FOR COMMENTS ONLY

(Not to be reproduced without permission of BIS or used as an Indian Standard)

**DRAFT AMENDMENT NO. 1
TO
IS 13098: 2024
AUTOMOTIVE VEHICLES TUBES FOR PNEUMATIC TYRES — SPECIFICATION**

ICS 83.160.01

Automotive Tyres, Tubes and Rims Sectional Committee, TED 7	Last Date for Comments: 27/September/2024
---	---

**DRAFT AMENDMENT NO. 1
TO
IS 13098: 2024 AUTOMOTIVE VEHICLES TUBES FOR PNEUMATIC TYRES —
SPECIFICATION**

[Page 2, Clause 6.1 d)] — Substitute the following for the existing:

d) Word ‘BUTYL’ and/or blue line of 2.0 mm *Min* width to identify tube of Class A.

(Page 1, Clause 4.1.3)— Substitute the following for the existing:

4.1.3 Set After Ageing Dumb-bell test pieces punched out in circumferential direction of the tube when subjected to test conditions and test procedure in accordance with Annex B shall have set after aging not more than 35 percent for Class A tubes and not more than 25 percent for Class B tubes.

Set after ageing are calculated as follows:

$$\text{Set After Ageing} = \frac{L_f - L_i}{L_i}$$

where,

L_f = Final length, and
 L_i = Initial Length

(TED 07)