

भारतीय मानक ब्यूरो  
BUREAU OF INDIAN STANDARDS

*Draft for Comments Only*

**Doc: TXD 01 (25561)WC**

May 2024

(Not to be reproduced without the prior permission of BIS or used as amendment to standard)

भारतीय मानक में संशोधन का मसौदा

**IS 1969 (Part 1) : 2018 वस्त्रादि - वस्त्रों के तनन गुणधर्म - पट्टीवाली विधि का प्रयोग कर अधिकतम बल एवं अधिकतम बल पर दीर्घीकरण ज्ञात करना**

( चौथा पुनरीक्षण )

संशोधन - २

*Draft Amendment to Indian Standard*

**AMENDMENT NO. 2**

**TO**

**IS 1969 (Part 1) : 2018 TEXTILES — TENSILE PROPERTIES OF FABRICS  
PART 1 DETERMINATION OF MAXIMUM FORCE AND ELONGATION AT  
MAXIMUM FORCE USING THE STRIP METHOD**

*(Fourth Revision)*

---

Physical Methods of Test Sectional Committee

Last date of receipt of comments:

TXD 01

05 July 2024

---

*(Foreword, para 7)* — Insert the following new para after para 6:

‘This standard also permits the use of Constant rate of extension (CRE) machine with rate of extension of 200 mm/min for testing of jute fabrics including their laminates. Details of which are given in National Annex B.’

*(Page 11, National Annex A)* — Insert the following National Annex B after National Annex A:

**‘NATIONAL ANNEX B**

**(Foreword)**

For testing of jute fabrics including their laminates, the use of constant rate of extension with the rate of extension of 200 mm/min is permitted. The gauge length shall be 200 mm.’

(TXD 01)