

भारतीय मानक ब्यूरो

BUREAU OF INDIAN STANDARDS

Draft for Comments Only

Doc: TXD 01 (26561)WC

September 2024

(Not to be reproduced without the prior permission of BIS or used as amendment to standard)

भारतीय मानक में संशोधन का मसौदा

**IS 6359 : 2023 वस्त्रादि के अनुकूलन की विधि**

( पहला पुनरीक्षण )

संशोधन - १

*Draft Amendment to Indian Standard*

**AMENDMENT NO. 1**

**TO**

**IS 6359 : 2023 METHOD FOR CONDITIONING OF TEXTILES**

*(First Revision)*

---

Physical Methods of Test Sectional Committee  
TXD 01

Last date of receipt of comments  
16 November 2024

---

*(Foreword, para 5)* — Insert the following new para after para 3:

“This standard also includes the allowance for uncertainty of measurement in the overall tolerances for relative humidity. However, although the tolerances for relative humidity appear more lenient, in practice, it is advisable that the laboratory shall essentially control the relative humidity to  $(65 \pm 2)$  percent.”

*(Page 1, Clause 5.2.3)* — Substitute the following for the existing:

“Tolerance limits for temperature and relative humidity shall be  $\pm 2$  °C and  $\pm 4$  percent respectively, for conditioning of all the textile materials except the fibres whose moisture regain value is more than 8 % such as cotton, wool, silk, jute, linen and viscose fibres etc. for which the tolerance limit for relative humidity shall be  $\pm 2$  percent.

NOTE — The textile materials referred in the above clause consist of fibres, yarns, fabrics, and made-up textiles including technical textile products.

(TXD 01)