
उन्नत रसायन विज्ञान सैल के चक्र जीवन
और ऊर्जा घनत्व का मापन — परीक्षण
पद्धतियाँ

Measurement of Cycle Life and Energy
Density for Advanced Chemistry Cells —
Method of Tests

ICS 29.220.30

© BIS 2022



भारतीय मानक ब्यूरो
BUREAU OF INDIAN STANDARDS
मानक भवन, 9 बहादुर शाह ज़फर मार्ग, नई दिल्ली - 110002
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI - 110 002
www.bis.gov.in www.standardsbis.in

FOREWORD

This Indian Standard was adopted by the Bureau of Indian Standards, after the draft finalized by the Secondary Cells and Batteries Sectional Committee had been approved by the Electrotechnical Division Council.

The Advanced Chemistry Cells (ACCs) are widely used in the manufacturing of battery packs for portable applications, industrial applications, use in e-vehicles etc. These cells shall be tested to determine their safety and performance characteristics before installation in the battery packs. This standard has been developed to assess the energy density and cycle life measurements of such ACCs.

The test methods specified in this standard applies primarily to lithium-ion cells; however, the same can also be used for testing of other chemistry cells. Any additional test conditions for such chemistry cells shall be as specified by the manufacturer.

Assistance has been derived in the preparation of this standard from the following standards:

- a) IS 16047 (Part 3) : 2018 'Secondary Cells and Batteries containing Alkaline or Other Non-Acid Electrolytes — Secondary Lithium Cells and Batteries for Portable Applications: Part 3 Prismatic and Cylindrical Lithium Secondary Cells'
- b) IS 16822 : 2019 'Secondary Cells and Batteries containing Alkaline or Other Non-Acid Electrolytes — Secondary Lithium Cells and Batteries for Use in Industrial Applications'.
- c) IS 16893 (Part 1) : 2018 'Secondary Lithium-Ion Cells for the Propulsion of Electric Road Vehicles: Part 1 Performance Testing'
- d) Schedule D 'Testing Standards' of programme agreement for Implementation of National Programme on ACC Battery Storage under the Production Linked Incentive (PLI) Scheme.

The composition of the Committee, responsible for the formulation of this standard is given at Annex A.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value.

*Indian Standard*MEASUREMENT OF CYCLE LIFE AND ENERGY DENSITY FOR
ADVANCED CHEMISTRY CELLS — METHOD OF TESTS**1 SCOPE**

This standard covers the method of measurement of cycle life and energy density for Advanced Chemistry Cells (ACCs).

The test methods specified in this standard applies primarily to secondary lithium ion cells.

NOTES

1 The test methods specified in this standard can also be used for testing of other secondary cells falling under the definition of ACCs.

2 Additional test conditions for such secondary cells (that is, other than secondary lithium-ion cells), if any, shall be specified by the manufacturer.

2 REFERENCES

The standards listed below contain provisions which, through reference in this text, constitute provisions of this standard. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the

possibility of applying the most recent editions of the standards listed below:

<i>IS No.</i>	<i>Title</i>
4905 : 2015	Random Sampling and Randomization Procedures (<i>first revision</i>)

3 TERMINOLOGY

For the purpose of this standard, the following terms and definitions shall apply:

3.1 Advanced Chemistry Cells (ACCs)

— The new generation technologies cells that can store electric energy either as an electrochemical or as a chemical energy and convert it back in the form of electric energy as and when required.

The cell technologies that demonstrate the cycle life and energy density, as mentioned in Table 1, will be classified as ACCs:

3.2 Energy Density — The amount of energy stored per unit weight of a cell and measured in Wh/kg.

Table 1 Advanced Chemistry Cells (ACCs)*(Clause 3.1)*

SI No.	Cycle Life	Energy Density (Wh/kg)				
		≥ 50	≥ 125	≥ 200	≥ 275	≥ 350
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	$\geq 1\ 000$				ACC E1C1	ACC E1C2
ii)	$\geq 2\ 000$			ACC E2C1	ACC E2C2	ACC E2C3
iii)	$\geq 4\ 000$		ACC E3C1	ACC E3C2	ACC E3C3	ACC E3C4
iv)	$\geq 10\ 000$	ACC E4C1	ACC E4C2	ACC E4C3	ACC E4C4	ACC E4C5

3.3 Cycle life — The number of charge and discharge cycles that a cell is able to support at a specified Depth of Discharge (DoD) before its capacity degrades to the End of Life (EoL) condition.

3.4 State of Health (SoH) — The ratio of actual capacity of a cell and the initial rated capacity of the cell expressed as a percentage.

3.5 End-of-life capacity (EoL) — The minimum SoH of the cells, post which they cannot fulfill the application's requirements due to a significant reduction in performance.

3.6 Room temperature — The temperature of $25\text{ °C} \pm 2\text{ °C}$.

3.7 Rate of Discharge (C-Rate) — A measure of the rate at which a cell is discharged or charged relative to its maximum capacity for example 1 C rate means that the discharge current will discharge the entire cell in 1 h and in the same cell discharging at 0.5 C would mean that discharge current will discharge the entire cell in 2 h.

3.8 Depth of discharge (DoD) — The percentage of energy cycled out of the cell on a given cycle with respect to the total capacity of the cell. The DoD can also be referred to as the fraction of the cell capacity which is used in every charge and discharge cycle.

3.9 Useable/Useful Energy — The total cumulative energy discharged by a cell during the entire cycle life at the specified DoD level and EoL capacity threshold.

3.10 State of Charge (SoC) — It denotes the capacity which is currently available as a function of the rated capacity. The value of the SoC varies between 0 percent and 100 percent. If the SoC is 100 percent, then the cell is said to be fully charged,

whereas a SoC of 0 percent indicates that the cell is completely discharged.

3.11 Power Capacity — The rate at which the energy is delivered per unit time by the cell and is measured in Watts.

3.12 Rated Capacity — The capacity value of a cell determined under specified conditions and declared by the manufacturer.

4 GENERAL

4.1 Only cell samples which are less than two months (60 days) old, from the date of manufacture, shall be used for the tests specified in this standard.

NOTES

1 Generally capacity of lithium ion cells gradually decreases.

2 The manufacturer shall inform the date of manufacture of the cells.

4.2 The ambient temperature shall be the room temperature. The cells received for testing shall be stored at a temperature of $25\text{ °C} \pm 5\text{ °C}$ until taken up for testing.

4.3 Before each test, the cell temperature shall be stabilized at room temperature by soaking at a temperature of $25\text{ °C} \pm 2\text{ °C}$ for a minimum of 12 h.

NOTES

1 Thermal stabilization of a cell is considered to be reached if after an interval of 1 h, the change of cell temperature is lower than 1 °C .

2 The soaking period of 12 h may be reduced if thermal stabilization is reached.

3 The cell temperature shall be measured either at the body or at the terminals.

4.4 Rate of Discharge (C-Rate)

The rate of discharge at which the energy density and cycle life tests are to be conducted shall be under standard test condition of 0.5 C charge and 0.5 C discharge unless otherwise specified by the manufacturer.

NOTE — The rate of charge/discharge specified by the manufacturer shall not be less than 0.5 C.

4.5 Charging Procedure for Test Purposes

Prior to charging, the cell shall be discharged at $25\text{ °C} \pm 2\text{ °C}$ at a constant C-rate, as per 4.4, down to a specified final voltage as declared by the manufacturer.

The charging procedure for test purposes shall be carried out at an ambient temperature of $25\text{ °C} \pm 2\text{ °C}$, using the method declared by the manufacturer.

4.6 Mass Measurement

The mass of a cell is measured at room temperature up to three significant figures with the tolerances specified in 5.

4.7 Depth of Discharge (DoD)

The minimum DoD for testing shall be 80 percent. Testing at any other higher DoD level is permissible, if declared by the manufacturer. The cycle life and energy density tests shall be carried out at the same level of DoD.

5 PARAMETER MEASUREMENT TOLERANCES

The overall accuracy of controlled or measured values, relative to the specified or actual parameters, shall be within the tolerances given below:

- a) ± 1 percent for voltage;
- b) ± 1 percent for current;
- c) $\pm 2\text{ °C}$ for temperature;
- d) ± 0.1 percent for time; and
- e) ± 0.1 percent for mass.

NOTES

1 These tolerances take into account the combined accuracy of the measuring instruments, the measurement technique used, and all other sources of error in the test procedure.

2 The details of the instrumentation used shall be provided while reporting the test results.

6 ENERGY CAPACITY MEASUREMENT (in Wh)

The energy capacity of a cell shall be measured in accordance with the following:

Step 1 — The cell shall be charged in accordance with 4.5.

Step 2 — The cell shall be stored, in an ambient temperature of $25\text{ °C} \pm 2\text{ °C}$, for the duration specified by the manufacturer or customer.

NOTE — The cell shall be at rest period during step 2.

Step 3 — The cell shall be discharged in an ambient temperature of $25\text{ °C} \pm 2\text{ °C}$ at a constant C-rate, in accordance with 4.4, to the end-of-discharge voltage that is provided by the cell manufacturer.

NOTE — The end-of-discharge voltage provided by the cell manufacturer shall correspond to at least a DoD of 80 percent, in accordance with 4.7.

Step 4 — Measure the discharge duration until the specified end-of-discharge voltage is reached. Calculate the discharge capacity of cell expressed in Ah up to three significant figures, by multiplying the discharge current (A) with the discharge duration (h).

NOTES

1 The rated capacity shall be reached within 03 discharges subsequent to the initial charge, if not met on the first discharge. Once the rated capacity has been met on any discharge, further discharge cycles for capacity shall not be continued.

2 The cell shall be considered as fail and the test shall be terminated in case:

- a) The measured capacity is less than the rated capacity; or
- b) The measured capacity exceeds the rated capacity by more than 20 percent.

Step 5 — Average Voltage Calculation

The value of the average voltage during discharging shall be obtained by integrating the discharge voltage over time and dividing the result by the discharge duration. The average voltage is calculated using the following method:

Discharge voltages U_1, U_2, \dots, U_n are noted every 5 s from the time the discharging starts and voltages that cut off the end-of-discharge voltage in less than 5 sec are discarded. The average voltage U_{avr} is then calculated in a simplified manner using equation (1) up to three significant figures by rounding off the result.

$$U_{avr} = \frac{U_1 + U_2 + \dots + U_n}{n} \dots \dots \dots (1)$$

Step 6 — The energy capacity expressed in Wh shall be calculated using Equation (2) up to three significant figures by rounding off the result.

$$W = C_d \times U_{avr} \dots \dots \dots (2)$$

where

W = energy capacity of the cell at room temperature (Wh) when discharged underspecified conditions;

C_d = discharge capacity (Ah) as calculated in Step 4;

U_{avr} = average voltage during discharging (V) as calculated in Step 5.

7 CALCULATION OF GRAVIMETRIC ENERGY DENSITY

7.1 Mass Measurement

Mass of the cell shall be measured in accordance with 4.6.

7.2 Energy Capacity Measurement

Energy capacity of the cell shall be determined in accordance with 6 at room temperature.

The mass energy density shall be calculated using equation (3) up to three significant figures by rounding off the result

$$\rho_{ed} = \frac{W}{m} \dots \dots \dots (3)$$

where

ρ_{ed} = gravimetric energy density (Wh/kg);

W = energy capacity of the cell at room temperature (Wh) when discharged underspecified conditions;

m = mass of the cell (kg).

Process b) and c) shall be repeated five times. The final result shall be calculated by taking average of best three readings.

8 TEST METHOD FOR CYCLE LIFE MEASUREMENT

A cell is generally chosen based on its high energy density and good power capability at the desired working voltage. However, the reliability of a cell depends on its ability to deliver the expected cycle life in the long run. High discharge currents can significantly reduce the cycle life of cells. The following steps illustrate the procedure for undertaking cycle life testing through a series of charge and discharge cycles. Before the charge and discharge cycle test, measure the energy capacity as the initial performance of the cell in accordance with 6 at $25 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$.

8.1 Charge and Discharge Cycle

The charge and discharge cycle test shall be performed as follows:

a) At the start of the test, cell temperature shall be stabilized to $25\text{ °C} \pm 2\text{ °C}$ in accordance with **4.3**.

b) Test phases

Phase 1 – The cell shall be discharged at $25\text{ °C} \pm 2\text{ °C}$ at a constant C-rate, in accordance with **4.4**, down to a specified final voltage. The final voltage shall be the same as that declared by the manufacturer.

Phase 2 – The cells shall be fully charged, in an ambient temperature of $25\text{ °C} \pm 2\text{ °C}$, by the method specified by the cell manufacturer. The charge time shall be less than 2 h for the constant current charging step.

Phase 3 – The cell shall be discharged, in an ambient temperature of $25\text{ °C} \pm 2\text{ °C}$ at constant C-rate, in accordance with **4.4**, until its voltage is equal to the end-of-discharge voltage that is provided by the cell manufacturer.

NOTE — The end-of-discharge voltage provided by the cell manufacturer shall correspond to at least DoD of 80 percent, in accordance with **4.7**.

Phase 4 – Phase 2 and 3 shall be repeated until the test termination specified in **8.1(d)**.

NOTE — The rest time between each phase shall be as specified by the cell manufacturer.

c) Periodical measurement of performance

After completion of every 100 cycles, the energy capacity of the cell shall be measured in accordance with **6**.

d) Termination of test

The cycle life test shall be terminated when either of the following conditions is satisfied.

Condition A – The test sequence from phase 2 to phase 4 has been repeated for equal number of cycles as declared by the cell manufacturer.

Condition B – Energy capacity is decreased to less than 80 percent of the observed value in the first cycle as per step 4 of **6**.

NOTE — If the voltage falls below the lower limit specified by the cell manufacturer during phase 3, the test shall be discontinued notwithstanding the stipulation in **8.1(d)**, and the cell performance shall be measured at this point as specified in **8.1(e)**.

9 SAMPLING

9.1 Sampling and Testing

9.1.1 Collection of Samples

9.1.1.1 For the purpose of this clause, the definitions given in IS 4905 shall apply.

9.1.1.2 The sample size should be at least four times the number of units required for testing, to take into account probable damages due to transportation and possible repetition of tests upon failure in a test. The number of cells required for each test shall be 05.

Explanatory Note — If the total number of exclusive cells required for all the tests is n , the sample size will be n . The four samples will totally contain $4 \times n$ cells. Only the first sample out of the four selected samples need be submitted for testing. The other three sets totaling $3 \times n$ cells are to be kept as back up for the above mentioned exigencies. If only five cells are required for each test and all the tests can sequentially be completed on those five cells then n will be 5.

9.1.1.3 The sample should be drawn from cells which have completed manufacture,

inclusive of all quality assurance programmes of the manufacturer, but before their assembly into batteries. The sample shall be drawn from batches which are not more than 2 months old.

9.1.1.4 The sample shall be collected as per method 1 in clause **8.6** of IS 4905 from the production where the identification of the units shall be by their serial numbers. Random numbers for the purposes shall be generated as per algorithm at clause **7** of IS 4905.

Audit records as per clause **7.4** of IS 4905 shall be maintained.

9.1.2 *Criteria for Acceptance*

All units of a selected sample shall pass the tests. In case a sample fails (results fall outside the eligibility matrix) in any of the tests, a further sample consisting of double the number of units should be tested for all

the tests. All units of this second sample shall pass in the tests.

9.2 Guidance on Samples used in Long Term Aging Test Procedures

9.2.1 Cells are subject to degradation in storage due to a variety of chemical mechanisms, such as limited thermal stability of materials in storage. Battery performance can degrade during use, due to parasitic reactions. Rates of degradation can be related to a number of factors, such as storage temperature or temperature variations.

9.2.2 The effect of degradation of performance can be estimated by real time storage measurements or by accelerated ageing at high temperatures.

9.2.3 Hence, the selection of cells to be done for long term aging/cycle life testing has to be done exclusively from the fresh batch of manufacturing.

ANNEX A

(Foreword)

COMMITTEE COMPOSITION

Secondary Cells and Batteries Sectional Committee, ETD 11

<i>Organization</i>	<i>Representative (s)</i>
NTPC Limited	SHRIMATI MEENAKSHI ANAND (<i>Chairperson</i>)
Amara Raja Batteries	SHRI JASMEET SINGH SHRI C NIRANJAN (<i>Alternate I</i>) SHRI C. B. RAMESH BABU (<i>Alternate II</i>)
Amco Batteries Limited	SHRI S. SANKARA PANDIAN SHRI N. S. PANDURANG (<i>Alternate</i>)
Bharat Battery Manufacturers Company Private Limited	SHRI SAHA S. P. SHRI GOSWAMI B. K. (<i>Alternate</i>)
Central Electricity Authority	SHRI O. P. SUMAN SHRI ASHOK KUMAR RAJPUT (<i>Alternate</i>)
Central Institute of Road Transport	SHRI SASTE D. P. SHRI V. P. GODBOLE (<i>Alternate</i>)
Central Power Research Institute	SHRI KULDEEP SINGH RANA
Central Public Works Department	SHRI P. K. GARG SHRI M. K. VERMA (<i>Alternate</i>)
Controllerate of Quality Assurance (Electronics), Ministry of Defence (DGQA)	DEPUTY CONTROLLER (E)
CSIR - Central Electrochemical Research Institute	PROF N. KALAISELVI DR SUNDAR MAYAVAN (<i>Alternate</i>)
Department of Telecommunications, Ministry of Communications and Information Technology	SHRI BHATIA K. L.
Development Commissioner Micro-Small and Medium Enterprises	SHRI MANOJ KUMAR SHRI IMRAN MUJAWAR (<i>Alternate</i>)
Directorate General of Mines Safety	SHRI AJAY SINGH SHRI MALAY JENA (<i>Alternate</i>)
Electrical Research and Development Association	SHRI RAKESH PATEL DR VINOD GUPTA (<i>Alternate</i>)

<i>Organization</i>	<i>Representative (s)</i>
Exide Industries Limited	SHRI SUBHANKAR CHAKRABARTY SHRI ANJAN ROY (<i>Alternate</i>)
Expert in Personal Capacity	DR RASHI GUPTA
HBL Power System Limited	SHRI SANJEEV KUMAR SHRI M. RAGHAVENDRA REDDY (<i>Alternate</i>)
High Energy Batteries India Limited	DR G. A. PATHANJALI SHRI J. SRIRENGARAJAN (<i>Alternate</i>)
Indian Cellular Association	SHRI PANKAJ MOHINDROO SHRI AMBRISH BAKAYA (<i>Alternate</i>)
Intertek India Private Limited	SHRI KRUNAL SHAH SHRI RAKESH CHAURASIA (<i>Alternate</i>)
Kirloskar Batteries Private Limited	SHRI SREEDHARA S. V. SHRI B. S. SHRINIVASAN RAO (<i>Alternate</i>)
Luminous Power Technologies Private Limited	SHRI BHASKAR BISHNU SHRI AMLAN KANTI DAS (<i>Alternate</i>)
Ministry of Electronics and Information Technology	SHRIMATI ASHA NANGIA DR BHARAT KUMAR YADAV (<i>Alternate</i>)
Ministry of Environment Forest and Climate Change	SHRI SATYENDRA KUMAR SHRI N. SUBRAHMANYAM (<i>Alternate</i>)
Ministry of New and Renewable Energy	SHRI VIKRAM DHAKA SHRI J. K. JETHANI (<i>Alternate</i>)
National Test House	SHRI D. K. KARMAKAR SHRI S. SINHA (<i>Alternate</i>)
NTPC Limited	SHRI SHUBHADEEP MANDAL
Nuclear Power Corporation of India Limited	DR S. P. PANDA MS SWATI R. PATIL (<i>Alternate</i>)
Panasonic India Private Limited	SHRI SHAILESH KUMAR DUBEY SHRI ANIL MEHTA (<i>Alternate</i>)
Power Grid Corporation of India	SHRI PRASAD SAI
Research Designs and Standards Organization (RDSO)	SHRI R. K. GUPTA

<i>Organization</i>	<i>Representative (s)</i>
SAFT India Private Limited	SHRI ARINDAM MUJUMDAR SHRI SHIRISH RAGHUNATH KULKARNI (Alternate)
Shreenath Smart Technologies Private Limited	SHRI NAKUL PATEL SHRI RAHIL PATEL (Alternate)
TATA Power Limited	SHRI ANAND BUDDHIWANT
Telecommunication Engineering Center	SHRI VINOD KUMAR SHRIMATI LAXMI (Alternate)
UL India Private Limited	MS RASHMI R SHRI ANAND KUMAR (Alternate)
Voluntary Organisation in Interest of Consumer Education (VOICE)	SHRI K. C. CHAUDHARY SHRI H. WADHWA (Alternate)
BIS Directorate General	SHRIMATI PRITI BHATNAGAR, SCIENTIST 'F' AND HEAD (ETD) [REPRESENTING DIRECTOR GENERAL (<i>Ex-officio</i>)]

Member Secretary
SHRI SHYAM KUMAR
Scientist 'C' (ETD), BIS

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 2016* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Head (Publication & Sales), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the website- www.bis.gov.in or www.standardsbis.in.

This Indian Standard has been developed from Doc No.: ETD 11 (18132).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones: 2323 0131, 2323 3375, 2323 9402

Website: www.bis.gov.in

Regional Offices:

	Telephones
Central : 601/A, Konnectus Tower -1, 6 th Floor, DMRC Building, Bhavbhuti Marg, New Delhi 110002	{ 2323 7617
Eastern : 8 th Floor, Plot No 7/7 & 7/8, CP Block, Sector V, Salt Lake, Kolkata, West Bengal 700091	{ 2367 0012 2320 9474
Northern : Plot No. 4-A, Sector 27-B, Madhya Marg, Chandigarh 160019	{ 265 9930
Southern : C.I.T. Campus, IV Cross Road, Taramani, Chennai 600113	{ 2254 1442 2254 1216
Western : Plot No. E-9, Road No.-8, MIDC, Andheri (East), Mumbai 400093	{ 2821 8093

Branches : AHMEDABAD. BENGALURU. BHOPAL. BHUBANESHWAR. CHANDIGARH. CHENNAI. COIMBATORE. DEHRADUN. DELHI. FARIDABAD. GHAZIABAD. GUWAHATI. HIMACHAL PRADESH. HUBLI. HYDERABAD. JAIPUR. JAMMU & KASHMIR. JAMSHEDPUR. KOCHI. KOLKATA. LUCKNOW. MADURAI. MUMBAI. NAGPUR. NOIDA. PANIPAT. PATNA. PUNE. RAIPUR. RAJKOT. SURAT. VISAKHAPATNAM.